



Designation: A511/A511M – 16

Standard Specification for Seamless Stainless Steel Mechanical Tubing and Hollow Bar¹

This standard is issued under the fixed designation A511/A511M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers seamless stainless tubing for use in mechanical applications or as hollow bar for use in the production of hollow components such as, but not limited to nozzles, reducers, and couplings by machining where corrosion-resistant or high-temperature strength is needed. The grades covered are listed in [Table 1](#), [Table 2](#), and [Table 3](#).

1.2 This specification covers seamless cold-finished mechanical tubing and hollow bar and seamless hot-finished mechanical tubing and hollow bar in sizes up to 12³/₄ in. [325 mm] in outside nominal diameter (for round tubing) with wall thicknesses or inside diameters as required.

1.3 Tubes for mechanical applications shall be furnished in one of the following shapes, as specified by the purchaser: round, square, rectangular, or special. Tubes to be used as hollow bar shall be furnished in round shape.

1.4 Optional supplementary requirements are provided and when desired, shall be stated in the order.

1.5 The values stated in inch-pound units are to be regarded as the standard. Within the text, the SI units are shown in square brackets. The values stated in each system are not exact equivalents; therefore, each system shall be used independently of the other.

2. Referenced Documents

2.1 ASTM Standards:²

- [A262 Practices for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels](#)
- [A1016/A1016M Specification for General Requirements for](#)

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.10 on Stainless and Alloy Steel Tubular Products.

Current edition approved May 1, 2016. Published May 2016. Originally approved in 1964. Last previous edition approved in 2015 as A511/A511M – 15a. DOI: 10.1520/A0511_A0511M-16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[Ferritic Alloy Steel, Austenitic Alloy Steel, and Stainless Steel Tubes](#)

[A1058 Test Methods for Mechanical Testing of Steel Products—Metric](#)

[E112 Test Methods for Determining Average Grain Size](#)

2.2 *Military Standards:*

[MIL-STD-129 Marking for Shipment and Storage](#)³

[MIL-STD-163 Steel Mill Products Preparation for Shipment and Storage](#)³

2.3 *Federal Standard:*

[Fed. Std. No. 123 Marking for Shipments \(Civil Agencies\)](#)³

3. Terminology

3.1 *Definitions:*

3.1.1 *hollow bar*—round tubing that is intended to produce engineering components by machining, generally specified by minimum outside diameter and maximum inside diameter.

3.1.2 *mechanical tubing*—tubing of various shapes used for mechanical and general engineering purposes, specified by nominal outside dimension and nominal wall.

4. Ordering Information

4.1 Orders for material under this specification should include the following as required to describe the desired material adequately:

4.1.1 Quantity (feet, mass, or number of pieces),

4.1.2 Name of material (seamless stainless steel mechanical tubing or hollow bar),

4.1.3 Mechanical Tubing Form only (round, square, rectangular, special, see Section 1),

4.1.4 Dimensions (round, nominal outside diameter and nominal wall thickness, (see 11.1 and 11.2) or minimum outside diameter and maximum inside diameter (see 11.3); square and rectangular, nominal outside dimensions and nominal wall thickness, see Section 12; other, specify),

4.1.5 Length (specific or random, see 11.4),

4.1.6 Manufacture (cold- or hot-finished, see 6.5),

4.1.7 Grade (Section 8),

³ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

*A Summary of Changes section appears at the end of this standard



TABLE 1 Chemical Requirements of Austenitic Stainless Steels

| Grade | Composition, % | | | | | | | | | | | Other Elements | | |
|----------|------------------------|----------------|-----------------|-------------|--------------|-----------|-----------|------------|------------------------|----------------------|-----------------------|----------------|---------------------------|--------------|
| | Carbon | Manganese, max | Phosphorus, max | Sulfur, max | Silicon, max | Nickel | Chromium | Molybdenum | Titanium | Niobium ² | Selenium | | Iron | |
| MT 302 | 0.08 to 0.20 | 2.00 | 0.040 | 0.030 | 1.00 | 8.0–10.0 | 17.0–19.0 | ... | ... | ... | ... | ... | ... | |
| MT 303 | 0.15 max | 2.00 | 0.20 | 0.15 min | 1.00 | 8.0–10.0 | 17.0–19.0 | ... | ... | ... | ... | ... | ... | |
| MT 303Se | 0.15 max | 2.00 | 0.040 | 0.040 | 1.00 | 8.0–11.0 | 17.0–19.0 | ... | ... | 0.12–0.2 | ... | ... | ... | |
| MT 304 | 0.08 max | 2.00 | 0.040 | 0.030 | 1.00 | 8.0–11.0 | 18.0–20.0 | ... | ... | ... | ... | ... | ... | |
| MT 304L | 0.035 max ^A | 2.00 | 0.040 | 0.030 | 1.00 | 8.0–13.0 | 18.0–20.0 | ... | ... | ... | ... | ... | ... | |
| MT 305 | 0.12 | 2.00 | 0.040 | 0.030 | 1.00 | 10.0–13.0 | 17.0–19.0 | ... | ... | ... | ... | ... | ... | |
| MT 309S | 0.08 max | 2.00 | 0.040 | 0.030 | 1.00 | 12.0–15.0 | 22.0–24.0 | ... | ... | ... | ... | ... | ... | |
| MT 310S | 0.08 max | 2.00 | 0.040 | 0.030 | 1.00 | 19.0–22.0 | 24.0–26.0 | ... | ... | ... | ... | ... | ... | |
| MT 316 | 0.08 max | 2.00 | 0.040 | 0.030 | 1.00 | 11.0–14.0 | 16.0–18.0 | 2.0–3.0 | ... | ... | ... | ... | ... | |
| MT 316L | 0.035 max ^A | 2.00 | 0.040 | 0.030 | 1.00 | 10.0–15.0 | 16.0–18.0 | 2.0–3.0 | ... | ... | ... | ... | ... | |
| MT 317 | 0.08 max | 2.00 | 0.040 | 0.030 | 1.00 | 11.0–14.0 | 18.0–20.0 | 3.0–4.0 | 5XC – 0.60 | ... | ... | ... | ... | |
| MT 321 | 0.08 max | 2.00 | 0.040 | 0.030 | 1.00 | 9.0–13.0 | 17.0–20.0 | ... | ... | ... | ... | ... | ... | |
| MT 347 | 0.08 max | 2.00 | 0.040 | 0.030 | 1.00 | 9.0–13.0 | 17.0–20.0 | ... | 10XC – 1.00 | ... | ... | ... | Cu 3.00–4.00 | |
| N08020 | 0.070 max | 2.00 | 0.045 | 0.035 | 1.00 | 32.0–38.0 | 19.0–21.0 | 2.00–3.00 | 8XC – 1.00 | ... | ... | ... | N 0.18–0.25 | |
| N08367 | 0.030 max | 2.00 | 0.040 | 0.030 | 1.00 | 23.5–25.5 | 20.0–22.0 | 6.00–7.00 | ... | ... | ... | ... | Cu 0.75 | |
| N08800 | 0.10 max | 1.50 | 0.045 | 0.015 | 1.00 | 30.0–35.0 | 19.0–23.0 | ... | 0.15–0.60 | ... | 39.5 min ^B | ... | Al 0.15–0.60 | |
| N08810 | 0.05–0.10 | 1.50 | 0.045 | 0.015 | 1.00 | 30.0–35.0 | 19.0–23.0 | ... | 0.15–0.60 | ... | 39.5 min ^B | ... | Al 0.15–0.60 | |
| N08811 | 0.06–0.10 | 1.50 | 0.045 | 0.015 | 1.00 | 30.0–35.0 | 19.0–23.0 | ... | 0.25–0.60 ^C | ... | 39.5 min ^B | ... | Al 0.25–0.60 ^C | |
| N08904 | 0.020 max | 2.00 | 0.040 | 0.030 | 1.00 | 23.0–28.0 | 19.0–23.0 | 4.0–5.0 | ... | ... | ... | ... | Cu 0.75 | |
| N08925 | 0.020 max | 1.00 | 0.045 | 0.030 | 0.50 | 24.0–26.0 | 19.0–21.0 | 6.0–7.0 | ... | ... | ... | ... | N 0.10–0.20 | |
| N08926 | 0.020 max | 2.00 | 0.030 | 0.010 | 0.50 | 24.0–26.0 | 19.0–21.0 | 6.0–7.0 | ... | ... | ... | ... | Cu 0.80–1.50 | |
| | | | | | | | | | | | | | | Cu 0.15–0.25 |
| | | | | | | | | | | | | | | Cu 0.40–1.50 |

^AFor small diameter or thin wall tubing or both, where many drawing passes are required, a maximum of 0.040 % carbon is necessary in grades MT-304L and MT-316L. Small outside diameter tubes are defined as those under a 0.500 in. [12.7 mm] outside diameter and light-wall tubes as those under a 0.049 in. [1.2 mm] average wall thickness (0.044 in. [1.1 mm] min wall thickness).

^BIron shall be determined arithmetically by difference of 100 minus the sum of the other specified elements.

^CThe range of (Al + Ti) shall be within 0.85–1.20 %.

^DThe terms Niobium (Nb) and Columbium (Cb) are alternate names for the same element.

TABLE 2 Chemical Requirements of Ferritic and Martensitic Stainless Steels

| Grade | Composition, % | | | | | | | | | | | |
|-----------------------|----------------|----------------|-----------------|-------------|--------------|-----------|-----------|------------|-----------|-----------|------------------------|-----------|
| | Carbon, max | Manganese, max | Phosphorus, max | Sulfur, max | Silicon, max | Nickel | Chromium | Molybdenum | Aluminum | Copper | Nitrogen | Selenium |
| Martensitic | | | | | | | | | | | | |
| MT 403 | 0.15 | 1.00 | 0.040 | 0.030 | 0.50 | 0.50 max | 11.5–13.0 | 0.60 max | ... | ... | ... | ... |
| MT 410 | 0.15 | 1.00 | 0.040 | 0.030 | 1.00 | 0.50 max | 11.5–13.5 | ... | ... | ... | ... | ... |
| MT 414 | 0.15 | 1.00 | 0.040 | 0.030 | 1.00 | 1.25–2.50 | 11.5–13.5 | ... | ... | ... | ... | ... |
| MT 416Se | 0.15 | 1.25 | 0.060 | 0.060 | 1.00 | 0.50 max | 12.0–14.0 | ... | ... | ... | ... | 0.12–0.20 |
| MT 431 | 0.20 | 1.00 | 0.040 | 0.030 | 1.00 | 1.25–2.50 | 15.0–17.0 | ... | ... | ... | ... | ... |
| MT 440A | 0.60 to 0.75 | 1.00 | 0.040 | 0.030 | 1.00 | ... | 16.0–18.0 | 0.75 max | ... | ... | ... | ... |
| Ferritic | | | | | | | | | | | | |
| MT 405 | 0.08 | 1.00 | 0.040 | 0.030 | 1.00 | 0.50 max | 11.5–14.5 | ... | 0.10–0.30 | ... | ... | ... |
| MT 429 | 0.12 | 1.00 | 0.040 | 0.030 | 1.00 | 0.50 max | 14.0–16.0 | ... | ... | ... | ... | ... |
| MT 430 | 0.12 | 1.00 | 0.040 | 0.030 | 1.00 | 0.50 max | 16.0–18.0 | ... | ... | ... | ... | ... |
| MT 443 | 0.20 | 1.00 | 0.040 | 0.030 | 1.00 | 0.50 max | 18.0–23.0 | ... | ... | 0.90–1.25 | ... | ... |
| MT 446–1 | 0.20 | 1.50 | 0.040 | 0.030 | 1.00 | 0.50 max | 23.0–30.0 | ... | ... | ... | 0.25 max | ... |
| MT 446–2 ^A | 0.12 | 1.50 | 0.040 | 0.030 | 1.00 | 0.50 max | 23.0–30.0 | ... | ... | ... | 0.25 max | ... |
| 29–4 | 0.010 | 0.30 | 0.025 | 0.020 | 0.20 | 0.15 max | 28.0–30.0 | 3.5–4.2 | ... | 0.15 max | 0.020 max | ... |
| 29–4–2 | 0.010 | 0.30 | 0.025 | 0.020 | 0.20 | 2.0–2.5 | 28.0–30.0 | 3.5–4.2 | ... | 0.15 max | 0.020 max ^B | ... |

^AMT446-2 is a lower carbon version of MT446-1, that has a lower tensile strength but improved ductility and toughness.

^BCarbon plus nitrogen = 0.025 max %.

TABLE 3 Chemical Requirements of Austenitic-Ferritic Stainless Steels^A

| Grade | Composition, % | | | | | | | | | | |
|---------------------|----------------|----------------|-----------------|-------------|--------------|-----------|-----------|------------|-----------|-----------|----------------|
| | Carbon | Manganese, max | Phosphorus, max | Sulfur, max | Silicon, max | Nickel | Chromium | Molybdenum | Nitrogen | Copper | Other Elements |
| S31260 | 0.030 | 1.00 | 0.030 | 0.030 | 0.75 | 5.5–7.5 | 24.0–26.0 | 2.5–3.5 | 0.10–0.30 | 0.20–0.80 | W 0.10–0.50 |
| S31803 | 0.030 | 2.00 | 0.030 | 0.020 | 1.00 | 4.5–6.5 | 21.0–23.0 | 2.5–3.5 | 0.08–0.20 | ... | ... |
| S32101 | 0.040 | 4.0–6.0 | 0.040 | 0.030 | 1.00 | 1.35–1.70 | 21.0–22.0 | 0.10–0.80 | 0.20–0.25 | 0.10–0.80 | ... |
| S32205 | 0.030 | 2.00 | 0.030 | 0.020 | 1.00 | 4.5–6.5 | 22.0–23.0 | 3.0–3.5 | 0.14–0.20 | ... | ... |
| S32304 | 0.030 | 2.50 | 0.040 | 0.040 | 1.00 | 3.0–5.5 | 21.5–24.5 | 0.05–0.60 | 0.05–0.20 | 0.05–0.60 | ... |
| S32506 | 0.030 | 1.00 | 0.040 | 0.015 | 0.90 | 5.5–7.2 | 24.0–26.0 | 3.0–3.5 | 0.08–0.20 | ... | W 0.05–0.30 |
| S32550 | 0.040 | 1.50 | 0.040 | 0.030 | 1.00 | 4.5–6.5 | 24.0–27.0 | 2.9–3.9 | 0.10–0.25 | 1.50–2.50 | ... |
| S32707 | 0.030 | 1.50 | 0.035 | 0.010 | 0.50 | 5.5–9.5 | 26.0–29.0 | 4.0–5.0 | 0.30–0.50 | 1.0 | Co 0.5–2.0 |
| S32750 | 0.030 | 1.20 | 0.035 | 0.020 | 0.80 | 6.0–8.0 | 24.0–26.0 | 3.0–5.0 | 0.24–0.32 | 0.50 | ... |
| S32760 ^B | 0.05 | 1.00 | 0.030 | 0.010 | 1.00 | 6.0–8.0 | 24.0–26.0 | 3.0–4.0 | 0.20–0.30 | 0.50–1.00 | W 0.50–1.00 |
| S32906 | 0.030 | 0.80–1.50 | 0.030 | 0.030 | 0.80 | 5.8–7.5 | 28.0–30.0 | 1.50–2.60 | 0.30–0.40 | 0.80 | ... |
| S32808 | 0.030 | 1.10 | 0.030 | 0.010 | 0.50 | 7.0–8.2 | 27.0–27.9 | 0.80–1.20 | 0.30–0.40 | ... | W 2.10–2.50 |
| S32950 | 0.030 | 2.00 | 0.035 | 0.010 | 0.60 | 3.5–5.2 | 26.0–29.0 | 1.00–2.50 | 0.15–0.35 | ... | ... |
| S39274 | 0.030 | 1.00 | 0.030 | 0.020 | 0.80 | 6.0–8.0 | 24.0–26.0 | 2.5–3.5 | 0.24–0.32 | 0.20–0.80 | W 1.50–2.50 |

^AMaximum, unless a range or minimum is indicated. Where ellipses (...) appear in this table, there is no requirement and analysis for the element need not be determined or reported.

^B% Cr + 3.3 X % Mo + 16X % N ≥ 40.

4.1.8 Condition (annealed, as cold worked, or with special heat treatment, controlled microstructural characteristics, or other condition as required, see Section 7),

4.1.9 Surface finish (special pickling, shot blasting, or polishing, as required, see Supplementary Requirement S5),

4.1.10 Specification designation,

4.1.11 Report of Chemical Analysis, if required (Sections 9 and 10),

4.1.12 Individual supplementary requirements, if required,

NOTE 1—Supplementary requirements S1 and S2 are required for hollow bar only (see Section 13).

4.1.13 End use,

4.1.14 Packaging,

4.1.15 Special marking (see 18.2),

4.1.16 Special packing (see 19.2), and

4.1.17 Special requirements.

5. General Requirements

5.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of Specification **A1016/A1016M** unless otherwise provided herein.

6. Materials and Manufacture

6.1 The steel may be made by any process.

6.2 If a specific type of melting is required by the purchaser, it shall be as stated on the purchase order.

6.3 The primary melting may incorporate separate degassing or refining and may be followed by secondary melting, such as electroslag remelting or vacuum-arc remelting. If secondary melting is employed, the heat shall be defined as all of the ingots remelted from a single primary heat.

6.4 Steel may be cast in ingots or may be strand cast. When steel of different grades is sequentially strand cast, identification of the resultant transition material is required. The producer shall remove the transition material by an established procedure that positively separates the grades.

6.5 The tubes shall be made by a seamless process and by either cold working or hot working as specified. Seamless steel tubing is a tubular product made without a welded seam. It is usually manufactured by hot working steel and then cold finishing the hot-worked tubing to produce the desired shape, dimensions, and properties.

7. Condition

7.1 Round seamless stainless mechanical tubing is generally supplied in the cold-worked and annealed condition (see 7.2 through 7.5). Square, rectangular, or other shapes of tubing are generally supplied annealed prior to final cold shaping. If some other condition is desired, details shall be included in the order. Round seamless hollow bar is generally applied in the hot-worked and annealed condition.

7.2 The thermal treatment for ferritic and martensitic steels shall be performed by a method and at a temperature selected by the manufacturer unless otherwise specified by the purchaser.

7.3 Unless otherwise specified, all austenitic mechanical tubing and hollow bar, except for UNS N08020 shall be furnished in the solution annealed condition. Unless otherwise specified in Table 4, the solution anneal shall consist of heating the material to a minimum temperature of 1900 °F [1040 °C] and quenching in water or rapidly cooling by other means. Alternatively, immediately following hot forming while the temperature of the mechanical tubing or hollow bar is not less than the specified minimum solution treatment temperature, tubes may be individually quenched in water or rapidly cooled by other means. This solution anneal shall precede final cold work, when cold-worked tempers are required. UNS N08020 shall be furnished in the stabilized annealed condition.

7.4 All austenitic-ferritic mechanical tubing and hollow bar shall be furnished in the solution annealed condition as prescribed in Table 5. Alternatively, immediately following hot forming, while the temperature of the mechanical tubing or hollow bar is not less than the specified minimum solution

treatment temperature, tubes may be individually quenched in water or rapidly cooled by other means.

7.5 If any controlled microstructural characteristics are required, these shall be specified so as to be a guide to the most suitable heat treatment.

8. Chemical Composition

8.1 The steel shall conform to the requirements as to chemical composition prescribed in Table 1, Table 2, or Table 3. Other grades are available.

9. Heat Analysis

9.1 An analysis of each heat of steel shall be made by the steel manufacturer to determine the percentages of the elements specified. If secondary melting processes are employed, the heat analysis shall be obtained from one remelted ingot or the product of one remelted ingot of each primary melt. The chemical composition thus determined, or that determined from a product analysis made by the tubular product manufacturer, shall be reported to the purchaser or the purchaser's representative and shall conform to the requirements specified. When requested in the order or contract, a report of this analysis shall be furnished to the purchaser.

10. Product Analysis

10.1 An analysis of either one billet or one tube shall be made for each heat of steel. The chemical composition thus determined shall conform to the requirements specified in Section 8.

10.2 If the original test for product analysis fails, retests of two additional billets or tubes shall be made. Both retests, for the elements in question, shall meet the requirements of the specification, otherwise all remaining material in the heat or lot shall be rejected or, at the option of the producer, each billet or tube may be individually tested for acceptance. Billets or tubes which do not meet the requirements of this specification shall be rejected.

11. Permissible Variations in Dimensions of Round Mechanical Tubing and Hollow Bar

11.1 *Nominal Outside Diameter and Nominal Wall Thickness (Cold Finished Mechanical Tubing and Hollow Bar)*—

TABLE 4 Heat Treatment of Austenitic Stainless Steels

| Grade | Temperature °F [°C] | Quench |
|--------|-------------------------------------|--|
| N08020 | 1700–1850 [925–1010] ^{A,B} | quenched in water or rapidly cooled by other means |
| N08367 | 2025 [1105] ^A | quenched in water or rapidly cooled by other means |
| N08810 | 2050 [1120] ^A | quenched in water or rapidly cooled by other means |
| N08811 | 2100 [1150] ^A | quenched in water or rapidly cooled by other means |
| N08904 | 2000 [1100] ^A | quenched in water or rapidly cooled by other means |
| N08925 | 2010–2100 [1100–1150] ^A | quenched in water or rapidly cooled by other means |
| N08926 | 2010–2100 [1100–1150] ^A | quenched in water or rapidly cooled by other means |

^AQuenched in water or rapidly cooled by other means, at a rate sufficient to prevent re-precipitation of carbides, as demonstrable by the capability of tubes, heat treated by either separate solution annealing or by direct quenching, passing Practices A262, Practice E. The manufacture is not required to run the test unless it is specified on the purchase order. Note that Practices A262 requires the test to be performed on sensitized specimens in the low-carbon and stabilized types and on specimens representative of the as-shipped condition for other types. In the case of low-carbon types containing 3 % or more molybdenum, the applicability of the sensitizing treatment prior to testing shall be a matter for negotiation between the seller and the purchaser.

^BMaterial shall be supplied in stabilized annealed condition.

TABLE 5 Heat Treatment of Austenitic-Ferritic Stainless Steels

| Grade | Temperature °F [°C] | Quench |
|--------|-----------------------|--|
| S31260 | 1870-2010 [1020-1100] | rapid cooling in air or water |
| S31803 | 1870-2010 [1020-1100] | rapid cooling in air or water |
| S32101 | 1870 [1020] min | quenched in water or rapidly cooled by other means |
| S32205 | 1870-2010 [1020-1100] | rapid cooling in air or water |
| S32304 | 1700-1920 [925-1050] | rapid cooling in air or water |
| S32506 | 1870-2050 [1020-1120] | rapid cooling in air or water |
| S32550 | 1900 [1040] min | rapid cooling in air or water |
| S32707 | 1975-2050 [1080-1120] | rapid cooling in air or water |
| S32750 | 1880-2060 [1025-1125] | rapid cooling in air or water |
| S32760 | 1960-2085 [1070-1140] | rapid cooling in air or water |
| S32808 | 1920-2100 [1050-1150] | rapid cooling in air or water |
| S32906 | 1870-2100 [1020-1150] | rapid cooling in air or water |
| S32950 | 1820-1880 [990-1025] | air cool |
| S39274 | 1880-2060 [1025-1125] | rapid cooling in air or water |

Variations in outside diameter and wall thickness shall not exceed the amounts prescribed in [Table 6](#).

11.2 Nominal Diameter and Nominal Wall Thickness (Hot Finished Mechanical Tubing and Hollow Bar)—

Variations in outside diameter and wall thickness shall not exceed the amounts prescribed in [Table 7](#).

11.3 Minimum Outside Diameter and Maximum Inside Diameter (Cold-Finished and Hot-Finished Hollow Bar)—

Variations in outside diameter and wall thickness shall not exceed the amounts prescribed in [Table 8](#).

11.4 Lengths (Cold Finished or Hot Finished)—Mechanical tubing and hollow bar are commonly furnished in mill lengths 5 ft [1.5 m] and over. When random lengths are ordered, mechanical tubing and hollow bar lengths may vary by an amount up to 7 ft [2.1 m]. Definite cut lengths are furnished, when specified, to the length tolerances shown in [Table 6](#) or [Table 7](#). For mechanical tubing and hollow bar ordered in multiple lengths, it is common practice to allow a definite amount over for each multiple for the purchaser's cutting operations. This amount depends on the type of purchaser's cutting and varies with differing wall thickness. The cutting allowance should be specified on the purchase order. When it is not specified, mechanical tubing and hollow bar are customarily supplied with the following allowance for each multiple:

| Wall Thickness, in. [mm] | Excess Length per Multiple, in. [mm] |
|-------------------------------|--|
| Up to 1/8 [3.2] | 1/8 [3] |
| Over 1/8 to 1/2 [3.2 to 12.7] | 3/16 [5] |
| Over 1/2 [12.7] | 1/4 [6] |

11.5 Straightness Tolerances (Cold Finished or Hot Finished Mechanical Tubing)—The deviation from straightness shall not exceed the amounts shown in [Table 9](#) when measured with a 3-ft [1-m] straightedge and feeler gauge. If determined by the dial indicator method, the values obtained will be approximately twice those determined by the straightedge feeler gauge method.

11.6 Straightness Tolerances (Cold Finished or Hot Finished Hollow Bar)—The deviation from straightness of any hollow bar length (L) shall not exceed 0.0015 L, and not exceeding 0.072 in. per 3 ft [2 mm per 1 m] when measured with a 3-ft [1-m] straight edge and feeler gage. If determined

by the dial indicator method, the values obtained will be approximately twice those determined by the straight edge – feeler gage method.

12. Permissible Variations in Dimensions of Square and Rectangular Mechanical Tubing

12.1 Square and rectangular seamless stainless mechanical tubing is supplied as cold worked unless otherwise specified. For this tubing, variations in dimensions from those specified shall not exceed the amounts prescribed in [Table 10](#), [Table 11](#), [Table 12](#), and [Table 13](#).

12.2 The squareness of sides is commonly determined by one of the following methods.

12.2.1 A square, with two adjustable contact points on each arm, is placed on two sides. A fixed feeler gauge is then used to measure the maximum distance between the free contact point and the surface of the tubing.

12.2.2 A square, equipped with a direct reading vernier, may be used to determine the angular deviation which, in turn, may be related to distance in inches.

12.3 The squareness of sides varies in accordance with the following equation:

$$\pm b = c \times 0.006$$

where:

b = tolerance for out-of-square, and

c = length of longest side.

Example: Rectangular tubes 2 by 1 may have sides fail to be 90° to each other by ± 0.012 in. [0.3 mm].

12.4 The twist in square and rectangular tubing may be measured by holding one end of the tubing on a surface plate and noting the height above the surface plate of either corner of the opposite end of the same side. Twist may also be measured by the use of a beveled protractor, equipped with a level, and noting the angular deviation on opposite ends, or at any point throughout the length.

13. Mechanical Properties – Hollow Bar

13.1 Tensile Requirements:

13.1.1 The material shall conform to the requirements of the tensile properties given in [Table S2.1](#).



TABLE 6 Permissible Variations in Outside Diameter, Ovality, Wall Thickness, and Cut-Length Variations (Cold-Finished Round Mechanical Tubing and Hollow Bar)^A

| Outside Nominal Diameter, in. [mm] | Prevailing Range of Commercially Available Metric Sizes, mm | Outside Diameter, ^B Tolerance, ^B in. [mm] Over and Under | Ovality, ^B Double Outside Diameter Tolerance when wall is: | Wall Thickness in % C.D. | | Permissible Variations in Cut Length, in. [mm] ^F |
|------------------------------------|---|--|---|--------------------------|-------|---|
| | | | | Over | Under | |
| Under 1/2 [13] | Under 12.7 | 0.005 [0.1] | less than 0.015 in. [0.4 mm] | 15 | 15 | 0 |
| 1/2 [13] to 1 1/2 [38], excl | 12.7 to 38.1, excl | 0.005 [0.1] | less than 0.065 in. [1.6 mm] | 10 | 10 | 0 |
| 1 1/2 [38] to 3 1/2 [90], excl | 38.1 to 88.9, excl | 0.010 [0.3] | less than 0.095 in. [2.4 mm] | 10 | 10 | 0 |
| 3 1/2 [90] to 5 1/2 [140], excl | 88.9 to 139.7, excl | 0.015 [0.4] | less than 0.150 in. [3.8 mm] | 10 | 10 | 0 |
| 5 1/2 [140] to 8 [200], excl | 139.7 to 203.2, excl | 0.030 [0.8] | less than 0.240 in. [6.1 mm] | 10 | 10 | 0 |
| 8 [200] to 8 5/8 [220], excl | 203.2 to 219.1, excl | 0.045 [1.1] | less than 0.300 in. [7.6 mm] | 10 | 10 | 0 |
| 8 5/8 [220] to 12 3/4 [325], incl | 219.1 to 323.9, incl | 0.062 [1.6] | less than 0.350 in. [8.9 mm] | 10 | 10 | 0 |

^ATolerances of tubes produced by the rod or bar mandrel process and which have an inside diameter under 1/2 in. [12.7 mm] (or an inside diameter under 5/8 in. [15.8 mm] when the wall thickness is more than 20 % of the outside diameter) are as shown in this table, except that wall thickness tolerances are 10 % over and under the specified wall thickness.

^BFor ovality values, the tolerance for average outside diameter at any one cross section does not exceed the outside diameter tolerance value for the applicable outside diameter.

^CMany tubes with wall thicknesses more than 25 % of outside diameter or with wall thicknesses over 1 1/4 in., [31.7 mm] or weighing more than 90 lb/ft [60.5 kg/m], are difficult to draw over a mandrel. Therefore, the wall thickness can vary 12 1/2 % over and under that specified. Also see Footnote (B).

^DFor those tubes with inside diameter under 1/2 in. [12.7 mm] (or under 5/8 in. [15.8 mm] when the wall thickness is more than 20 % of the outside diameter) which are not commonly drawn over a mandrel, Footnote (A) is not applicable. Therefore, the wall thickness can vary 15 % over and under that specified, and the inside diameter is governed by both the outside diameter and wall thickness tolerances.

^EThese tolerances apply to cut lengths up to and including 24 ft. [7.3 m]. For lengths over 24 ft. [7.3 m], an additional over tolerance of 1/8 in. [3 mm] for each 10 ft [3 m] or fraction thereof shall be permissible, up to a maximum tolerance of 1/2 in. [13 mm].