



Designation: E2470 – 09 (Reapproved 2015)^{ε1}

Standard Specification for Polyester Grade Ethylene Glycol¹

This standard is issued under the fixed designation E2470; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Editorial change was made in Subsection 1.2 in May 2016.

1. Scope*

1.1 This specification covers polyester grade ethylene glycol.

1.2 Review the current Safety Data Sheets (SDS) for detailed information concerning toxicity, first aid procedures, handling and safety precautions.

1.3 The following applies to all specified limits in this standard; for purposes of determining conformance with this standard, an observed value or a calculated value shall be rounded off “to the nearest unit” in the last right-hand digit used in expressing the specification limit, in accordance with the rounding-off method of Practice E29.

1.4 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.5 The following safety hazards caveat pertains only to the test methods portion, Section 5, described in this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:²

D482 Test Method for Ash from Petroleum Products

¹ This specification is under the jurisdiction of ASTM Committee D16 on Aromatic, Industrial, Specialty and Related Chemicals and is the direct responsibility of Subcommittee D16.14 on Alcohols & Glycols.

Current edition approved June 1, 2015. Published June 2015. Originally approved in 2009. Last previous edition approved in 2009 as E2470 – 09. DOI: 10.1520/E2470-09R15E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

D1078 Test Method for Distillation Range of Volatile Organic Liquids

D1209 Test Method for Color of Clear Liquids (Platinum-Cobalt Scale)

D1722 Test Method for Water Miscibility of Water-Soluble Solvents

D4052 Test Method for Density, Relative Density, and API Gravity of Liquids by Digital Density Meter

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E202 Test Methods for Analysis of Ethylene Glycols and Propylene Glycols

E300 Practice for Sampling Industrial Chemicals

E1064 Test Method for Water in Organic Liquids by Coulometric Karl Fischer Titration

E1615 Test Method for Iron in Trace Quantities Using the FerroZine Method

E2193 Test Method for Ultraviolet Transmittance of Monoethylene Glycol (using Ultraviolet Spectrophotometry)

E2313 Test Method for Aldehydes in Mono-, Di-, and Triethylene Glycol (using Spectrophotometry)

E2409 Test Method for Glycol Impurities in Mono-, Di-, Tri- and Tetraethylene Glycol and in Mono- and Dipropylene Glycol (Gas Chromatographic Method)

E2469 Test Method for Chloride in Mono-, Di- and Triethylene Glycol by Ion Chromatography

E2679 Test Method for Acidity in Mono-, Di-, Tri- and Tetraethylene Glycol by Non-Aqueous Potentiometric Titration

E2680 Test Method for Appearance of Clear, Transparent Liquids (Visual Inspection Procedure)

3. Requirements

3.1 Polyester grade ethylene glycol shall conform to the specification chemical and physical requirements (see Table 1).

4. Sampling

4.1 Sample ethylene glycol in accordance with the appropriate sections of Practice E300 for liquid samples.

5. Test Methods

5.1 Test each composite sample for chemical and physical requirements using the test methods specified in 3.1. Many of

*A Summary of Changes section appears at the end of this standard

TABLE 1 Chemical and Physical Specification Requirements

Specification Requirements	min	max	ASTM Test Method
Acidity as Acetic Acid, % mass (m/m)	—	0.002	E2679
Aldehydes as Acetaldehyde, ug/g	—	not reported	E2313
Appearance, Clear & Free from Suspended Matter	pass	—	E2680
Chloride as Cl, ug/g	—	0.2	E2469
Color, platinum cobalt	—	5	D1209
Glycols	99.9	—	E2409
Ethylene glycol, % mass (m/m)	—	0.05	
Diethylene glycol, % mass (m/m)	—	0.1	E1615
Iron, ug/g	—	—	E2193
Ultraviolet Transmittance	70	—	
at 220 nm, %T	90	—	
at 250 nm, %T	94	—	
at 275 nm, %T	98	—	
at 350 nm, %T	—	0.05	E1064
Water, % mass (m/m)	—	max	ASTM Test Method
Typical Properties	min	max	
Ash, % mass (m/m)	—	0.004	D482
Distillation Range	196	—	D1078
Initial Boiling Point, C	—	200	
Dry Point, C	—	—	
Relative Density at	1.1151	1.1156	D4052
20/20 C	or	or	
or	1.1129	1.1134	
25/25 C	—	—	
Water Miscibility	miscible	—	D1722

these test methods, along with alternative test methods and technologies, can be found in Test Methods E202. In case of a dispute, test methods identified in 3.1 of this specification shall be the preferred test methods.

6. Packaging, Package Markings, and Transportation

6.1 The packaging, labeling, and transportation of commercial quantities shall conform to applicable federal, state, and

local regulation. Conformance is the responsibility of the manufacturer and the shipper.

7. Keywords

7.1 ethylene glycol; polyester grade

SUMMARY OF CHANGES

Subcommittee E15.02 has identified the location of selected changes to this standard since the last issue (E2470-07) that may impact the use of this standard.

(1) Replaced two test methods within the specification with test methods that have been recently adopted by E15 and reflect newer technologies used in the industry.

(2) Section 2, Referenced Documents, was revised.
(3) Table 1 was revised.
(4) Added Summary of Changes section.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/