



Designation: F 1291 – 99

Standard Test Method for Measuring the Thermal Insulation of Clothing Using a Heated Manikin¹

This standard is issued under the fixed designation F 1291; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

The type of clothing worn by people directly affects the heat exchange between the human body and the environment. The insulation provided by a clothing ensemble is dependent upon the designs and fabrics used in the component garments, the amount of body surface area covered by clothing, distribution of the fabric layers over the body, looseness or tightness of fit, and the increased surface area for heat loss. Insulation measurements made on fabrics alone do not take these factors into account. Measurements of the resistance to dry heat loss provided by clothing can be used to determine the thermal comfort or stress of people in cold to comfortable environments. However, the moisture permeability of clothing is more important in environmental conditions where heat balance can only be achieved by the evaporation of sweat.

1. Scope

1.1 This test method covers determination of the insulation value of a single garment or a clothing ensemble. It describes measurement of the resistance to dry heat transfer from a constant skin temperature manikin (with a human skin temperature pattern) to a relatively calm, cool environment.

1.1.1 This is a static test that provides a baseline clothing measurement on a standing manikin.

1.1.2 The effects of body position and movement are not addressed in this test method.

1.2 The insulation values obtained apply only to the particular garments, as tested, and for the specified thermal and environmental conditions of each test, particularly with respect to air movement, are not addressed in this test method.

1.2.1 The insulation values obtained apply only to the particular ensembles evaluated and for the specified thermal and environmental conditions of each test, particularly with respect to air movement past the manikin.

1.3 The values stated in either clo or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system shall be used inde-

pendently of the other. Combining values from the two systems may result in nonconformance with the test method.

2. Referenced Documents

2.1 ASTM Standards:

D 123 Terminology Relating to Textiles²

D 1518 Test Method for Thermal Transmittance of Textile Material²

2.2 ASHRAE Standards:

ASHRAE 55-1981 Thermal Environmental Conditions for Human Occupancy³

Handbook of Fundamentals, Chapter 8 on Physiological Principles, Comfort and Health³

2.3 ISO Standards:

ISO 7730 1994 Moderate Thermal Environments—Determination of the PMV and PPD Indices and Specification of the Conditions for Thermal Comfort⁴

ISO 9920 1995 Ergonomics of the Thermal Environment—Estimation of the Thermal Insulation and Evaporation Resistance of a Clothing Ensemble⁴

3. Terminology

3.1 Definitions:

² *Annual Book of ASTM Standards*, Vol 07.01.

³ Available from American Society of Heating, Refrigerating, and Air-Conditioning Engineers, 1791 Tullie Circle, N.E. Atlanta, GA 30329.

⁴ Available from American National Standards Institute, 11 W. 42nd St., 13th Floor, New York, NY 10036.

¹ This test method is under the jurisdiction of ASTM Committee F-23 on Protective Clothing and is the direct responsibility of Subcommittee F23.60 on Human Factors.

Current edition approved June 10, 1999. Published August 1999. Originally published as F1291-90. Last previous edition F 1291-96.

3.1.1 *clo, n*—unit of thermal resistance defined as the insulation required to keep a resting man (producing heat at the rate of 58 W/m²) comfortable in an environment at 21°C, air movement 0.1 m/s, or roughly the insulation value of typical indoor clothing.

3.1.1.1 *total clo, n*—clo plus the thermal resistance from the air boundary layer, (*clo_t*).

3.1.1.2 *Discussion*—Numerically, one clo is equal to 0.155 K m²/W.

3.1.2 *clothing ensemble, n*—a group of garments worn together on the body at the same time.

3.1.3 *garment, n*—a single item of clothing (for example, shirt).

3.1.4 *thermal insulation, n*—the resistance to dry heat transfer by way of conduction, convection, and radiation.

3.1.5 *total insulation (I_T), n*—the total resistance to dry heat loss from the manikin, that includes the resistance provided by the clothing and the air layer around the clothed manikin.

3.1.5.1 *Discussion*—Total insulation (*I_T*) values are measured directly with a manikin. They can be used to compare different clothing ensembles as long as each test is conducted using the same experimental procedures and test conditions. Intrinsic clothing insulation values (*I_{cl}*) are determined by subtracting the air layer resistance around the clothed manikin from the *I_T* value for the ensemble. Intrinsic clothing insulation (*I_{cl}*) values are used in several thermal comfort and clothing standards (see 2.2 and 2.3). Information on determining *I_{cl}* from measured *I_T* values is given in ISO Standard 9920 and ASHRAE Transactions.⁵

4. Significance and Use

4.1 This test method can be used to quantify and compare the insulation provided by different garments and clothing systems. For example, variations in the design and fabric used in garments can be evaluated. The effects of garment layering, closure, and fit can be measured for clothing ensembles. The insulation values for ensembles can be used in models that predict the physiological responses of people in different environmental conditions.

4.2 The measurement of the insulation provided by clothing is complex and dependent on the apparatus and techniques used. It is not practical in a test method of this scope to establish details sufficient to cover all contingencies. Departures from the instructions in this test method may lead to significantly different test results. Technical knowledge concerning the theory of heat transfer, temperature, and air motion measurement, and testing practices is needed to evaluate which departures from the instructions given in this test method are significant. Standardization of the method reduces, but does not eliminate, the need for such technical knowledge. Any departures should be reported with the results.

4.3 The insulation values should be reported in clo units and SI units as standard procedure. Conversion factors to other units are given in Test Method D 1518.

5. Apparatus

5.1 *Manikin*⁶—A standing manikin shall be used that is formed in the shape and size of an adult male or female and heated to a constant, average skin temperature, with a skin temperature distribution similar to that of a human being.

5.1.1 *Size and Shape*—The manikin shall be constructed to simulate the body of a human being; that is, it shall consist of a head, chest/back, abdomen/buttocks, arms, hands (preferably with fingers extended to allow gloves to be worn), legs, and feet. Total surface area shall be 1.8 ± 0.3 m², and height shall be 180 ± 10 cm. The manikin's dimensions should correspond to those required for standard sizes of garments because deviations in fit will affect the results.

5.1.2 *Surface Temperature*—The manikin shall be constructed so as to maintain a constant temperature distribution over the nude body surface, with no local hot or cold spots. The mean skin temperature of the manikin shall be between 32 and 35°C (89.6 and 95°F). It is recommended that the average temperature of the hands and feet be lower in studies of clothing for cold or comfortable conditions. Local deviations from the mean skin temperature shall not exceed ± 3°C. Temperature uniformity of the nude manikin shall be evaluated at least once annually using an infrared thermal imaging system or equivalent method. This procedure should also be repeated after repairs or alterations are completed that could affect temperature uniformity, for example, replacement of a heating element.

5.2 *Power-Measuring Instruments*—Power to the manikin shall be measured so as to give an accurate average over the period of a test. If time proportioning or phase proportioning is used for power control, then devices that are capable of averaging over the control cycle are required. Integrating devices (watt-hour meters) are preferred over instantaneous devices (watt meters). Overall accuracy of the power monitoring equipment must be within ± 2 % of the reading for the average power for the test period. Since there are a variety of devices and techniques used for power measurement, no specified calibration procedures shall be given. However, an appropriate power calibration procedure is to be developed and documented.

5.3 *Equipment for Measuring the Manikin's Skin Temperature*—The mean skin temperature may be measured with point sensors or distributed temperature sensors.

5.3.1 *Point Sensors*—Point sensors may be thermocouples, resistance temperature devices (RTD's), thermistors, or equivalent sensors. They shall be no more than 3 mm thick and shall be well bonded, both mechanically and thermally, to the manikin's surface. Lead wires shall be bonded to the surface or pass through the interior of the manikin, or both. The sensors shall be distributed so that each one represents the same surface area or each sensor temperature should be area-weighted when calculating the mean skin temperature for the body. A minimum of 15 point sensors are required. It is recommended that

⁵ McCullough, E. A., Jones, B. W., and Huck, J., *ASHRAE Transactions*, Vol 91, Part 2, 1985, pp. 29–47.

⁶ Information on laboratories with heated manikins can be obtained from the Institute for Environmental Research, Kansas State University, Manhattan, KS 66506.