



Designation: F 1295 – 01

## Standard Specification for Wrought Titanium-6 Aluminum-7 Niobium Alloy for Surgical Implant Applications [UNS R56700]<sup>1</sup>

This standard is issued under the fixed designation F 1295; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This specification covers the chemical, mechanical, and metallurgical requirements for wrought annealed titanium-6 aluminum-7 niobium alloy bar and wire to be used in the manufacture of surgical implants (1-4).<sup>2</sup>

1.2 The values stated in inch-pound units are to be regarded as the standard. The SI equivalents in parentheses are for information only.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

E 8 Test Methods for Tension Testing of Metallic Materials<sup>3</sup>

E 120 Test Methods for Chemical Analysis of Titanium and Titanium Alloys<sup>4</sup>

E 1409 Test Method for Determination of Oxygen in Titanium and Titanium Alloys by the Insert Gas Fusion Technique<sup>4</sup>

E 1447 Test Method for Determination of Hydrogen in Titanium and Titanium Alloys by the Insert Gas Fusion Thermal Conductivity Method<sup>5</sup>

F 981 Practice for Assessment of Compatibility of Biomaterials for Surgical Implants with Respect to Effect of Materials in Muscle and Bone<sup>6</sup>

#### 2.2 ISO Standards:

ISO 5832-11 Implants for Surgery—Metallic Materials—Part 11: Wrought Titanium 6–Aluminum 7–Niobium Alloy<sup>7</sup>

ISO 6892 Metallic Materials—Tensile Testing<sup>7</sup>

#### 2.3 Aerospace Material Specification:

AMS 2249 Chemical Check Analysis Limits, Titanium and Titanium Alloys<sup>8</sup>

#### 2.4 American Society for Quality Standard:

ASQ C1 Specification of General Requirements for a Quality Program<sup>9</sup>

### 3. Product Classification

3.1 Bar—Rounds or flats from 0.1875 in. (4.76 mm) to 4 in. (101.60 mm) in diameter or thickness. Other sizes and shapes by special order.

3.2 Forging Bar—Bar as described in 3.1, used for the production of forgings, may be furnished in the hot rolled condition.

3.3 Wire—Rounds or flats less than 0.1875 in. (4.76 mm) in diameter or thickness.

### 4. Ordering Information

4.1 Include with inquiries and orders for material under this specification the following information:

4.1.1 Quantity (weight or number of pieces),

4.1.2 Applicable ASTM designation, date of issue.

4.1.3 Form (bar or wire),

4.1.4 Condition (see 5.3),

4.1.5 Mechanical Properties (if applicable for special conditions),

4.1.6 Finish (see 5.2),

4.1.7 Applicable dimensions including size, thickness, width, or drawing number,

4.1.8 Special tests, if any,

4.1.9 Other requirements.

### 5. Materials and Manufacture

5.1 The various titanium mill products covered in this specification normally are formed with the conventional forging and rolling equipment found in primary ferrous and nonferrous plants. The alloy is usually multiple melted in arc

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devices and is the direct responsibility of Subcommittee F04.12 on Metallurgical Materials.

Current edition approved October 10, 2001. Published January 2002. Originally published as F 1295 – 92. Last previous edition F 1295 – 97a.

<sup>2</sup> The boldface numbers in parentheses refer to a list of references at the end of the text.

<sup>3</sup> *Annual Book of ASTM Standards*, Vols 01.02, 02.01, 02.02, 02.03, and 03.01.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 03.05.

<sup>5</sup> *Annual Book of ASTM Standards*, Vol 03.06.

<sup>6</sup> *Annual Book of ASTM Standards*, Vol 13.01.

<sup>7</sup> Available from American National Standards Institute, 25 W. 43rd St., 4th Floor, New York, NY, 10036.

<sup>8</sup> Available from Society of Automotive Engineers, 400 Commonwealth Dr., Warrendale, PA 15096.

<sup>9</sup> Available from American Society for Quality, 600 N. Plankinton Ave., Milwaukee, WI 53203.

furnaces (including furnaces such as plasma arc and electron beam) of a type conventionally used for reactive metals.

5.2 *Finish*—The mill product may be furnished to the implant manufacturer as descaled or pickled, sandblasted, chemically milled, ground, machined, peeled, polished, or as specified by the purchaser.

5.3 *Condition*—Material shall be furnished in the annealed or hot rolled condition.

## 6. Chemical Requirements

6.1 The heat analysis shall conform to the chemical composition of Table 1. Ingot analysis may be used for reporting all chemical requirements, except hydrogen. Samples for hydrogen shall be taken from the finished mill product. The supplier shall not ship material outside the limits specified in Table 1.

6.1.1 Requirements for the major and minor elemental constituents are listed in Table 1. Also listed are important residual elements. Analysis for elements not listed in Table 1 is not required to certify compliance with this specification.

### 6.2 Product Analysis

6.2.1 Product analysis tolerances do not broaden the specified heat analysis requirements but cover variations between laboratories in the measurement of chemical content. The manufacturer shall not ship material that is outside the limits specified in Table 1. The product analysis tolerances shall conform to Table 2.

6.2.2 The product analysis is either for the purpose of verifying the composition of a heat or manufacturing lot or to determine variations in the composition within the heat.

6.2.3 Acceptance or rejection of a heat or manufacturing lot of material may be made by the purchaser on the basis of this product analysis tolerance.

6.3 For referee purposes, use Test Methods E 120, E 1409, and E 1447 or other analytical methods agreed upon between the purchaser and the supplier.

6.4 Ensure that the samples for chemical analysis are representative of the material being tested. The utmost care must be used in sampling titanium for chemical analysis because of its affinity for elements such as oxygen, nitrogen, and hydrogen. In cutting samples for analysis, therefore, the operation should be carried out insofar as possible in a dust-free atmosphere. Cutting tools should be clean and sharp. Samples for analysis should be stored in suitable containers.

## 7. Mechanical Requirements

7.1 The material supplied under this specification shall conform to the mechanical properties given in Table 3.

**TABLE 1 Chemical Requirements**

Element	Composition, %
Aluminum	5.50 to 6.50
Niobium	6.50 to 7.50
Tantalum	0.50 max
Iron	0.25 max
Oxygen	0.20 max
Carbon	0.08 max
Nitrogen	0.05 max
Hydrogen	0.009 max
Titanium <sup>A</sup>	Balance

<sup>A</sup>The percentage of titanium is determined by difference and need not be determined or certified.

**TABLE 2 Product Analysis Tolerances<sup>A</sup>**

Tolerance Under the Minimum <sup>B</sup> or Over the Maximum Limit	
Aluminum	0.10
Niobium	0.10
Tantalum	0.10
Iron	0.10
Oxygen	0.02
Carbon	0.02
Nitrogen	0.02
Hydrogen	0.002

<sup>A</sup>Refer to AMS 2249.

<sup>B</sup>Under minimum limit not applicable for elements where only a maximum percentage is indicated.

**TABLE 3 Annealed<sup>A</sup> Mechanical Properties for Bar and Wire<sup>B</sup>**

Ultimate Tensile Strength, min, psi, (MPa)	Yield Strength (0.2 % Offset), min, psi, (MPa)	Elongation, <sup>C</sup> min, %	Reduction of Area, min, %
130 500 (900)	116 000 (800)	10	25

<sup>A</sup>Mechanical properties for the hot rolled condition may be established by agreement between the supplier and purchaser.

<sup>B</sup>Up to 4.00-in. (101.60-mm) diameter or thickness.

<sup>C</sup>Elongation of material 0.062 in. (1.575 mm) or greater in diameter or thickness shall be measured using a gage length of 4D or 4W or 5.65 √ So, where So is the original cross-sectional area. The gage length must be reported with the test results. The method for determining elongation of material under 0.062 in. (1.57 mm) in diameter or thickness may be negotiated. Alternately, a gage length corresponding to ISO 6892 may be used when agreed upon between supplier and purchaser.

7.2 Specimens for tension tests shall be machined and tested in accordance with Test Methods E 8. Tensile properties shall be determined using a strain rate of 0.003 to 0.007 in./in./min. (mm/mm/min) through the specified yield and then the cross-head speed shall be increased so as to produce fracture in approximately one additional minute.

7.3 *Number of Tests*—Perform a minimum of two tension tests from each lot. A lot is defined as the total number of a specific mill product produced under the same conditions at essentially the same time. Should either of the two test specimens not meet the specified requirements, test two additional test pieces representative of the same lot in the same manner. The lot will be in compliance only if both additional test pieces meet the specified requirements. If a specimen fails outside the gage, the test is null in accordance with Test Methods E 8, and a retest shall be performed.

## 8. Special Requirements

8.1 The microstructure shall be a fine dispersion of the alpha and beta phases resulting from processing in the alpha plus beta field. There shall be no continuous alpha network at prior beta grain boundaries. There shall be no coarse, elongated alpha platelets.

8.2 Determine the beta transus temperature for each heat by a suitable method and report on the material certification if required by the purchaser.

8.3 Alpha case is not permitted for products supplied with a machined, ground, or chemically milled surface finish. For other products, there shall be no continuous layer of alpha case when examined at 100 X magnification.

## 9. Certification

9.1 The supplier's certification that the material was manufactured in accordance with this specification together with a