



Designation: D7178 – 16

Standard Practice for Determining the Number of Constrictions “ m ” of Non- Woven Geotextiles as a Complementary Filtration Property¹

This standard is issued under the fixed designation D7178; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice describes the procedure used along with existing test method to determine the number of constrictions m of mechanically bonded non-woven geotextiles, based on thickness, mass per unit area and fiber properties

1.2 The number of constrictions is a property of non-woven geotextiles, which is complementary to opening size to predict their filtration behavior. It can be used to differentiate non-woven geotextiles with similar opening sizes but different structures (thickness, weight, fiber diameter, etc.). However, more research is needed to assess its significance when comparing two products with different opening sizes.

1.3 Consideration of the number of constriction is relevant in filtration applications where piping or clogging concerns are to be controlled with a high level of confidence, that is, for filters applications in critical soils.

1.4 This standard is for design purposes only and is not intended for quality control purposes.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

D1577 Test Methods for Linear Density of Textile Fibers

D4439 Terminology for Geosynthetics

D4751 Test Method for Determining Apparent Opening Size of a Geotextile

D5199 Test Method for Measuring the Nominal Thickness of Geosynthetics

D5261 Test Method for Measuring Mass per Unit Area of Geotextiles

D6767 Test Method for Pore Size Characteristics of Geotextiles by Capillary Flow Test

3. Terminology

3.1 *Definitions*—For definitions of terms used in this test method, refer to Terminology D4439.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *constriction*—in the non-woven geotextile, a “window” delimited by three or more fibers, through which soil particles could migrate.

3.2.2 *filtration paths*—under the forces induced by fluid flows, soil particles may travel in the geotextile filter along filtration paths. Each of these paths is composed of a sequence of constrictions of various size and shape.

3.2.3 *number of constrictions, m* —average number of constrictions for a filtration path.

3.2.4 *fiber count, T* —a measure of the linear density of the fiber expressed in tex, where 1 tex = 10^{-6} kg/m.

3.2.4.1 *Discussion*—The fiber count is sometime expressed in “Denier” (equivalent to the weight in grams of a theoretical 9000 meters long fiber). The value in “Tex” can be obtained from the value in Denier considering that 1 Denier = 9 Tex.

3.2.5 *opening size*—largest significant opening of a non-woven geotextile as measured using Test Method D6767.

NOTE 1—Although Test Method D4751 (Apparent Opening Size) is widely used to characterize geotextiles, it may often not be sufficient for advanced filtration investigations such as those requiring consideration of the number of constriction as a significant parameter. The “bubble-point” measurement technique proposed in Test Method D6767 shall thus be preferred to AOS per Test Method D4751.

4. Summary of Practice

4.1 The physical properties of the geotextile are evaluated according to specific procedures and the number of constriction m is determined based on Eq 1.

5. Significance and Use

5.1 This practice provides a calculation method for determining the number of constrictions m of a non-woven geotextile (or of a layer of a composite material). This standard is not

¹ This practice is under the jurisdiction of ASTM Committee D35 on Geosynthetics and is the direct responsibility of Subcommittee D35.03 on Permeability and Filtration.

Current edition approved June 1, 2016. Published June 2016. Originally published 2006. Last previous version approved 2011 as D7178 – 06 (2011). DOI: 10.1520/D7178-16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

applicable to woven geotextiles, knitted geotextiles, heat-bonded geotextiles or any other type of geosynthetic.

5.2 The number of constriction represents the number of “windows” delimited by three or more fibers, in which soil particles could migrate. In that regard, it can be basically defined by the following equation: $m = \frac{t}{d_c}$ where t is the thickness and d_c the average distance between two constrictions. This value has been found to be relevant to explain the different filtration behaviors of non-woven geotextiles with similar opening sizes but different structures for various soil conditions (see [Appendix X1](#) for details).

5.3 This value will be used in filtration research to evaluate the prediction of filtration efficiency and effectiveness of various non-woven geotextiles with similar opening sizes (Test Method [D6767](#)).

5.4 Interpretation of the significance of m as calculated using this standard shall be done with care as some non-woven structures may not reflect the hypothesis used to establish the proposed equation (see [Appendix X1](#) for details).

6. Procedure

6.1 Condition specimens at $23 \pm 2^\circ\text{C}$ and 65 % relative humidity for not less than 24 h.

6.2 Determine the mass per unit area and thickness of the geotextile according to Test Methods [D5261](#) and [D5199](#).

NOTE 2—Although the thickness of non-woven geotextiles is influenced by the normal load, the number of constriction shall be calculated considering the geotextile thickness under 2 kPa for standardization purpose. Practically, the number of constriction is not influenced by the thickness as it represents the structure of the non-woven (number of “windows” delimited by three or more fibers, in which soil particles could migrate as defined in [5.2](#)), which does not depend on the normal load.

6.3 Determine the fiber count of the fibers per Test Methods [D1577](#) using the data available from MQA or suppliers certificate. Report values by classes of average fiber count associated to the type of polymer as well as the percentage of each class found in the geotextile sample (that is, respective percentages of polypropylene / xx tex, polypropylene / yy tex, polyester / zz tex, etc.).

6.3.1 Calculate the number of constrictions m of the geotextile using [Eq 1](#) (dimensionless value). Result must be rounded to the closest unit.

$$m_i = \frac{1}{2} \times \sqrt{\pi \cdot \mu_i \cdot t_i} \times \sum_k p_k \cdot \sqrt{\frac{1}{T_k}} \quad (1)$$

where:

- i = specimen number,
- m_i = number of constriction for the geotextile specimen i ,
- μ_i = mass per unit area of the geotextile specimen i (g/m^2) as measured in [6.2](#),
- t_i = thickness of the geotextile specimen i (mm) as measured in [6.2](#),
- k = class of fibers with a given fiber count and type of polymer,
- p_k = percentage (in decimal unit, that is, 10 % = 0.1) of fibers from a class of fibers k , and
- T_k = fiber count (tex) associated to a class of fibers k as measured in [6.3](#).

NOTE 3—If the fiber count T_k is available in Denier, divide the available value by 9 to obtain the value in Tex.

7. Report

7.1 Report the following information:

7.1.1 State that the number of constriction was calculated as directed in Practice [D7178](#);

7.1.2 Complete geotextile identification;

7.1.3 Statement of conditioning;

7.1.4 Thickness and mass per unit area of the geotextile: individual values and average;

7.1.5 Fiber count distribution / polymer as evaluated in [6.3](#). If it was assumed that only one type of polymer was used to manufacture the geotextile, state this on report;

7.1.6 Number of constriction as calculated in [6.3.1](#); and

7.1.7 Report any deviation from the described standard practice.

8. Precision and Bias

8.1 Precision and bias has not been established yet.

9. Keywords

9.1 clogging; constriction; filtration; geotextile; mechanically bonded; non-woven; number of constrictions; opening size; piping