



Designation: D3487 – 16

Standard Specification for Mineral Insulating Oil Used in Electrical Apparatus¹

This standard is issued under the fixed designation D3487; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers unused mineral insulating oil of petroleum origin for use as an insulating and cooling medium in new and existing power and distribution electrical apparatus, such as transformers, regulators, reactors, circuit breakers, switchgear, and attendant equipment.

1.2 This specification is intended to define a mineral insulating oil that is functionally interchangeable and miscible with existing oils, is compatible with existing apparatus and with appropriate field maintenance,² and will satisfactorily maintain its functional characteristics in its application in electrical equipment. This specification applies only to new insulating oil as received prior to any processing.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

2. Referenced Documents

2.1 ASTM Standards:³

- D92 Test Method for Flash and Fire Points by Cleveland Open Cup Tester
- D97 Test Method for Pour Point of Petroleum Products
- D117 Guide for Sampling, Test Methods, and Specifications for Electrical Insulating Oils of Petroleum Origin
- D445 Test Method for Kinematic Viscosity of Transparent and Opaque Liquids (and Calculation of Dynamic Viscosity)
- D611 Test Methods for Aniline Point and Mixed Aniline Point of Petroleum Products and Hydrocarbon Solvents

¹ This specification is under the jurisdiction of ASTM Committee D27 on Electrical Insulating Liquids and Gases and is the direct responsibility of Subcommittee D27.01 on Mineral.

Current edition approved June 15, 2016. Published July 2016. Originally approved in 1976. Last previous edition approved in 2009 as D3487 – 09. DOI:10.1520/D3487-16.

² Refer to the Institute of Electrical and Electronic Engineers, Inc. (IEEE) C 57.106, Guide for Acceptance and Maintenance of Insulating Oil in Equipment. Available from IEEE Operations Center, 445 Hoes Lane, Piscataway, NJ 08854-4141, USA.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- D923 Practices for Sampling Electrical Insulating Liquids
- D924 Test Method for Dissipation Factor (or Power Factor) and Relative Permittivity (Dielectric Constant) of Electrical Insulating Liquids
- D971 Test Method for Interfacial Tension of Oil Against Water by the Ring Method
- D974 Test Method for Acid and Base Number by Color-Indicator Titration
- D1275 Test Method for Corrosive Sulfur in Electrical Insulating Liquids
- D1298 Test Method for Density, Relative Density, or API Gravity of Crude Petroleum and Liquid Petroleum Products by Hydrometer Method
- D1500 Test Method for ASTM Color of Petroleum Products (ASTM Color Scale)
- D1524 Test Method for Visual Examination of Used Electrical Insulating Liquids in the Field
- D1533 Test Method for Water in Insulating Liquids by Coulometric Karl Fischer Titration
- D1816 Test Method for Dielectric Breakdown Voltage of Insulating Liquids Using VDE Electrodes
- D1903 Practice for Determining the Coefficient of Thermal Expansion of Electrical Insulating Liquids of Petroleum Origin, and Askarels
- D2112 Test Method for Oxidation Stability of Inhibited Mineral Insulating Oil by Pressure Vessel
- D2300 Test Method for Gassing of Electrical Insulating Liquids Under Electrical Stress and Ionization (Modified Pirelli Method)
- D2440 Test Method for Oxidation Stability of Mineral Insulating Oil
- D2668 Test Method for 2,6-*di-tert*-Butyl- *p*-Cresol and 2,6-*di-tert*-Butyl Phenol in Electrical Insulating Oil by Infrared Absorp
- D2717 Test Method for Thermal Conductivity of Liquids
- D2766 Test Method for Specific Heat of Liquids and Solids
- D2864 Terminology Relating to Electrical Insulating Liquids and Gases
- D3300 Test Method for Dielectric Breakdown Voltage of Insulating Oils of Petroleum Origin Under Impulse Conditions
- D4052 Test Method for Density, Relative Density, and API Gravity of Liquids by Digital Density Meter

- D4059 Test Method for Analysis of Polychlorinated Biphenyls in Insulating Liquids by Gas Chromatography
- D4768 Test Method for Analysis of 2,6-Ditertiary-Butyl Para-Cresol and 2,6-Ditertiary-Butyl Phenol in Insulating Liquids by Gas Chromatography
- D5837 Test Method for Furanic Compounds in Electrical Insulating Liquids by High-Performance Liquid Chromatography (HPLC)
- D5949 Test Method for Pour Point of Petroleum Products (Automatic Pressure Pulsing Method)
- D5950 Test Method for Pour Point of Petroleum Products (Automatic Tilt Method)
- 2.2 IEEE Standard²
- C57.106 Guide for Acceptance and Maintenance of Insulating Oil in Equipment

3. Terminology

3.1 Definitions:

3.1.1 *Type I Mineral Oil*—an oil for apparatus where normal oxidation resistance is required. Some oils may require the addition of a suitable oxidation inhibitor to achieve this.

3.1.2 *Type II Mineral Oil*—an oil for apparatus where greater oxidation resistance is required. This is usually achieved with the addition of a suitable oxidation inhibitor.

3.1.2.1 *Discussion*—During processing of inhibited mineral oil under vacuum and elevated temperatures, partial loss of inhibitor and volatile portions of mineral oil may occur. The common inhibitors, 2,6-ditertiary-butyl para-cresol (DBPC/BHT) and 2,6-ditertiary-butyl phenol (DPB), are more volatile than transformer oil. If processing conditions are too severe, oxidation stability of the oil may be decreased due to loss of inhibitor. The selectivity for removal of moisture and air in preference to loss of inhibitor and oil is improved by use of a low processing temperature.

Conditions that have been found satisfactory for most inhibited mineral oil processing are:

Temperature, °C	Minimum Pressure	
	Pa	Torr, Approximate
40	5	0.04
50	10	0.075
60	20	0.15
70	40	0.3
80	100	0.75
90	400	3.0
100	1000	7.5

If temperatures higher than those recommended for the operating pressure are used, the oil should be tested for inhibitor content and inhibitor added as necessary to return inhibitor content to its initial value. Attempts to dry apparatus containing appreciable amounts of free water may result in a significant loss of inhibitor even at the conditions recommended above.

3.1.3 *additives*—chemical substances that are added to mineral insulating oil to achieve required functional properties.

3.1.4 *properties*—those properties of the mineral insulating oil which are required for the design, manufacture, and operation of the apparatus. These properties are listed in Section 5.

3.2 Other definitions of terms related to this specification are given in Terminology D2864.

3.3 More information on tests related to this specification can be found in Guide D117.

4. Sampling and Testing

4.1 Take all oil samples in accordance with Practices D923.

4.2 Make each test in accordance with the latest revision of the ASTM test method specified in Section 5.

4.3 The oil shall meet the requirements of Section 5 at the unloading point.

NOTE 1—Because of the different needs of the various users, items relating to packaging, labeling, and inspection are considered to be subject to supplier and user agreement.

NOTE 2—In addition to all other tests listed herein, it is sound engineering practice for the apparatus manufacturer to perform an evaluation of new types of insulating oils in insulation systems, prototype structures, or full-scale apparatus, or any combination thereof, to assure suitable service life.

4.4 Make known to the user the generic type and amount of any additive used, for assessing any potential detrimental reaction with other materials in contact with the oil.

5. Property Requirements

5.1 Mineral insulating oil conforming to this specification shall meet the property limits given in Table 1. The significance of these properties is discussed in Appendix X2.