



Designation: ~~D3774–96 (Reapproved 2012)~~ D3774 – 96 (Reapproved 2016)

Standard Test Method for Width of Textile Fabric¹

This standard is issued under the fixed designation D3774; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This test method covers the measurement of the width of fabrics, pile or napped surface width, or both. The method is applicable to full rolls, bolts of fabric, and short specimens removed from a roll or bolt. Unless otherwise specified, measurements shall include the selvages when present.

1.2 The method offers two options:

1.2.1 *Option A*—Full Roll or Bolt.

1.2.2 *Option B*—Short Specimen Removed from Full Roll or Bolt.

1.3 The values stated in either SI units or U.S. customary units are to be regarded as standard. The U.S. customary units may be approximate.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D123 Terminology Relating to Textiles](#)

[D1776 Practice for Conditioning and Testing Textiles](#)

2.2 *Other Standard:*

[ANSI/ASQC Z1.4—Inspection by Attributes](#)³

3. Terminology

3.1 The following terms are relevant to this standard: width, *of a fabric*; width, *of a raised-surface fabric*; width, *of a fabric woven on a shuttleless loom*.

3.2 For definitions of all other textile terms see Terminology [D123](#).

4. Summary of Test Method

4.1 The width of the fabric is measured directly by using a metal rule.

4.2 Option A offers two procedures for the measurement of fabric width, or pile width or napped surface width, or both, in full rolls or bolts. The first procedure is essentially a tension-free method, the second procedure provides for measurements made during finishing or inspection operations that may impart tension to the fabric.

4.3 Option B covers the measurement of fabric width, pile surface width or napped surface width, or both, when only a short length of fabric is available for testing. This procedure is applicable when a small swatch of fabric is sent to the laboratory to be used as the test specimen.

¹ This test method are under the jurisdiction of ASTM Committee [D13](#) on Textiles and are the direct responsibility of Subcommittee [D13.60](#) on Fabric Test Methods, Specific.

Current edition approved ~~July 1, 2012~~ July 1, 2016. Published ~~August 2012~~ July 2016. Replaces Sections 13 to 17 of Methods D1910 – 89, Test for Construction Characteristics of Woven Fabrics. Originally approved in 1996. Last previous edition approved in ~~2008~~ 2012 as ~~D3774–96(2008)~~ [D3774–96\(2012\)](#).¹ DOI: ~~10.1520/D3774-96R12~~ 10.1520/D3774-96R16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

5. Significance and Use

5.1 Option A procedures of Test Method D3774 for width are considered satisfactory for acceptance testing of commercial shipments because they are used extensively in the trade.

5.1.1 In case of a dispute arising from differences in reported test values when using Test Method D3774 for acceptance testing of commercial shipments, the purchaser and the supplier should conduct comparative tests to determine if there is a statistical bias between their laboratories. Competent statistical assistance is recommended for the investigation of bias. As a minimum, the two parties should take a group of test specimens which are as homogeneous as possible and which are from a lot of material of the type in question. The test specimens should then be randomly assigned in equal numbers to each laboratory for testing. The average results from the two laboratories should be compared using Student's *t*-test for unpaired data and an acceptable probability level chosen by the two parties before testing is begun. If a bias is found, either its cause must be found and corrected or the purchaser and the supplier must agree to interpret future test results in the light of the known bias.

6. Apparatus

6.1 Measuring device, metre (yard) stick or steel tape having 1-mm ($\frac{1}{16}$ -in.) graduations and a length that is greater than the width of fabric to be measured.

7. Sampling

7.1 As a lot sample for acceptance testing, take at random the number of rolls of fabric as directed in an applicable material specification or other agreement between the purchaser and the supplier.

7.2 For Option A, consider rolls of fabric to be the primary sampling units. Consider the rolls of fabric in the lot sample as the laboratory sample and the points at which measurements are made within the rolls as test specimens.

7.3 For Option B, cut a full width swatch at least 2 m (2 yd) long from each lot sampling unit as a laboratory sampling unit, taking care that the weave is not distorted within the swatches. Consider the points at which the measurements are made within the swatch as test specimens. This option is not suitable for acceptance testing because the results are applicable to that swatch only.

8. Conditioning

8.1 Condition the specimens as directed in Practice **D1776**.

8.2 When full rolls or bolts of fabric cannot be properly conditioned in a reasonable time with available facilities, perform the tests without conditioning and report the actual conditions prevailing at the time of the test. Such results may not correspond with the results obtained after testing conditioned specimens in the standard atmosphere for testing textiles.

9. Procedure

9.1 Make all measurements, when possible, in the standard atmosphere for testing textiles, which is $21 \pm 1^\circ\text{C}$ ($70 \pm 2^\circ\text{F}$) and $65 \pm 2\%$ relative humidity.

9.2 *Option A—Full Roll or Bolt:*

9.2.1 *Free of Tension*—Lay the fabric on a smooth horizontal surface without tension in any direction. Measure the width as defined in **D123** to the nearest 1 mm ($\frac{1}{16}$ in.), perpendicular to the selvages using the measuring device or steel tape. Take the measurement in at least five widely spaced places along the length of the roll or bolt. Make no measurement within 1 m (1 yd) of the ends of the roll or bolt. When specified, measurements of width of pile or napped surfaces may be made at the same time. Calculate and record the average of all measurements to the nearest 1 mm ($\frac{1}{16}$ in). Record the minimum and maximum values for each roll and for the lot.

9.2.2 *Running Under Tension*—When agreed upon by all parties concerned, take five measurements of width to the nearest 1 mm ($\frac{1}{16}$ in.) at any convenient time during the finishing or inspection operations using the measuring device. Make no measurement within 1 m (1 yd) of the ends of the roll or bolt. When specified, measurements of width of pile or napped surfaces may be made at the same time. Calculate and record the average of all measurements to the nearest 1 mm ($\frac{1}{16}$ in). Record the minimum and maximum values for each roll and for the lot.

9.3 *Option B—Laboratory Sample Removed From Full Roll or Bolt:*

9.3.1 Lay the fabric on a smooth horizontal surface without tension in any direction and free of wrinkles or distortion. Measure the width of the fabric as defined in **3.1** at three or more points separated by at least 0.3 m (1 ft) along the length of the fabric. Do not make measurements closer than 150 mm (6 in.) to the cut ends. Calculate the average of all measurements on the specimen to the nearest 1 mm ($\frac{1}{16}$ in.). Record the average measurement, the maximum measurement, and the minimum measurement.

10. Report

10.1 State that the specimen was tested as directed in Test Method D3774. Describe the material or product sampled and the source of each specimen.