
Petroleum and natural gas industries - Steel pipes for use as casing or tubing for wells (ISO 11960:1996)

Petroleum and natural gas industries - Steel pipes for use as casing or tubing for wells (ISO 11960:1996)

Erdöl- und Erdgasindustrien - Stahlrohre zur Verwendung als Futter- oder Steigrohre für Bohrungen (ISO 11960:1996)

Industries du pétrole et du gaz naturel - Tubes en acier utilisés comme tubes de cuvelage ou tubes de production dans les puits (ISO 11960:1996)

<https://standards.iteh.ai/catalog/standards/sist/11778d95-ba89-4c59-82fe-a13986930c99/sist-en-iso-11960-2001>

Ta slovenski standard je istoveten z: EN ISO 11960:1998

ICS:

75.180.10	Oprema za raziskovanje in odkopavanje	Exploratory and extraction equipment
77.140.75	Jeklene cevi in cevni profili za posebne namene	Steel pipes and tubes for specific use

SIST EN ISO 11960:2001**en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 11960:2001

<https://standards.iteh.ai/catalog/standards/sist/11778d95-ba89-4c59-82fe-a13986930c99/sist-en-iso-11960-2001>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 11960

January 1998

ICS 75.180.10; 77.140.70

Descriptors: see ISO document

English version

Petroleum and natural gas industries - Steel pipes for use as
casing or tubing for wells (ISO 11960:1996)

Industries du pétrole et du gaz naturel - Tubes en acier
utilisés comme tubes de cuvelage ou tubes de production
dans les puits (ISO 11960:1996)

Erdöl- und Erdgasindustrien - Stahlrohre zu Verwendung
als Futter- oder Steigrohre für Bohrungen (ISO
11960:1996)

This European Standard was approved by CEN on 23 November 1997.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/11778d95-ba89-4c59-82fe-a13986930c99/sist-en-iso-11960-2001>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Page 2
EN ISO 11960:1998

Foreword

The text of the International Standard from Technical Committee ISO/TC 67 "Materials, equipment and offshore structures for petroleum and natural gas industries" of the International Organization for Standardization (ISO) has been taken over as an European Standard by Technical Committee CEN/TC 12 "Materials, equipment and offshore structures for petroleum and natural gas industries", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 1998, and conflicting national standards shall be withdrawn at the latest by July 1998.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 11960:1996 has been approved by CEN as a European Standard without any modification.

(standards.iteh.ai)

SIST EN ISO 11960:2001

<https://standards.iteh.ai/catalog/standards/sist/11778d95-ba89-4c59-82fe-a13986930c99/sist-en-iso-11960-2001>



INTERNATIONAL
STANDARD

ISO
11960

First edition
1996-07-01

**Petroleum and natural gas industries —
Steel pipes for use as casing or tubing for
wells**

iTeh STANDARD PREVIEW

(standards.iteh.ai)

*Industries du pétrole et du gaz naturel — Tubes en acier utilisés comme
tubes de cuvelage ou tubes de production dans les puits*

SIST EN ISO 11960:2001

<https://standards.iteh.ai/catalog/standards/sist/11778d95-ba89-4c59-82fe-a13986930c99/sist-en-iso-11960-2001>



Reference number
ISO 11960:1996(E)

Contents

	Page
1 Scope.....	1
2 Normative references.....	1
3 Definitions	2
4 Information to be supplied by the purchaser.....	3
4.1 Casing.....	3
4.2 Tubing.....	4
5 Process of manufacture	5
5.1 General.....	5
5.2 Heat treatment.....	5
5.3 Straightening	6
5.4 Traceability	6
6 Material requirements	6
6.1 Chemical requirements	6
6.2 Mechanical properties requirements.....	6
7 Dimensions, masses, tolerances and pipe ends	21
7.1 Dimensions and masses	21
7.2 Diameter.....	21
7.3 Wall thickness	21
7.4 Mass.....	21
7.5 Length	33
7.6 Casing jointers.....	33
7.7 Height and trim of electric weld flash	33
7.8 Straightness	34
7.9 Drift requirements.....	34
7.10 Tolerances on dimensions and masses	34
7.11 Pipe ends.....	35

© ISO 1996

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

7.12	Coupling make-up and thread protection	36
8	Couplings	36
8.1	Material	36
8.2	Process of manufacture	37
8.3	Performance properties	37
8.4	Mechanical properties	37
8.5	Dimensions and tolerances	37
8.6	Regular couplings	37
8.7	Special clearance couplings — Groups 1, 2 and 3	39
8.8	Combination couplings	39
8.9	Reducing couplings	40
8.10	Seal-ring couplings	40
8.11	Special bevel couplings — Groups 1, 2 and 3	40
8.12	Threading	40
8.13	Surface inspection	40
8.14	Measurement of imperfection	40
8.15	Repair and removal of imperfections and defects	41
8.16	Thread plating — Group 4	41
8.17	Couplings and coupling blank protection — Group 4	41
9	Inspection and testing	41
9.1	General	41
9.2	Testing of chemical composition	42
9.3	Testing of mechanical and technological properties	43
9.4	Hydrostatic test	49
9.5	Dimensional testing	51
9.6	Visual inspection	53
9.7	Non-destructive inspection	53
9.8	Test methods and results	55
9.9	Invalidation of tests	57
9.10	Retests	57
10	Marking	58
10.1	General	58
10.2	Couplings and connectors	59
10.3	Pipe and pup-joints	59
10.4	Die-stamp marking requirements	61
10.5	Die-stamp marking placement	61
10.6	Paint-stencil marking	62
10.7	Colour code identification — All groups	62

iTeh STANDARD PREVIEW
 (standards.iteh.ai)
<https://standards.iteh.ai/catalog/standards/sist/11778d95-ba89-4c59-82fe-a13986930c99/sist-en-iso-11960-2001>

10.8	Thread marking — All groups	62
10.9	Triangle make-up marking	63
10.10	Pipe processor markings — All groups	63
10.11	Alternate drift casing markings — All groups	63
11	Coating and protection	63
11.1	Coatings — All groups	63
11.2	Thread protectors	63
12	Documents	64
12.1	Certification	64
12.2	Certification requirements — Group 4	64
12.3	Groups 1, 2 and 3	64
12.4	Retention of records	64
Annexes		
A	Dimensions and end finish	65
B	Supplementary requirements	70
C	Purchaser inspection	86
D	Bibliography	87

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 11960:2001](https://standards.iteh.ai/catalog/standards/sist/11778d95-ba89-4c59-82fe-a13986930c99/sist-en-iso-11960-2001)

<https://standards.iteh.ai/catalog/standards/sist/11778d95-ba89-4c59-82fe-a13986930c99/sist-en-iso-11960-2001>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

iTeh STANDARD PREVIEW

International Standard ISO 11960 was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum and natural gas industries*, Subcommittee SC 5, *Casing, tubing and drill pipe*.

<https://standards.iteh.ai/catalog/standards/sist/11778d95-0a89-4c59-821c-a15986950c99/sist-en-iso-11960-2001>
SIST EN ISO 11960:2001
This first edition cancels and replaces ISO 2645:1975, which has been technically revised.

Annexes A, B and C form an integral part of this International Standard. Annex D is for information only.

Introduction

This International Standard includes requirements of various nature. These are identified by the use of certain words or phrases.

- **Shall** is used to indicate that a provision is mandatory.
- **Should** is used to indicate that a provision is not mandatory, but recommended as good practice.
- **May** is used to indicate that a provision is optional.

In addition, in certain cases, this International Standard offers **Alternative requirements**. These offer different options, either:

- **At purchaser's discretion** in which case such option shall be mentioned on the purchase order. These cases are recognized by the use of the words or phrases such as **alternative** or **at purchaser's discretion**.
- **At manufacturer's discretion** in which case such option shall be notified to the purchaser. Such cases are identified by the use of the phrase **at manufacturer's discretion**.
- **By agreement between purchaser and manufacturer**. Such cases are recognized by the use of the phrase **by agreement between interested parties**.

This International Standard, when this phrase is used, intends to

either

waive the application of a requirement (either mandatory or recommended) and leave it to both purchaser and manufacturer to use the requirement or not;

or

offer one (or several) alternative requirement(s), the selection of which is left to both purchaser and manufacturer.

Petroleum and natural gas industries — Steel pipes for use as casing or tubing for wells

1 Scope

1.1 This International Standard specifies the technical delivery conditions for steel pipes (casing, tubing and liners), pup-joints and connectors.

This International Standard is applicable to the following connections in accordance with ISO 10422:

- short, round-thread casing;
- long, round-thread casing;
- buttress-thread casing;
- extreme-line casing;
- non-upset tubing;
- external-upset tubing;
- integral-joint tubing.

The applicable types of end finishing for each size are described in annex A (tables A.1 to A.3).

For such connections, this International Standard specifies the technical delivery conditions for couplings and thread protection.

Threading requirements are not considered in this International Standard. Dimensional requirements on threads and thread gauges, stipulations on gauging practice, gauge specifications, as well as instruments and methods for inspection of threads are given in ISO 10422.

This International Standard may also be used for tubulars with connections not covered by ISO standards.

1.2 The products described by this International Standard are gathered in four groups as follows.

- Group 1: all casing and tubing in grades H, J, K and N.
- Group 2: all casing and tubing in restricted yield strength grades C, L and T.
- Group 3: all seamless casing and tubing and 139,70 mm and larger electric-welded (EW) casing in high strength grade P.
- Group 4: all special service casing in grade Q.

1.3 Supplementary requirements, that may be agreed between interested parties, for non-destructive inspection, coupling blanks, upset casing, electric-welded casing, impact testing, seal-ring couplings and certificates are specified in annex B.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers currently valid International Standards.

ISO 31-0:1992, *Quantities and units — Part 0: General principles*.

ISO 643:1983, *Steels — Micrographic determination of the ferritic or austenitic grain size*.

ISO 6506:1981, *Metallic materials — Hardness test — Brinell test*.

ISO 6508:1986, *Metallic materials — Hardness test — Rockwell test (scales A - B - C - D - E - F - G - H - K)*.

ISO 6892:1984, *Metallic materials — Tensile testing*.

ISO 7500-1:1986, *Metallic materials — Verification of static uniaxial testing machines — Part 1: Tensile testing machines*.

ISO 10422:1993, *Petroleum and natural gas industries — Threading, gauging, and thread inspection of casing, tubing and line pipe threads — Specification*.

ISO/TR 9769:1991, *Steel and iron — Review of available methods of analysis*.

API Bul 5A2:1988, *Bulletin on Thread Compounds for Casing, Tubing and Line Pipe*.

API Bul 5C2:1987, *Bulletin on Performance Properties of Casing, Tubing and Drill Pipe*.

ASTM A370-92, *Test Methods and Definitions for Mechanical Testing of Steel Products*.

ASTM A919-84 (1993), *Terminology relating to Heat Treatment of Metals*.

ASTM E23-94a, *Test Methods for Notched Bar Impact Testing of Metallic Materials*.

ASTM E83-94, *Practice for Verification and Classification of Extensometers*.

ASTM E165-94, *Practice for Liquid Penetrant Inspection*.

ASTM E213-93, *Practice for Ultrasonic Inspection of Metal Pipe and Tubing*.

ASTM E273-93, *Practice for Ultrasonic Examination of Longitudinal Welded Pipe and Tubing*.

ASTM E309-93a, *Practice for Eddy-Current Examination of Steel Tubular Products Using Magnetic Saturation*.

ASTM E570-91, *Practice for Flux Leakage Examination of Ferromagnetic Steel Tubular Products*.

ASTM E709-95, *Practice for Magnetic Particle Examination*.

NACE TM-01-77:1986, *Testing of Metals for Resistance to Sulfide Stress Cracking at Ambient Temperature*.

ASNT-TC-1A:1984, *Recommended Practice for Certification of NDT Personnel*.

3 Definitions

For all terms related to heat treatment operations, the definitions in ASTM A919 apply.

For the purposes of this International Standard, the following definitions apply.

3.1 product: Pipe, coupling, connector, coupling stock and coupling blank, either individually or collectively as applicable.

3.2 connection: Threaded assembly of tubular components.

3.3 pipe: Casing, tubing, plain-end casing liners, pup-joints and connectors, individually or as a group, as applicable.

3.4 coupling: Internally threaded cylinder for joining two lengths of threaded pipe.

3.5 connector: One-piece tubular section not including pipe or couplings, used for the purpose of joining or changing from one size, mass or type of thread connection to the same or another size, mass or type of threaded connection.

3.6 coupling stock: Tubular component used for the manufacture of coupling blanks.

3.7 coupling blank: Material used to produce an individual coupling.

NOTE 1 Coupling blanks may be obtained from coupling stock, forgings or centrifugal castings.

3.8 casing: A pipe run from the surface and intended to line the walls of a drilled well.

3.9 tubing: A pipe placed within a well to produce well fluids or to inject fluids.

3.10 plain-end casing liner: Casing provided unthreaded with a wall thickness often greater than that specified for J55.

3.11 pup-joint: Length of casing, tubing or plain-end casing liner shorter than Range 1.

3.12 seamless pipe: A wrought steel tubular product made without a welded seam, manufactured by hot working steel and, if necessary, by subsequently cold finishing the hot-worked tubular product to produce the desired shape, dimensions and properties.

3.13 electric-welded pipe: Pipe having one longitudinal seam formed by electric-resistance or electric-induction welding, without the addition of filler metal, wherein the edges to be welded are mechanically pressed together and the heat for welding is generated by the resistance to flow of electric current.

3.14 thread protector: Cap or insert used to protect threads and seals during handling, transportation and storage.

3.15 special processes: Final operations which are performed during pipe manufacturing that affect product attributes, except chemistry and dimensions.

NOTE 2 The special processes are:

Manufacturing condition	Special processes
Seamless: as-rolled	Final reheating practice and hot sizing or stretch reducing. If applicable, upsetting, cold finishing.
heat treated	Heat treatment
Electric welded: as-rolled	Sizing and seam welding. If applicable, seam heat treatment and upsetting.
heat treated	Seam welding and full body heat treatment

3.16 interested parties: The manufacturer and the purchaser of the products.

4 Information to be supplied by the purchaser

4.1 Casing

4.1.1 In placing orders for pipe to be manufactured in accordance with this International Standard, the purchaser shall specify the following on the purchase order.

Stipulation	Section
International Standard ISO 11960	—
Quantity	—
Type of pipe or couplings:	
Casing	
Threaded or plain-end	7.11
Type of connection — round (short or long), buttress, extreme-line threads, or other connection	table A.1, 7.11
With or without couplings	7.11
Special clearance couplings	tables 27, 28, A.1, 8.7
Liners	table A.2, 7.11
Size designation or outside diameter	tables A.1, A.2
Nominal mass or wall thickness	tables A.1, A.2
Grade and type where applicable	tables A.1, A.2
Length range	7.5, table 24
Seamless or electric welded	5.1, table 1
Material certification	12.1, SR15
Delivery date and shipping instructions	—
Inspection by purchaser	annex C

4.1.2 The purchaser should also state on the purchase order his requirements concerning the following stipulations, which are optional with the purchaser.

Stipulation	Section
Heat treatment	5.2
Heat and supplementary analyses	9.2
Casing jointers	7.6
Casing with couplings detached	7.12
Alternate drifting requirements	7.9
Coupling make-up (other than power-tight)	7.12
Pipe coatings	11.1
Seal-ring couplings	8.10, SR13.1, SR13.2
Coupling blanks	8.1, SR9
Statistical impact testing — Q125 grade	6.2.3.6, SR12
Additional markings	clause 10

4.1.3 The following stipulations are subject to agreement between interested parties.

Stipulation	Section
Hydrostatic pressure test for handling-tight make-up, connectors and group 4 pup-joints	9.4
Alternate hydrostatic test pressures	9.4
Thread and storage compound	7.12
Thread protectors	11.2
Marking requirements	10.1
Non-destructive inspection	9.7, SR1, SR2 and SR11
Alternate chemical analysis procedures — Q125 grade	9.2
Reduced section tensile specimens — Q125 grade	9.3.3
Alternate F factor in SR12 — Q125 grade	SR12.2
Cold rotary straightening — Q125 grade	5.3

Coupling blanks — Q125 grade only	SR9
Upset casing — Q125 grade only	SR10
Electric-welded casing — P110 and Q125 grade	SR11
Supplementary Coupling thread plating — Q125 grade only Sulfide stress cracking test — C90 and T95 grade Additional hardness testing — C90 and T95 grade	8.16 6.2.13 9.3.2.3
Quality assurance requirements (e.g. one of the ISO 9000 series)	—

4.2 Tubing

4.2.1 In placing orders for pipe to be manufactured in accordance with this International Standard, the purchaser shall specify the following on the purchase order.

Stipulation	Section
International Standard ISO 11960	—
Quantity	—
Type of pipe or couplings:	
Tubing	
Non-upset, external-upset or integral-joint	table A.3
Threaded, plain-end, or special end	7.11
With or without couplings	7.11
Special bevel couplings	tables A.3 and 30, 8.11
Special clearance couplings	tables A.3, 29, 30, 8.7
Size designation or outside diameter	table A.3
Nominal mass or wall thickness	table A.3
Grade	table A.3
Length range	7.5, table 24
Seamless or electric welded	5.1, table 1
Material certification	12.1, SR15
Delivery date and shipping instructions	—
Inspection by purchaser	annex C

4.2.2 The purchaser should also state on the purchase order his requirements concerning the following stipulations, which are optional with the purchaser.

Stipulation	Section
Heat treatment	5.2
Heat and supplementary analyses	9.2
Coupling make-up (other than power-tight)	7.12
Pipe coatings	11.1
Seal-ring couplings	8.10, SR13.1, SR13.2
Tubing with couplings detached	7.12
Additional markings	clause 10

4.2.3 The following stipulations are subject to agreement between interested parties.

Stipulation	Section
Hydrostatic pressure test for handling-tight make-up and pup-joints	9.4
Alternate hydrostatic test pressures	9.4
Thread and storage compound	7.12
Thread protectors	11.2
Marking requirements	10.1
Non-destructive inspection	9.7, SR1, SR2 and SR11
Supplementary Sulfide stress cracking test — C90 and T95 grade Additional hardness testing — C90 and T95 grade	6.2.13 9.3.2.3
Quality assurance requirements (e.g. one of the ISO 9000 series)	—

5 Process of manufacture

5.1 General

The various grades and groups of pipe furnished according to this International Standard shall be made to a fine grain practice. Steel made to a fine grain practice contains one or more grain refining elements, such as aluminium, niobium, vanadium or titanium in amounts intended to result in the steel having a fine austenitic grain size.

Pipe furnished according to this International Standard shall be made by the seamless or electric weld process as shown in table 1 and as specified on the purchase order. Pup-joints and connectors may be made from standard casing or tubing or by machining heavy wall casing, tubing or bar stock. Couplings shall be manufactured by one of the processes listed in 8.2. Cold-drawn tubular products without appropriate heat treatment are not acceptable.

5.2 Heat treatment

5.2.1 General

Product shall be heat treated in accordance with a documented procedure as stipulated in table 1 for the particular grade and type specified on the purchase order. Heat-treated upset pipe shall be heat treated the full length after upsetting. Pipe and coupling stock requiring heat treatment shall be heat treated the full length. Individually heat-treated coupling blanks are acceptable. All pipe processed through a hot stretch mill (i.e., stretch reduced) shall be considered normalized, provided the exit temperature be above the upper critical temperature (A_{r3}) for the steel being processed, and the pipe be air cooled.

The weld seam of electric-welded pipe shall be heat treated after welding to a minimum temperature of 538 °C or processed in such a manner that no untempered martensite remains.

NOTE 3 A_{r3} refers to the critical temperature for the austenite-to-ferrite transformation on cooling.

5.2.2 Group 1

Grade N80 pipe and coupling stock shall be normalized or, at the manufacturer's discretion, shall be normalized and tempered. Grade N80Q pipe and coupling stock shall be quenched and tempered (including the interrupted quenching followed by controlled cooling method) the full length. Grade J55 and K55 casing and grade J55 tubing shall be heat treated if so specified on the purchase order.

NOTES

4 Interrupted quenching is quenching in which the pipe being quenched is removed from the quenching medium while the pipe is at a temperature substantially higher than that of the quenching medium.

5 Controlled cooling is cooling from an elevated temperature in a predetermined manner to avoid hardening, cracking or internal damage to produce a desired microstructure or mechanical properties.

Table 1 — Process of manufacture and heat treatment

Group	Grade	Type	Manufacturing process ¹⁾	Heat treatment	Tempering temperature min. °C
1	H40	—	S or EW	none	—
	J55	—	S or EW	none 2)	—
	K55	—	S or EW	none 2)	—
	N80	—	S or EW	3)	—
	N80	Q	S or EW	Q and T	—
2	L80 ⁴⁾	1	S or EW	Q and T	566
	L80	9Cr	S	Q and T ⁵⁾	593
	L80	13Cr	S	Q and T ⁵⁾	593
	C90	1	S	Q and T	621
	C90	2	S	Q and T	621
	C95	—	S or EW	Q and T	538
	T95	1	S	Q and T	649
T95	2	S	Q and T	649	
3	P110	—	S or EW ^{6, 7)}	Q and T	—
4	Q125	1	S or EW ⁷⁾	Q and T	—
	Q125	2	S or EW ⁷⁾	Q and T	—
	Q125	3	S or EW ⁷⁾	Q and T	—
	Q125	4	S or EW ⁷⁾	Q and T	—

1) S = seamless process; EW = electric welded process.
 2) Full-length normalized, normalized and tempered (N and T), or quenched and tempered (Q and T), at the manufacturer's discretion or if so specified on the purchaser order.
 3) Full-length normalized or normalized and tempered at the manufacturer's discretion.
 4) The manufacturer shall use a process that is documented to yield not less than 50 % martensite.
 5) Type 9Cr and 13Cr may be air quenched.
 6) Special chemical requirements for electric-welded P110 casing are specified in table 2.
 7) Special requirements unique to electric-welded P110 and Q125 casing are specified in annex B (SR11). When electric-welded P110 and Q125 casing is furnished, the provisions of SR11 are automatically in effect.

5.2.3 Group 2

When requested by the purchaser, the manufacturer shall produce evidence to show that the tempering practice will result in the pipe attaining the minimum tempering temperature.

5.2.4 Groups 3 and 4

Pipe and couplings furnished to this International Standard shall be quenched and tempered.