

Designation: D5064 - 07 (Reapproved 2012) D5064 - 16

Standard Practice for Conducting a Patch Test to Assess Coating Compatibility¹

This standard is issued under the fixed designation D5064; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers the procedures for testing assessing coating compatibility when maintenance of an in-place coating system is being contemplated. It does not eoveraddress procedures for assessing the integrity of the existing coating to determine if it can be repainted, nor does it establish the compatibility of the maintenance coating system with the substrate or corrosion products. The practice is intended for use in the field. SSPC-TU 3 discusses the risks associated with the maintenance painting practice known as overcoating.

Note 1—Pass-Fail Criteria (for example, adhesion requirements) are not established by this practice. These should be established by the user or specifier with input from the supplier.coating manufacturer.

- 1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.
- 1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:²

D16 Terminology for Paint, Related Coatings, Materials, and Applications

D3359 Test Methods for Measuring Adhesion by Tape Test

D4138 Practices for Measurement of Dry Film Thickness of Protective Coating Systems by Destructive, Cross-Sectioning Means

D4414 Practice for Measurement of Wet Film Thickness by Notch Gages

D4541 Test Method for Pull-Off Strength of Coatings Using Portable Adhesion Testers

D6132 Test Method for Nondestructive Measurement of Dry Film Thickness of Applied Organic Coatings Using an Ultrasonic Coating Thickness Gage D6677 Test Method for Evaluating Adhesion by Knife a877fc-0/32-4b6d-a8d8-ea95e9533dd9/astm-d5064-16

D7091 Practice for Nondestructive Measurement of Dry Film Thickness of Nonmagnetic Coatings Applied to Ferrous Metals and Nonmagnetic, Nonconductive Coatings Applied to Non-Ferrous Metals

D7234 Test Method for Pull-Off Adhesion Strength of Coatings on Concrete Using Portable Pull-Off Adhesion Testers 2.2 SSPC Standards:³

TU 3 Technology Update 3 Overcoating

3. Terminology

3.1 Definitions—For definitions of terms used in this practice, refer to Terminology D16.

4. Summary of Test Method

4.1 The materials under test are applied to the previously painted surface after proper-surface preparation. After the appropriate time has elapsed, the test patch is examined for visual defects and adhesion is determined assessed.

¹ This practice is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.46 on Industrial Protective Coatings.

Current edition approved June 1, 2012 July 1, 2016. Published August 2012 August 2016. Originally approved in 1990. Last previous edition approved in 2007:2012 as D5064 - 07.D5064 - 07 (2012). DOI: 10.1520/D5064-07R12.10.1520/D5064-16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's standard's Document Summary page on the ASTM website.

³ Available from Society for Protective Coatings (SSPC), 800 Trumbull Drive, Pittsburgh, PA 15205, http://www.sspc.org.