



Designation: **D4751 – 12 D4751 – 16**

Standard Test Method Methods for Determining Apparent Opening Size of a Geotextile¹

This standard is issued under the fixed designation D4751; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This test method covers the determination the apparent opening size (AOS) of a geotextile by sieving glass beads through a geotextile.

1.2 This test method shows the values in both SI units and inch-pound units. SI units is the technically correct name for the system of metric units known as the International System of Units. Inch-pound units is the technically correct name for the customary units used in the United States. The values in inch-pound units are provided for information only.

1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory requirements prior to use.

2. Referenced Documents

2.1 ASTM Standards:²

C136 Test Method for Sieve Analysis of Fine and Coarse Aggregates

D1776 Practice for Conditioning and Testing Textiles

D4238 Test Method for Electrostatic Propensity of Textiles (Withdrawn 1996)³

D4354 Practice for Sampling of Geosynthetics and Rolled Erosion Control Products (RECPs) for Testing

D4439 Terminology for Geosynthetics

E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

3. Terminology

3.1 Definitions: For general geosynthetics terms used in this standard, refer to Terminology D4439.

3.2 Definitions: <https://www.astm.org/standards/sist/718e4a5b-1a8b-4c56-98cf-5b1dc6e87ffb/astm-d4751-16>

3.2.1 apparent opening size (AOS), O_{95} , n —for a geotextile, a property that indicates the approximate largest particle that would effectively pass through the geotextile.

4. Summary of Test Method

4.1 A geotextile specimen is placed in a sieve frame, and sized glass beads are placed on the geotextile surface. The geotextile and frame are shaken laterally so that the jarring motion will induce the beads to pass through the test specimen. The procedure is repeated on the same specimen with various size glass beads until its apparent opening size has been determined.

5. Significance and Use

5.1 Using a geotextile as a medium to retain soil particles necessitates compatibility between it and the adjacent soil. This test method is used to indicate the apparent opening size in a geotextile, which reflects the approximate largest opening dimension available for soil to pass through.

¹ This test method is under the jurisdiction of ASTM Committee D35 on Geosynthetics and is the direct responsibility of Subcommittee D35.03 on Permeability and Filtration.

Current edition approved July 1, 2012/July 1, 2016. Published August 2012/August 2016. Originally approved in 1993. Last previous version approved in 2004/2012 as D4751 – 04/D4751-12. DOI: 10.1520/D4751-12.10.1520/D4751-16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

5.2 Test Method D4751 for the determination of opening size of geotextiles is acceptable for testing of commercial shipments of geotextiles. Current estimates of precision, between laboratories, are being established.

5.2.1 In case of a dispute arising from differences in reported test results when using Test Method D4751 for acceptance testing of commercial shipments, the purchaser and the supplier should conduct comparative tests to determine if there is a statistical bias between their laboratories. Competent statistical assistance is recommended for the investigation of bias. As a minimum, the two parties should take a group of test specimens that are homogeneous as possible and that are from a lot of material of the type in question. The test specimens should then be randomly assigned in equal numbers to each laboratory for testing. The average results from the two laboratories should be compared using Student's *t*-test for unpaired data and an acceptable probability level chosen by the two parties before the testing is begun. If a bias is found, either its cause must be found and corrected or the purchaser and the supplier must agree to interpret future test results in the light of the known bias.

6. Apparatus

6.1 *Mechanical Sieve Shaker*—A mechanical sieve shaker, which imparts lateral and vertical motion to the sieve, causing the particles thereon to bounce and turn so as to present different orientations to the sieving surface, should be used. The sieve shaker should be a constant frequency device utilizing a tapping *arm* to impart the proper motion to the glass beads.⁴

NOTE 1—Care should be given to the cork or rubber contact point on shakers when the vertical motion comes from an arm striking the cork or rubber. Excessive wear on the cork or rubber could affect the motion imparted to the glass beads and, therefore, the test result.

6.2 *Pan, Cover, and 200-mm (8-in.) Diameter Sieves.*

6.3 *Spherical Glass Beads*,⁵ in size fractions in accordance with Table 1. It is only necessary to have on hand the bead size fractions necessary for the range of geotextiles for which testing is anticipated. The sizing of all beads shall be verified prior to each use by sieving on the pairs of sieves shown in Table 1. Prepare at least 50 g of each size fraction to be used prior to beginning the test. Bead sizes to be used in this test method are shown in Table 1.

6.4 *Balance*, having a capacity adequate for the mass of samples anticipated and accurate to ±0.05 g.

6.5 *Static Elimination*, to prevent the accumulation of static electricity when the beads are shaken on the surface of geotextile.⁶ Commercially available devices or anti-static sprays are acceptable.

6.6 *Pan*, for collecting sieved beads.

6.7 *Flexible Rubber Template*, Either a square shaped flexible rubber template with a 203mm(8 in) diameter hole cut in it, or a 203 mm (8 in) diameter template, constructed from a durable, yet flexible material such as rubber or neoprene. This template is used to trace the 203 mm (8 in) diameter circles on the geotextile fabric for mounting into the sieves described in 6.2. (See Fig. 1)

ASTM D4751-16

³The last approved version of this historical standard is referenced on www.astm.org.

⁴A sieve shaker of this type is available from W. S. Tyler, Inc., 8200 Tyler Blvd., Mentor, OH 44060. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend.

⁵Glass beads available from Cataphote Division, Ferro Corporation, P.O. Box 2369, Jackson, MS 39205, or Potters Industries, Inc., 377-T, Route 17, Hasbrouck Heights, NJ 07604, or beads of equal quality have been found satisfactory for this purpose.

⁶Static Eliminators available from Staticmaster Ionizing Units, Model #2U500, Nuclear Products Co., P.O. Box 5178, El Monte, CA 91733, or Western Static Eliminators Co., 215-219 S. Western Avenue, Chicago, IL 60612, have been found satisfactory for this purpose. For other availability addresses, see Footnote 7 of Test Method D4238.

TABLE 1 Glass Bead Sizes

mm	Bead Size Range		Bead Size Designation ^A		
	Passing	Retained	mm	Sieve Number	
	Sieve Number ^B	mm	Sieve Number ^B	Sieve Number	
2.0	10	1.70	12	1.7	12
1.4	14	1.18	16	1.18	16
1.00	18	0.850	20	0.850	20
0.710	25	0.600	30	0.600	30
0.500	35	0.425	40	0.425	40
0.355	45	0.300	50	0.300	50
0.250	60	0.212	70	0.212	70
0.180	80	0.150	100	0.150	100
0.125	120	0.106	140	0.106	140
0.090	170	0.075	200	0.075	200

^A The designated bead size is the "retained on" size of the sieve pair used to size the beads. For example, beads designated No. 40 are beads that pass the No. 35 sieve and are retained on the No. 40 sieve. These beads are typically sold as 35-40 beads.

^B See Specification E11.

DETERMINATION OF APPARENT
OPENING SIZE OF GEOTEXTILE

DATE: _____
TEST BY: _____
COMP BY: _____
CHECK BY: _____

Range (mm) US Std Mesh	Minimum Dia. (mm)	Wt. F+G* W/ Beads	Wt. F+G	Wt. Beads	% Retained	Wt. Pan W/ Beads	Wt. Pan	Wt. Beads	% Passing	Wt. F+G Before	Wt. F+G After	Wt. Retained in Geotextile	% Retained in Geotextile
2.0 - 1.70	1.70												
1.4 - 1.18	1.18												
1.0 - .850	.850												
.710 - .60	.600												
.50 - .425	.425												
.355 - .30	.300												
.25 - .212	.212												
.18 - .15	.150												
.125 - .106	.106												
.09 - .075	.075												

GEOTEXTILE DESCRIPTION: _____

* F=FRAME

G=GEOTEXTILE <https://standards.iteh.ai/catalog/standards/sist/718c4a5b-1a8b-4c56-98cf-5b1dc6e87ffb/astm-d4751-16>

FIG. 12 Sample Worksheet

7. Sampling

7.1 Sampling of Planar Geotextiles

7.1.1 Lot Sample—For routine quality control testing, divide the product into lots and take the lot sample as directed in Practice D4354, Section 7 Procedure B Sampling for Quality Assurance Testing. For Specification Conformance testing, sample as directed in Practice D4354, Section 6 Procedure A—Sampling for Specification Conformance.

7.1.2 Laboratory Sample—As a laboratory sample for acceptance testing, take a full width swatch 1-m (1-yd) long from the end of each roll of fabric in the lot sample, after first discarding a minimum of 1 m (1 yd) of fabric from the very outside of the roll.

7.1.3 Test Specimens—Cut five specimens from each swatch in the laboratory sample with each specimen being cut to fit the appropriate sieve pan. Cut the specimens from a single swatch spaced along a diagonal line on the swatch.

7.2 Sampling of Circular-Knitted Sock Geotextiles

7.2.1 Lot Sample for manufacturers quality control (MQC) testing – Divide rolls of sock covered perforated pipe Circular-Knitted Sock Geotextile Fabric into lots and take the lot sample as directed in Practice D4354, Section 7, Procedure B Sampling for Quality Assurance Testing.

7.2.2 Laboratory Sample—To obtain a laboratory sample for MQC testing of the Circular-Knitted Sock Geotextile, follow the procedure below:

7.2.2.1 Apply the knitted sock Geotextile sample over the outside of the corresponding diameter of a 406 mm (16 in) length of perforated tubing or reasonable facsimile:

7.2.2.2 Tie a knot in each end of the fabric so as to fully encase the pipe in the fabric.

7.2.2.3 Using the knot from one end of the fabric, suspend the geotextiles encased pipe vertically. Gently suspend a 1.13 kg (2.5 lb) weight from the bottom to ensure intimate contact with the perforated pipe. See Fig. 2.



Fig 1a

iTeh Standards
<https://standards.iteh.ai>
Document Preview

ASTM D4751-16

<https://standards.iteh.ai/catalog/standards/sist/4287-16-01/astm-d4751-16>



Fig 1b



Fig 1c

Round Template



Fig 1d

FIG. 31—Semilog Plot

NOTE 2—Pipes with diameters larger than 75 mm (3 in.—6 in.) may require heavier weights to ensure intimate contact between the pipe and sock material.

Allow the suspended pipe with weight to hang for 2 minutes.

7.2.2.4 Using a flexible 203 mm (8 in.) diameter round template as a guide, trace a circle on the surface of the fabric using an indelible marker. See Fig. 2.

7.2.2.5 Remove the fabric from the pipe section by untying or cutting off the knots at one or both ends in the fabric. Cut the fabric tube in a lengthwise direction at a position opposing the drawn circle, taking care to not cut the fabric within the circle. If so desired, the length of the specimen may be shortened by cutting the fabric in a cross wise direction, taking care not to cut the fabric closer than 75 mm (3 in.) from the outside of the circle. The result will be a planar specimen of more or less rectangular shape with a circle drawn approximately in its center.

7.3 *Lot Sample for Specification Conformance Testing*—Sample as directed in Practice D4354 Section 8, Procedure C—Sampling for Specification Conformance.

7.3.1 *Laboratory Sample*—To obtain a laboratory sample of the Circular Knitted Geotextile Fabric for acceptance testing of each lot of pipe, follow the procedure below:

7.3.1.1 Select a 3m (10 ft) section on each lot of the sock covered pipe to be tested.

7.3.2 Using a length of string, twine or cord, secure the fabric to the pipe at each end of the 3m (10 ft) pipe section that was chosen in 7.3.3.1 in order to prevent the sock fabric from contracting lengthwise when the sock covered pipe sample is removed from the roll or pipe section. Remove the 3m (10 ft) sock covered pipe section from the roll or pipe section by cutting the pipe at each end of the 3 m (10 ft) sample, outside of the ties.

7.3.3 *Test Specimens*—With the fabric still secured to the pipe sample, use the flexible rubber template, to draw five 2003 mm (8 in.) diameter circles at various locations around the circumference of each laboratory sample, equally spaced along its length and not closer than 100 mm (4 in.) from either end of the pipe sample.

7.3.3.1 Remove the ties from the laboratory sample and remove the fabric from the pipe.

7.3.3.2 When securing specimens by wedging between two sieve frames cut the laboratory sample in a cross wise direction to create 5 specimens taking care not to make these cuts closer than 75mm (3 in.) from the outside of the circle. Continue to prepare the specimens by cutting the fabric in a lengthwise direction at a position opposing the circle. Care must be taken not to cut through the circle. The result will be the creation of 5 planar fabric specimens of more or less a rectangular shape with a circle drawn at its center.

8. Specimen Preparation

8.1 Weigh the specimens and then submerge them in distilled water for 1 h at the standard atmosphere for testing. Bring the specimens to moisture equilibrium in the atmosphere for testing geosynthetics. Equilibrium is considered to have been reached when the change in the mass of the specimen in successive weighings made at intervals of not less than 2 h does not exceed 0.1 g.

NOTE 3—It is recognized that in practice, geosynthetic materials are frequently not weighed to determine when moisture equilibrium has been reached. While such a method cannot be accepted in cases of dispute, it may be sufficient in routine testing to expose the material to the standard atmosphere for testing geosynthetics for a reasonable period of time before the specimens are tested. A time of at least 24 h has been found acceptable in most cases. However, certain fibers may contain more moisture upon receipt than after conditioning. When this is known, a preconditioning cycle, as described in Practice D1776, may be agreed upon by the contractual parties.

9. Procedure

9.1 Run the test at the atmosphere for testing geotextiles in such a manner that static electricity is prevented from affecting test results. If standard atmosphere cannot be maintained and static electricity is noticed, two methods are available that will prevent static electricity:

9.1.1 Install static eliminating devices equally spaced about the circumference of sieve and one on center of cover, or

9.1.2 Apply commercially available anti-static spray uniformly to the geotextile.

9.2 Secure the geotextile in such a way that it is taut, without wrinkles or bulges. The geotextile must not be stretched or deformed such that it changes or distorts the openings in the fabric. Two systems may be used to secure the geotextiles sample:

9.2.1 Wedge between two sieve frames.

9.2.2 Secure with hoop inside the sieve frame.

NOTE 4—For knitted sock geotextiles, some manipulation of the specimens may be necessary to ensure that the marked out circle is fitted to the sieve frame properly.

9.3 Prior to use, sieve the glass beads in the laboratory to verify size of beads.

NOTE 5—All size glass beads are sieved through a single specimen of geotextile unless the geotextile has an average thickness equal to or greater than 2.3 mm (0.091 in.). A geotextile of this thickness or greater (especially nonwovens) may trap beads within the layers of the fabric, which may pass through

the specimen when testing with a different bead size, thus creating an error in the test results. In the case of the thicker geotextiles, a different specimen may be used for each bead size; however, it should be noted in the report that different specimens were used.

9.4 Start with the smallest diameter glass beads that will be tested. Place 50 g of one size glass beads on the center of the geotextile.

9.5 Place cover and pan on sieve frame and place in shaker. Shake sieves for 10 min.

9.6 Place the glass beads still on the surface of the specimen in a pan and weigh. Include beads that fall off as a result of turning the specimen over and tapping the rims of the sieves.

NOTE 6—This step provides information concerning the amount of glass beads trapped within the geotextile and the amount of any beads lost during testing.

9.7 Weigh the glass beads that pass through the specimen, and record data. (See Fig. 1 for a sample worksheet which can be used to record the desired data).

9.8 Repeat 9.3 through 9.7 using the next larger bead size fraction. Repeat the trial using succeeding larger bead size fractions until the weight of beads passing through the specimen is 5 % or less. Perform the trials such that the percent passing decreases from a value greater than 5 % to a value less than or equal to 5 %.

9.9 Repeat 9.2 to 9.8 for all five specimens.

10. Calculation

10.1 For each size of beads tested with each specimen, compute to the nearest percent the beads passing through the specimen using Eq 1:

$$B = 100 P/T \quad (1)$$

where:

B = beads passing through specimen, %;

P = mass of glass beads in the pan, g, and

T = total mass of glass beads used, g.

10.2 Record calculations and percent beads passing (see Fig. 1).

10.3 Assign the AOS for each specimen as the size designation in millimetres (see 6.3) of the beads of which 5 % or less pass.

10.4 Determine the AOS for the test by averaging the AOS values of the five specimens.

11. Plotting

11.1 It is often desirable to determine the AOS value by plotting the percentage of beads passing the specimen versus the bead size for each of the bead sizes used for each specimen. When plotting is desirable, proceed as follows:

11.1.1 For each specimen, plot the values of Percent Passing (Ordinate) versus Bead Size, mm (Abseissa) on semi-log graph (see Fig. 3). Draw a straight line connecting the two data points representing the bead sizes that are immediately on either side of the 5 % passing ordinate. The particle size in mm (abseissa) at the intersection of the straight line plotted and the 5 % passing ordinate is the AOS of the specimen in mm, that is, the theoretical bead size that would result in exactly 5 % passing the specimen.

11.1.2 Determine the sample AOS, in mm, by averaging the five AOS values obtained by the graphic interpolation in 11.1.1.

11.1.3 Determine the sample AOS, expressed in terms of sieve number, as the number of the U.S. Sieve (see the sieve number column under Bead Size Designation of Table 1) having nominal opening, in millimetres, equal to or next larger than the AOS, in millimetres, obtained in 11.1.1.

12. Report

12.1 Report that the specimens were tested as directed in Test Method D4751. Describe the material or product sampled and the method of sampling used.

12.2 Report the following information:

12.2.1 Results in written form indicating the bead size ranges used in millimetres.

12.2.2 If requested, plots of bead size versus percentage beads passing for each specimen will be provided (as described in Section 11):

12.2.3 The average determined from five specimens as the apparent opening size (AOS = O_{95}) in millimetres.

12.2.4 Weight of each sample.

12.2.5 Type of sieve shaker used.

12.2.6 When requested, express the AOS in terms of sieve number. The AOS expressed this way shall be the number of the U.S. Standard Sieve (see Specification E11) having nominal openings, in millimetres, next larger than or equal to the AOS, in millimetres.

12.2.7 Any deviation from the described test method.