

---

**Pohištvo - Ugotavljanje vžiglјivosti oblazinjenega pohištva - 2. del: Vir vžiga: enakovreden plamenu vžigalice (ISO 8191-2:1988, modified)**

Furniture - Assessment of the ignitability of upholstered furniture - Part 2: Ignition source: Match flame equivalent (ISO 8191-2:1988 modified)

Möbel - Bewertung der Entzündbarkeit von Polstermöbeln - Teil 2: Eine einem Streichholz vergleichbare Gasflamme (ISO 8191-2:1988 modifiziert)

Ameublement - Evaluation de l'allumabilité des meubles rembourrés - Partie 2: Source d'allumage: Flamme équivalente a une allumette (ISO 8191-2:1988 modifiée)

<https://standards.iteh.ai/catalog/standards/sist/852ae3ce-1013-4761-8359-69cf4e653c85/sist-en-1021-2-1995>

**Ta slovenski standard je istoveten z: EN 1021-2:1993**

---

**ICS:**

13.220.40	Sposobnost vžiga in obnašanje materialov in proizvodov pri gorenju	Ignitability and burning behaviour of materials and products
97.140	Pohištvo	Furniture

**SIST EN 1021-2:1995**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 1021-2:1995

<https://standards.iteh.ai/catalog/standards/sist/852ae3ce-1013-4761-8359-69cf4e653c85/sist-en-1021-2-1995>

EUROPEAN STANDARD

EN 1021-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 1993

UDC 645.4:620.193:536.468.08:662.53

Descriptors: Furnishing, furniture, stuffings, fire tests, flammability tests, flames, simulation, matches

English version

**Furniture - Assessment of the ignitability of  
upholstered furniture - Part 2: Ignition source:  
Match flame equivalent (ISO 8191-2:1988  
modified)**

Ameublement - Evaluation de l'allumabilité des  
meubles rembourrés - Partie 2: Source  
d'allumage: Flamme équivalente à une allumette  
(ISO 8191-2:1988 modifiée)

Möbel - Bewertung der Entzündbarkeit von  
Polstermöbeln - Teil 2: Zündquelle: Eine einem  
Streichholz vergleichbare Gasflamme  
(ISO 8191-2:1988 modifiziert)

(standards.iteh.ai)

SIST EN 1021-2:1995

<https://standards.iteh.ai/catalog/standards/sist/852ae3ce-1013-4761-8359-69cf4e653c85/sist-en-1021-2-1995>

This European Standard was approved by CEN on 1993-10-01. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

**CEN**

European Committee for Standardization  
Comité Européen de Normalisation  
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

## Contents list

0.	Introduction . . . . .	3
1.	Scope . . . . .	3
2.	Definitions . . . . .	3
	2.1 progressive smouldering . . . . .	3
	2.2 flaming . . . . .	3
3.	Criteria of ignition . . . . .	3
	3.1 Progressive smouldering ignition . . . . .	3
	3.2 Flaming ignition . . . . .	4
4.	Principle . . . . .	4
5.	Health and safety of operators . . . . .	4
	5.1 General . . . . .	4
	5.2 Enclosure . . . . .	4
	5.3 Extinguishers . . . . .	5
6.	Apparatus . . . . .	5
	6.1 Test rig . . . . .	5
	6.2 Test enclosure . . . . .	5
	6.3 Clock . . . . .	6
	6.4 Ignition source : gas flame ignition source 1 . . . . .	6
	6.5 Gas flow control . . . . .	6
7.	Atmospheres for conditioning and testing . . . . .	7
	7.1 Conditioning . . . . .	7
	7.2 Testing . . . . .	7
8.	Test assembly . . . . .	7
	8.1 General . . . . .	7
	8.2 Cover material and interliner . . . . .	7
	8.3 Upholstery filling . . . . .	8
9.	Test procedure . . . . .	8
	9.1 Preparation . . . . .	8
	9.2 Ignition source application . . . . .	9
	9.3 Final examination . . . . .	9
10.	Test report . . . . .	10
	ANNEX A (informative) . . . . .	13
	ANNEX B (informative) . . . . .	15
	ANNEX C (informative) . . . . .	16
	ANNEX D (normative) . . . . .	17

## Foreword

This European Standard has been prepared by the Technical Committee CEN/TC 207 "Furniture" the secretariat of which is held by IBN.

The European Standard is based on ISO 8191-2 "Assessment of the ignitability for upholstered furniture", to which modifications were introduced following a PQ-Procedure.

This European Standard shall be given the status of National Standard, either by publication of an identical text or by endorsement, at the latest by April 1994, and conflicting National Standards shall be withdrawn at the latest by April 1994.

According to the CEN/CENELEC Internal Regulations, the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 1021-2:1995

<https://standards.iteh.ai/catalog/standards/sist/852ae3ce-1013-4761-8359-69cf4e653c85/sist-en-1021-2-1995>

## 0. Introduction

This part of the standard is one of a series of standards concerned with the ignitability of upholstered furniture using various ignition sources. The ignition source used in this part of the standard is a gas flame equivalent to a match flame.

## 1. Scope

This part of the standard lays down a test method to assess the ignitability of material combinations, such as covers and fillings used in upholstered seating, when subjected to a small flame as an ignition source.

The test measures only the ignitability of a combination of materials used in upholstered seating and not the ignitability of a particular finished item of furniture incorporating these materials. They give an indication of, but cannot guarantee, the ignition behaviour of the finished item of furniture.

## 2. Definitions iTeh STANDARD PREVIEW

For the purposes of this part of the standard, the following definitions apply.

2.1 **progressive smouldering** : exothermic oxidation, not accompanied by flaming, that is self-propagating, i.e. independent of the ignition source. It may or may not be accompanied by incandescence.

2.2 **flaming** : undergoing combustion in the gaseous phase with the emission of light.

## 3. Criteria of ignition

### 3.1 Progressive smouldering ignition

For the purposes of this part of the standard, all the following types of behaviour are considered to be progressive smouldering ignitions :

- a) any test assembly that displays escalating combustion behaviour so that it is unsafe to continue the test and active extinction is necessary;
- b) any test assembly that smoulders until it is essentially consumed within the test duration;
- c) any test assembly that smoulders to the extremities of the specimen, viz. upper or lower margins, either side or to its full thickness, within the duration of the test;
- d) any test assembly that smoulders for more than one hour;

- e) any test assembly that, on final examination, shows evidence of charring other than discolouration, for more than 100 mm in any direction apart from upwards from the nearest part of the original position of the source.

NOTE - In practice it has been found that there is usually a clear distinction between materials which may char under the influence of the ignition source but which do not propagate further (non-progressive combustion) and those where smouldering develops in extent and spreads (progressive combustion).

### 3.2 Flaming ignition

For the purposes of this part of the standard, all the following types of behaviour are considered to be flaming ignitions :

- a) any test assembly that displays escalating combustion behaviour so that it is unsafe to continue the test and active extinction is necessary;
- b) any test assembly that burns until it is essentially consumed within the test duration;
- c) any test assembly on which any flame front reaches the lower margin, either side or passes through its full thickness within the duration of the test.
- d) any flaming which continues for more than 120 s after removal of the burner tube.

## 4. Principle

To subject an assembly of upholstery materials to a match flame equivalent ignition source. The assembly is arranged to represent in stylized form a junction between a seat and back (or seat and arm) such as might occur in a typical chair. The ignitability of an assembly is determined by applying smoker's materials such as a match flame equivalent. The test method measures the ignitability of the overall composite of materials, i.e. cover(s), interliner, infill material, etc., as constructed on the test rig. The results shall not be stated as being applicable to the general behaviour of any individual component (see also annex A).

## 5. Health and safety of operators

### 5.1 General

The test method specified in this part of the standard presents a considerable hazard; suitable precautions shall be taken.

### 5.2 Enclosure

For safety, the test should be conducted in a non-combustible fume cupboard. If such a cupboard is not available, a test enclosure should be constructed (see 6.2) so that the operator is protected from the fumes.

### 5.3 Extinguishers

Adequate means of extinguishing the assembly should be provided, bearing in mind that some combinations may produce severe flaming during the test. A hand and/or fixed water spray which can be directed over the burning area can be useful. Other means such as fire extinguishers (water and halogenated hydrocarbons), fire blankets and a bucket of water will assist.

In some cases smouldering may be difficult to extinguish completely and complete immersion in water may be necessary.

## 6. Apparatus

### 6.1 Test rig

A suitable test rig is illustrated in figures 1 and 2. It shall consist of two rectangular frames hinged together and capable of being locked at right angles to each other.

The frames shall be made from nominal 25 mm x 3 mm flat steel bar and shall securely hold mesh steel platforms set  $(6 \pm 1)$  mm below the top edge of the frames (mesh size should be such that an open mesh area of approximately 15 mm<sup>2</sup> to 150 mm<sup>2</sup> exists).

The internal width and height of the back frame shall be  $(450 \pm 2)$  mm x  $(300 \pm 2)$  mm and the width and depth of the base frame  $(450 \pm 2)$  mm x  $(150 \pm 2)$  mm. A standard edging section may be used around the mesh steel platform to give protection and greater rigidity. [SIST EN 1021-2:1995](https://standards.iteh.ai/catalog/standards/sist/852ae3ce-1013-4761-8359-1995)

The sides of the frame shall extend beyond the back of each frame to provide for the hinge holes and to form the back legs. The hinge rod shall be of nominal 10 mm diameter steel, continuous across the back of the rig and its axis  $(22,5 \pm 0,5)$  mm beyond the back member of each frame.

The frames shall be lockable at right angles by a bolt or pin through each of the pairs of members forming the back legs. The front legs may be welded across the front corners of the base frame. The height of the legs shall be such as to leave a gap not less than 50 mm high between the base and frame and the supporting surface.

For the tests, the rig shall be sited within the enclosure (see 5.2) and the testing shall be performed in a basically draught-free environment permitting an adequate supply of air and removal of smoke from the area of the apparatus.

### 6.2 Test enclosure

The test enclosure shall consist of either a room with a volume greater than 20 m<sup>3</sup> (which contains adequate oxygen for testing) or a smaller enclosure with a through flow of air. Inlet and extraction systems providing an air flow rate of less than 0,2 m/s in the locality of the rig provide adequate oxygen without disturbing the burning behaviour.



### 6.3 Clock

The clock shall be capable of measuring for a period of at least 1 h with an accuracy of 1 s.

### 6.4 Ignition source : gas flame ignition source 1, which is a match-flame equivalent

**NOTE** - This source has been designed to give a calorific output approximating to that of a burning match. It is envisaged that larger flaming ignition sources will be covered by further parts of the standard.

A burner tube consisting of a length of stainless steel tube [(8 ± 0,1) mm outside diameter, (6,5 ± 0,1) mm internal diameter and (200 ± 5) mm in length] is connected by flexible tubing to a cylinder containing butane via a flowmeter, fine control valve, on-off valve (optional) and cylinder regulator providing outlet pressure of nominal 2,8 kPa<sup>1</sup>.

**NOTE** - Where tubing of these dimensions is not readily available, stainless steel tubing of approximately similar dimensions may be used provided that the 50 mm length at the "flame" end of the tube is machined to the given size.

The flowmeter shall be calibrated to supply a butane gas flow rate at 25° C of (45 ± 2) ml/min. The flexible tubing connecting the output of the flowmeter to the burner tube shall be 2,5 m to 3 m in length with an internal diameter of (7 ± 1) mm.

This corresponds to a flame height of approximately 35 mm at 25° C.

### 6.5 Gas flow control

It is essential that the rate of supply of gas to the burner tube conforms to the flow rate specified. Some difficulties have been reported with the supply and measurement of the gas, particularly where the gas cylinder has, of necessity, to be stored in an environment cooler than the defined test conditions and/or at some distance from the test rig.

In these cases, and other situations where difficulties occur, it is important that there should be sufficient length of tubing inside the controlled environment (10°C to 30° C) to ensure that the gas equilibrates to the required temperature before flow measurement. One way to assist this is to pass the gas (before flow measurement) through a metal tube immersed in water maintained at 25° C so that flow corrections for temperature variations can be avoided.

---

<sup>1</sup> 1kPa = 10<sup>3</sup> N/m<sup>2</sup> = 10 mbar

Great care also needs to be exercised with the measurement and setting of the flow rate of the gas. Direct reading flowmeters, even those obtained with a direct gas calibration, need to be checked when initially installed and also at regular intervals during testing by a method capable of accurately measuring the absolute gas flow at the burner tube. One way of doing this is to connect the burner tube with a short length of tubing (about 7 mm inside diameter) to a soap bubble flowmeter, such that the upward passage of a soap film meniscus in a glass tube of calibrated volume (e.g. a burette) over a known period of time gives an absolute measurement of the flow.

## 7. Atmospheres for conditioning and testing

### 7.1 Conditioning

Prior to conditioning described below, all outer cover materials shall be subjected to the water soaking and drying procedure described in Annex D.

The materials to be tested shall be conditioned for at least 16 h immediately before the tests in the following atmosphere:

- temperature :  $(23 \pm 2)^\circ\text{C}$
- relative humidity :  $(50 \pm 5) \%$

### 7.2 Testing

The test shall be carried out in an atmosphere having a temperature between  $10^\circ\text{C}$  and  $30^\circ\text{C}$  and a relative humidity between 15 % and 80 %.

## 8. Test assembly

### 8.1 General

The test assembly materials shall be representative samples of the cover, filling and other components such as any interliner, which may be used in a real assembly.

**NOTE** - The test assemblies may be made up with identical materials in the horizontal and vertical sections.

### 8.2 Cover material and interliner

The cover size needed for each test shall be 800 mm (+10/-0) mm x 650 mm (+10/-0) mm.

The long dimension shall be cut parallel to the machine direction. The cover may be constructed from smaller pieces of material, provided that the location of the resulting seams does not occur within 100 mm of the area likely to be affected by the test.

The cover shall have cut-outs 325 mm from one end on both sides. The cut-outs shall be positioned so that when assembled on the test rig, the lay of the pile is down the back assembly and from the hinge to the front of the base frame. The size of these cut-outs shall be approximately 50 mm base width x 100 mm height x 25 mm top width.

Where fabric interliner is used, it shall be cut to the same dimensions, and in the same orientation as the cover, for fitting to the test rig under the cover.

### 8.3 Upholstery filling

Two test assemblies are necessary for each test, with the following dimensions :

- a) one piece  $(450 \pm 5)$  mm x  $(300 \pm 5)$  mm x  $(75 \pm 2)$  mm thick;
- b) one piece  $(450 \pm 5)$  mm x  $(150 \pm 5)$  mm x  $(75 \pm 2)$  mm thick.

Some cushioning assemblies may consist of several layers that may be typically felt, wadding or different foams. Where the total thickness exceeds 75 mm, reproduce the upper 75 mm of the cushioning assembly except that the upper layer(s) shall not be continued over and round the edges of the assembly.

Where the filling is less than 75 mm thick, the test assembly shall be built up to the required thickness by adding a further layer of the bottom material to the underside.

Some kinds of loose packing materials (e.g. foam crumb, feathers) may be evaluated by this test method. In these cases the loose packing shall be built up beneath the covering materials to reproduce the 75 mm thickness of the assembly at a realistic packing density. Where necessary, a finer grid material or air-porous fabric may be laid over the expanded metal of the test rig to retain the filling.

If the loose infill is enclosed in an interlining (or ticking), it is acceptable to make up two bags of the interlining suitably filled and to the overall dimensions given above for use as the upholstery filling beneath the cover(s).

The method is unsuitable and cannot be used with composites where the loose infill material flows out of the assembly during the test and either extinguishes, moves, or adversely affects the burning of the ignition source.

## 9. Test procedure

### 9.1 Preparation

- 9.1.1 Open out the test rig and thread the cover fabric and fabric interliner, if any, behind the hinge bar.
- 9.1.2 Place the filling samples under the covering fabric, locating them in the frame recesses.
- 9.1.3 Allow a 20 mm overlap on the inside of the frame, and fasten the fabric over the top, bottom and sides using clips.

**NOTE** - This action places the cover under some tension and it may be found easier to carry out if the frames are folded together to compress the upholstery partially.

- 9.1.4 Ensure that the fabric is secure and under even tension. Then lock the frames at right angles by the bolts or pins.
- 9.2 Ignition source application
- 9.2.1 Light the gas emerging from the burner tube, adjust the gas flow to the specified rate (see 6.4) and allow the flame to stabilize for at least 2 min.
- 9.2.2 Position the burner tube axially along the junction between the seat and back so that the flame is not less than 50 mm from the nearest side, edge, or from any marks left by any previous test, and simultaneously start the clock.
- 9.2.3 Allow the gas to burn for a period of  $(15 \pm 1)$  s, then terminate the ignition process by carefully removing the burner tube from the test piece.
- 9.2.4 Observe the progress of combustion, and record any evidence of progressive smouldering or flaming in the interior and/or cover. Disregard any flames, afterglow, smoking or smouldering, that cease within 120 s of the removal of the burner tube.
- 9.2.4 If progressive smouldering ignition (see 3.1) or flaming ignition (see 3.2) of the upholstery components is observed, extinguish the test assembly and record this. In these circumstances discontinue testing and complete the test report (see clause 10).

<https://standards.iteh.ai/catalog/standards/sist/852ae3ce-1013-4761-8359-074603347382/en-1021-2-1993>  
If progressive smouldering ignition or flaming ignition is not observed, repeat the test in a fresh position not less than 50 mm from any previous test damage. If progressive smouldering ignition or flaming ignition is not observed in this retest, record this and carry out the final examination (see 9.3).

**NOTE** - If preferred this repeat test may be carried out concurrently with the first test.

### 9.3 Final examination

Cases of progressive smouldering ignition undetected from the outside have been reported. Immediately after completion of the test programme on the assembly, dismantle and examine it internally for progressive smouldering ignition (see 3.1.e). If this is found, extinguish the test assembly, and record a failed result for the relevant test source. For safety reasons ensure that all smouldering has ceased before the rig is left unattended.