



Designation: C94/C94M – 16a

Standard Specification for Ready-Mixed Concrete¹

This standard is issued under the fixed designation C94/C94M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers ready-mixed concrete as defined in 3.2.2 (Note 1). Requirements for quality of ready-mixed concrete shall be either as stated in this specification or as ordered by the purchaser. When the purchaser's requirements, as stated in the order, differ from those in this specification, the purchaser's requirements shall govern. This specification does not cover the placement, consolidation, curing, or protection of the concrete after delivery to the purchaser.

NOTE 1—Concrete produced by volumetric batching and continuous mixing is covered in Specification C685. Fiber-reinforced concrete is covered in Specification C1116.

1.2 The values stated in either SI units, shown in brackets, or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 As used throughout this specification the manufacturer produces ready-mixed concrete. The purchaser buys ready-mixed concrete.

1.4 The text of this standard references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

1.5 *This standard does not purport to address all the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. (Warning—Fresh hydraulic cementitious mixtures are caustic and may cause chemical burns to skin and tissue upon prolonged use.)*²

¹ This specification is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.40 on Ready-Mixed Concrete.

Current edition approved Aug. 1, 2016. Published August 2016. Originally approved in 1933. Last previous edition approved in 2016 as C94/C94M-16. DOI: 10.1520/C0094_C0094M-16A.

² See Section on Safety Precautions, Manual of Aggregate and Concrete Testing, *Annual Book of ASTM Standards*, Vol 04.02.

2. Referenced Documents

2.1 ASTM Standards:³

- C31/C31M Practice for Making and Curing Concrete Test Specimens in the Field
- C33/C33M Specification for Concrete Aggregates
- C39/C39M Test Method for Compressive Strength of Cylindrical Concrete Specimens
- C125 Terminology Relating to Concrete and Concrete Aggregates
- C138/C138M Test Method for Density (Unit Weight), Yield, and Air Content (Gravimetric) of Concrete
- C143/C143M Test Method for Slump of Hydraulic-Cement Concrete
- C150/C150M Specification for Portland Cement
- C172/C172M Practice for Sampling Freshly Mixed Concrete
- C173/C173M Test Method for Air Content of Freshly Mixed Concrete by the Volumetric Method
- C231/C231M Test Method for Air Content of Freshly Mixed Concrete by the Pressure Method
- C260/C260M Specification for Air-Entraining Admixtures for Concrete
- C330/C330M Specification for Lightweight Aggregates for Structural Concrete
- C494/C494M Specification for Chemical Admixtures for Concrete
- C567/C567M Test Method for Determining Density of Structural Lightweight Concrete
- C595/C595M Specification for Blended Hydraulic Cements
- C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete
- C637 Specification for Aggregates for Radiation-Shielding Concrete
- C685 Specification for Concrete Made by Volumetric Batching and Continuous Mixing
- C989/C989M Specification for Slag Cement for Use in Concrete and Mortars

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

- C1017/C1017M** Specification for Chemical Admixtures for Use in Producing Flowing Concrete
- C1064/C1064M** Test Method for Temperature of Freshly Mixed Hydraulic-Cement Concrete
- C1077** Practice for Agencies Testing Concrete and Concrete Aggregates for Use in Construction and Criteria for Testing Agency Evaluation
- C1116** Specification for Fiber-Reinforced Concrete and Shotcrete
- C1157/C1157M** Performance Specification for Hydraulic Cement
- C1240** Specification for Silica Fume Used in Cementitious Mixtures
- C1602/C1602M** Specification for Mixing Water Used in the Production of Hydraulic Cement Concrete
- C1611/C1611M** Test Method for Slump Flow of Self-Consolidating Concrete

2.2 *ACI Documents:*⁴

- ACI 211.1** Standard Practice for Selecting Proportions for Normal, Heavyweight, and Mass Concrete
- ACI 211.2** Standard Practice for Selecting Proportions for Structural Lightweight Concrete
- ACI 301** Standard Specifications for Structural Concrete
- ACI 305R** Guide to Hot Weather Concreting
- ACI 306R** Guide to Cold Weather Concreting
- ACI 318** Building Code Requirements for Structural Concrete and Commentary

2.3 *Other Documents:*⁵

- NIST 105-1** National Institute of Standards and Technology Handbook

3. Terminology

3.1 *Definitions*—The terms used in this specification are defined in Terminology **C125**.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *concrete, central-mixed, n*—ready-mixed concrete mixed completely in a stationary mixer.

3.2.2 *concrete, ready-mixed, n*—concrete manufactured and delivered to a purchaser in a fresh state.

3.2.3 *concrete, shrink-mixed, n*—ready-mixed concrete partially mixed in a stationary mixer with mixing completed in a truck mixer.

3.2.4 *concrete, truck-mixed, n*—ready-mixed concrete completely mixed in a truck mixer.

3.2.5 *water, target batch, n*—quantity of water to be added to the batch through the water measuring system after compensating for the quantity of ice, if used, surface moisture on the aggregates and water in the admixtures, when applicable, and by subtracting a quantity of water that is anticipated to be

⁴ Available from American Concrete Institute (ACI), P.O. Box 9094, Farmington Hills, MI 48333-9094, <http://www.concrete.org>.

⁵ NIST Handbook 105-1 (revised 1990), “Specifications and Tolerances for Reference Standards and Field Standard Weights and Measures-1. Specifications and Tolerances for Field Standard Weights (NIST Class F),” National Institute of Standards and Technology, U.S. Dept. of Commerce, <http://www.nist.gov/pml/wmd/upload/105-1.pdf>.

added at the jobsite or in transit to adjust slump or slump flow of the concrete batch.

4. Basis of Purchase

4.1 The basis of purchase shall be a cubic yard or cubic metre of fresh concrete as discharged from the transportation unit.

4.2 The volume of fresh concrete in a given batch shall be determined from the total mass of the batch divided by the density of the concrete. The total mass of the batch shall be determined as the net mass of the concrete in the batch as delivered, including the total mixing water as defined in **9.3**. The density shall be determined in accordance with Test Method **C138/C138M**. The yield shall be determined as the average of at least three measurements, one from each of three different transportation units sampled in accordance with Practice **C172/C172M**.

NOTE 2—It should be understood that the volume of hardened concrete may be, or appear to be, less than expected due to waste and spillage, over-excavation, spreading forms, some loss of entrained air, or settlement of wet mixtures, none of which are the responsibility of the producer.

5. Materials

5.1 In the absence of designated applicable material specifications, the following material specifications shall be used:

5.2 *Cementitious Materials:*

5.2.1 *Hydraulic Cement*—Hydraulic cement shall conform to Specification **C150/C150M**, Specification **C595/C595M**, or Specification **C1157/C1157M**.

5.2.2 *Supplementary Cementitious Materials*—Coal fly ash or natural pozzolans shall conform to Specification **C618**. Slag cement shall conform to Specification **C989/C989M**. Silica fume shall conform to Specification **C1240**.

5.3 *Aggregates*—Normal weight aggregates shall conform to Specification **C33/C33M**. Lightweight aggregates shall conform to Specification **C330/C330M** and heavyweight aggregates shall conform to Specification **C637**.

5.4 *Water*—Water shall conform to Specification **C1602/C1602M**.

5.5 *Air-Entraining Admixtures*—Air-entraining admixtures shall conform to Specification **C260/C260M** (Note 3).

5.6 *Chemical Admixtures*—Chemical admixtures shall conform to Specification **C494/C494M** or **C1017/C1017M** as applicable (Note 3).

NOTE 3—In any given instance, the required dosage of air-entraining, accelerating, and retarding admixtures may vary. Therefore, a range of dosages should be allowed, which will permit obtaining the desired effect.

NOTE 4—Interchanging kinds, characteristics, types, classes, or grades of the materials permitted in ready-mixed concrete may produce concrete of different properties.

6. Ordering Information

6.1 In the absence of designated applicable general specifications, the purchaser’s order shall include the following:

6.1.1 Designated size, or sizes, of coarse aggregate,

6.1.2 Slump, or slumps, desired at the point of delivery (see Section 7 for acceptable tolerances),

6.1.3 Slump flow, or flows, desired at the point of delivery (see Section 7 for acceptable tolerances),

6.1.4 Total air content at the point of delivery for concrete that will be exposed to cycles of freezing and thawing or anticipated exposure of the concrete (see Section 8 for sampling for air content tests and tolerances).

NOTE 5—Table 1 provides total air contents for concrete that vary by exposure condition and aggregate size. Total air contents less than those shown in Table 1 may be specified or used for concrete that is not subject to freezing and thawing. This may be done to improve workability and cohesiveness, reduce the rate of bleeding, reduce the water content for a given consistency, or achieve required lightweight concrete density. Specified total air contents higher than those shown in Table 1 may reduce strength without any further improvement of durability.

Exposure conditions for freezing and thawing environments in Table 1 correspond to the following:

Moderate Exposure—Concrete exposed to freeze-thaw cycles but not in contact with the ground or with limited exposure to water, limiting the ability to cause saturation of a portion of the concrete prior to freezing. The concrete shall not receive deicing salts or other aggressive chemicals. Examples include: exterior beams, columns, walls, girders, footings below the frost line, or elevated slabs where application of deicing salt is not anticipated. The air content requirements for this exposure are consistent with those for Exposure Class F1 of ACI 318.

Severe Exposure—Concrete exposed to freeze-thaw cycles while in contact with the ground or with frequent exposure to water, potentially causing saturation of a portion of the concrete prior to freezing. The concrete may receive deicing chemicals or other aggressive chemicals. Examples include: pavements, bridge decks, curbs, gutters, sidewalks, canal linings, or exterior water tanks or sumps. The air content requirements for this exposure are consistent with those for Exposure Classes F2 and F3 of ACI 318.

6.1.5 Which of Options A, B, or C shall be used as a basis for determining the proportions of the concrete to produce the required quality,

6.1.6 When lightweight concrete is specified, the equilibrium density,

NOTE 6—The density of fresh concrete is the only measurable density of lightweight concrete at the time of delivery. The density of fresh concrete is always higher than the equilibrium or oven-dry density. Therefore, for acceptance of lightweight concrete based on density at the time of delivery, a relationship between the equilibrium density and density of fresh concrete needs to be established. Definitions of, and methods for determining or calculating equilibrium and oven-dry density, are covered by Test Method C567/C567M.

6.1.7 When high-density or heavyweight concrete is specified, the density of fresh concrete, and

NOTE 7—High-density or heavyweight concrete typically contains aggregate with a relative density of 3.3 or greater conforming to Specification C637. This concrete is used for radiation shielding or other

applications where higher density is required by design. For acceptance of density at the time of delivery, a relationship between the fresh density and the density of hardened concrete required by design should be established.

6.1.8 If desired, any of the optional requirements of Table 2 in Specification C1602/C1602M.

6.1.9 Purchaser shall state any drum revolution limit as to when the concrete discharge must begin. If no drum revolution limit is stated by purchaser, the manufacturer shall determine and communicate the limit to the purchaser prior to delivery.

6.2 If a project specification applies, the order shall include applicable requirements for the concrete to be produced in compliance with the specification.

6.3 If the type, kind, or class of cementitious materials in 5.2.1 and 5.2.2 are not designated by the purchaser, it is permitted to use cementitious materials in concrete mixtures that will satisfy the concrete properties and other requirements of the purchaser as ordered.

6.4 Option A:

6.4.1 When the purchaser requires the manufacturer to assume full responsibility for the selection of the proportions for the concrete mixture (Note 8), the purchaser shall also specify the following:

6.4.1.1 Requirements for compressive strength as determined on samples taken from the transportation unit at the point of discharge evaluated in accordance with Section 18. The purchaser shall specify the requirements in terms of the compressive strength of standard specimens cured under standard laboratory conditions for moist curing (see Section 18). Unless otherwise specified the age at test shall be 28 days.

NOTE 8—The purchaser, in selecting requirements for which he assumes responsibility should give consideration to requirements for workability, placeability, durability, surface texture, and density, in addition to those for structural design. The purchaser is referred to Standard Practice ACI 211.1 and Standard Practice ACI 211.2 for the selection of proportions that will result in concrete suitable for various types of structures and conditions of exposure. The water-cement ratio of most structural lightweight concretes cannot be determined with sufficient accuracy for use as a specification basis.

6.4.2 At the request of the purchaser, the manufacturer shall, prior to the actual delivery of the concrete, furnish a statement to the purchaser, giving the dry masses of cement and saturated surface-dry-masses of fine and coarse aggregate and quantities, type, and name of admixtures (if any) and of water per cubic yard or cubic metre of concrete that will be used in the manufacture of each class of concrete ordered by the purchaser. The manufacturer shall also furnish evidence satisfactory to the purchaser that the materials to be used and proportions selected will produce concrete of the quality specified.

TABLE 1 Total Air Content for Air-Entrained Concrete Exposed to Cycles of Freezing and Thawing

| Exposure Condition (See Note 5) | Total Air Content, % | | | | | | |
|------------------------------------|--|----------|----------|----------|-----------|----------|----------|
| | Nominal Maximum Sizes of Aggregate, mm [in.] | | | | | | |
| | 9.5 [¾] | 12.5 [½] | 19.0 [¾] | 25.0 [1] | 37.5 [1½] | 50.0 [2] | 75.0 [3] |
| Moderate | 6.0 | 5.5 | 5.0 | 4.5 | 4.5 | 4.0 | 3.5 |
| Severe | 7.5 | 7.0 | 6.0 | 6.0 | 5.5 | 5.0 | 4.5 |

6.5 Option B:

6.5.1 When the purchaser assumes responsibility for the proportioning of the concrete mixture, he shall also specify the following:

6.5.1.1 Cement content in kilograms per cubic metre [pounds per cubic yard] of concrete,

6.5.1.2 Maximum allowable water content in litres per cubic metre [gallons per cubic yard] of concrete, including surface moisture on the aggregates, but excluding water of absorption (Note 8), and

6.5.1.3 If admixtures are required, the type, name, and dosage to be used. The cement content shall not be reduced when admixtures are used under this option without the written approval of the purchaser.

6.5.2 At the request of the purchaser, the manufacturer shall, prior to the actual delivery of the concrete, furnish a statement to the purchaser giving the sources, densities, and sieve analyses of the aggregates and the dry masses of cement and saturated-surface-dry masses of fine and coarse aggregate and quantities, type and name of admixture (if any) and of water per cubic yard or cubic metre of concrete that will be used in the manufacture of each class of concrete ordered by the purchaser.

6.6 Option C:

6.6.1 When the purchaser requires the manufacturer to assume responsibility for the selection of the proportions for the concrete mixture with the minimum allowable cement content specified (Note 9), the purchaser shall also specify the following:

6.6.1.1 Required compressive strength as determined on samples taken from the transportation unit at the point of discharge evaluated in accordance with Section 18. The purchaser shall specify the requirements for strength in terms of tests of standard specimens cured under standard laboratory conditions for moist curing (see Section 18). Unless otherwise specified the age at test shall be 28 days.

6.6.1.2 Minimum cement content in kilograms per cubic metre [pounds per cubic yard] of concrete.

6.6.1.3 If admixtures are required, the type, name, and dosage to be used. The cement content shall not be reduced when admixtures are used.

NOTE 9—Option C can be distinctive and useful only if the designated minimum cement content is at about the same level that would ordinarily be required for the strength, aggregate size, and slump or slump flow specified. At the same time, it must be an amount that will be sufficient to ensure durability under expected service conditions, as well as satisfactory surface texture and density, in the event specified strength is attained with it. For additional information refer to Standard Practice ACI 211.1 and Standard Practice 211.2 referred to in Note 8.

6.6.2 At the request of the purchaser, the manufacturer shall, prior to the actual delivery of the concrete, furnish a statement to the purchaser, giving the dry masses of cement and saturated surface-dry masses of fine and coarse aggregate and quantities, type, and name of admixture (if any) and of water per cubic yard or cubic metre of concrete that will be used in the manufacture of each class of concrete ordered by the purchaser. He shall also furnish evidence satisfactory to the purchaser that the materials to be used and proportions selected will produce

concrete of the quality specified. Whatever strengths are attained the quantity of cement used shall not be less than the minimum specified.

6.7 The proportions arrived at by Options A, B, or C for each class of concrete and approved for use in a project shall be assigned a designation to facilitate identification of each concrete mixture delivered to the project. This is the designation required in 14.1.7 and supplies information on concrete proportions when they are not given separately on each delivery ticket as outlined in 14.2. A certified copy of all proportions as established in Options A, B, or C shall be on file at the batch plant.

6.8 The purchaser shall ensure that the manufacturer is provided copies of all reports of tests performed on concrete samples taken to determine compliance with specification requirements. Reports shall be provided on a timely basis.

7. Tolerances in Slump or Slump Flow

7.1 Unless other tolerances are indicated by the purchaser, the following shall apply.

7.1.1 When slump is stated as a “maximum” or “not to exceed” requirement:

Tolerances for “Maximum” or “Not to Exceed” Slumps

| For Slump of: | Tolerance |
|-------------------------|-------------------------|
| 75 mm [3 in.] or less | +0 and – 40 mm [1½ in.] |
| More than 75 mm [3 in.] | +0 and – 65 mm [2½ in.] |

7.1.2 When slump is stated as a target or nominal slump:

Tolerances for Target or Nominal Slumps

| For Slump of: | Tolerance |
|--|------------------|
| 50 mm [2 in.] and less | ± 15 mm [½ in.] |
| More than 50 to 100 mm [2 through 4 in.] | ± 25 mm [1 in.] |
| More than 100 mm [4 in.] | ± 40 mm [1½ in.] |

7.1.3 When the purchaser states a slump flow requirement for self-consolidating concrete:

Tolerances for Slump Flow

| For Slump Flow | Tolerance |
|---------------------------------------|------------------|
| Less than or equal to 550 mm [22 in.] | ± 40 mm [1½ in.] |
| More than 550 mm [22 in.] | ± 65 mm [2½ in.] |

7.1.4 The slump tolerances are applicable when water addition in accordance with 12.7 is permitted.

7.2 Concrete shall be available within the permissible range of slump or slump flow for a period of 30 min starting either on arrival at the job site or after the initial slump adjustment permitted in 12.7, whichever is later. The first and last ¼ m³ [¼ yd³] discharged are exempt from this requirement. If the user is unprepared for discharge of the concrete from the vehicle, the producer shall not be responsible for the limitation of minimum slump or slump flow after 30 min have elapsed starting either on arrival of the vehicle at the prescribed destination or at the requested delivery time, whichever is later.

8. Air-Entrained Concrete

8.1 Unless otherwise specified, for air-entrained concrete the total air contents in Table 1 shall apply based on the

exposure condition stated in the purchase order. It is permitted to reduce the total air content values in **Table 1** by one percentage point for concretes with a specified compressive strength greater than or equal to 35 MPa [5000 psi]. Total air content that differs from the values in **Table 1** is permitted for concrete not exposed to cycles of freezing and thawing (**Note 5**).

8.2 The air content of air-entrained concrete when sampled from the transportation unit at the point of discharge shall be within a tolerance of ± 1.5 of the specified value.

8.3 When a preliminary sample taken within the time limits of **12.7** and prior to discharge for placement shows an air content below the specified level by more than the allowable tolerance in accordance with **8.2**, the manufacturer may use additional air entraining admixture to achieve the desired air content level, followed by a minimum of 30 revolutions at mixing speed, so long as the revolution limit of **6.1.9** is not exceeded (see **Note 10**).

NOTE 10—Acceptance sampling and testing in accordance with Practice **C172/C172M** is not obviated by this provision. Increasing the air content may increase the slump or slump flow.

9. Measuring Materials

9.1 Except as otherwise specifically permitted, cementitious materials shall be measured by mass. When supplementary cementitious materials are used in the concrete mixtures, the cumulative mass is permitted to be measured with hydraulic cement, but in a batch hopper and on a scale which is separate and distinct from those used for other materials. The mass of the hydraulic cement shall be measured before supplementary cementitious materials. When the quantity of cementitious material exceeds 30 % of the full capacity of the scale, the measured quantity of the hydraulic cement shall be within ± 1 % of the required mass, and the cumulative measured quantity of hydraulic cement plus supplementary cementitious materials shall also be within ± 1 % of the required cumulative mass at each intermediate weighing. For smaller batches to a minimum of 1 m³ [1 yd³], the measured quantity of the hydraulic cement and the measured cumulative quantity of hydraulic cement plus supplementary cementitious materials used shall be not less than the required amount nor more than 4 % in excess. When the purchaser requires alternate methods of measuring cementitious materials, measurement methods and reporting shall be stated in the order (see **Note 11**).

NOTE 11—Cementitious materials in bags may be used when requested or permitted by the purchaser.

9.2 Aggregate shall be measured by mass. Batch mass measurements shall be based on dry materials and shall be the required mass of dry materials plus the total mass of moisture (both absorbed and surface) contained in the aggregate.

9.2.1 For aggregates measured in individual or cumulative weigh batchers, when the required intermediate or final mass is less than 30 % of the scale capacity the aggregate mass shall be within ± 0.3 % of scale capacity or within ± 3 % of the required mass, whichever is less.

9.2.2 When aggregates are measured in an individual weigh batcher and the required mass of aggregate is equal to or

greater than 30 % of the scale capacity, the quantity of aggregate shall be within ± 2 % of the required mass. When aggregates are measured in a cumulative aggregate weigh batcher, and the required intermediate and final cumulative mass of aggregate components is equal to or greater than 30 % of the scale capacity, the quantity of aggregate at each successive weighing shall be within ± 1 % of the required mass.

NOTE 12—The batching accuracy limit of 0.3 % of scale capacity establishes a reasonable minimum weighing tolerance limit that is independent of the quantity of material being weighed. It generally governs for smaller batch quantities weighed in weigh batchers (scales).

9.3 Mixing water shall consist of water added to the batch, ice added to the batch, water occurring as surface moisture on the aggregates, and water introduced in the form of admixtures. The added water shall be measured by mass or volume to an accuracy of 1 % of the required total mixing water. Added ice shall be measured by mass. In the case of truck mixers, any wash water retained in the drum for use in the next batch of concrete shall be accurately measured; if this proves impractical or impossible the wash water shall be discharged prior to loading the next batch of concrete. Total water (including any wash water) shall be measured or weighed to an accuracy of ± 3 % of the specified total amount.

9.4 Chemical admixtures in powdered form shall be measured by mass. Liquid chemical admixtures shall be batched by mass or volume. Admixtures measured by either mass or volume, shall be batched with an accuracy of ± 3 % of the total amount required or plus or minus the amount or dosage required for 50 kg [100 lb] of hydraulic cement, whichever is greater.

NOTE 13—Admixture dispensers of the mechanical type capable of adjustment for variation of dosage, and of simple calibration, are recommended.

10. Batching Plant

10.1 Bins with adequate separate compartments shall be provided in the batching plant for fine and for each required size of coarse aggregate. Each bin compartment shall be designed and operated so as to discharge efficiently and freely, with minimum segregation, into the weighing hopper. Means of control shall be provided so that, as the quantity desired in the weighing hopper is approached, the material shall be shut off with precision. Weighing hoppers shall be constructed so as to eliminate accumulations of tare materials and to discharge fully.

10.2 Indicating devices shall be in full view and near enough to be read accurately by the operator while charging the hopper. The operator shall have convenient access to all controls.

10.3 Scales shall be considered accurate if their accuracy is verified through the normally used capacity in accordance with **Table 2** and load indicated relative to applied test load is within ± 0.15 % of the total capacity of the scale or 0.4 % of the net applied load, whichever is greater. The minimum quantity and sequence of applied test loads used to verify material scales shall conform to **Table 2** and its notes.

TABLE 2 Minimum Field Standard Weights and Test Loads^A

| Device Capacity | Minimum (in terms of device capacity) | | Minimum Loads for Verification of Scale Accuracy |
|--|--|-------------------------|--|
| | Field Standard Weights | Test Loads ^C | |
| 0 to 2000 kg [0 to 4000 lb] | 100 % | 100 % | |
| 2001 to 20 000 kg [4001 to 40 000 lb] | Greater of ^B 10 % or 500 kg [1000 lb] | 50 % ^D | Field standard weights or test load to used capacity, if greater than minimum specified. Strain-load tests ^E are permitted to be used above test load minimums. During initial verification, a scale shall be tested to full capacity. |

^A If the configuration and set up of the scale system prevents access or application of adequate field standard weights or if an unsafe condition is created by the verification process then the use of the scale above the verified position shall be discontinued until corrective measures have been completed.

^B Field standard weights used in verifying accuracy of weighing devices shall comply with requirements of NIST Handbook 105-1.

^C The term "test load" means the sum of the combination of field standard weights and any other applied load used in the conduct of a test using substitution test methods. Substitution Test—In the substitution test procedure, material or objects are substituted for field standard weights, or a combination of field standard weights and previously quantified material or objects, using the scale under test as a comparator. Additional test weights or other known test loads may be added to the known test load to verify the accuracy of higher weight ranges on the scale.

^D The scale shall be tested from zero to at least 10 % of scale capacity using field standard weights, and then to at least 50 % of scale capacity using a series of substitution load tests that utilize field standard weights equaling at least 10 % of scale capacity.

^E A strain-load test shall be conducted to verify the accuracy from 50 % of scale capacity to the used capacity of the scale. At least one load test shall be performed in each quarter of scale capacity. Strain-Load Test—In the strain-load test procedure, an unknown quantity of material or objects are used to establish a reference load or tare to which field standard weights or substitution test loads are added.

10.4 All exposed fulcrums, clevises, and similar working parts of scales shall be kept clean. Beam scales shall be equipped with a balance indicator sensitive enough to show movement when a weight equal to 0.1 % of the nominal capacity of the scale is placed in the batch hopper. Pointer travel shall be a minimum of 5 % of the net-rated capacity of the largest weigh beam for underweight and 4 % for overweight.

10.5 The device for the measurement of the added water shall be capable of delivering to the batch the quantity required within the accuracy required in 9.3. The device shall be so arranged that the measurements will not be affected by variable pressures in the water supply line. Measuring tanks shall be equipped with outside taps and valves to provide for checking their calibration unless other means are provided for readily and accurately determining the amount of water in the tank.

NOTE 14—The scale accuracy limitations of the National Ready Mixed Concrete Association Plant Certification meet the requirements of this specification.

11. Mixers and Agitators

11.1 Mixers will be stationary mixers or truck mixers. Agitators will be truck mixers or truck agitators.

11.1.1 Stationary mixers shall be equipped with a metal plate or plates on which are plainly marked the mixing speed of the drum or paddles, and the maximum capacity in terms of the volume of mixed concrete. When used for the complete mixing of concrete, stationary mixers shall be equipped with an acceptable timing device that will not permit the batch to be discharged until the specified mixing time has elapsed.

11.1.2 Each truck mixer or agitator shall have attached thereto in a prominent place a metal plate or plates on which are plainly marked the gross volume of the drum, the capacity of the drum or container in terms of the volume of mixed concrete, and the minimum and maximum mixing speeds of rotation of the drum, blades, or paddles. When the concrete is truck mixed as described in 12.5, or shrink mixed as described in 12.4, the volume of mixed concrete shall not exceed 63 % of

the total volume of the drum or container. When the concrete is central mixed as described in 12.3, the volume of concrete in the truck mixer or agitator shall not exceed 80 % of the total volume of the drum or container. Truck mixers and agitators shall be equipped with means to readily verify the number of revolutions of the drum, blades, or paddles.

11.2 Mixers shall be capable of combining the ingredients of the concrete within the specified time for stationary mixers in 12.3 or the specified number of revolutions for truck mixers in 12.5, into a thoroughly mixed and uniform mass and of discharging the concrete so that not less than five of the six requirements shown in Table A1.1 shall have been met.

NOTE 15—The sequence or method of charging the mixer will have an important effect on the uniformity of the concrete.

11.3 The agitator shall be capable of maintaining the mixed concrete in a thoroughly mixed and uniform mass and of discharging the concrete with a satisfactory degree of uniformity as defined by Annex A1.

11.4 Slump tests of individual samples taken after discharge of approximately 15 % and 85 % of the load will provide a quick check of the probable degree of uniformity (Note 16). These two samples shall be obtained within an elapsed time of not more than 15 min. If these slumps differ more than that specified in Annex A1, the mixer or agitator shall not be used unless the condition is corrected, except as provided in 11.5.

NOTE 16—No samples should be taken before 10 % or after 90 % of the batch has been discharged. Due to the difficulty of determining the actual quantity of concrete discharged, the intent is to provide samples that are representative of widely separated portions, but not the beginning and end of the load.

11.5 Use of the equipment is permitted when operation with a longer mixing time, a smaller load, or a more efficient charging sequence will permit the requirements of Annex A1 to be met.

11.6 Mixers and agitators shall be examined or their mass determined as frequently as necessary to detect changes in