



Designation: E11 – 16

Standard Specification for Woven Wire Test Sieve Cloth and Test Sieves¹

This standard is issued under the fixed designation E11; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This document specifies the technical requirements for; the woven wire test sieve cloth (sieve cloth) used in test sieves, the construction of test sieves, standard and non-standard test sieve frame sizes, and test procedures used to inspect sieve cloth and the test sieves. This specification applies to test sieves manufactured with sieve cloth having a nominal aperture size ranging from 125 millimetres (mm) down to 20 micrometres (μm).

1.2 Additional reference information can be found in Specifications E161, E323, E2016, and in Test Methods C430 and E2427.

1.3 The values stated in SI units shall be considered standard for the dimensions of the sieve cloth openings and the wire diameters used in the sieve cloth. The values stated in inch-pound units shall be considered standard with regard to the sieve frames, pans, and covers.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

C430 Test Method for Fineness of Hydraulic Cement by the 45- μm (No. 325) Sieve

E161 Specification for Precision Electroformed Sieves

E323 Specification for Perforated-Plate Sieves for Testing Purposes

E1638 Terminology Relating to Sieves, Sieving Methods, and Screening Media

¹ This specification is under the jurisdiction of ASTM Committee E29 on Particle and Spray Characterization and is the direct responsibility of Subcommittee E29.01 on Sieves, Sieving Methods, and Screening Media.

Current edition approved Aug. 1, 2016. Published August 2016. Originally approved in 1925. Last previous edition approved in 2015 as E11 – 15. DOI: 10.1520/E0011-16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

E2016 Specification for Industrial Woven Wire Cloth

E2427 Test Method for Acceptance by Performance Testing for Sieves

2.2 Federal Standard:³

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)

2.3 Military Standard:³

MIL-STD-129 Marking for Shipment and Storage

2.4 ISO Standard:⁴

ISO 3310-1 Test Sieves—Technical Requirements and Testing – Part 1: Test Sieves of Metal Wire Cloth

3. Terminology

3.1 *Definitions*—Additional terms can be found in Terminology E1638.

3.1.1 *aperture*—the dimension defining an opening in a screening surface.

3.1.2 *backing cloth*—a wire mesh support layer used directly under the sieve cloth with an opening coarser than the sieve designation.

3.1.3 *crimp*—the corrugation in the warp and shute wire, or both. The crimp in the wires is formed either during the weaving process, or with a crimping machine prior to weaving. If formed during the weaving process, the tension existing between the warp and shute wires fundamentally determines the respective amount or depth of crimp, which locks the wires in place, and in part establishes the firmness of the sieve cloth.

3.1.4 *firmness*—a subjective term referring to the planar rigidity of sieve cloth (as a roll good, not mounted in a test sieve frame), established by the tensile strength of the material, the relationship of the mesh to wire diameters, the type of weave, and amount of crimp in the wires. The absence of firmness in sieve cloth is termed *sleaziness*.

3.1.5 *matched test sieve*—a test sieve that reproduces the performance results of another test sieve within user defined limits for a designated material (for information only and may not be in compliance with this specification).

³ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, http://www.dodssp.daps.mil.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Nominal Dimensions and Permissible Variations for Sieve Cloth and Compliance, Inspection and Calibration Test Sieves

(1)	(2a)	(2b)	(3) ^A	(4)	(5)	(6)	(7)	(8)	(9) ^{B,C}	(10)	(11) ^{B,C}	(13)	(14)	(15)	
Standard	Sieve Designation		Nominal Sieve Opening	±Y Variation for Average Opening	+X Maximum Variation for Opening	Resulting Maximum Individual Opening	Compliance Sieves		Inspection Sieves		Calibration Sieves		Typical Wire Diameter	Permissible Average Wire Diameter	
	U.S. Alternative	Metric Alternative					Sample Openings per 100 ft ²	Maximum Standard Deviation	Sample Openings per Sieve	Maximum Standard Deviation	Sample Openings per Sieve	Maximum Standard Deviation		Min	Max
mm	in.	mm	mm	mm	mm	mm	per 100 ft ²	Maximum Standard Deviation	Sample Openings per Sieve	Maximum Standard Deviation	Sample Openings per Sieve	Maximum Standard Deviation	mm	mm	mm
125	5 in.		5.00	3.30	4.06	129.06	20	—	all	—	all	—	8.00	6.8	9.2
106	4.24 in.		4.24	2.80	3.59	109.59	20	—	all	—	all	—	6.30	5.4	7.2
100	4 in.		4.00	2.65	3.44	103.44	20	—	all	—	all	—	6.30	5.4	7.2
90	3½ in.		3.50	2.39	3.18	93.18	20	—	all	—	all	—	6.30	5.4	7.2
75	3 in.		3.00	2.00	2.78	77.78	20	—	all	—	all	—	6.30	5.4	7.2
63	2½ in.		2.50	1.69	2.44	65.44	20	—	all	—	all	—	5.60	4.8	6.4
53	2.12 in.	56	2.20	1.50	2.24	58.24	20	—	all	—	all	—	5.00	4.3	5.8
50	2 in.		2.12	1.42	2.15	55.15	20	—	all	—	all	—	5.00	4.3	5.8
45	1¾ in.		2.00	1.34	2.06	52.06	20	—	all	—	all	—	5.00	4.3	5.8
			1.75	1.21	1.91	46.91	20	—	all	—	all	—	4.50	3.8	5.2
			1.57	1.08	1.75	41.75	20	—	all	—	all	—	4.50	3.8	5.2
37.5	1½ in.		1.50	1.01	1.67	39.17	20	1.103	all	—	all	—	4.50	3.8	5.2
			1.40	0.961	1.60	37.10	20	1.035	all	—	all	—	4.00	3.4	4.6
31.5	1¼ in.	35.5	1.25	0.855	1.47	32.97	20	0.907	all	—	all	—	4.00	3.4	4.6
			1.10	0.762	1.35	29.35	20	0.802	all	—	all	—	3.55	3.0	4.1
26.5	1.06 in.		1.06	0.722	1.29	27.79	20	0.758	all	—	all	—	3.55	3.0	4.1
25	1.00 in.		1.00	0.682	1.24	26.24	20	0.715	all	—	all	—	3.55	3.0	4.1
22.4	7/8 in.		0.875	0.613	1.14	23.54	150	0.641	15	0.431	30	0.460	3.15	2.7	3.6
			0.787	0.548	1.05	21.05	150	0.575	15	0.368	30	0.393	3.15	2.7	3.6
19	¾ in.		0.750	0.522	1.01	20.01	150	0.548	15	0.350	30	0.374	3.15	2.7	3.6
			0.709	0.495	0.97	18.97	150	0.521	15	0.314	30	0.335	3.15	2.7	3.6
16	5/8 in.		0.625	0.441	0.89	16.89	150	0.467	15	0.278	30	0.297	2.80	2.4	3.2
			0.551	0.387	0.81	14.81	150	0.414	15	0.251	30	0.268	2.80	2.4	3.2
13.2	0.530 in.		0.530	0.365	0.78	13.98	150	0.393	15	0.229	30	0.244	2.50	2.1	2.9
12.5	½ in.		0.500	0.346	0.75	13.25	150	0.374	15	0.198	30	0.211	2.50	2.1	2.9
11.2	7/16 in.		0.438	0.311	0.69	11.89	150	0.340	15	0.189	30	0.202	2.24	1.9	2.6
			0.394	0.279	0.64	10.64	150	0.308	15	0.171	30	0.182	2.00	1.7	2.3
9.5	3/8 in.		0.375	0.265	0.61	10.11	150	0.294	15	0.155	30	0.165	1.80	1.5	2.1
			0.354	0.251	0.59	9.59	150	0.281	15	0.147	30	0.157	1.80	1.5	2.1
8	5/16 in.		0.312	0.224	0.54	8.54	150	0.254	15	0.140	30	0.149	1.80	1.5	2.1
			0.280	0.200	0.50	7.60	150	0.230	15	0.127	30	0.136	1.60	1.3	1.9
6.7	0.265 in.		0.265	0.189	0.48	7.18	150	0.219	15	0.116	30	0.123	1.60	1.3	1.9
6.3	¼ in.		0.250	0.178	0.46	6.76	150	0.208	15	0.111	30	0.118	1.60	1.3	1.9
5.6	No. 3½		0.223	0.159	0.42	6.02	150	0.189	15	0.106	30	0.113	1.40	1.2	1.7
			0.197	0.142	0.39	5.39	150	0.172	15	0.096	30	0.103	1.40	1.2	1.7
4.75	No. 4		0.187	0.135	0.37	5.12	150	0.165	15	0.092	40	0.097	1.25	1.06	1.50
			0.177	0.128	0.36	4.86	150	0.158	15	0.088	40	0.093	1.25	1.06	1.50
4	No. 5		0.157	0.114	0.33	4.33	150	0.143	15	0.084	40	0.089	1.25	1.06	1.50
			0.140	0.102	0.30	3.85	200	0.130	20	0.076	40	0.081	1.12	0.95	1.30
3.35	No. 6		0.132	0.096	0.29	3.64	200	0.125	20	0.071	40	0.071	1.00	0.85	1.15
			0.124	0.091	0.28	3.43	200	0.119	20	0.067	40	0.068	1.00	0.85	1.15
2.8	No. 7		0.110	0.081	0.26	3.06	200	0.108	20	0.064	40	0.064	1.00	0.85	1.15
			0.0984	0.073	0.24	2.74	200	0.099	20	0.060	40	0.064	0.90	0.77	1.04
2.36	No. 8		0.0937	0.069	0.23	2.59	200	0.095	20	0.056	40	0.056	0.90	0.77	1.04
			0.0882	0.065	0.22	2.46	200	0.091	20	0.054	40	0.057	0.90	0.77	1.04
2	No. 10		0.0787	0.059	0.20	2.20	250	0.083	25	0.051	50	0.051	0.80	0.68	0.92
			0.0709	0.053	0.19	1.99	250	0.077	25	0.051	50	0.051	0.80	0.68	0.92
1.7	No. 12		0.0661	0.050	0.18	1.88	250	0.074	25	0.051	50	0.051	0.80	0.68	0.92
			0.0630	0.047	0.17	1.77	250	0.070	25	0.051	50	0.051	0.80	0.68	0.92
1.4	No. 14		0.0555	0.042	0.16	1.56	400	0.064	40	0.051	80	0.052	0.71	0.60	0.82
			0.0492	0.038	0.15	1.40	400	0.058	40	0.045	80	0.047	0.63	0.54	0.72

TABLE 1 Continued

(1)	(2a)	(2b)	(3) ^A	(4)	(5)	(6)	(7)	(8)	(9) ^{B,C}	(10)	(11) ^{B,C}	(12)	(13)	(14)	(15)
Standard	Sieve Designation		Nominal Sieve Opening	±Y Variation for Average Opening	+X Maximum Variation for Opening	Resulting Maximum Individual Opening	Compliance Sieves		Inspection Sieves		Calibration Sieves		Typical Wire Diameter	Permissible Average Wire Diameter	
	U.S. Alternative	Metric Alternative					Sample Openings per 100 ft ²	Maximum Standard Deviation	Sample Openings per Sieve	Maximum Standard Deviation	Sample Openings per Sieve	Maximum Standard Deviation		Sample Openings per Sieve	Maximum Standard Deviation
1.18	No. 16		0.0469	0.036	0.14	1.32	400	0.056	40	0.043	80	0.045	0.63	0.54	0.72
1	No. 18		0.0441	0.034	0.14	1.26	400	0.054	40	0.042	80	0.044	0.56	0.48	0.64
µm		µm	in.	µm	µm	µm							mm		
850	No. 20		0.0354	27.6	118	1018	400	45.51	40	35.22	80	36.74	0.500	0.43	0.58
			0.0331	26.2	114	964	400	43.66	40	33.79	80	35.25	0.500	0.43	0.58
			0.0315	24.8	109	909	400	41.79	40	32.34	80	33.74	0.450	0.38	0.52
710	No. 25		0.0278	22.2	101	811	500	38.36	50	30.43	100	31.62	0.450	0.38	0.52
			0.0248	19.9	93	723	500	35.23	50	27.95	100	29.04	0.400	0.34	0.46
600	No. 30		0.0234	19.0	91	691	500	34.04	50	27.00	100	28.06	0.400	0.34	0.46
			0.0220	17.9	87	647	500	32.43	50	25.73	100	26.73	0.355	0.30	0.41
500	No. 35		0.0197	16.2	80	580	600	29.96	60	24.21	120	25.09	0.315	0.27	0.36
			0.0177	14.7	75	525	600	27.86	60	22.51	120	23.32	0.280	0.24	0.32
425	No. 40		0.0165	14.0	73	498	600	26.79	60	21.65	120	22.43	0.280	0.24	0.32
			0.0157	13.3	70	470	600	25.71	60	20.78	120	21.52	0.250	0.21	0.29
355	No. 45		0.0139	12.0	65	420	800	23.72	80	19.68	160	20.30	0.224	0.19	0.26
			0.0124	10.8	60	375	800	21.90	80	18.17	160	18.75	0.200	0.17	0.23
300	No. 50		0.0117	10.4	58	358	800	21.20	80	17.59	160	18.15	0.200	0.17	0.23
			0.0110	9.8	56	336	800	20.26	80	16.81	160	17.34	0.180	0.15	0.21
250	No. 60		0.0098	8.9	52	302	800	18.82	80	15.61	160	16.11	0.160	0.13	0.19
			0.0088	8.1	49	273	800	17.53	80	14.54	160	15.01	0.160	0.13	0.19
212	No. 70		0.0083	7.8	47	259	800	16.93	80	14.05	160	14.49	0.140	0.12	0.17
			0.0079	7.4	45	245	800	16.32	80	13.54	160	13.97	0.140	0.12	0.17
180	No. 80		0.0070	6.8	43	223	1000	15.27	100	12.91	200	13.28	0.125	0.106	0.150
			0.0063	6.3	40	200	1000	14.20	100	12.00	200	12.34	0.112	0.095	0.130
150	No. 100		0.0059	6.0	38	188	1000	13.65	100	11.53	200	11.86	0.100	0.085	0.115
			0.0055	5.7	37	177	1000	13.09	100	11.06	200	11.38	0.100	0.085	0.115
125	No. 120		0.0049	5.2	34	159	1000	12.23	100	10.33	200	10.63	0.090	0.077	0.104
			0.0044	4.8	32	144	1000	11.46	100	9.68	200	9.96	0.080	0.068	0.092
106	No. 140		0.0041	4.7	31	137	1000	11.10	100	9.38	200	9.65	0.071	0.060	0.082
			0.0039	4.5	30	130	1000	10.73	100	9.07	200	9.33	0.071	0.060	0.082
90	No. 170		0.0035	4.2	29	119	1000	10.10	100	8.53	200	8.78	0.063	0.054	0.072
			0.0031	3.9	27	107	1000	9.45	100	7.99	250	8.33	0.060	0.048	0.064
75	No. 200		0.0029	3.7	26	101	1000	9.12	100	7.70	250	8.04	0.050	0.043	0.058
			0.0028	3.6	25	96	1000	8.85	100	7.48	250	7.80	0.050	0.043	0.058
63	No. 230		0.0025	3.4	24	87	1000	8.29	100	7.01	250	7.31	0.045	0.038	0.052
			0.0022	3.2	22	78	1000	7.79	100	6.58	250	6.87	0.040	0.034	0.046
53	No. 270		0.0021	3.1	21	74	1000	7.56	100	6.39	250	6.67	0.036	0.031	0.041
			0.0020	3.0	21	71	1000	7.34	100	6.20	250	6.47	0.036	0.031	0.041
45	No. 325		0.0017	2.8	20	65	1000	6.95	100	5.87	250	6.13	0.032	0.027	0.037
			0.0016	2.7	19	59	1000	6.55	100	5.54	300	5.83	0.032	0.027	0.037
38	No. 400		0.0015	2.6	18	56	1000	6.38	100	5.39	300	5.69	0.030	0.024	0.035
			0.0014	2.6	18	54	1000	6.22	100	5.26	300	5.54	0.030	0.024	0.035
32	No. 450		0.0012	2.4	17	49	1000	5.87	100	4.96	300	5.23	0.028	0.023	0.033
25	No. 500		0.0010	2.2	15	40	1000	5.23	100	4.42	300	4.66	0.025	0.021	0.029
20	No. 635		0.0008	2.1	13	33	1000	4.73	100	4.00	300	4.22	0.020	0.017	0.023

^A Column 3—These numbers are only approximate but are in use for reference; the sieve shall be identified by the standard designation in millimetres or micrometres.

^B Columns 9 and 11—See Annex A1, which specifies that all openings will be inspected for test sieves having 15 openings or less.

^C Columns 9 and 11—These number of sample openings are based on an 8-in. diameter test sieve.

3.1.6 *mesh*—the number of wires or openings per linear inch (25.4 mm) counted from the center of any wire to a point exactly 1 in. (25.4 mm) distant, including the fractional distance between either thereof.

3.1.7 *plain weave*—sieve cloth in which the warp wires and shute wires pass over one and under one in both directions.

3.1.8 *shute wires*—the wires running the short way of, or across the cloth as woven (also referred to as the shoot, fill, or weft wires).

3.1.9 *sieve*—an apparatus for the purpose of sieving, consisting of a separating media mounted in a frame.

3.1.10 *sieve cloth*—woven wire cloth conforming to this specification.

3.1.11 *test sieve (wire cloth)*—a sieve manufactured by mounting sieve cloth in a frame, designed for use in particle size analysis by sieving.

3.1.11.1 *compliance test sieve*—a test sieve manufactured using sieve cloth which has been inspected prior to being mounted in the sieve frame; and that meets the requirements of Table 1 in part based on the standard deviation of the required number of sample openings per 100 square feet of sieve cloth (Column 7) not exceeding the maximum allowable for a confidence level of 66 % (Column 8).

3.1.11.2 *inspection test sieve*—a test sieve manufactured using sieve cloth which has been inspected after being mounted in the sieve frame; and that meets the requirements of Table 1 in part based on the standard deviation of the required number of sample openings in the test sieve (Column 9) not exceeding the maximum allowable for a confidence level of 99 % (Column 10).

3.1.11.3 *calibration test sieve*—a test sieve manufactured using sieve cloth which has been inspected after being mounted in the sieve frame; and that meets the requirements of Table 1 in part based on the standard deviation of the required number of sample openings in the test sieve (Column 11) not exceeding the maximum allowable for a confidence level of 99.73 % (Column 12).

3.1.11.3.1 *Discussion*—Calibration sieves have had at least twice as many openings measured as Inspection sieves.

3.1.12 *twill weave*—sieve cloth in which the warp wires and shute wires pass over two and under two wires in both directions.

3.1.13 *warp wires*—the wires running the long way of the cloth as woven.

4. Ordering Information

4.1 Orders for items under this specification should include the following information as required:

4.1.1 Description of item(s) (Test Sieve or Sieve Cloth),

4.1.2 ASTM E11 designation and year of issue,

4.1.3 Quantity of each item, and

4.1.4 Sieve designation (Table 1, Standard Column 1, Alternate Column 2).

4.1.4.1 Test sieves can be supplied based on different levels of confidence as Compliance Sieves, Inspection Sieves, and Calibration Sieves.

4.2 Test sieves in standard circular or nonstandard frame:

4.2.1 Nominal sieve frame diameter (see Table 2), and

4.2.2 Nominal sieve frame height (see Table 2).

4.3 Description of nonstandard sieve.

5. Sieve Cloth Requirements

5.1 The sieve cloth used in test sieves shall meet the requirements of Table 1 and shall be designated Specification E11 Sieve Cloth. The number of inspected apertures shall be in accordance with Table 1 (Column 7). Sieve cloth conforming to this specification shall be woven from stainless steel, brass, or bronze. Sieve cloth with openings greater than or equal to 75 micrometres shall be woven using a plain weave. For sieve cloth with openings equal to or less than 63 micrometres the sieve cloth may be supplied using a twill weave. The sieve cloth shall not be coated or plated.

5.2 All measurements of openings and wire diameters shall be made along the midpoints of the openings as shown in Fig. 1.

5.3 There shall be no punctures or obvious defects in the sieve cloth.

6. Technical Requirements

6.1 *Opening Sizes, Tolerances, and Standard Deviation:*

6.1.1 Four tolerances shall be applied: the variation for average opening (Y), the maximum variation (X), the maximum standard deviation and the average wire diameter. The opening tolerances apply to the opening sizes, measured on the midpoint of the opening (see Fig. 1), and applied separately in both the warp and shute directions.

6.1.2 The average opening size shall not exceed the sieve designation by more than $\pm Y$ (Table 1, Column 4):

$$Y = \left(\frac{w^{0.98}}{27} + 1.6 \right) 0.9 \quad (1)$$

where Y and w are expressed in micrometres.

TABLE 2 Dimensions of Standard Frames

Nominal Diameter, in.	Diameter Tolerance, in. (mm)	Typical Frame ^A
	Inside at Top ^B	Nominal Height, in. (mm)
3	3.000 + 0.030 / -0.000 (76.2 + 0.76 / -0.00)	1¼ (31.8) FH ^C 5⁄8 (15.9) HH
6	6.000 + 0.030 / -0.000 (152.4 + 0.76 / -0.00)	1¾ (44.5) FH 1 (25.4) HH
8	8.000 + 0.030 / -0.000 (203.2 + 0.76 / -0.00)	2 (50.8) FH 1 (25.4) HH
10	10.000 + 0.030 / -0.000 (254 + 0.76 / -0.00)	3 (76.2) FH 1½ (38.1) HH
12	12.000 + 0.030 / -0.000 (304.8 + 0.76 / -0.00)	3¼ (82.6) FH 2 (50.8) IH 1¾ (41.3) HH

^A Frame height measured from top of frame to top of sieve cloth.

^B Measured 0.2 in. (5 mm) below the top of the frame.

^C FH = full height; HH = half height; IH = intermediate height.




FIG. 1 Aperture Size

6.1.3 The maximum opening size measured shall not exceed the nominal opening size w (Table 1, Column 1), by more than X (Table 1, Column 5):

$$X = \left(\frac{2w^{0.75}}{3} + 4w^{0.25} \right) 0.9 \quad (2)$$

where X and w are expressed in micrometres.

6.1.4 The intermediate value Z shall be stated as follows:

$$Z = \frac{X + Y}{2} \quad (3)$$

6.1.5 The maximum standard deviation is calculated based on the Gaussian normal distribution curve, truncated at the left end at 0 and at the right end at $w + X$. The area under the curve to the maximum value $w + X$ minus the area under the curve to the intermediate value Z , is equal to this critical area between $(w + Z)$ and $(w + X)$ not exceeding more than 5 % of the openings (see Appendix X2). The tolerances for sigma are then calculated based on:

$$\frac{\Phi\left(\frac{X}{\sigma}\right) - \Phi\left(\frac{Z}{\sigma}\right)}{\Phi\left(\frac{X}{\sigma}\right) - \Phi\left(\frac{-w}{\sigma}\right)} = 0.05 \quad (\text{see Appendix X4})$$

and the results are given in Table 1 for Compliance sieve cloth (Column 8).

6.1.5.1 In order to increase the probability or acceptance confidence level from 66 % at one-sigma to $X\sigma$, specifically 99 % (2.58σ) and 99.73 % (3σ) for Inspection and Calibration sieves respectively, these maximum standard deviation values are determined by dividing sigma by a correction or K-factor. These K-factors are determined based on approximation to a Chi-square distribution for the sample variance as follows:

$$K = 1 + X\sigma / \sqrt{2(n - 1)} \quad (4)$$

6.1.5.2 The applicable resulting K-factors (see Appendix X3) are then applied and the maximum standard deviation tolerances are determined as follows:

$$\sigma_x = \text{sigma} / K \quad (5)$$

6.1.5.3 The resulting tolerances are given in Table 1 for Inspection Sieves (Column 10) and for Calibration Sieves (Column 12), and are presented for convenience based on the K-factors per the required minimum number of openings.

6.1.6 The actual standard deviation of the openings in the warp and weft directions, when taken separately, shall not exceed the values shown in Table 1 for each type. If the number of sample openings is less than 15, the maximum standard deviation is not evaluated. If more than the minimum number of openings are measured, the maximum standard deviation shall be calculated (see Eq 5) based on the corresponding K-factor calculation (see Eq 4).

6.1.6.1 The population standard deviation σ is obtained by measuring all of the full openings N found in the test sieve and is calculated from the following equation:

$$\sigma = \sqrt{\frac{1}{N} \sum_{i=1}^N (w_i - \bar{w})^2} \quad (6)$$

6.1.6.2 The sample standard deviation s is calculated from the measurement of the number of apertures, n as listed in Table 1 (Column 8 for Sieve Cloth, Column 10 for Inspection Sieves, and Column 12 for Calibration Sieve), using the following equation:

$$s = \sqrt{\frac{1}{n-1} \sum_{i=1}^n (w_i - \bar{w})^2} \quad (7)$$

6.2 Wire Diameters:

6.2.1 The wire diameters given in Table 1, Column 13 are typical.

6.2.2 The average wire diameter in a test sieve or sieve cloth shall fall between the tolerance (d_{\min} and d_{\max}) given in Table 1, Column 14 and 15, respectively. It is recognized that mechanical deformation of the wire occurs during weaving, and therefore the diameter measured after weaving may be different than the wire diameter before weaving. The average wire diameter shall be calculated based on the same number of sample apertures measured in accordance with Table 1.

6.2.3 The wires shall be crimped in such a manner that the cloth exhibits firmness, as agreed between the user and the supplier, as applied to roll goods.

6.3 Test Sieve Frames:

6.3.1 *General Requirements*—Frames for test sieves shall be constructed in such a manner to be rigid. The sieve cloth shall be mounted on a frame without distortion, looseness, or waviness. The method used to attach the sieve cloth to the frame shall be done so the material being sieved will not become caught in the joint between the sieve cloth and the frame.

6.3.2 *Standard Frames*—Sieve frames shall be circular. Typical frame sizes are 3 in., 6 in., 8 in., 10 in., and 12 in. diameter (or 76, 152, 203, 254, or 305 mm). Tolerances for dimensions of test sieve frames are given in Table 2. Frames shall be made of a noncorrosive material such as brass or stainless steel. The bottom of the frame shall be constructed so as to provide an easy sliding or nesting fit with any sieve frame of the same nominal diameter conforming to the specified dimensions.

6.3.3 The joint or fillet at the point where the sieve cloth and frame meet will provide a minimum clear sieving surface with a diameter equal to the nominal diameter, less 0.5 in. (13 mm) on up to and including 8 in. frames, and 1.0 in. (25 mm) on greater than 8 in. frames.

6.4 *Nonstandard Sieves:*

6.4.1 *Nonstandard Frames*—Other sieve frames may be square, rectangular, circular, or non-metal. The frame may have the sieve cloth permanently attached, or it may be designed so the sieve cloth is replaceable. The provisions of 6.3.1 apply. Nonstandard test sieves may be certified in accordance with Section 7.

6.4.2 *Sieves with Backing Cloth*—Backing cloth specifications can vary in accordance with the test sieve manufacturer. The use of a backing cloth will affect the sieve performance. Test sieves with a backing cloth can only be supplied as Compliance Sieves.

7. Test Sieve and Sieve Cloth Documentation and Certification

7.1 Documentation of the measurement of the openings in the sieve cloth must assure that the test sieve is traceable and certifiable. All test sieve certificates must be traceable by the test sieve serial number. Inspection and Calibration sieves must also include the date, name and signature of the person certifying to the test sieve quality.

7.2 Test sieves may be supplied as Compliance, Inspection, or Calibration Sieves.

7.2.1 A Compliance sieve certificate shall state that the test sieve has been manufactured with sieve cloth that has been inspected and found to be in compliance with the requirements

of Specification E11. The Certificate does not require any statistical documentation.

7.2.2 An Inspection sieve certificate shall state at a minimum the value for the average aperture size, separately in both the warp and shute direction of the sieve cloth. A Certificate with this inspection data must be supplied.

7.2.3 A Calibration sieve certificate shall state at a minimum the number of apertures and wire diameters measured, the average aperture size, standard deviation and average wire diameter, separately in both the warp and shute directions of the sieve cloth. A Certificate with this inspection data must be supplied.

8. Marking or Labeling of Test Sieves

8.1 Each test sieve supplied shall bear a label marked with the following information:

8.1.1 “Test Sieve,”

8.1.2 The “ASTM E11” designation,

8.1.3 Name of the manufacturer or distributor,

8.1.4 Test sieve designation from Table 1, Column 1, and

8.1.5 Alternate test sieve designation from Table 1, Column 2 (optional).

8.1.6 Each test sieve shall have a unique serial number permanently marked onto the sieve frame, skirt, or nameplate.

8.1.7 The test sieve may also be labeled with the Grade designation.

9. Keywords

9.1 aperture; calibration sieve; compliance sieve; inspection sieve; opening; particle size; sieve; sieve analysis; sieve cloth; sieve designation; test sieve; woven wire test sieve cloth

SUPPLEMENTARY REQUIREMENTS

The following supplementary requirements shall apply only when specified by the purchaser in the contract or order.

S1. Responsibility for Inspection

S1.1 Unless otherwise specified in the contract or purchase order, the producer is responsible for the performance of all inspection and test requirements specified herein. Except as otherwise specified in the contract or order, the producer may use his own or any other suitable facilities for the performance of the inspections and tests requirements specified herein, unless disapproved by the purchaser. The purchaser shall have the right to perform any of the inspections and tests set forth in this specification where such inspections are deemed necessary to ensure that materials meet the specification.

S2. Government Procurement

S2.1 Unless otherwise specified in the contract, the material shall be in packaged in accordance with the suppliers’ standard practice that will be acceptable to the carrier at lowest rates. Containers and packing shall comply with the Uniform Freight Classification rules or National Motor Classification rules. Marking for shipment of such materials shall be in accordance with Fed. Std. No. 123 for civil agencies, and MIL-STD-129 for military agencies.