



Designation: D5740 – 16

## Standard Guide for Writing Material Standards in the Classification D4000 Format<sup>1</sup>

This standard is issued under the fixed designation D5740; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### INTRODUCTION

This guide has been prepared to aid in the writing of material standards using the Classification **D4000** format. The following template is included which might be used directly for a draft document simply by filling in the blanks. See appendixes for additional explanatory information.

Standard Classification System for and Basis for Specification for \_\_\_\_\_ Molding and Extrusion Materials (\_\_\_\_\_)

#### 1. Scope\*

1.1 This classification system covers \_\_\_ materials suitable for \_\_\_\_\_. The inclusion or exclusion of recycled plastics in this classification system must be addressed here.

1.2 The properties included in this standard are those required to identify the compositions covered. Other requirements necessary to identify particular characteristics important to specialized applications are to be specified by using suffixes as given in Section 5.

1.3 This classification system and subsequent line callout (specification) are intended to provide a means of calling out plastic materials used in the fabrication of end items or parts. It is not intended for the selection of materials. Material selection can be made by those having expertise in the plastic field only after careful consideration of the design and the performance required of the part, the environment to which it will be exposed, the fabrication process to be employed, the costs involved, and the inherent properties of the material other than those covered by this standard.

NOTE 1—Insert **Note 1** here to show the appropriate ISO equivalency statement.

1.4 The following precautionary caveat pertains only to the test method portion, Section 11, of this classification system: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility*

*of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

#### 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

**D618 Practice for Conditioning Plastics for Testing**

**D883 Terminology Relating to Plastics**

**D1600 Terminology for Abbreviated Terms Relating to Plastics**

**D3892 Practice for Packaging/Packing of Plastics**

**D4000 Classification System for Specifying Plastic Materials**

**D5205 Classification System and Basis for Specification for Polyetherimide (PEI) Materials**

**D5630 Test Method for Ash Content in Plastics**

**D6779 Classification System for and Basis of Specification for Polyamide Molding and Extrusion Materials (PA)**

**D7209 Guide for Waste Reduction, Resource Recovery, and Use of Recycled Polymeric Materials and Products (Withdrawn 2015)**<sup>3</sup>

NOTE 2—Omit **D7209** if use of recycled plastic is not allowed.

**E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications**

<sup>1</sup> This guide is under the jurisdiction of ASTM Committee **D20** on Plastics and is the direct responsibility of Subcommittee **D20.94** on Government/Industry Standardization.

Current edition approved Sept. 1, 2016. Published September 2016. Originally approved in 1995. Last previous edition approved in 2011 as D5740 – 11. DOI: 10.1520/D5740-16.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.

\*A Summary of Changes section appears at the end of this standard

2.2 ISO Standards:<sup>4</sup>

ISO 3451-1 Plastics—Determination of Ash Content—Part 1: General Methods

3. Terminology

3.1 Except for the terms defined below, the terminology used in this classification system is in accordance with Terminologies D883 and D1600.

4. Classification

4.1 \_\_\_ materials are classified into groups according to their composition. These groups are subdivided into classes and grades as shown in the Basic Property Table (Table \_\_\_). An example of a basic property table can be found in Classification System D6779. The property table contains a footnote referring to Section \_\_\_ for reference to specimen source and preparation.

NOTE 3—An example of this classification system is given as follows: The specification \_\_\_ indicates the following:

- \_ = \_\_\_ as found in Terminology D1600,
- \_ = \_\_\_ (group),
- \_ = \_\_\_ (class), and
- \_ = requirements given in Table \_\_\_ (grade).

4.1.1 Reinforced, filled, and lubricated versions of \_\_\_ materials that are found in Table \_\_\_ are classified according to the reinforcement used and the nominal level, by weight percent, of the reinforcement. The grade is identified by a single letter that indicates the filler or reinforcement used and two digits, in multiples of 5, that indicate the nominal quantity in percent by weight. Thus, a grade containing 35 % glass reinforcement would be indicated by \_\_\_ G35. This specification indicates

- \_ = \_\_\_ as found in Terminology D1600,
- \_ = \_\_\_ (group),
- \_ = \_\_\_ (class), and
- \_ = 35 % glass reinforcement and requirements given Table \_\_\_ (grade).

The reinforcement letter designations and associated tolerance levels are shown in the following table:

TABLE 1 Reinforcement-Filler<sup>A</sup> Symbols<sup>B</sup> and Tolerances

Symbol	Material	Tolerance
C	Carbon and graphite	±2 %
D	Alumina trihydrate	±2 %
E	Clay	±2 %
F	Cellulose	±2 %
G	Glass	±2 %
H	Aramid	±2 %
J	Boron	±2 %
K	Calcium carbonate	±2 %
L	Lubricants (for example: PTFE, graphite)	Depends upon material and process—to be specified.
M	Mineral	±2 %
N	Natural organic (for example: cotton, sisal, hemp, flax)	±2 %
P	Mica	±2 %
Q	Silica	±2 %
R	Combinations of reinforcements and/or fillers	±2 %
S	Synthetic organic	±2 %
T	Talcum	±2 %

<sup>4</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

V	Metal	±2 %
W	Wood	±2 %
X	Not specified	To be specified

<sup>A</sup>Ash content of filled and/or reinforced materials is to be determined using either Test Method D5630 or ISO 3451-1 where applicable.

<sup>B</sup>Additional symbols will be added to this table as required.

NOTE 4—This part of the classification system uses the percent of reinforcements or additives, or both, in the callout of the modified basic material. The types and percentages of reinforcements and additives are sometimes shown on the supplier’s technical data sheet. If necessary, additional callout of these reinforcements and additives can be accomplished by use of the suffix part of the system (see Section 5).

NOTE 5—Materials containing reinforcements or fillers, or both, at nominal levels not in multiples of five are included in the nearest grade designation. For example, a material with a nominal glass fiber level of 33 % is included with Grade G35 as shown in 4.1.1.

4.1.2 To facilitate incorporation of future or special materials the “other” category for group (00), class (0), and grade (0) is shown in Table \_\_\_.

4.2 Reinforced, filled, and lubricated versions of \_\_\_ materials that are not in Table \_\_\_ are classified in accordance with Tables \_\_\_ and A or B. Table \_\_\_ is used to specify the Group or the group and class of \_\_\_ and Table A or B is used to specify the property requirements.

4.2.1 Reinforced, filled, and lubricated variations of the basic materials are identified by a single letter from Table 1 that indicates the filler and/or reinforcement used and two digits that indicate the nominal quantity in percent by weight. A second letter, from Table 1a, when desired, is used to indicate the form or structure of the reinforcement and/or filler, but is not used for functional mixtures. Thus, a letter designation G for glass, E for beads or spheres or balls, and 33 for percent by weight, GE33, specifies a reinforced or filled material with 33 percent by weight in the form of glass beads, spheres, or balls. The reinforcement letter designations and associated tolerance levels are shown in the previous table. Form and structure letter designations are shown in the following table:

TABLE 1a Symbols for the Form or Structure of Fillers and Reinforcing Materials

Symbol	Form or Structure
C	Chips, cuttings
D	Fines, powders
E	Beads, spheres, balls
F	Fiber
G	Ground
H	Whisker
K	Knitted fabric
L	Layer
M	Mat (fabric, thick)
N	Non-woven (fabric, thin)
P	Paper
R	Roving
S	Flake
T	Cord
V	Veneer
W	Woven fabric
Y	Yarn
X	Not specified

4.2.2 Specific requirements for reinforced, filled, or lubricated \_\_\_ materials shall be shown by a six-character designation. The designation will consist of the letter “A” or “B” and