



Designation: **A779/A779M—12 A779/A779M – 16**

Standard Specification for Steel Strand, Seven-Wire, Uncoated, Compacted for Prestressed Concrete¹

This standard is issued under the fixed designation A779/A779M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers two types and three grades of compacted, seven-wire, uncoated strand for use in prestressed concrete construction. The two types of strand are low-relaxation and stress-relieved (normal-relaxation). The three grades are 245 [1700], 260 [1800] and 270 [1860].

1.2 This specification is applicable for orders in either inch-pound units (as Specification A779) or in SI units (as Specification A779M).

1.3 The values stated in either inch-pound or SI units are to be regarded as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the specification.

2. Referenced Documents

2.1 ASTM Standards:²

[A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products](#)

[A994 Guide for Editorial Procedures and Form of Product Specifications for Steel, Stainless Steel, and Related Alloys](#)

[A1061/A1061M Test Methods for Testing Multi-Wire Steel Prestressing Strand](#)

2.2 U.S. Military Standard³

[MIL-STD-129 Marking for Shipment and Storage](#)

2.3 U.S. Federal Standard³

[Fed. Std. No. 123 Marking for Shipments \(Civil Agencies\)](#)

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *compacted strand*—strand that has been compacted by drawing through a die or a similar compacting process and subsequently stress-relieved prior to winding into reels or reelless packs.

3.1.2 *lot*—all of the compacted strand of the same grade in the reels or reelless packs produced on the same production equipment and submitted for inspection at the same time.

3.1.3 *strand*—a group of wires having a center wire enclosed tightly by six helically placed outer wires with a uniform pitch of not less than 14 and not more than 18 times the nominal diameter of the strand.

4. Classification

4.1 *Grade 245 [1700]*—Nominal diameter of 0.7 in. [18.0 mm] with tensile strength of 247 ksi [1705 MPa] based on nominal area of the strand.

4.2 *Grade 260 [1800]*—Nominal diameter of 0.6 in. [15.2 mm] with tensile strength of 263 ksi [1815 MPa] based on nominal area of the strand.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.05 on Steel Reinforcement.

Current edition approved Sept. 1, 2012/Sept. 1, 2016. Published October 2012/September 2016. Originally approved in 1980. Last previous edition approved in 2010/2012 as [A779/A779M—10/A779/A779M – 12](#). DOI: [10.1520/A0779_A0779M-12.10.1520/A0779_A0779M-16](#).

² For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, [http://dodssp.daps.dla.mil](#).

*A Summary of Changes section appears at the end of this standard



TABLE 1 Breaking Strength Requirements

Nominal Diameter of Strand		Specified Minimum Breaking Strength of Strand, lbf [kN]	Nominal Steel Area of Strand		Nominal Mass (Weight) of Strands lb/1000 ft [kg/1000 m]
in.	[mm]		in. ²	[mm ²]	
0.5	[12.7]	Grade 270 [1860] 47 000 [209]	0.174	[112]	600 [890]
(0.6)	[15.2]	Grade 260 [1800] 67 440 [300]	0.256	[165]	873 [1295]
0.7	[18.0]	Grade 245 [1700] 85 430 [380]	0.346	[223]	1176 [1750]

4.3 *Grade 270 [1860]*—Nominal diameter of 0.5 in. [12.7 mm] with tensile strength of 270 ksi [1860 MPa] based on nominal area of the strand.

5. Ordering Information

5.1 It shall be the responsibility of the purchaser to specify all requirements that are necessary for material ordered to this specification. Such requirements to be considered include, but are not limited to, the following:

- 5.1.1 Quantity (feet [metres]),
- 5.1.2 Type of strand (low-relaxation or stress-relieved (normal-relaxation)),
- 5.1.3 Grade and nominal diameter of strand (Section 4),
- 5.1.4 Load-elongation curve, if desired (12.2.1),
- 5.1.5 Outside inspection, if required (Section 13),
- 5.1.6 Packaging (16.1), and
- 5.1.7 ASTM designation and date of issue.

6. Materials and Manufacture

6.1 The steel shall be of such quality that, when processed, the finished wire shall be free of detrimental flaws and undue segregation.

6.2 Wire from which the strand is to be fabricated shall be in the cold-drawn condition and have a common dry-drawn finish.

6.3 After stranding and compacting, all low-relaxation strand shall be subjected to a continuous thermal-mechanical treatment to produce the prescribed mechanical properties. For stress-relieved (normal-relaxation) strand, only thermal treatment is necessary. Temper colors which result from the stress-relieving operation are considered normal for the finished appearance of this strand.

7. Chemical Requirements

7.1 The chemical analysis of each heat shall be determined in accordance with Test Methods, Practices, and Terminology A751.

7.2 Variations in production processes and equipment necessitate the individual selection of an appropriate chemical composition at the discretion of the manufacturer.

7.3 Phosphorus and sulfur values shall not exceed the following:

Phosphorus 0.040 % max

Sulfur 0.050 % max

8. Mechanical Property Requirements

8.1 Tests for mechanical properties shall be conducted in accordance with Test Methods A1061/A1061M.

8.2 *Breaking Strength*—The breaking strength of the finished strand shall conform to the values specified in Table 1.

8.3 *Yield Strength*—Yield strength in pounds [kN] shall be measured at 1 % extension under load. The minimum load at 1 % extension shall conform to the specified values shown in Table 2. Initial loads are listed in Table 2.

8.3.1 The extension under load shall be measured by an extensometer calibrated with the smallest division not larger than 0.0001 in. /in. [0.0001 mm/mm] of gage length.

8.4 *Elongation*—The total elongation of the strand under maximum load shall not be less than 3.5 % using a gage length of not less than 24 in. [600 mm]. It shall be permissible to determine the total elongation value by adding, to the 1.0 % yield extension, the percent extension or movement between the jaws gripping the strand after yield determination. The percent is calculated on the new base length of jaw-to-jaw distance.

8.5 *Relaxation Properties*—Low-relaxation strand shall have relaxation losses of not more than 2.5 % when initially loaded to 70 % of specified minimum breaking strength after 1000 hours of testing.