



Designation: A945/A945M – 16

Standard Specification for High-Strength Low-Alloy Structural Steel Plate with Low Carbon and Restricted Sulfur for Improved Weldability, Formability, and Toughness¹

This standard is issued under the fixed designation A945/A945M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope*

1.1 This specification covers high-strength low-alloy structural steel plate intended for use in welded construction of naval ships where a savings in weight [mass] is important. Plates that conform to this specification offer improved weldability, formability, and toughness resulting from the specified alloying elements with limitations on carbon, sulfur, and residual element contents. Grades 50 and 65 may be provided as-rolled, control-rolled, thermo-mechanical control processed (including accelerated cooling), normalized, or quenched and tempered as required to meet the specified mechanical requirements.

1.2 The maximum thickness or weight [mass] of plates shall be as follows:

Grade	Plate thickness, max, in. [mm]	Plate weight [mass], max, lb/ft ² [kg/m ²]
50	2 [50]	81.7 [393]
65	2½ [65]	102 [502]

1.3 If the steel is to be welded, it is presupposed that a welding procedure suitable for the grade of steel and intended use or service will be utilized.

1.4 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text the SI units are shown in brackets. The values stated in each system are not exact equivalents, therefore, each system is to be used independently of the other without combining values in any way.

2. Referenced Documents

2.1 *ASTM Standards*:²

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is under the direct responsibility of Subcommittee A01.02 on Structural Steel for Bridges, Buildings, Rolling Stock and Ships.

Current edition approved Sept. 1, 2016. Published September 2016. Originally approved in 1995. Last previous edition approved in 2011 as A945/A945M – 06 (2011). DOI: 10.1520/A0945_A0945M-16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- [A6/A6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling](#)
- [A370 Test Methods and Definitions for Mechanical Testing of Steel Products](#)
- [A673/A673M Specification for Sampling Procedure for Impact Testing of Structural Steel](#)
- [A700 Guide for Packaging, Marking, and Loading Methods for Steel Products for Shipment](#)
- [E208 Test Method for Conducting Drop-Weight Test to Determine Nil-Ductility Transition Temperature of Ferritic Steels](#)

3. General Requirements for Delivery

3.1 Plates furnished under this specification shall conform to the applicable requirements of the current edition of Specification [A6/A6M](#).

3.2 If specified in the purchase order, plates ordered under this specification shall be prepared for shipment in accordance with the requirements of the current edition of Specification [A700](#).

4. Materials and Manufacture

4.1 The steel shall be made to fine grain practice.

4.2 Grade 65 plates less than 1 in. [25 mm] in thickness shall be provided from continuously cast product.

4.3 Except as specified in [5.1](#) and [5.2](#), the plates after finish-rolling shall be in one of the following conditions: as-rolled, control-rolled, or thermo-mechanical control processed (including accelerated cooling).

5. Heat Treatment

5.1 Grade 50 plates and Grade 65 plates are normally furnished without heat treatment. The manufacturer has the option to normalize or quench and temper such plates to meet the mechanical requirements of Section [7](#) provided that the heat treatment is reported on the test report.

5.2 Grade 65 plates greater than 1¼ in. [32 mm] in thickness shall be furnished in the quenched and tempered heat treatment.

*A Summary of Changes section appears at the end of this standard