



Designation: **A356/A356M – 11** **A356/A356M – 11 (Reapproved 2016)**

Standard Specification for Steel Castings, Carbon, Low Alloy, and Stainless Steel, Heavy-Walled for Steam Turbines¹

This standard is issued under the fixed designation A356/A356M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers one grade of martensitic stainless steel and several grades of ferritic steel castings for cylinders (shells), valve chests, throttle valves, and other heavy-walled castings for steam turbine applications.

1.2 Optional supplementary requirements (S1 through S5) shall apply as selected by and specified by the purchaser.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3.1 Within the text, the SI units are shown in brackets.

2. Referenced Documents

2.1 *ASTM Standards*:²

[A370 Test Methods and Definitions for Mechanical Testing of Steel Products](#)

[A488/A488M Practice for Steel Castings, Welding, Qualifications of Procedures and Personnel](#)

[E94 Guide for Radiographic Examination](#)

[E125 Reference Photographs for Magnetic Particle Indications on Ferrous Castings](#)

[E165 Practice for Liquid Penetrant Examination for General Industry](#)

[E186 Reference Radiographs for Heavy-Walled \(2 to 4½ in. \(50.8 to 114 mm\)\) Steel Castings](#)

[E280 Reference Radiographs for Heavy-Walled \(4½ to 12 in. \(114 to 305 mm\)\) Steel Castings](#)

[E446 Reference Radiographs for Steel Castings Up to 2 in. \(50.8 mm\) in Thickness](#)

[E709 Guide for Magnetic Particle Testing](#)

2.2 *Manufacturers' Standardization Society of the Valve and Fittings Industry Standard*:³

[SP-55 Quality Standard for Steel Castings for Valves, Flanges, Fittings, and Other Piping Components \(Visual Method\)](#)

3. Classification

3.1 The castings are furnished in the grades shown in [Table 1](#).

4. Ordering Information

4.1 Orders for material to this specification should include the following information:

4.1.1 A description of the casting by pattern number or drawing (dimensional tolerances shall be included on the casting drawing),

4.1.2 Grade of steel,

4.1.3 Options in the specification, and

4.1.4 The supplementary requirements desired, including the standards of acceptance.

¹ This specification is under the jurisdiction of ASTM Committee [A01](#) on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee [A01.18](#) on Castings.

Current edition approved Oct. 1, 2011; Sept. 1, 2016. Published November 2011; September 2016. Originally approved in 1952. Last previous edition approved in 2007 as [A356/A356M – 07](#); [A356/A356M – 11](#). DOI: [10.1520/A0356_A0356M-11-10.1520/A0356_A0356M-11R16](#).

² For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Manufacturers Standardization Society of the Valve and Fittings Industry (MSS), 127 Park St., NE, Vienna, VA 22180-4602, [http://www.mss-hq.org](#).

*A Summary of Changes section appears at the end of this standard

TABLE 1 Chemical Requirements^A

Grade/ UNS Number	Material	Composition, %												
		Carbon	Manganese	Silicon	Phosphorus, max	Sulfur, max	Molybdenum	Chromium	Nickel	Vanadium	Columbium	Nitrogen	Aluminum	Other
J03502	1 carbon steel	0.35 ^B max	0.70 ^B max	0.60 max	0.035	0.030	
J12523	2 ½ % molybdenum	0.25 ^B max	0.70 ^B max	0.60 max	0.035	0.030	0.45-0.65	
J12540	5 ½ % chromium, ½ % molybdenum	0.25 ^B max	0.70 ^B max	0.60 max	0.035	0.030	0.40-0.60	0.40-0.70	
J12073	6 1¼ % chromium, ½ % molybdenum	0.20 max	0.50-0.80	0.60 max	0.035	0.030	0.45-0.65	1.00-1.50	
J11697	8 1 % chromium, 1 % molybdenum, vanadium	0.20 max	0.50-0.90	0.20-0.60	0.035	0.030	0.90-1.20	1.00-1.50	...	0.05-0.15	
J21610	9 1 % chromium, 1 % molybdenum, vanadium	0.20 max	0.50-0.90	0.20-0.60	0.035	0.030	0.90-1.20	1.00-1.50	...	0.20-0.35	
J22090	10 2¼ % chromium, 1 % molybdenum	0.20 max	0.50-0.80	0.60 max	0.035	0.030	0.90-1.20	2.00-2.75	
CA6NM	martensitic chromium	0.06 max	1.00 max	1.00 max	0.040	0.030	0.4-1.0	11.5-14.0	3.5-4.5	
J91540	nickel													

^A Where ellipses appear in this table, there is no requirement and the element need not be analyzed for or reported.

^B For each 0.01 % reduction in carbon below the maximum specified, an increase of 0.04 percentage points of manganese over the maximum specified for that element will be permitted up to 1.00.

5. Melting Process

5.1 The steel shall be made by the open-hearth or electric-furnace process.

5.2 Deoxidation Practice:

5.2.1 Deoxidation of the carbon and low-alloy steel grades shall be by manganese and silicon. Furnace or ladle deoxidation with other agents is permissible with the approval of the purchaser.

5.2.2 The purchaser may specify that no aluminum be added.

5.2.3 Vacuum deoxidation is acceptable. The specific method shall be subject to approval by the purchaser.

6. Heat Treatment

6.1 *Preliminary Heat Treatment*—The castings may receive such preliminary heat treatment as the founder may elect to employ.

6.2 Heat Treatment for Final Properties:

6.2.1 *Normalizing*—The castings shall be heated to and held at the proper temperature for a sufficient time to effect the desired transformation and withdrawn from the furnace and allowed to cool to effect complete transformation.

6.2.2 *Tempering*—The casting shall be heated to and held at the proper temperature, which shall be below the transformation range, and then cooled under suitable conditions. The tempering temperature shall not be less than 1100°F [595°C].

6.2.3 *Stress Relieving*—The stress relieving operation shall be carried out in the same manner as tempering. The temperature shall be within 50°F [28°C], but not exceeding the final tempering temperature.

6.3 Stainless Steel Casting:

6.3.1 *Normalizing*—The castings shall be heated to 1850°F [1010°C] minimum, held sufficiently at that temperature to uniformly heat the castings, and air cooled to below 200°F [93°C].

6.3.2 *Tempering*—The castings shall be final tempered from 1050 to 1150°F [565 to 620°C].

6.3.3 *Stress Relieving*—The stress relieving operation shall be performed in the same manner as tempering. Temperature shall be between 1050°F [565°C] and 1150°F [620°C].

7. Chemical Composition

7.1 The steel shall conform to the requirements given in [Table 1](#).

8. Tensile Requirements

8.1 Tensile properties shall conform to the requirements listed in [Table 2](#) as determined by the test specimen set forth in [Section 9](#).

8.2 Tension tests shall be performed in accordance with Test Methods and Definitions [A370](#).

9. Number of Tests and Retests

9.1 One tension test shall be made from each heat in each heat-treatment charge and from each casting on which attached coupons are specified. The bar from which the test specimen is taken shall be heat treated with the casting represented.

9.2 If any test specimen shows defective machining or develops flaws, it shall be discarded and another specimen substituted from the same heat.

9.3 If the results of the mechanical tests for any lot or casting do not conform to the requirements specified, the founder may reheat treat and retest such lot or casting.

10. Test Specimen

10.1 Tension test specimens and samples for microexamination may be taken from coupons conforming substantially to the dimensions shown in [Fig. 1](#) and from the locations in the coupon as indicated in [Fig. 1](#). These coupons shall have been cast attached to the castings, except as provided in [10.2](#), and have remained attached, without partial severing, until the completion of the heat treatment for final properties.

TABLE 2 Tensile Requirements

Grade	Material	Tensile Strength, min, ksi [MPa]	Yield Strength, min, ksi [MPa]	Elongation in 2 in. [50 mm] min, %	Reduction of Area, min, %
1	carbon steel	70 [485]	36 [250]	20.0	35.0
2	½ % molybdenum	65 [450]	35 [240]	22.0	35.0
5	½ % chromium, ½ % molybdenum	70 [485]	40 [275]	22.0	35.0
6	1¼ % chromium, ½ % molybdenum	70 [485]	45 [310]	22.0	35.0
8	1 % chromium, 1 % molybdenum, vanadium	80 [550]	50 [345]	18.0	45.0
9	1 % chromium, 1 % molybdenum, vanadium	85 [585]	60 [415]	15.0	45.0
10	2¼ % chromium, 1 % molybdenum	85 [585]	55 [380]	20.0	35.0
CA6NM	martensitic chromium nickel	110 [760]	80 [550]	15.0	35.0