



Designation: A660/A660M – 11 (Reapproved 2016)

# Standard Specification for Centrifugally Cast Carbon Steel Pipe for High-Temperature Service<sup>1</sup>

This standard is issued under the fixed designation A660/A660M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 This specification<sup>2</sup> covers carbon steel pipe made by the centrifugal casting process intended for use in high-temperature, high-pressure service. Pipe ordered under this specification shall be suitable for fusion welding, bending, and other forming operations.

1.2 Several grades of carbon steels are covered. Their compositions are given in [Table 1](#).

1.3 Supplementary requirements (S1 to S9) of an optional nature are provided. The supplementary requirements call for additional tests to be made, and when desired shall be so stated in the order, together with the number of such tests required.

1.4 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of each other. Combining values from the two systems may result in nonconformance with the specification.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>3</sup>

[A530/A530M Specification for General Requirements for Specialized Carbon and Alloy Steel Pipe](#)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved Sept. 1, 2016. Published September 2016. Originally approved in 1972. Last previous edition approved in 2011 as A660/A660M – 11. DOI: 10.1520/A0660\_A0660M-11R16.

<sup>2</sup> For ASME Boiler and Vessel Code applications see related Specification SA-660 in Section II of that Code.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[E94 Guide for Radiographic Examination Using Industrial Radiographic Film](#)

[E114 Practice for Ultrasonic Pulse-Echo Straight-Beam Contact Testing](#)

[E125 Reference Photographs for Magnetic Particle Indications on Ferrous Castings](#)

[E142 Method for Controlling Quality of Radiographic Testing \(Withdrawn 2000\)](#)<sup>4</sup>

[E186 Reference Radiographs for Heavy-Walled \(2 to 4½ in. \(50.8 to 114 mm\)\) Steel Castings](#)

[E381 Method of Macroetch Testing Steel Bars, Billets, Blooms, and Forgings](#)

[E446 Reference Radiographs for Steel Castings Up to 2 in. \(50.8 mm\) in Thickness](#)

2.2 *ANSI Standards:*

[B36.10 American Standard for Welded and Seamless Wrought Steel Pipe](#)<sup>5</sup>

[B46.1 Surface Texture](#)<sup>5</sup>

2.3 *MSS Standards:*

[SP-54 Quality Standard for Steel Castings for Valves, Flanges, and Fittings and Other Piping Components - Radiographic Examination Method](#)<sup>6</sup>

## 3. Ordering Information

3.1 Orders for material under this specification should include the following, as required, to describe the desired material adequately:

3.1.1 Quantity (feet, metres, or number of lengths),

3.1.2 Name of material (centrifugally cast pipe),

3.1.3 Grade ([Table 1](#)),

3.1.4 Size (outside or inside diameter and minimum wall thickness),

3.1.5 Length (specific or random), (Permissible Variations in Length Section of Specification [A530/A530M](#)),

<sup>4</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

<sup>5</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

<sup>6</sup> Available from Manufacturers Standardization Society of the Valve and Fittings Industry (MSS), 127 Park St., NE, Vienna, VA 22180-4602, <http://www.mss-hq.com>.

\*A Summary of Changes section appears at the end of this standard

**TABLE 1 Chemical Requirements**

	Composition, max, %		
	Grade WCA	Grade WCB	Grade WCC
Carbon	0.25 <sup>A</sup>	0.30	0.25 <sup>B</sup>
Manganese	0.70 <sup>A</sup>	1.00	1.20 <sup>B</sup>
Phosphorus	0.035	0.035	0.035
Sulfur	0.035	0.035	0.035
Silicon	0.60	0.60	0.60

<sup>A</sup> For each reduction of 0.01 % below the specified maximum carbon content, an increase of 0.04 % manganese above the specified maximum will be permitted up to a maximum of 1.10 %.

<sup>B</sup> For each reduction of 0.01 % below the specified maximum carbon content, an increase of 0.04 % manganese above the specified maximum will be permitted to a maximum of 1.40 %.

3.1.6 End finish (Ends Section of Specification **A530/A530M**),

3.1.7 Optional Requirements (Sections **7.2**, **8.2**, **8.3**, **11.1**, Section **12** and S1 to S9 (Supplementary Requirements),

3.1.8 Test report required (Certification Section of Specification **A530/A530M**),

3.1.9 Specification designation, and

3.1.10 Special requirements.

#### 4. General Requirements

4.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of Specification **A530/A530M** unless otherwise provided herein.

#### 5. Materials and Manufacture

##### 5.1 Machining:

5.1.1 All centrifugally cast pipe shall have both the inner and outer surfaces machined.

5.1.2 After heat treatment, the pipe shall be machined to a finish with a roughness value no greater than 250  $\mu\text{in}$ . [6.35  $\mu\text{m}$ ] arithmetical average deviation (AA), terms as defined in ANSI B46.1 unless otherwise specified.

##### 5.2 Heat Treatment:

5.2.1 All pipe shall receive a heat treatment proper for its design and chemical composition.

5.2.2 Castings shall be heat treated after they have been allowed to cool below the transformation range.

#### 6. Temperature Control

6.1 Furnace temperatures for heat treating shall be effectively controlled by pyrometers.

#### 7. Chemical Requirements

7.1 The steel shall conform to the requirements as to chemical composition prescribed in **Table 1**.

##### 7.2 Product Analysis:

7.2.1 At the request of the purchaser, a product analysis shall be made by the manufacturer on every heat.

7.2.2 The results of these analyses shall be reported to the purchaser or his representative, and shall conform to the requirements specified in **Table 1**.

7.2.3 If the analysis of one of the tests specified in **7.2.1** does not conform to the requirements specified, an analysis of each pipe from the same heat may be made, and all pipes conforming to the requirements shall be accepted.

#### 8. Mechanical Requirements

##### 8.1 Tensile Properties:

8.1.1 The material shall conform to the requirements as to tensile properties prescribed in **Table 2**.

8.1.2 *Transverse or Longitudinal Tension Test*—One test shall be made on a specimen from one end of one length of pipe representing each heat in each heat-treatment lot.

##### 8.2 Flattening Test:

8.2.1 A flattening test shall be performed when requested by the purchaser or when stated by the purchaser on the order that the pipe is to be upset, swaged, expanded, bent, or formed by some other operation.

8.2.2 A flattening test need not be performed on heavy wall pipe which is not to be upset, swaged, expanded, bent, or formed in some other manner.

8.2.3 When required by **8.2**, a test shall be made on specimens cut from one end of each length of pipe.

8.2.4 A flattening test when required shall be performed in accordance with the requirements for seamless and centrifugally cast pipe in the Flattening Test Requirements Section of Specification **A530/A530M**.

NOTE 1—In heavy-walled small-diameter tubing the flattening test specimen may be bored out so that the *OD/t* ratio will be greater than 11.0.

##### 8.3 Hydrostatic Test:

8.3.1 Each length of pipe shall be hydrostatically tested in accordance with the Hydrostatic Test Requirements Section of Specification **A530/A530M** when requested by the purchaser and stated on the order. If performance of the hydrostatic test is not required by the purchaser, the manufacturer shall guarantee pipe to pass the test and mark each length of pipe with the letters “NH” immediately following the specification number, indicating that the pipe has not been hydrostatically tested.

8.3.2 When required by **8.3**, each length of pipe shall be subjected to the hydrostatic test. The test pressure shall be maintained for not less than 5 min.

#### 9. Permissible Variation in Wall Thickness

9.1 The wall thickness shall not vary over the specified minimum wall thickness by more than 10 %. There shall be no variation under the specified minimum wall thickness.

NOTE 2—A system of standard pipe sizes has been approved by the American National Standards Institute, as ANSI B36.10. This system may

**TABLE 2 Tensile Requirements**

	WCA		WCB		WCC	
	ksi	MPa	ksi	MPa	ksi	MPa
Tensile strength, min	60	415	70	485	70	485
Yield strength, min	30	210	36	250	40	275
Elongation in 2 in. or 50 mm, min, %	24		22		22	
Reduction of area, min, %	35		35		35	