



Designation: D4349 – 16

Classification System and Basis for Specification for Polyphenylene Ether (PPE) Materials¹

This standard is issued under the fixed designation D4349; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope*

1.1 This classification system covers the basic polymers and copolymers known as polyphenylene ethers and polyphenylene oxides, as well as filled, modified, and reinforced versions. Recycled materials are included in this standard as Class 5 of Table PPE.

NOTE 1—Addition to the natural polymer or copolymer of pigments, colorants, or other additives can cause the final composition to no longer meet the requirements specified for the natural polymer or copolymer.

NOTE 2—The preferred abbreviation for polyphenylene ether is PPE, as noted in Terminology **D1600**.

1.2 This classification system and subsequent line callout (specification) are intended to provide a means of calling out plastic materials used in the fabrication of end items or parts. It is not intended for the selection of materials. Material selection should be made by those having expertise in the plastic field after careful consideration of the design and the performance required of the part, the environment to which it will be exposed, the fabrication process to be employed, the costs involved, and the inherent properties of the material other than those covered by this standard.

1.3 There may be other requirements necessary to identify particular characteristics important to specific applications. These are to be specified by using the suffixes described in Section 5.

1.4 The values stated in SI units are to be regarded as standard.

NOTE 3—There is no known ISO equivalent to this standard.

¹ This classification system is under the jurisdiction of ASTM Committee **D20** on Plastics and is the direct responsibility of Subcommittee **D20.15** on Thermoplastic Materials.

Current edition approved Sept. 1, 2016. Published September 2016. Originally approved in 1989. Last previous edition approved in 2010 as D4349 - 10. DOI: 10.1520/D4349-16.

2. Referenced Documents

2.1 *ASTM Standards*:²

D256 Test Methods for Determining the Izod Pendulum Impact Resistance of Plastics

D618 Practice for Conditioning Plastics for Testing

D638 Test Method for Tensile Properties of Plastics

D648 Test Method for Deflection Temperature of Plastics Under Flexural Load in the Edgewise Position

D790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials

D792 Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement

D883 Terminology Relating to Plastics

D1600 Terminology for Abbreviated Terms Relating to Plastics

D3892 Practice for Packaging/Packing of Plastics

D4000 Classification System for Specifying Plastic Materials

D7209 Guide for Waste Reduction, Resource Recovery, and Use of Recycled Polymeric Materials and Products (Withdrawn 2015)³

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

2.2 *Underwriters Laboratories*:

UL 94 Standards for Tests for Flammability for Parts in Devices and Appliances⁴

3. Terminology

3.1 The terminology used in this classification is in accordance with Terminologies **D883** and **D1600**.

3.2 The polyphenylene ether materials will be designated PPE as specified in Terminology **D1600**.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from Underwriters Laboratories (UL), 2600 N.W. Lake Rd., Camas, WA 98607-8542, <http://www.ul.com>.

*A Summary of Changes section appears at the end of this standard

4. Classification

4.1 Polyphenylene ether-based materials are classified into groups according to their compositions. These groups are subdivided into classes and grades, as shown in Basic Property Table PPE.

NOTE 4—An example of this classification system is as follows:
The specification ASTM D4349 PPE 0223 would indicate:

- PPE = polyphenylene ether,
- 02 = polystyrene-modified material (Group),
- 2 = flame retarded (Class Description), and
- 3 = requirements given in Table PPE.

4.1.1 Reinforced, filled, and lubricated versions of PPE materials are classified according to the reinforcement used and the nominal level, by weight percent, of the reinforcement. The grade is identified by a single letter that indicates the filler or reinforcement used and two digits that indicate the nominal quantity in percent by weight. Thus, a grade containing 15 % glass reinforcement would be indicated by PPE0110 G15. This callout indicates:

- PPE = polyphenylene ether ___ as found in Terminology D1600,
- 01 = unmodified (group),
- 1 = general purpose (class),
- 0 = other (grade), and
- G15 = 15 % glass reinforcement

The reinforcement letter designations and associated tolerance levels are shown in Table 1.

TABLE 1 Reinforcement-Filler,^A Symbols,^B and Tolerances

Symbol	Material	Tolerance
C	Carbon and graphite	±2 %
D	Alumina trihydrate	±2 %
E	Clay	±2 %
F	Cellulose	±2 %
G	Glass	±2 %
H	Aramid	±2 %
J	Boron	±2 %
K	Calcium carbonate	±2 %
L	Lubricants (for example: PTFE, graphite)	Depends upon material and process—to be specified.
M	Mineral	±2 %
N	Natural organic (for example: cotton, sisal, hemp, flax)	±2 %
P	Mica	±2 %
Q	Silica	±2 %
R	Combinations of reinforcements and/or fillers	±3 %

^AAsh content of filled and/or reinforced materials is to be determined using either Test Method D5630 or ISO 3451-1 where applicable.

^BAdditional symbols will be added to this table as required.

NOTE 5—This part of the system uses the type and percentage of additives, fillers, and reinforcements to designate the modification of the basic material. The types and percentages are sometimes shown on the suppliers technical data sheet. If necessary, additional control of these compositional variables can be accomplished using the suffix part of the system, Section 5.

NOTE 6—Materials containing reinforcements or fillers, or both, at nominal levels not in multiples of five are included in the nearest grade designation. For example, a material with a nominal glass fiber level of 33 % is included with Grade G35 as shown in 4.1.1.

4.1.1.1 Although the values listed are necessary to include the range of properties available in existing materials, not every possible combination of the properties exist or can be obtained.

TABLE PPE Requirements for Polyphenylene Ether (PPE) Materials

NOTE 1—Values given are for natural materials only. Other colors can be different.^A

Group Description	Class Description	Grade Description	Heat Deflection, min		Specific Gravity, ASTM D792, min	Tensile Strength, D638, ^{B,C} MPa, min	Flexural Modulus, D790, ^{B,C} MPa, min	Izod Impact, D256, ^{B,D} J/m, min	
			at 1.82 MPa, D648, ^{B,C}	at 0.45 MPa, D648, ^{B,C}					
01 Unmodified	1 general purpose	0 other	E						
	2 flame retarded ^F	0 other	E						
	0 other	0 other	E						
02 PS modified materials	1 general purpose	1	90	N/A ^G	1.03	32	1750	265	
		2	100	N/A ^G	1.03	38	1900	240	
		3	100	N/A ^G	1.03	44	2150	185	
		4	110	N/A ^G	1.04	55	2300	160	
		5	130	N/A ^G	1.05	57	2300	160	
	2 flame retarded ^F	0 other
		1	67	N/A ^G	1.06	36	2200	190	
		2	80	N/A ^G	1.07	40	2250	130	
		3	85	N/A ^G	1.07	48	2350	100	
		4	105	N/A ^G	1.07	55	2350	160	
	03 PA modified materials	1 general purpose	0 other
			0 other
			1	N/A ^G	145	1.05	50	2000	170
			2	N/A ^G	155	1.05	50	2000	160
			3	N/A ^G	170	1.05	50	1800	530
2 flame retarded ^F		4	N/A ^G	180	1.05	55	2000	185	
		5	N/A ^G	195	1.05	58	2200	160	
		0 other	
		0 other	
		0 other	
04 Other	1 general purpose	0 other		

Group Description	Class Description	Grade Description	Heat Deflection, min		Specific Gravity, ASTM D792, min	Tensile Strength, D638, ^{B, C} MPa, min	Flexural Modulus, D790, ^{B, C} MPa, min	Izod Impact, D256, ^{B, D} J/m, min
			at 1.82 MPa, D648, ^B °C	at 0.45 MPa, D648, ^B °C				
05 Rework modified	2 flame retarded ^F	0 other
	0 other	0 other
	1 general purpose	0 other
	2 flame retarded ^F	0 other
	0 other	0 other

^A Use Tables A and B where necessary for colored materials.
^B See Table 2 for drying and molding conditions. Table 3 for test specimen sizes.
^C MPa × 145 = psi.
^D J/m × 0.01873 = ft-lbf/in.
^E Unfilled materials currently not available. Use Table A.
^F Flammability ratings determined in accordance with UL 94.
^G N/A—Not applicable for grade description.

TABLE A Reinforced Polyphenylene Ether Materials, Details Requirements

Designation Order Number	Property	Cell Limits									
		0	1	2	3	4	5	6	7	8	9
1	Heat deflection temperature, ^A D648, ^B 1.82 MPa, °C, min	unspecified	100	110	120	130	140	150	160	170	specify value
2	Heat deflection temperature, ^A D648, ^B 0.45 MPa, °C, min	unspecified	180	190	200	210	220	230	240	250	specify value
3	Tensile strength, D638, ^B MPa, ^C min	unspecified	45	55	65	80	100	120	140	160	specify value
4	Flexural modulus, D790, ^B MPa, ^C min	unspecified	2000	3000	4000	5000	6000	7500	9000	10 500	specify value
5	Izod impact, D256, ^B J/m, ^D min	unspecified	25	50	75	100	125	150	200	250	specify value

^A For specifying HDT use the “order number” corresponding to the appropriate test conditions for the material being defined. It is intended that one or the other of these requirements be used unless specific agreement between the supplier and the user requires both.
^B See Table 3 for test specimen sizes.
^C MPa × 145 = psi.
^D J/m × 0.01873 = ft-lbf/in.

TABLE B Unreinforced Polyphenylene Ether Materials, Details Requirements

Designation Order Number	Property	Cell Limits									
		0	1	2	3	4	5	6	7	8	9
1	Heat deflection temperature, ^A D648, ^B 1.82 MPa, °C, min	unspecified	65	75	85	95	105	115	125	135	specify value
2	Heat deflection temperature, ^A D648, ^B 0.45 MPa, °C, min	unspecified	125	135	145	155	165	175	185	195	specify value
3	Tensile strength, D638, ^B MPa, ^C min	unspecified	30	35	40	45	50	55	60	65	specify value
4	Flexural modulus, D790, ^B MPa, ^C min	unspecified	1500	1800	2100	2400	2700	3000	3300	3600	specify value
5	Izod impact, D256, ^B J/m, ^D min	unspecified	100	150	200	250	300	400	500	600	specify value

^A For specifying HDT use the “order number” corresponding to the appropriate test conditions for the material being defined. It is intended that one or the other of these requirements be used unless specific agreement between the supplier and the user requires both.
^B See Table 3 for test specimen sizes.
^C MPa × 145 = psi.
^D J/m × 0.01873 = ft-lbf/in.