



Standard Specification for Fiberglass (Glass-Fiber-Reinforced Thermosetting-Resin) Pipe and Pipe Fittings, Adhesive Bonded Joint Type, for Aviation Jet Turbine Fuel Lines¹

This standard is issued under the fixed designation D5677; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope-Scope*

1.1 This specification covers a reinforced plastic pipe and fittings system made from epoxy resin and glass-fiber reinforcement, together with adhesive for joint assembly, intended for service up to 150°F (65.6°C) and 150-psig (1034-kPa) operating pressure and surges up to 275 psig (1896 kPa) in aviation jet turbine fuel lines installed below ground.

1.2 The dimensionless designator NPS has been substituted in this specification for such traditional terms as *nominal diameter*, *size*, and *nominal size*.

1.3 The values stated in inch-pound units are to be regarded as standard. The values in parentheses are for information only.

1.4 The following safety hazards caveat pertains only to the test method portion, Section 9, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no known ISO equivalent to this standard.

2. Referenced Documents

2.1 *ASTM Standards*:²

D381 Test Method for Gum Content in Fuels by Jet Evaporation

D883 Terminology Relating to Plastics

D1599 Test Method for Resistance to Short-Time Hydraulic Pressure of Plastic Pipe, Tubing, and Fittings

D1600 Terminology for Abbreviated Terms Relating to Plastics

D1655 Specification for Aviation Turbine Fuels

D2310 Classification for Machine-Made “Fiberglass” (Glass-Fiber-Reinforced Thermosetting-Resin) Pipe

D2412 Test Method for Determination of External Loading Characteristics of Plastic Pipe by Parallel-Plate Loading

D3241 Test Method for Thermal Oxidation Stability of Aviation Turbine Fuels

D3567 Practice for Determining Dimensions of “Fiberglass” (Glass-Fiber-Reinforced Thermosetting Resin) Pipe and Fittings

D3951 Practice for Commercial Packaging

D5685 Specification for “Fiberglass” (Glass-Fiber-Reinforced Thermosetting-Resin) Pressure Pipe Fittings

F412 Terminology Relating to Plastic Piping Systems

F1173 Specification for Thermosetting Resin Fiberglass Pipe Systems to Be Used for Marine Applications

2.2 *Military Specification*:

MIL-T-5624 Turbine Fuel, Aviation, Grades JP-4, JP-5 and JP-5/JP-8 ST³

2.3 *ANSI Standard*:

B16.5 Steel Pipe Flanges and Flanged Fittings⁴

¹ This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.23 on Reinforced Plastic Piping Systems and Chemical Equipment.

Current edition approved Nov. 1, 2010/Sept. 1, 2016. Published March 2011/September 2016. Originally approved in 1995. Last previous edition approved in 2005/2010 as D5677–05/D5677–05 (2010). DOI: 10.1520/D5677-05R10.1520/D5677-16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

³ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://dodssp.daps.dla.mil>.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>—<http://www.ansi.org>.

*A Summary of Changes section appears at the end of this standard

3. Terminology

3.1 *Definitions*—Definitions are in accordance with Terminologies **D883** and **F412**, and abbreviations are in accordance with Terminology **D1600**, unless otherwise indicated.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *conductive*—a pipe or fitting that meets the requirements for conductivity listed in Section 6 of Specification **F1173**.

3.3 *Abbreviations:*

3.3.1 *RTRP, n*—reinforced thermosetting resin pipe.

4. Classification

4.1 *General:*

4.1.1 Pipe meeting this specification is classified by type, grade, and class similar to Classification **D2310**.

4.1.2 Fittings meeting this specification are also classified by type (method of manufacture) and grades (generic type of resin).

4.2 *Pipe:*

4.2.1 Type I Filament-Wound Pipe Nonconductive

4.2.2 Type Ia Filament-Wound Pipe Conductive

4.2.3 Type II Centrifugally Cast Pipe

4.3 *Fittings:*

4.3.1 Type I Filament-Wound Fittings Nonconductive

4.3.2 Type Ia Filament Wound Fittings Conductive

4.3.3 Type II Molded Fittings Nonconductive

4.4 *Grade:*

4.4.1 Grade 1 Glass-Fiber-Reinforced Epoxy Resin (Pipe and Fittings)

4.5 *Classes (Pipe Only):*

4.5.1 Class A No Liner

4.5.2 Class C Epoxy Resin Liner Nonreinforced

4.5.3 Class F Epoxy Resin Liner Reinforced

5. Materials and Manufacture

5.1 *General*—The fiberglass pipe shall be round and straight, and the pipe and fittings shall be of uniform density, resin content, and surface finish. All pipe ends shall be cut at right angles to the axis of the pipe and any sharp edges removed. The bore of the pipe and fittings shall have a smooth, uniform surface with no exposed fibers and may be permitted to contain a liner. The liner, if used, shall be composed of an epoxy resin formulation and may be permitted to contain a reinforcement.

5.2 *Material*—The pipe and fittings shall be made from epoxy resins and glass-fiber reinforcement of commercial first quality. Fillers, colorants, and other materials may be permitted to be added, provided the pipe and fittings meet all the requirements of this specification. Epoxy pipe shall be joined only with epoxy fittings.

5.3 *Adhesive*—Adhesive for joint assembly shall be a material suitable for providing a seal between the pipe and fittings in continuous service up to 150°F (65°C) and 150 psig (1034 kPa) with surges to 275 psig (1896 kPa). The adhesive shall be supplied as a kit which includes containers of all components in the amounts needed for each adhesive mixture. Instructions for use shall be marked on each container or listed on an instruction sheet included in each adhesive kit. When specified in the contract or purchase order, adhesive kits shall be furnished in a sufficient quantity for the particular procurement of pipe and fittings.

6. Dimensions

6.1 *Pipe*—The pipe shall be 1, 1.5, 2, 3, 4, 5, 6, 8, 10, 12, 14, and 16-in. (50, 80, 100, 16, 18, 20, 22, and 24-in. (25, 40, 50, 80, 100, 125, 150, 200, 250, 300, 350 and 400-mm)350, 400, 450, 500, 550, and 600-mm) nominal sizes as specified and shall have the dimensions and tolerances shown in **Table 1**. unless otherwise agreed upon by the purchaser and seller.

6.1.1 *Length*—Unless other lengths are specified on the purchase order, the length of the pipe shall be 20 ft (6.1 m), 30 ft (9.2 m), or 40 ft (12.2 m) with a plus tolerance of 2 ft (0.6 m) and a minus tolerance of 5 ft (1.5 m).

6.1.2 *Wall Thickness*—The minimum wall thickness of the pipe shall be not less than 87.5 % of the average wall thickness of the pipe as measured in Section 8 and tested in Section 9.

6.1.3 *Fittings*—Fittings shall be 1, 1.5, 2, 3, 4, 6, 8, 10, 12, 14, and 16-in. (50, 16, 18, 20, 22, and 24-in. (25, 40, 50, 80, 100, 150, 200, 250, 300, 350 and 400-mm)350, 400, 500, 550, and 600-mm) nominal sizes, as specified, and shall have dimensions suitable for joining to the pipe and enabling the pipe and fitting joint to meet the requirements of this specification. For purposes of this specification, fittings shall include couplings and flanges.

6.1.4 *Flanges*—Flanges shall conform to the bolt hole sizes and pattern for 150-lb steel flanges in accordance with ANSI B16.5.

TABLE 1 Dimensions of Pipe

NOTE 1—Nominal pipe diameters of 14 (350 mm) and 16 in. (406.4 mm) are available and approved with 14.000 (355.6 mm) and 16.000 (406.4 mm) outside diameters or inside diameters.

Nominal Pipe Diameter		Outside Diameter		Tolerance, Type I and Type Ia		Tolerance, Type II	
in.	(mm)	in.	(mm)	in.	(mm)	in.	(mm)
2 ± 0.30	(50)	2.375	(60.32)	±0.060 – 0.018	(±1.52 – 0.46)	±0.012	(±0.30)
3	(75)	3.500	(88.90)	±0.060 – 0.018	(±1.52 – 0.46)	±0.012	(±0.30)
4	(100)	4.500	(114.30)	±0.060 – 0.018	(±1.52 – 0.46)	±0.015	(±0.38)
6	(150)	6.625	(168.28)	±0.066 – 0.028	(±1.68 – 0.71)	±0.025	(±0.64)
8	(200)	8.625	(219.08)	±0.086 – 0.040	(±2.28 – 1.02)	±0.025	(±0.64)
10	(250)	10.750	(273.05)	±0.108 – 0.048	(±2.74 – 1.22)	±0.025	(±0.64)
12	(300)	12.750	(323.05)	±0.128 – 0.056	(±3.25 – 1.42)	±0.025	(±0.64)
14	(350)	14.000	(355.60)	±0.145 – 0.064	(±3.68 – 1.63)	±0.035	(±0.89)
16	(400)	16.000	(406.40)	±0.165 – 0.074	(±4.19 – 1.88)	±0.035	(±0.89)

TABLE 1 Dimensions of Pipe

NOTE 1—Nominal pipe diameters of 14 in. (350 mm), 16 in. (400 mm), 18 in. (450 mm), 20 in. (500 mm), 22 in. (550 mm), and 24 (600 mm) are available and approved with outside diameters or inside diameters as specified in Table 1.

Nominal Pipe Diameter		Outside Diameter		Tolerance, Type I and Type Ia		Tolerance, Type II	
in.	(mm)	in.	(mm)	in.	(mm)	in.	(mm)
1	(25)	1.315	(33.40)	+0.060 – 0.016	(+1.52 – 0.41)	±0.009	(±0.229)
1.5	(40)	1.900	(48.26)	+0.060 – 0.018	(+1.52 – 0.46)	±0.009	(±0.229)
2	(50)	2.375	(60.32)	+0.060 – 0.018	(+1.52 – 0.46)	±0.012	(±0.30)
3	(75)	3.500	(88.90)	±0.060 – 0.018	(±1.52 – 0.46)	±0.012	(±0.30)
4	(100)	4.500	(114.30)	±0.060 – 0.018	(±1.52 – 0.46)	±0.015	(±0.38)
5	(125)	5.563	(141.30)	±0.060 – 0.028	(±1.68 – 0.71)	±0.025	(±0.64)
6	(150)	6.625	(168.28)	±0.066 – 0.028	(±1.68 – 0.71)	±0.025	(±0.64)
8	(200)	8.625	(219.08)	±0.086 – 0.040	(±2.28 – 1.02)	±0.025	(±0.64)
10	(250)	10.750	(273.05)	±0.108 – 0.048	(±2.74 – 1.22)	±0.025	(±0.64)
12	(300)	12.750	(323.05)	±0.128 – 0.056	(±3.25 – 1.42)	±0.025	(±0.64)
14	(350)	14.000	(355.60)	±0.145 – 0.064	(±3.68 – 1.63)	±0.035	(±0.89)
16	(400)	16.000	(406.40)	±0.165 – 0.074	(±4.19 – 1.88)	±0.035	(±0.89)
18	(450)	18.000	(457.20)	±0.250	±6.35		
20	(500)	20.000	(508.00)	±0.250	±6.35		
22	(550)	22.000	(558.80)	±0.250	±6.35		
24	(600)	24.000	(609.60)	±0.250	±6.35		

ASTM D5677-16

<https://standards.iteh.ai/catalog/standards/sist/9dd0fde3-2404-4811-961f-f1725b70cd1/astm-d5677-16>

7. Performance Requirements

7.1 *Joint Strength*—Pipe, fittings, adhesive, and joints shall show no porosity or other evidence of failure when tested in accordance with 9.2.2.

7.2 *Hydrostatic Strength*—Pipe, fittings, adhesive, and joints shall withstand a hydrostatic pressure of 300 psi (2068 kPa) without any indication of porosity, delamination, splitting, or other evidence of failure when tested in accordance with 9.2.3.

7.3 *Impact Resistance*—Pipe and fittings shall show no porosity or visual evidence of damage that would affect serviceability when tested in accordance with 9.2.4.

7.4 *Boil Resistance*—Pipe and fittings shall show no evidence of delamination or other impairment and shall have a weight gain no greater than 1.0 % when tested in accordance with 9.2.5.

7.5 *External Load Resistance*—When tested as specified in 9.2.6, the pipe shall show no visual evidence of cracking, crazing, or other damage that could allow leakage of fuel through the pipe wall at 5 % deflection and no visual evidence of delamination, rupture, or other structural damage at 10 % deflection.

7.6 Degradation Resistance:

7.6.1 *Pipe and Fittings*—Pipe and fittings exposed to JP-5 and JP-5/JP-8 ST fuels, or Jet A and Jet A-1, in accordance with 9.2.7, shall exhibit no visual evidence of deterioration as a result of exposure to the fuels and shall have short-time rupture strengths of not less than 90 % of the short-time rupture strengths of unexposed pipe and fittings when tested in accordance with 9.2.7.1.

7.6.2 *Fuels*—JP-5 and JP-5/JP-8 ST-ST, or Jet A and Jet A-1 fuels contained within pipe and fittings in accordance with 4.2 and 4.3, shall not vary from control samples of the fuels in thermal stability and existent gum properties when tested, as specified, in accordance with 9.2.7.2.

7.6.3 *Hydrostatic Proof Test*—Pipe and fittings shall withstand a hydrostatic pressure of 225/275 psi (1551 kPa) without any indication of porosity when tested in accordance with 9.2.8.