



Designation: D6937 – 16

## Standard Test Method for Determining Density of Emulsified Asphalt<sup>1</sup>

This standard is issued under the fixed designation D6937; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

### 1. Scope

1.1 This test method covers the determination of density of emulsified asphalt used in highway construction. This unit is computed by determining the mass of an emulsified asphalt contained in a standard measure of known volume.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This test method does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

- 2.1 *ASTM Standards:*  
**E1 Specification for ASTM Liquid-in-Glass Thermometers**

### 3. Significance and Use

3.1 This test method provides a controlled laboratory test for the determination of quantitative volumes of emulsified asphalt for use in bills of lading, invoicing, and application rates.

### 4. Sample Conditioning for Testing

4.1 All emulsified asphalts shall be properly stirred to achieve homogeneity before testing.

4.2 All emulsified asphalts with viscosity testing requirements of 50°C shall be heated to 50 ± 3°C in the original sample container in a water bath or oven. The container should be vented to relieve pressure. After the sample reaches 50 ± 3°C, stir the sample to achieve homogeneity.

4.3 Emulsified asphalts with viscosity testing requirements of 25°C should be mixed or stirred at 25 ± 3°C in the original sample container to achieve homogeneity.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.42 on Emulsified Asphalt Test.

Current edition approved Sept. 15, 2016. Published September 2016. Originally approved in 2004. Last previous edition approved in 2008 as D6937 – 08. DOI: 10.1520/D6937-16.

NOTE 1—Emulsified asphalts with viscosity testing requirements of 25°C may be heated and stirred as specified in 4.2 if necessary. In the event the 4.2 method is used, the sample should be cooled to 25 ± 3°C before testing.

### 5. Apparatus

5.1 *Density Cup*—Stainless steel measure of known standard volume (83.2 mL).

5.2 *Balance*—capable of being read to the nearest 0.01 g.

5.3 *Water Bath*—constant-temperature, maintained at 25 ± 0.5°C.

5.4 *Thermometer*—ASTM 17C conforming to the requirements of Specification E1 or equivalent thermometric device.

### 6. Procedure

6.1 Stir the emulsified asphalt sample and place in a constant-temperature water bath maintained at 25 ± 0.5°C and bring sample to temperature.

6.2 Place the measure and its cap on the balance, tare, and zero the balance.

6.3 Remove the emulsified asphalt sample from the bath and stir, using care to avoid trapping air in the sample. If necessary, strain through a 850- $\mu$ m sieve to remove any skin or film that might be present in the emulsified asphalt.

6.4 Bring the measure to approximately 25°C and pour the emulsified asphalt into the measure, filling it completely (or within 2 mm of the rim).

6.5 Start placing the cap into the measure and remove, with a clean dry rag or paper, the excess emulsified asphalt oozing through the orifice in the cap.

6.6 When the cap is placed on tightly, clean the measure carefully, determine the mass on the tared balance to the nearest 0.01 g, and record.

### 7. Calculation

7.1 Calculate the density of the emulsified asphalt as follows:

$$W = (G)(11.98) \quad (1)$$

where:

$W$  = unit density of the emulsified asphalt, as expressed in g/L, and