



Designation: **F1325 – 91 (Reapproved 2008)^{ε1} F1325 – 91 (Reapproved 2016)**

Standard Specification for Stainless Steel Suture Needle Holders-General Workmanship Requirements and Corresponding Test Methods¹

This standard is issued under the fixed designation F1325; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Subsections 3.1.2 and 4.1 were editorially corrected in December 2008.

1. Scope

1.1 This specification covers general workmanship aspects of stainless steel suture needle holders intended for reuse in surgery.

2. Referenced Documents

2.1 *ASTM Standards*:²

E18 Test Methods for Rockwell Hardness of Metallic Materials

E92 Test Methods for Vickers Hardness and Knoop Hardness of Metallic Materials

E140 Hardness Conversion Tables for Metals Relationship Among Brinell Hardness, Vickers Hardness, Rockwell Hardness, Superficial Hardness, Knoop Hardness, Scleroscope Hardness, and Leeb Hardness

F899 Specification for Wrought Stainless Steels for Surgical Instruments

F921 Terminology Relating to Hemostatic Forceps

F1089 Test Method for Corrosion of Surgical Instruments

3. Terminology

3.1 *Definitions*:

3.1.1 *modified working end*—working surfaces possessing superior hardness characteristics which are either the result of depositing various materials on the base metal or the result of permanently securing an insert (such as by brazing) to the base metal.

3.1.2 *Discussion*—The typical method of modifying the working end of the suture needle holder is to use jaw inserts or to plasma deposit (flame plate) materials with improved wear characteristics such as tungsten carbide or stellite (trademarked). For the jaw insert method, the insert is brazed to the jaw face with a uniform deposit of silver solder which is free of crevices at all interfaces. For the flame plating method, a uniform layer of material is deposited which is 0.004 ± 0.001 in. thick.

3.2 Definitions applicable to stainless steel suture needle holders and the terms specified herein, shall be in accordance with Definitions of Terms—Terminology F921.

4. Materials

4.1 All component parts of the instrument other than the modified working end shall be fabricated from martensitic stainless steel type 410, 410X, 416, 420A, 420B, 420C, 420F, 420F Mod, and 440B per Specification F899 (see Note 1). The modified working end may be made of stellite (trademarked), tungsten carbide, or other suitable material.

NOTE 1—Free-machining grades of stainless steel are inappropriate for use due to their lower corrosion resistance and toughness.

5. Requirements

5.1 Heat treatment and hardness for component parts.

¹ This specification is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devices and is the direct responsibility of Subcommittee F04.33 on Medical/Surgical Instruments.

Current edition approved Feb. 1, 2008; Oct. 1, 2016. Published March 2008; October 2016. Originally approved in 1991. Last previous edition approved in 2002 as F1325 – 91 (2002) (2008)^{ε1}. DOI: 10.1520/F1325-91R08E01.10.1520/F1325-91R16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's standard's Document Summary page on the ASTM website.