



Designation: B124/B124M – 16a

Standard Specification for Copper and Copper Alloy Forging Rod, Bar, and Shapes¹

This standard is issued under the fixed designation B124/B124M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification establishes the requirements for copper and copper alloy rod, bar, and shapes intended for hot forging. The following coppers and copper alloys are involved:

Copper UNS Nos.	Copper Alloy UNS Nos.	Copper Alloy EN 1412 Nos.
C11000	C27450	CW612N
C14500	C27451	CW617N
C14700	C35330	
	C36500	
	C37000	
	C37700	
	C46400	
	C46750	
	C48200	
	C48500	
	C48600	
	C49250	
	C49255	
	C49260	
	C49265	
	C49300	
	C49340	
	C49345	
	C49350	
	C49355	
	C49360	
	C61900	
	C62300	
	C63000	
	C63200	
	C64200	
	C64210	
	C65500	
	C67500	
	C67600	
	C69150	
	C69240	
	C69300	
	C70620	
	C71520	
	C77400	
	C87700	
	C87710	

NOTE 1—Additional information about forging practice and forgings produced from these alloys is given in **Appendix X1** and in Specification **B283/B283M**.

1.2 *Units*—The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory requirements prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- B249/B249M** Specification for General Requirements for Wrought Copper and Copper-Alloy Rod, Bar, Shapes and Forgings
- B283/B283M** Specification for Copper and Copper-Alloy Die Forgings (Hot-Pressed)
- E54** Test Methods for Chemical Analysis of Special Brasses and Bronzes (Withdrawn 2002)³
- E62** Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods) (Withdrawn 2010)³
- E75** Test Methods for Chemical Analysis of Copper-Nickel and Copper-Nickel-Zinc Alloys (Withdrawn 2010)³
- E76** Test Methods for Chemical Analysis of Nickel-Copper Alloys (Withdrawn 2003)³
- E121** Test Methods for Chemical Analysis of Copper-Tellurium Alloys (Withdrawn 2010)³
- E478** Test Methods for Chemical Analysis of Copper Alloys

¹ This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.02 on Rod, Bar, Wire, Shapes and Forgings.

Current edition approved Oct. 1, 2016. Published October 2016. Originally approved in 1939. Last previous edition approved in 2016 as B124/B124M-16. DOI: 10.1520/B0124_B0124M-16A.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

*A Summary of Changes section appears at the end of this standard

2.2 Other Standards:

EN 1412 Copper and Copper Alloys—European Numbering System⁴

EN 12165 Copper and Copper Alloys—Wrought and Unwrought Forging Stock⁴

ISO 3110, Part 2 (TC 26 Ref. No. N 670 E/F) Determination of Aluminum Content: Flame Atomic Absorption Spectrometric Method⁴

JIS H 1068:2005 Methods for Determination of Bismuth in Copper and Copper Alloys⁵ (Japanese Industrial Standards)

4.2 The following options are available and, when required, should be specified at the time of placing of the order:

4.2.1 Mechanical Properties for Temper designated (Mechanical Properties Section),

4.2.2 Certification (Specification **B249/B249M**),

4.2.3 Test Report (Specification **B249/B249M**),

4.2.4 When product is ordered for ASME Boiler and Pressure Vessel Code Application (see Certification Section of Specification **B249/B249M**), and

4.2.5 Shapes; dimensional tolerances required and agreed upon (see **10.1.3**).

3. General Requirements

3.1 The following sections of Specification **B249/B249M**, as applicable, constitute a part of this specification:

- 3.1.1 Terminology,
- 3.1.2 Material and Manufacture,
- 3.1.3 Workmanship, Finish, and Appearance,
- 3.1.4 Sampling,
- 3.1.5 Number of Tests and Retests,
- 3.1.6 Specimen Preparation,
- 3.1.7 Test Methods,
- 3.1.8 Significance of Numerical Limits,
- 3.1.9 Inspection,
- 3.1.10 Rejection and Reheating,
- 3.1.11 Certification,
- 3.1.12 Mill Test Reports,
- 3.1.13 Packaging and Package Marking, and
- 3.1.14 Supplementary Requirements.

3.2 In addition, when a section with a title identical to that referenced in **3.1**, appears in this specification, it contains additional requirements that supplement those appearing in Specification **B249/B249M**.

4. Ordering Information

4.1 Include the following information when placing orders for products under this specification:

- 4.1.1 ASTM designation and year of issue (B124/B124M – XX), or EN 12165 and year of issue;
- 4.1.2 Copper or Copper-Alloy UNS No. designation, or EN 1412 No. designation;
- 4.1.3 Form (rod, bar, or shape) and size (Dimensions and Permissible Variations Section),
- 4.1.4 Permissible Variations (Dimensions and Permissible Variations Section),
- 4.1.5 Temper (Temper Section),
- 4.1.6 Length (Dimensions and Permissible Variations Section),
- 4.1.7 Quantity: total weight for each size and form,
- 4.1.8 If the product is purchased for agencies of the U.S. government (see the Supplementary Requirements Section of this specification for additional requirements, if specified.)

5. Materials and Manufacture

5.1 Materials:

5.1.1 The material of manufacture shall be a cast rod, bar, or billet of the designated copper or copper-alloy of such purity and soundness to be suitable for processing into the products prescribed herein.

5.1.2 In the event that heat identification or traceability is required, the purchaser shall specify the details desired.

NOTE 2—Due to the discontinuous nature of the processing of castings into wrought products, it is not always practical to identify a specific casting analysis with a specific quantity of finished material.

5.2 Manufacture:

5.2.1 The product shall be manufactured by such hot-working, cold-working, and annealing processes as to produce a uniform wrought structure in the finished product.

5.2.2 The product shall be hot- or cold-worked to the finished size and subsequently annealed, when required, to meet the temper properties specified.

6. Chemical Composition

6.1 The material shall conform to the chemical composition requirements in **Table 1** for the copper or copper alloy UNS No. or EN 1412 No. designation specified in the ordering information.

6.1.1 These composition limits do not preclude the presence of other elements. By agreement between the manufacturer and the purchaser, limits may be established and analysis required for unnamed elements.

6.2 For alloys in which either copper or zinc is listed as “remainder,” copper or zinc is the difference between the sum of results of all elements determined and 100 %. When all elements in **Table 1** for the specified copper-alloy are determined, the sum of results shall be as follows:

Copper Alloy UNS or EN 1412 No.	Sum of Results, % min
CW612N, CW617N	99.8
C36500, C37000, C46400, C48200, C48500, C48600, C69150	99.6
C27450, C27451, C35330, C37700, C46750, C49250, C49255, C49260, C49265, C49300, C49340, C49345, C49350, C49355, C49360, C61900, C62300, C63000, C63200, C64200, C64210, C65500, C67500, C67600, C69240, C69300, C70620, C71520, C77400	99.5
C87700, C87710	99.2

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁵ Available from Japanese Standards Association (JSA), Mita MT Bldg., 3-13-12 Mita, Minato-ku, Tokyo, 108-0073, Japan, <http://www.jsa.or.jp>.



TABLE 1 Chemical Requirements

Copper or Copper Alloy UNS or EN 1412 No.	Composition, %											Copper Plus Elements with Specific Limits Present, min			
	Copper	Lead	Tin	Iron	Nickel (incl Co)	Aluminum	Silicon	Manganese	Zinc	Sulfur	Tellurium		Phos- phorus	Arsenic	Bismuth
C11000	99.90 min ^A
C14500 ^B	99.90 min ^C	0.40-0.7	0.004-0.012
C14700 ^B	99.90 min ^D	0.20-0.50	...	0.002-0.005
C27450	60.0-65.0	0.25 max	...	0.35 max	remainder	99.5
C27451	61.0-65.0	0.25 max	...	0.35 max	remainder	0.05-0.20	99.5
C35330	59.5-64.0	1.5-3.5	remainder02-.25
C36500	58.0-61.0	0.25-0.7	0.25 max	0.15 max	remainder	99.6
C37000	59.0-62.0	0.8-1.5	...	0.15 max	remainder	99.6
C37700	58.0-61.0	1.5-2.5	...	0.30 max	remainder	99.5
C46400	59.0-62.0	0.20 max	0.50-1.0	0.10 max	remainder	99.6
C46750 ^E	59.2-62.5	0.25 max	1.00-1.80	0.10 max	0.50 max	remainder	0.05-0.15	99.5
C48200	59.0-62.0	0.40-1.0	0.50-1.0	0.10 max	remainder	99.6
C48500	59.0-62.0	1.3-2.2	0.50-1.0	0.10 max	remainder	99.6
C48600	59.0-62.0	1.0-2.5	.30-1.5	remainder02-.25
C49250 ^F	58.0-61.0	0.09 max	0.30 max	0.50 max	remainder	1.8-2.4	99.5
C49255 ^G	58.0-60.0	0.01 max	0.50 max	0.10 max	0.10-0.30	0.10 max	...	remainder	0.10 max	1.7-2.9	99.5
C49260 ^H	58.0-63.0	0.09 max	0.50 max	0.50 max	...	0.10 max	...	remainder	0.05-0.15	0.50-1.8	99.5
C49265 ^F	58.0-62.0 ^A	0.09-0.25	0.50 max	0.30 max	...	0.10 max	...	remainder	0.05-0.12	0.50-1.3	99.5
C49300 ^I	58.0-62.0	0.01 max	1.0-1.8	0.10 max	1.5 max	0.10 max	0.03 max	remainder	0.20 max	0.50-2.0	99.5
C49340 ^J	60.0-63.0	0.09 max	0.50-1.5	0.12 max	...	0.10 max	...	remainder	0.05-0.15	0.50-2.2	99.5
C49345 ^F	60.0-64.0 ^A	0.09-0.25	0.50-1.5	0.30 max	...	0.10 max	...	remainder	0.05-0.12	0.50-1.3	99.5
C49350 ^K	61.0-63.0	0.09 max	1.5-3.0	0.12 max	...	0.30 max	...	remainder	0.04-0.15	0.50-2.5	99.5
C49355 ^L	63.0-69.0	0.09 max	0.50-2.0	0.10 max	...	1.0-2.0	0.10 max	27.0-35.0	0.50-1.5	99.5
C49360	remainder	0.09 max	1.0-2.0	2.0-3.5	...	19.0-22.0	0.50-1.5	99.5
C61900	remainder ^A	0.02 max	0.6 max	3.0-4.5	...	8.5-10.0	...	0.8 max	99.5
C62300	remainder ^A	...	0.6 max	2.0-4.0	1.0 max	8.5-10.0	0.25 max	0.50 max	99.5

TABLE 1 Continued

Copper Alloy UNS or EN 1412 No.	Composition, %											Copper Plus Elements with Specific Limits Present, min			
	Copper	Lead	Tin	Iron	Nickel (incl Co)	Aluminum	Silicon	Manganese	Zinc	Sulfur	Tellurium		Phos- phorus	Arsenic	Bismuth
C63000	remainder ^A	...	0.20 max	2.0–4.0	4.0–5.5	9.0–11.0	0.25 max	1.5 max	0.30 max	99.5
C63200	remainder ^A	0.02 max	...	3.5–4.3 ^M	4.0–4.8 ^M	8.7–9.5	0.10 max	1.2–2.0	99.5
C64200	remainder ^A	0.05 max	0.20 max	0.30 max	0.25 max	6.3–7.6	1.5–2.2	0.10 max	0.50 max	0.09 max	...	99.5
C64210	remainder ^A	0.05 max	0.20 max	0.30 max	0.25 max	6.3–7.0	1.5–2.0	0.10 max	0.50 max	0.09 max	...	99.5
C65500	remainder ^A	0.05 max	...	0.8 max	0.6 max	...	2.8–3.8	0.50–1.3	1.5 max	99.5
C67500	57.0–60.0 ^A	0.20 max	0.50–1.5	0.8–2.0	...	0.25 max	...	0.05–0.50	remainder	99.5
C67600	57.0–60.0 ^A	0.50–1.0	0.50–1.5	0.40–1.3	0.05–0.50	remainder	99.5
C69150 ^A	82.5–87.5	0.05 max	0.025 max	0.25 max	0.20 max	0.7–1.3	0.02 max	0.25–0.6	remainder	99.6
C69240	71.0–72.5	0.25 max	0.30 max	0.20 max	0.10–0.50	...	1.8–2.2	0.6–1.2	remainder	0.06–0.12	99.5
C69300	73.0–77.0 ^A	0.09 max	0.20 max	0.10 max	0.10 max	...	2.7–3.4	0.10 max	remainder	0.04–0.15	99.5
C70620 ^N	86.5 min ^A	0.02 max	...	1.0–1.8	9.0–11.0	1.0 max	0.50 max	0.02 max	...	0.02 max	99.5
C71520 ^N	65.0 min ^A	0.02 max	...	0.40–1.0	29.0–33.0	1.0 max	0.50 max	0.02 max	...	0.02 max	99.5
C77400	43.0–47.0 ^A	0.09 max	9.0–11.0	remainder	99.5
C87700 ^O	87.5 min	0.09 max	2.0 max	0.50 max	0.25 max ^P	...	2.5–3.5	0.8 max	7.0–9.0	0.15 max	99.2
C87710 ^O	84 min	0.09 max	2.0 max	0.50 max	0.25 max ^P	...	3.0–5.0	0.8 max	9.0–11.0	0.15 max	99.2
CW612N	59.0–60.0	1.6–2.5	0.3 max	0.3 max	0.3 max ^P	0.05 max	remainder	99.8
CW617N	57.0–59.0	1.6–2.5	0.3 max	0.3 max	0.3 max ^P	0.05 max	remainder	99.8

^A Silver counts as copper.

^B Includes oxygen-free or deoxidized grades with deoxidizers (such as phosphorus, boron, lithium, or others) in amount agreed upon.

^C This includes copper + silver + tellurium + phosphorus.

^D This includes copper + silver + sulfur + phosphorus.

^E Includes antimony 0.05–0.15

^F Includes cadmium 0.001 % max.

^G Includes cadmium 0.01, selenium 0.02–0.07.

^H Includes cadmium 0.001 % max.

^I Includes antimony 0.50 % max and selenium 0.20 % max.

^J Includes cadmium 0.001 % max.

^K Includes antimony 0.02–0.10 %.

^L Includes boron 0.001 % max.

^M Iron content shall not exceed nickel content.

^N Carbon shall be 0.05 % max.

^O Antimony shall be 0.10 % max.

^P Not including Co.