



Designation: D7704 – 16

# Standard Test Method for Total Aldehydes in Styrene Monomer by Potentiometric Titration<sup>1</sup>

This standard is issued under the fixed designation D7704; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 This test method covers the wet chemical determination of total aldehydes in styrene monomer. Total aldehydes are calculated and reported as benzaldehyde. The Range of Concentration for this test method is 0.004 weight % to 0.013 weight %.

1.2 Limit of Detection (LOD) and Limit of Quantification (LOQ) is 0.0006 and 0.0020 weight %, respectively

1.3 In determining conformance of the test results using this method to applicable specifications, results shall be rounded off in accordance with the rounding-off method of Practice E29.

1.4 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard with the exception: weight % should be used rather than mass %.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

D1193 Specification for Reagent Water

D3437 Practice for Sampling and Handling Liquid Cyclic Products

D6809 Guide for Quality Control and Quality Assurance Procedures for Aromatic Hydrocarbons and Related Materials

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D16 on Aromatic Hydrocarbons and Related Chemicals and is the direct responsibility of Subcommittee D16.07 on Styrene, Ethylbenzene and C9 and C10 Aromatic Hydrocarbons.

Current edition approved June 1, 2016. Published October 2016. Originally approved in 2011. Last previous edition approved in 2012 as D7704 – 12. DOI: 10.1520/D7704-16.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

2.2 *Other Documents:*

OSHA Regulations, 29 CFR paragraphs 1910.1000 and 1910.1200<sup>3</sup>

## 3. Summary of Test Method

3.1 An alcoholic solution of hydroxylamine hydrochloride is added to a specimen of styrene monomer. Active aldehydes present react in accordance with Eq 1:



The amount of hydrochloric acid released, which is equivalent to the aldehyde present in the sample, is titrated with standard alcoholic potassium hydroxide solution.

## 4. Significance and Use

4.1 This test method is suitable for determining the quantity of aldehydes, both for quality control and quality assurance of the product.

## 5. Interferences

5.1 Ketones, if present, interfere by partially reacting with the reagent.

5.2 Methanol used in this procedure may partially react with aldehydes to form (hemi)acetals.

## 6. Apparatus

6.1 *Titration Vessel*, 150 mL.

6.2 *Combined pH – Glass Electrode*, dedicated for non-aqueous liquids.

6.3 *Stirring Bar*, 30 mm.

6.4 *Titration Stand* with stirrer.

6.5 *Pipets*, 25 mL.

6.6 *Volumetric Flasks*, 100 mL.

6.7 *Burets*, 5 mL. (Microburets are preferred.)

6.8 *Exchange Unit*, 5 mL.

<sup>3</sup> Available from DLA Document Services, Building 4/D, 700 Robbins Ave., Philadelphia, PA 19111-5094, http://quicksearch.dla.mil.

\*A Summary of Changes section appears at the end of this standard