



Designation: ~~D4103 – 90 (Reapproved 2009)~~ **D4103 – 90 (Reapproved 2016)**

Standard Practice for Preparation of Substrate Surfaces for Coefficient of Friction Testing¹

This standard is issued under the fixed designation D4103; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers procedures for the preparation of OVCT (Official Vinyl Composition Tile) and wood panels for subsequent use in tests to measure the coefficient of friction.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D1436 Test Methods for Application of Emulsion Floor Polishes to Substrates for Testing Purposes](#)

3. Significance and Use

3.1 The reliability of any of the practices using panels prepared by these procedures may be dependent upon the manner and care in which the test panels are prepared. Having these practices in a single procedure eliminates the necessity for covering these details in all of the practices wherein the panels are used.

4. Test Panels (OVCT)

4.1 *Preparation of OVCT for Testing Emulsion Floor Polishes*—For interlaboratory and specification testing, tiles of OVCT shall be used.³ The tiles are prepared for use as follows:

4.1.1 Thoroughly scrub all tiles using No. 00 steel wool and any suitable aqueous type wax remover or stripper. Scrub hard to help smooth out high and low spots on the tile. Rinse well with clear water, towel dry, and air dry for 15 to 30 min in a rack that allows air to reach both sides of the tile.

4.1.2 Apply two coats of any suitable floor polish using any method as prescribed in Section 5. Allow to dry 2 h between coats and a minimum of an overnight dry (15 to 16 h) after the second coat.

4.1.3 The next day, strip off all the polish from the tiles following the procedure used in 4.1.1.

4.1.4 Repeat the coating (4.1.2) and stripping (4.1.1) operations four more times. A total of ten coats of polish will then have been applied and removed.

NOTE 1—These tiles may be used and reused for testing many times after having been prepared once in accordance with 4.1.1 – 4.1.4. Tiles should be discarded when they show excessive wear or when erratic results are obtained when used with testing devices. At least 25 tests can be run before this will be noticed.

4.1.5 When scrubbing the tiles it is often found that they become distorted and are no longer flat. Any of the devices used for measuring coefficient of friction will give poor reproducibility if the tiles are not flat. Therefore, it is recommended that the tiles be flattened prior to coating for a test. The following procedure is suggested:

¹ This practice is under the jurisdiction of ASTM Committee D21 on Polishes and is the direct responsibility of Subcommittee D21.06 on Slip Resistance. Current edition approved March 1, 2009; Oct. 1, 2016. Published July 2009/October 2016. Originally approved in 1982. Last previous edition approved in 2002/2009 as D4103 – 90 (2002) (2009). DOI: 10.1520/D4103-90R09-10.1520/D4103-90R16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ OVCT is Official Vinyl Composition Tile. The sole source of supply of the apparatus known to the committee at this time is Chemical Specialties Manufacturers Assn., 1001 Connecticut Ave., N.W., Washington, D.C. 20036. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,² which you may attend.