This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



Designation: E2781 - 11 E2781 - 16

# Standard Practice for Evaluation of Methods for Determination of Kinetic Parameters by Thermal AnalysisCalorimetry and Differential Scanning Calorimetry<sup>1</sup>

This standard is issued under the fixed designation E2781; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\varepsilon$ ) indicates an editorial change since the last revision or reapproval.

# 1. Scope-Scope\*

1.1 It is the purpose of this practice to provide kinetic parameters for reference materials used for evaluation of thermal analysis methods, apparatus, and software where enthalpy and temperature are measured. This practice addresses both exothermic and endothermic, nth order, and autocatalytic reactions.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 There is no International Organization for Standardization (ISO) equivalent to this standard.

1.4 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

#### 2. Referenced Documents

2.1 ASTM Standards:<sup>2</sup>

E473 Terminology Relating to Thermal Analysis and Rheology

E698 Test Method for Kinetic Parameters for Thermally Unstable Materials Using Differential Scanning Calorimetry and the Flynn/Wall/Ozawa Method

- E1142 Terminology Relating to Thermophysical Properties
- E1641 Test Method for Decomposition Kinetics by Thermogravimetry Using the Ozawa/Flynn/Wall Method
- E1981 Guide for Assessing Thermal Stability of Materials by Methods of Accelerating Rate Calorimetry
- E2041 Test Method for Estimating Kinetic Parameters by Differential Scanning Calorimeter Using the Borchardt and Daniels Method

E2070 Test Method for Kinetic Parameters by Differential Scanning Calorimetry Using Isothermal Methods

## 3. Terminology

3.1 Definitions—Specific technical terms used in this practice are defined in Terminologies E473 and E1142, including differential scanning calorimetry.

### 4. Summary of Practice

4.1 Kinetics is the study of the relationship of the extent of a chemical reaction to the independent parameters of time and temperature. This relationship is often described using the Arrhenius expression where:

$$d\alpha/dt = Zf(\alpha)exp(-E/RT)$$
<sup>(1)</sup>

where:

 $\alpha$  = fraction left to react,  $f(\alpha)$  = some function of ( $\alpha$ ),

#### \*A Summary of Changes section appears at the end of this standard

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959. United States

<sup>&</sup>lt;sup>1</sup> This practice is under the jurisdiction of ASTM Committee E37 on Thermal Measurements and is the direct responsibility of Subcommittee E37.02 on Standard Reference Materials.

Current edition approved March 1, 2011 Nov. 1, 2016. Published April 2011 November 2016. Originally approved in 2011. Last previous edition approved in 2011 as E2781 - 11. DOI: 10.1520/E2781-11.10.1520/E2781-116.

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.



- E = activation energy (J/mol),
- $R = \text{gas constant} (=8.314 \text{ J mol}^{-1} \text{ K}^{-1}),$
- T = absolute temperature (K), and
- Z = pre-exponential factor (1/sec).

4.2 For many reactions of interest the description of the function of amount left to react is of the form:

$$f(\alpha) = \alpha^m \left(1 - \alpha\right)^n \tag{2}$$

where *m* and *n* are the overall reaction orders. This form of the concentration dependence is known as the auto-catalytic form or the Sestak-Berggren reaction. (1):<sup>3</sup> If the value of *m* equals 0, then  $f(\alpha)$  reduces to the form of  $f(\alpha) = (1 - \alpha)^n$  commonly eall-called *n*th order reaction.

4.3 Eq 1 may be evaluated in either its exponential or logarithmic form:

$$ln(d\alpha/dt) = lnZ + ln(f(\alpha)) - E/RT$$
(3)

4.4 The study of kinetics involves the determination of values of E,Z,m, and n for a given reaction.

Note 1-Activation energy and pre-exponential factor are not independent parameters but are inter-related.

NOTE 2—The descriptions provided in Eq 1-3 are only mathematical models. That is, they represent the fitting of mathematical equations to often "noisy" experimental data. In practice, no such model will faithfully describe the complete reaction(s) under all conditions for the materials described in this practice.

4.5 Values for the kinetic parameter are typically in the ranges indicated below:

 log Z:
 8 to 30 with Z in s<sup>-1</sup>

 E:
 50 to 250 kJ/mol

 m:
 0.0 to 2.0

 m:
 0.0 to 2.0

4.6 By their nature, thermally reactive materials may change with time. For this reason, certified reference materials are not available for use in the evaluation of kinetic parameters. The user of this standardpractice may synthesize or purchase from a commercial laboratory supply house materials of suitable purity for use in this standardpractice.

Note 3-Storage of reference materials in a refrigerator may prolong shelf life. Observe manufacturersmanufacturer's recommendations.

4.7 The recommended values for the thermal active thermally reactive materials identified in this standard practice are taken from "best values" found in the open literature as described in the accompanying Research Report <u>RR:E37-1029</u> tables...<sup>4</sup>

#### 5. Significance and Use

5.1 The kinetic parameters provided in this standard<u>practice</u> may be used to evaluate the performance of a standard, apparatus, techniques, or software for the determination parameters (such as Test Methods E698, E1641, E2041, or E2070) using thermal analysis techniques such as differential scanning calorimetry, and accelerating rate calorimetry (Guide E1981). The results obtained by these approaches may be compared to the values provided by this practice.

NOTE 4-Not all reference materials are suitable for each measurement technique.

# 6. Hazards

6.1 Thermally reactive materials evolve heat as part of the indicated reaction. Build up of this heat may lead to a dangerous over-pressure condition or to a self accelerating reaction. Operators shall use caution when working with such materials. Operators shall use as small amount of material as is practical for the measurement.

6.2 The reference materials described in this standardpractice and their decomposition products may be explosive, carcinogenic, hazardous, toxic, or corrosive. Handling of these materials should be performed by trained workers who are knowledgeable with the Material-Safety Data Sheets (MSDS)(SDS) for each material. Tetramethyl succinonitrile (TMSN), a decomposition product of azobisisobutyronitrile (AIBN), is considered a very toxic (neurotoxic agent) and hazardous substance.

# 7. Procedure

7.1 Experimentally determined kinetic parameters are compared to the values described in this practice as their quotient, expressed as percent. Thus values less than unity or 100 % indicate that the determined value is less than the reference value while those greater than unity or 100 % indicate that the determined value is greater than the reference value.

<sup>&</sup>lt;sup>3</sup> The boldface numbers in parentheses refer to a list of references at the end of this standard.Sestak, and J., Berggren, G., "Study of the Kinetics of the Mechanism of Solid-Solid Reactions at Increasing Temperature," *Thermochimica Acta*, Vol 3, 1971, pp. 1–12.

<sup>&</sup>lt;sup>4</sup> Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:E37-1029. Contact ASTM Customer Service at service@astm.org.



# 8. Calculation

8.1 Conformance = (Observed Value × 100 %)/(Referenced Value)

Note 5—Generally speaking, experimentally determined kinetic parameters E and log Z are considered to be in agreement if they have conformance between 80 and 120 % of the values described in Table 1. Experimentally determined values m and n are considered to be in agreement if they have conformance between 70 and 130 % of the values described in Table 1.

NOTE 6-The value of log Z depends upon the concentration of the reactant.

#### 9. Report

9.1 Identification of the kinetic method being examined.

- 9.1.1 Identification of the reference material being used for the comparison, its source, and purity.
- 9.1.2 The comparison quotient (conformance) for each kinetic parameter.

#### 10. Precision and Bias

- 10.1 This practice is used to determine the bias of kinetic values determined by other standards or candidate standards.
- 10.2 This practice does not generate experimental data and has no precision.

# 11. Keywords

11.1 activation energy; kinetics; pre-exponential factor; reaction order; thermal analysis

## **REFERENCES**

- (1) Sestak, and J., Berggren, G., "Study of the Kinetics of the Mechanism of Solid-Solid Reactions at Increasing Temperature," *Thermochimica Acta*, Vol 3, 1971, pp. 1–12.
- (2) Yasutake, H., Kogyo Kayku (Journal of the Industrial Explosives Society (Japan)), Vol 52, 1991, p. 350.
- (3) Wrabetz, K., and Wong, J., Fresenius Zeitschrift fur Analytische Chemie, Vol 329, 1987, p. 487.
- (4) Torfs, J.C.M., Leen, D., Dorrepaal, A.J., and Heijens, J.C., Analytical Chemistry, Vol 56, 1984, p. 2863.
- (5) Gimzewski, E., and Audley, G., "Thermal Hazards: Calculating Adiabatic Behavior from DSC Data," *Thermochimica Acta*, Vol 214, 1993, pp. 129–140.
- (6) Griffiths, J.F., Gilligan, M.F., and Gray, P., Combustion and Flame, Vol 24, 1975, p. 11.
- (7) MacNeil, D.D., Christensen, L., Landucci, J., Paulsen, J.M., and Dahn, J.R., Journal of the Electrochemical Society, Vol 147, 2000, p. 970.
- (8) Oxley, J.C., Smith, J.L., Rogers, E., Ye, W., Ardai, A.A., and Henly, T.J., Energy Fuels, Vol 14, 2000, p. 1252.

#### TABLE 1 Kinetic Parameters for Kinetic Reference Materials (Derived from Tables 2-6)

NOTE 1—where:

- E =activation energy,
- Z = pre-exponential factor,
- n = reaction order,
- m = reaction order,
- H = enthalpy of reaction of the pure material, and DSC = differential scanning calorimeters.

| Material               | <i>E</i> , kJ/mol | log ( <i>Z</i> ,1/s) | п   | т   | <i>H</i> , kJ/g | Description   |
|------------------------|-------------------|----------------------|-----|-----|-----------------|---|
| Di-t-butylperoxide     | 158.1             | 15.80                | 1.0 | 0.0 | 1.34            | Generally tested in liquid form as a 10 to<br>20 %<br>solution in toluene. Kinetic parameters are<br>solvent<br>sensitive. Suitable for calorimeters. |
| Azidotriphenylmethane  | 165.1             | 19.00                | 1.0 | 0.0 |                 | Suitable for DSC.   |
| Azobenzene             | 102.5             | 11.98                | 1.0 | 0.0 | 0.254           | Solid material, endothermic; Suitable for DSC.  |
| Azobisisobutyronitrile | 128.5             | 15.12                | 1.0 | 0.0 |                 | Suitable for calorimeters and DSC.  |
| Phenyltetrazolthiol    | 143               | 20.4                 | 1.7 | 1.3 |                 | Suitable for DSC.   |