



## Designation: F1861–08 (Reapproved 2012)<sup>ε1</sup> F1861 – 16

# Standard Specification for Resilient Wall Base<sup>1</sup>

This standard is issued under the fixed designation F1861; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

---

<sup>ε1</sup> NOTE—The word “heterogeneous” was added to 4.2.2 editorially in December 2012.

---

## 1. Scope

1.1 This specification covers resilient wall base. These products are manufactured from rubber or thermoplastic materials, or a combination thereof. Wall base is used to provide a functional, as well as decorative border, between walls and floors. This specification does not include rigid products.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 The following safety caveat pertains to the test methods portion, Section 12, of this specification: *This standard does not purport to address all the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 The following documents of the issue in effect on the date of the material purchase form a part of this specification to the extent referenced herein:

### 2.2 ASTM Standards:<sup>2</sup>

D883 Terminology Relating to Plastics

D1566 Terminology Relating to Rubber

D1755 Specification for Poly(Vinyl Chloride) Resins

F137 Test Method for Flexibility of Resilient Flooring Materials with Cylindrical Mandrel Apparatus

F141 Terminology Relating to Resilient Floor Coverings

F386 Test Method for Thickness of Resilient Flooring Materials Having Flat Surfaces

F410 Test Method for Wear Layer Thickness of Resilient Floor Coverings by Optical Measurement

F925 Test Method for Resistance to Chemicals of Resilient Flooring

F1515 Test Method for Measuring Light Stability of Resilient Flooring by Color Change

### 2.3 Other Standards:

ANSI/ASQC Z1.4–2003 Z1.4–2003(R2013) Sampling Procedures and Tables for Inspection by Attributes<sup>3</sup>

## 3. Terminology

3.1 *Definitions*—For definitions of other terms used in this standard, see Terminology F141.

## 4. Classification

4.1 *Types*—Wall base shall be of the following types, as specified (see 5.1.2, 6.1, and 7.1).

4.1.1 *Type TS*—rubber, vulcanized thermoset.

4.1.2 *Type TP*—rubber, thermoplastic.

4.1.3 *Type TV*—vinyl, thermoplastic.

4.2 *Groups*—Wall base shall be one of the following groups, as specified (see 5.1.2, 6.2.1, and 6.2.2):

---

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee F06 on Resilient Floor Coverings and is the direct responsibility of Subcommittee F06.80 on Specifications.

Current edition approved Nov. 15, 2012; Nov. 1, 2016. Published November 2012/December 2016. Originally approved in 1998. Last previous edition approved in 2008 as F1861–08–08 (2012)<sup>ε1</sup>. DOI: 10.1520/F1861-08R12E01-10.1520/F1861-16.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

- 4.2.1 *Group 1*—solid (homogeneous).
- 4.2.2 *Group 2*—layered (multiple layers/heterogeneous).
- 4.2.3 Either group may be specified with any of the types above. It is not necessary to specify group when either is acceptable.
- 4.3 *Styles*—Wall base shall be of the following styles as specified (see 5.1.2, 6.3, and Fig. 1):
  - 4.3.1 *Style A*—straight.
  - 4.3.2 *Style B*—cove.
  - 4.3.3 *Style C*—butt-to.
  - 4.3.4 *Style D*—sculptured.
- 4.4 *Corners*—Where specified, both inside and outside 90° factory-made corners should be specified by style. Corners must meet the same height and thickness requirements as wall base (see Section 9).

NOTE 1—Factory-made corners and wall base may have visual color differences due to process and material variations. Consult the manufacturer to ensure color acceptability between factory-made corners and wall base prior to ordering.

**5. Ordering Information**

5.1 Purchasers shall state whether this specification is to be used, select the preferred options permitted herein, and include the following information in the invitation to bid or purchase order:

- 5.1.1 Title, number, and date of this specification,
- 5.1.2 Type, group, and style, (see Sections 4, 6, and 7),
- 5.1.3 Factory-made corners, if required (see 4.4),
- 5.1.4 Color (see 6.2),
- 5.1.5 Quantity: in pieces, linear feet, or cartons,
- 5.1.6 Height required (see 9.1),
- 5.1.7 Thickness required (see 9.2),
- 5.1.8 Length required (see 9.3, 9.3.1, and Section 15),
- 5.1.9 Lot information, if other than as specified in ANSI/ASQC Z1.4-2003;Z1.4-2003(R2013), (see 11.1 and 13.1),
- 5.1.10 Sampling, if other than as specified in ANSI/ASQC Z1.4-2003;Z1.4-2003(R2013), (see 11.1),
- 5.1.11 Statement requesting certification, if certification of compliance is required (see Section 14),
- 5.1.12 Packing requirements, if other than as specified (see Section 16),
- 5.1.13 Palletization, if required,
- 5.1.14 Marking required, if other than specified (see Section 15), and
- 5.1.15 Other requirements.

**6. Materials and Manufacture**

6.1 *Materials*—Any polymeric material or combination of polymeric materials is acceptable if, in combination with processing chemicals, fillers, and colorants, the material can be formed into wall base, which satisfies all the requirements of this specification (see 5.1 and 7.1). Other suitable recycled polymeric material may be incorporated as a part of the total polymeric content.




FIG. 1 Typical Profiles of Wall Base

6.2 *Color*—The color shall be as specified in the contract or order (see 5.1.4).

NOTE 2—The colors and styles that are available are indicated in individual manufacturer’s current catalogs. As manufactured, colors may vary somewhat in hue or shade from the catalog.

NOTE 3—Where color match is a concern, obtain current samples from the manufacturer to verify color acceptability.

6.2.1 *Solid Wall Base*— The color shall be uniform throughout the entire thickness of the wall base.

6.2.2 *Layered Wall Base*—The surface color need not extend through the entire thickness of the wall base, but must extend throughout the entire wear layer. Layered wall base shall have a minimum wear layer thickness of 0.002 in. (0.05 mm) when measured in accordance with Test Method F410 and shall not delaminate under normal use.

6.3 *Styles*—The style shall be as specified in the contract or order (see 5.1.2).

6.3.1 *Straight Wall Base*—The exposed surface of straight (toeless) wall base is vertical, as illustrated by the first cross-sectional profile in Fig. 1.

6.3.1.1 *Fit to Wall*—Top return lip of wall base shall fit firmly against the wall when the vertical portion of the cove base is adhered to the wall.

6.3.2 *Cove Wall Base*— The exposed surface of cove wall base shall be distinguished by a “toe” at its bottom edge as illustrated by the second cross-sectional profile in Fig. 1.

6.3.2.1 *Fit to Floor*— The toe shall be curved, or angled, or both, to allow it to fit snugly against the floor when the vertical portion of the cove base is adhered to the wall.

6.3.2.2 *Intersection at Toe*—The intersection of the exposed surfaces of the toe and the vertical portion of the cove base shall be rounded and smooth to facilitate maintenance.

6.3.2.3 *Fit to Wall*—Top return lip of wall base shall fit firmly against the wall when the vertical portion of the cove base is adhered to the wall.

6.3.3 *Butt-to Wall Base*—The exposed surface of butt-to wall base shall be distinguished by a “toe,” which butts against the flooring as illustrated by the third cross-sectional profile in Fig. 1.

6.3.3.1 *Fit to Floor*— The leading edge of the toe of the butt-to base shall be square to allow a tight, flush fit to the finished flooring when the vertical portion of the butt-to base is adhered to the wall.

6.3.3.2 *Intersection at Toe*—The intersection of the exposed surfaces of the toe and the vertical portion of the butt-to base shall be designed to facilitate maintenance.

6.3.3.3 *Fit to Wall*—Top return lip of wall base shall fit firmly against the wall when the vertical portion of the cove base is adhered to the wall.

6.3.4 *Sculptured Wall Base*—The exposed surface of sculptured wall base shall have an appearance replicating carved wood or chiseled stone, as illustrated by the fourth cross-sectional profile in Fig. 1.

6.3.4.1 *Fit to Wall*—Top return lip of wall base shall fit firmly against the wall when the vertical portion of the cove base is adhered to the wall.

## 7. Material Definitions

7.1 The following definitions will be used in classifying material according to 4.1:

7.1.1 *Rubber, Vulcanized Thermoset*—The polymeric binder of this compound shall satisfy the definition of rubber, and have been vulcanized, as defined in Terminology D1566.

7.1.2 *Rubber, Thermoplastic*—The polymeric binder of this compound shall satisfy the definition of rubber, but remain thermoplastic, as defined in Terminology D883.

7.1.3 *Vinyl, Thermoplastic*—The polymeric binder of this compound shall satisfy the definition of poly (vinyl chloride) in Terminology D883 and Specification D1755 but remain thermoplastic as defined in Terminology D883.

## 8. Performance Requirements

8.1 *Flexibility*— Unless otherwise specified in the contract or order (see 5.1), the wall base shall show no visible cracks, breaks, or other evidence of weakness when tested in accordance with Test Method F137 using a ¼ in. (6.35 mm) diameter mandrel. This requirement is not applicable for sculptured wall base thicker than 0.125 in. (3.17 mm) in thickness.

NOTE 4—Cove wall base shall be tested with the mandrel perpendicular to the cove when oriented as in use.

8.2 *Staining of Adjacent Surfaces Induced by Wall Base*—Wall base shall contain no ingredient which will cause staining of the finished surfaces adjacent to it when aged by the method specified in 12.1 – 12.7.

8.3 *Resistance to Light*—When tested in accordance to Test Method F1515, the color change of the wall base shall have an average ΔE no greater than 8.0 after 200 h of exposure to light, simulated by a properly fitted xenon-arc radiant energy source.

8.4 *Resistance to Chemicals*—When tested in accordance with Test Method F925, the wall base shall have no more than a slight change in surface dulling, surface attack, or staining when exposed to the following chemicals:

8.4.1 White vinegar (5 % acetic acid).

8.4.2 Rubbing alcohol (70 % isopropyl alcohol).