



Designation: D281 – 12 (Reapproved 2016)

Standard Test Method for Oil Absorption of Pigments by Spatula Rub-out¹

This standard is issued under the fixed designation D281; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This test method covers the determination of the oil absorption of pigments by the spatula rub-out technique.

1.2 The values stated in SI units are to be regarded as standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D1483 Test Method for Oil Absorption of Pigments by Gardner-Coleman Method

3. Summary of Test Method

3.1 A stiff, putty-like paste is formed by the dropwise addition of linseed oil to pigment that is being thoroughly rubbed with a spatula. The amount of oil required to produce the end point is used to calculate an oil absorption value.

4. Significance and Use

4.1 The oil absorption value obtained by this test method gives information about the vehicle demand of the pigment when it is used in a pigment paste. Oil absorption values can be used to characterize pigments or batches of a given pigment.

4.2 This test method differs from Test Method D1483 in that D1483 involves only a gentle stirring and folding of the pigment, whereas this test method requires a thorough rubbing

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.24 on Physical Properties of Liquid Paints and Paint Materials.

Current edition approved Dec. 1, 2016. Published December 2016. Originally approved in 1928. Last previous edition approved in 2012 as D281 – 12. DOI: 10.1520/D0281-12R16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

action. Because the end points are different, the values obtained from the two test methods generally differ.

5. Apparatus and Materials

5.1 *Balance*, capable of weighing to 0.001 g.

5.2 *Dropping Bottle*, fitted with ground-in pipet and rubber bulb or buret, graduated in 0.1-mL divisions.

5.3 *Smooth Glass Rub-up Plate or Marble Slab* (glass should have a surface similar to Hoover Muller Plates).

5.4 *Spatula*, sharp-edged, steel, having a blade of 15 or 20 mm by 100 mm (1/2 or 3/4 by 4 in.).

5.5 *Oil*, linseed, raw, conforming to the following specification:

Specific Gravity	0.926–0.931
Boiling Point	>149°C
Acid Number	3 ± 1
Saponification Value	185–196
Iodine Value	170 minimum
Gardner Color	13 maximum

5.5.1 Linseed oil used in comparative tests must have the same acid value. Other liquids, such as refined oil, may be used by mutual agreement.

6. Procedure

6.1 *Procedure A (Weighing Bottle)*—Weigh exactly 1 g, or any multiple thereof (Note 1), of the thoroughly mixed and air dried pigment and place upon a glass plate or marble slab. Weigh to 0.01 g a dropping bottle containing raw linseed oil along with the pipet and rubber bulb. Add the linseed oil gradually, drop by drop (by means of the pipet), to the pigment. After the addition of each drop, thoroughly incorporate the oil by rubbing up with the spatula. The test is complete when exactly enough oil has been incorporated with the pigment to produce a very stiff, putty-like paste, that does not break or separate. Weigh the bottle and oil to 0.01 g and determine by difference the weight of oil used. The time that it took to run the test (in minutes) should be noted. Subsequent tests on the same kind of pigment should be performed in approximately the same period of time. Any device capable of measuring minutes may be used.