



## Standard Practice for Incorporating Pigments by High Speed Dispersion<sup>1</sup>

This standard is issued under the fixed designation D6619; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This practice covers the dispersion of pigments using a laboratory size high-speed impeller mill. It is similar in technical content to ISO 8780-3.

NOTE 1—This practice is restricted to mill bases of moderately high viscosity due to either high vehicle concentration or high pigment concentration, or both, which can produce high shear force. It is not intended to provide a means of formulating either pilot plant or full-scale mill base compositions (scaling up the process from laboratory equipment to factory mills is not simple).

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

#### 2.1 ISO Standards:

**ISO 8780-3 Pigments and Extenders—Methods of Dispersion for Assessment of Dispersion Characteristics—Dispersion Using a High Speed Impeller Mill<sup>2</sup>**

### 3. Significance and Use

3.1 High speed dispersion is a commonly used dispersion method in the coatings industry. For the purpose of this practice, “high speed” would normally be understood to be a range of RPM between 3 000 and 10 000. This practice provides a reference for its use, so that a producer and user can standardize on an incorporation technique. This will minimize differences in the millbase, and allow the interested parties to concentrate on the physical, chemical, or optical methods to be run.

### 4. Apparatus

4.1 *High-speed Impeller Mill*, consisting of a cylindrical vessel and a horizontal disk stirrer blade driven by a motor. A disk with a serrated edge is commonly used.

4.1.1 *Drive Unit*—The power rating of the drive unit shall be sufficient to maintain the peripheral speed of the disk at an agreed value. A reduced rotational speed shall be available for pre-mixing in accordance with 6.2. The motor of the drive unit shall be mounted on a stand together with the impeller shaft so that its height can be adjusted. There shall be a clamping device for the vessel at the foot of the stand, such that the impeller shaft is concentric with the vessel.

#### 4.1.2 *Disk and Vessel:*

4.1.2.1 The diameters of the vessel and the disk shall be such that there is adequate clearance between the disk periphery and the walls of the vessel (see Fig. 1). If the disk is serrated, it shall be mounted so that the direction of movement of the serrations is such that the mill base flows in the directions shown in Fig. 1.

4.1.2.2 The degree of dispersion achieved will depend on the type of disk used. Fig. 1 shows only one type.

4.1.2.3 The type and diameter of the disk, the geometry of the vessel, and the speed of the disk shall be agreed upon and recorded in the test report.

NOTE 2—A vessel with a double wall to allow circulation of a liquid to control the temperature should be employed, if necessary. A lid with a central aperture may also be provided.

NOTE 3—The diameter of a vessel used in an industrial scale mill is normally two to three times the diameter of the impeller, or sometimes even greater. The vessel/disk geometry and the disk speed specified make allowance for the small diameter of a laboratory disk.

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.24 on Physical Properties of Liquid Paints and Paint Materials.

Current edition approved Feb. 1, 2012 Dec. 1, 2016. Published February 2012 December 2016. Originally approved in 2000. Last previous edition approved in 2006 2012 as D6619 – 00 (2006) (2012). DOI: 10.1520/D6619-00R12.10.1520/D6619-00R16.

<sup>2</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.