



Designation: ~~D2489/D2489M – 08~~ D2489/D2489M – 16

Standard Practice for ~~Test Method for~~ Estimating Degree of Particle Coating of Bituminous- Aggregate ~~Asphalt~~ Mixtures¹

This standard is issued under the fixed designation D2489/D2489M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This practice provides an estimate of the degree of particle coating in a bituminous-aggregate mixture on the basis of the percentage of coarse particles classified as being completely coated.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

~~D8 Terminology Relating to Materials for Roads and Pavements~~

~~D979 Practice for Sampling Bituminous Paving Mixtures~~

~~D995 Specification for Mixing Plants for Hot-Mixed, Hot-Laid Bituminous Paving Mixtures (Withdrawn 2009)~~³

~~D3665 Practice for Random Sampling of Construction Materials~~

~~D4215 Specification for Cold-Mixed, Cold-Laid Bituminous Paving Mixtures~~

~~E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves~~

3. Terminology

3.1 For definitions of terms, see Terminology ~~D8~~: M D2489/D2489M-16

3.2 For descriptions of mixing plant terms, see Mixing Plants, Specification ~~D995~~: bb018f1b/astm-d2489-d2489m-16

4. Significance and Use

4.1 The procedure in this practice for estimating the percentage of coated particles after varying mixing times is used to establish the least mixing time required to produce satisfactory coating for a given set of conditions. This procedure can also be used to sample cold mixtures from stockpiles to determine that satisfactory coating has been retained in the stockpile.

4.2 This procedure is used with hot-mixed, hot-laid bituminous paving mixtures or with cold-mixed, cold-laid bituminous paving mixtures such as specified in Specification ~~D4215~~.

NOTE 1—Even when a paving mixture complies with the “percent of coated particles” that may be specified, there is no assurance that the asphalt cement is uniformly distributed throughout the mixture.

4.3 This practice should not be used for acceptance/rejection by owner agencies.

¹ This practice-test method is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.23 on Plant-Mixed Bituminous Asphalt Surfaces and Bases.

Current edition approved Dec. 1, 2008 Dec. 1, 2016. Published December 2008 December 2016. Originally approved in 1966. Last previous edition approved in 2002 2008 as ~~D2489 – 02~~ D2489/D2489M – 08. DOI: 10.1520/D2489_D2489M-08-10.1520/D2489_D2489M-16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

5. Apparatus

- 5.1 *Sieves*, 9.5 mm [$\frac{3}{8}$ in.] and 4.75 mm [No. 4]. The sieves shall conform to Specification **E11**.
- 5.2 *Stopwatch*, for checking actual mixing time of batch plants.
- 5.3 *Thermometer*, range at least from 10°C [50°F] to 204°C [400°F].
- 5.4 *Sample Shovel*.
- 5.5 *Sample Trays*.

6. Sampling

- 6.1 *Batch Plant*—Permit the plant to operate at an established mixing time per batch (timed by a stopwatch).
- 6.2 *Continuous Mix Plant*—Establish a mixing time by use of the following formula:

$$\text{mixing time} = \text{pug mill contents, kg [lb]} / \text{pug mill output, kg/s [lb/s]} \quad (1)$$

- 6.3 *Drum Mix Plant*—Operate the plant at a steady state condition for a period of time long enough to complete the sampling.
- 6.4 Samples should be taken at the site of the bituminous mixing plant immediately after discharge from the plant from three truck loads selected at random in accordance with Practice **D3665** and sampled in accordance with Practice **D979**. Approximately 2.5 to 4.0 kg [5 to 8 lb] is required to perform the procedure.
- 6.5 If sampling truck loads is impractical, sample from the roadway before compaction starts at three locations selected at random in accordance with Practice **D3665** and sampled in accordance with Practice **D979**.
- 6.6 If sampling from a cold mixed stockpile, sample at three locations selected at random in accordance with Practice **D3665** and sampled in accordance with Practice **D979**.

7. Procedure

- 7.1 Sieve each sample immediately while it is still hot on a 9.5-mm [$\frac{3}{8}$ in.] sieve, or a 4.75-mm [No. 4] sieve for material with a maximum 9.5-mm [$\frac{3}{8}$ in.] size. Take a sample large enough to yield between 200 and 500 coarse particles retained on the 9.5-mm [$\frac{3}{8}$ in.] or 4.75-mm [No. 4] sieve. Do not overload the sieves. If necessary, sieve the sample in two or three operations. Reduce shaking to a minimum to prevent recoating of uncoated particles.
- 7.2 Place particles on a clean surface in a one-particle layer and start count immediately.
- 7.3 Very carefully examine each particle under direct sunlight, fluorescent light, or similar light conditions. If even a tiny speck of uncoated stone is noted, classify the particle as “partially coated.” If completely coated, classify the particle as “completely coated.”

8. Report

- 8.1 Report the estimated percentage of coated particles as follows:

$$\text{estimated \% of coated particles} = 100 \quad (2)$$

$$\frac{\text{(number of completely coated particles)}}{\text{(total number of particles)}}$$

9. Keywords

- 9.1 bituminous-aggregate mixtures; bituminous paving mixtures; particle coating

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/

1. Scope

- 1.1 This test method provides an estimate of the degree of particle coating in an asphalt-aggregate mixture on the basis of the percentage of coarse particles classified as being completely coated.