



Standard Test Method for Density of Hydraulic Cement¹

This standard is issued under the fixed designation C188; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This test method covers the determination of the density of hydraulic cement. Its particular usefulness is in connection with the design and control of concrete mixtures.

1.2 The density of hydraulic cement is defined as the mass of a unit volume of the solids.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 **Warning**—Fresh hydraulic cementitious mixtures are caustic and may cause chemical burns to skin and tissue upon prolonged exposure.²

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

- 2.1 *ASTM Standards*:³
- C114 Test Methods for Chemical Analysis of Hydraulic Cement
 - C125 Terminology Relating to Concrete and Concrete Aggregates
 - C604 Test Method for True Specific Gravity of Refractory Materials by Gas-Comparison Pycnometer
 - C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials
 - D2638 Test Method for Real Density of Calcined Petroleum

¹ This test method is under the jurisdiction of ASTM Committee C01 on Cement and is the direct responsibility of Subcommittee C01.25 on Fineness.

Current edition approved Dec. 15, 2016. Published December 2016. Originally approved in 1944. Last previous edition approved in 2015 as C188 – 15. DOI: 10.1520/C0188-16.

² Section on Safety, Manual of Cement Testing, *Annual Book of ASTM Standards*, Vol. 04.01.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

Coke by Helium Pycnometer

3. Terminology

3.1 *Definitions*—For definitions of terms used in this test method, refer to Terminology C125.

4. Significance and Use

4.1 This test method provides a procedure for the determination of density of hydraulic cement samples using non-instrumental techniques.

5. Apparatus

5.1 *Le Chatelier flask*—The standard flask, which is circular in cross section, with shape and dimensions conforming essentially to Fig. 1 (Note). The requirements in regard to tolerance, inscription and length, spacing, and uniformity of graduation will be rigidly observed. There shall be a space of at least 10 mm between the highest graduation mark and the lowest point of grinding for the glass stopper.

5.1.1 The material of construction shall be excellent quality glass, transparent and free of striae. The glass shall be chemically resistant and shall have small thermal hysteresis. The flasks shall be thoroughly annealed before being graduated. They shall be of sufficient thickness to ensure reasonable resistance to breakage.

5.1.2 The neck shall be graduated from 0 to 1 mL and from 18 to 24 mL in 0.1-mL graduations. The error of any indicated capacity shall not be greater than 0.05 mL.

5.1.3 Each flask shall bear a permanent identification number and the stopper, if not interchangeably ground, shall bear the same number. Interchangeable ground-glass parts shall be marked on both members with the standard-taper symbol, followed by the size designation. The standard temperature shall be indicated, and the unit of capacity shall be shown by the letters “mL” placed above the highest graduation mark.

5.2 Kerosine, free of water, or naphtha, having a density greater than 0.73 g/mL at $23 \pm 2^\circ\text{C}$ shall be used in the density determination.

*A Summary of Changes section appears at the end of this standard