



Designation: ~~D3019~~—~~08~~ D3019/D3019M – 17

Standard Specification for Lap Cement Used with Asphalt Roll Roofing, Non-Fibered, ~~Asbestos-Fibered, and Non-Asbestos-Fibered~~¹

This standard is issued under the fixed designation ~~D3019~~; D3019/D3019M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers lap cement consisting of asphalt dissolved in a volatile petroleum solvent with or without mineral or other stabilizers, or both, for use with roll roofing. The fibered version of these cements excludes the use of asbestos fibers.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as the standard. ~~The values given in parentheses are for information only.~~ stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 The following precautionary caveat applies only to the test method portion, Section 5, of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

~~D36~~D36/D36M Test Method for Softening Point of Bitumen (Ring-and-Ball Apparatus)

~~D65~~D6511/D6511M Test Methods for Solvent Bearing Bituminous Compounds

3. Classification

3.1 *Type I*—Brushing consistency non-fibered lap cement intended for use in the exposed-nailing method of roll roofing application. Type I lap cement contains no mineral or other stabilizers.

3.1.1 *Grade 1*—Made with an air-blown asphalt.

3.1.2 *Grade 2*—Made with a vacuum-reduced or steam-refined asphalt.

3.2 *Type II*—Heavy brushing or light troweling consistency lap cement intended for use in the concealed-nailing method of roll roofing application. Type II lap cement contains a quantity of short-fibered asbestos.

3.2 *Type III*—Heavy brushing or light troweling consistency fibered lap cement intended for use in the concealed-nailing method of roll roofing application. Type III lap cement contains a quantity of mineral or other stabilizers, or both, but contains no asbestos.

4. Physical Requirements

4.1 The material shall conform to the requirements prescribed in [Table 1](#).

5. Sampling

5.1 See Section 4, Sampling, of Test Methods ~~D65~~D6511/D6511M.

6. Test Methods

6.1 Determine composition and physical requirements by using the procedures in Test Methods ~~D65~~D6511/D6511M and Test Method ~~D36~~D36/D36M.

6.2 *Strength of Lap:*

¹ This specification is under the jurisdiction of ASTM Committee [D08](#) on Roofing and Waterproofing and is the direct responsibility of Subcommittee [D08.05](#) on Solvent-Bearing Bituminous Compounds for Roofing and Waterproofing.

Current edition approved ~~Feb. 15, 2008~~Jan. 1, 2017. Published ~~March 2008~~January 2017. Originally approved in 1972. Last previous edition approved in ~~2007~~2008 as ~~D3019-94 (2007)~~D3019-08. DOI: ~~10.1520/D3019-08~~10.1520/D3019_D3019M-17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.