



Designation: ~~D1248~~—~~12~~ **D1248** – 16

Standard Specification for Polyethylene Plastics Extrusion Materials for Wire and Cable¹

This standard is issued under the fixed designation D1248; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification provides for the identification of polyethylene plastics extrusion materials for wire and cable in such a manner that the seller and the purchaser can agree on the acceptability of different commercial lots or shipments. The tests involved in this specification are intended to provide information for identifying materials according to the types, classes, categories, and grades covered. It is not the function of this specification to provide specific engineering data for design purposes.

1.2 This specification does not allow for the use of recycled plastics (see **Note 3**).

1.3 The values stated in SI units are to be regarded as the standard. The values given in parentheses are mathematical conversions to inch-pound units that are provided for information only and are not considered standard.

1.4 The following safety hazards caveat pertains only to the test method portion, Section 12, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no known ISO equivalent to this standard.

NOTE 2—This standard has undergone major revision from the reapproval of 1989 and now covers only polyethylene for wire and cable applications. For information regarding molding and extrusion materials, see Specification **D4976**. For information regarding plastic pipe materials, see Specification **D3350**.

NOTE 3—See Guide **D7209** and 3.1.2 of this standard for information and definitions related to recycled plastics.

2. Referenced Documents

2.1 *ASTM Standards:*²

D150 Test Methods for AC Loss Characteristics and Permittivity (Dielectric Constant) of Solid Electrical Insulation

D257 Test Methods for DC Resistance or Conductance of Insulating Materials [8cf8-c5cbfa1835e2/astm-d1248-16](https://doi.org/10.1520/D1248-16)

D618 Practice for Conditioning Plastics for Testing

D638 Test Method for Tensile Properties of Plastics

D746 Test Method for Brittleness Temperature of Plastics and Elastomers by Impact

D792 Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement

D1238 Test Method for Melt Flow Rates of Thermoplastics by Extrusion Plastometer

D1505 Test Method for Density of Plastics by the Density-Gradient Technique

D1531 Test Methods for Relative Permittivity (Dielectric Constant) and Dissipation Factor by Fluid Displacement Procedures (Withdrawn 2012)³

D1603 Test Method for Carbon Black Content in Olefin Plastics

D1693 Test Method for Environmental Stress-Cracking of Ethylene Plastics

D2565 Practice for Xenon-Arc Exposure of Plastics Intended for Outdoor Applications

D2633 Test Methods for Thermoplastic Insulations and Jackets for Wire and Cable

D2839 Practice for Use of a Melt Index Strand for Determining Density of Polyethylene

D2951 Test Method for Resistance of Types III and IV Polyethylene Plastics to Thermal Stress-Cracking (Withdrawn 2006)³

¹ This specification is under the jurisdiction of ASTM Committee **D20** on Plastics and is the direct responsibility of Subcommittee **D20.15** on Thermoplastic Materials. Current edition approved April 1, 2012; Nov. 15, 2016. Published May 2012; December 2016. Originally approved in 1952. Last previous edition approved in 2005 as **D1248-05-D1248-12**. DOI: [10.1520/D1248-12](https://doi.org/10.1520/D1248-12); [10.1520/D1248-16](https://doi.org/10.1520/D1248-16).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

*A Summary of Changes section appears at the end of this standard

D3182 Practice for Rubber—Materials, Equipment, and Procedures for Mixing Standard Compounds and Preparing Standard Vulcanized Sheets

D3349 Test Method for Absorption Coefficient of Ethylene Polymer Material Pigmented with Carbon Black

D3350 Specification for Polyethylene Plastics Pipe and Fittings Materials

D3636 Practice for Sampling and Judging Quality of Solid Electrical Insulating Materials

D3892 Practice for Packaging/Packing of Plastics

D4329 Practice for Fluorescent Ultraviolet (UV) Lamp Apparatus Exposure of Plastics

D4703 Practice for Compression Molding Thermoplastic Materials into Test Specimens, Plaques, or Sheets

D4976 Specification for Polyethylene Plastics Molding and Extrusion Materials

D6360 Practice for Enclosed Carbon-Arc Exposures of Plastics

D7209 Guide for Waste Reduction, Resource Recovery, and Use of Recycled Polymeric Materials and Products (Withdrawn 2015)³

E1131 Test Method for Compositional Analysis by Thermogravimetry

G151 Practice for Exposing Nonmetallic Materials in Accelerated Test Devices that Use Laboratory Light Sources

G153 Practice for Operating Enclosed Carbon Arc Light Apparatus for Exposure of Nonmetallic Materials

G154 Practice for Operating Fluorescent Ultraviolet (UV) Lamp Apparatus for Exposure of Nonmetallic Materials

G155 Practice for Operating Xenon Arc Light Apparatus for Exposure of Non-Metallic Materials

2.2 *Federal Specification*:⁴

L-P-390C Plastic, Molding, and Extrusion Materials, Polyethylene and Copolymers (Low, Medium, and High Density)

NOTE 4—In accordance with the DOD: “L-P-390C, dated 10 August 1971, is inactivated for new design and is no longer used, except for replacement purposes. Future acquisition for this product, when used in new design, should refer to ASTM **D4976**, ‘STANDARD SPECIFICATION FOR POLYETHYLENE PLASTICS MOLDING AND EXTRUSION MATERIALS.’”

3. Terminology

3.1 *Definitions of Terms Specific to This Standard*:

3.1.1 *polyethylene plastics, n*—plastics or resins prepared by the polymerization of no less than 50 % ethylene and no less than 95 weight % of total olefins.

3.1.2 *recycled plastics, n*—plastics feedstocks or products composed of recovered plastic material that may or may not that include a percentage of post-consumer material, but not including those materials and by-products generated from, and commonly reused, within an original manufacturing process and, reworked, reprocessed, and regrind plastic and purge from the same manufacturing process.

3.2 Historical usage and user group conventions have resulted in inconsistent terminology used to categorize and describe polyethylene resins and compounds. The following terminology is in use in ASTM specifications pertaining to polyethylene:

3.2.1 *Specification D1248*:

3.2.1.1 Type (0, I, II, III, IV) = density ranges (same, respectively, as Class in Specification **D4976**).

3.2.1.2 Class (A, B, C, D) = composition and use.

3.2.1.3 Category (1, 2, 3, 4, 5) = melt index ranges (same as Grade in Specification **D4976**).

3.2.1.4 Grade (E, J, D, or W followed by one or two digits) = specific requirements from tables.

3.2.2 *Specification: D3350*

3.2.2.1 Type (I, II, III) = density ranges (same as Types I, II, and III in Specification D1248 and Classes 1, 2, and 3 in Specification **D4976**).

3.2.2.2 Class = a line callout system consisting of “PE” followed by six cell numbers from Table 1 plus a letter (A, B, C, D, E) denoting color and UV stabilizer.

3.2.2.3 Grade = simplified line callout system using “PE” followed by density and slow crack growth cell numbers from Table 1.

3.2.3 *Specification: D4976*

3.2.3.1 Group (1, 2) = branched or linear polyethylene.

3.2.3.2 Class (5, 1, 2, 3, 4) = density ranges (same, respectively, as Type in Specification D1248).

3.2.3.3 Grade (1, 2, 3, 4, 5) = melt index ranges (same as Category in Specification D1248).

4. Classification

4.1 This specification recognizes that polyethylene plastics are identified primarily on the basis of two characteristics, namely, density and flow rate (previously identified as melt index). The former is the criterion for assignment as to type, the latter for designation as to category. Other attributes important to the user for certain applications are covered by three general classes and by specifying in greater detail, by grades, a minimum number of key characteristics covered too broadly or not at all by the type, class, and category designations.

⁴ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://dodssp.daps.dla.mil>.

4.1.1 Types:

4.1.1.1 This specification provides for the identification of five types of polyethylene plastics extrusion materials for wire and cable by density in accordance with 10.1 and 12.1.1, and the requirements prescribed in Table 1 and Note 5, Note 6, and Note 12.

NOTE 5—It is recognized that some high-density polyethylene plastics of very high molecular weight may typically have densities slightly less than 0.960 yet in all other respects they are characteristic of Type IV materials. Similarly, there are other polyethylene plastics of very high molecular weight having densities slightly less than 0.941 which in all other respects are more characteristic of Type III than of Type II materials.

NOTE 6—While the original Type III now has been divided into two ranges of density (Types III and IV), both are still described by the term *high density*.

4.1.1.2 Material supplied under these types shall be of such nominal density, within the ranges given, as agreed upon between the manufacturer and the purchaser subject to the tolerances specified in 4.1.1.3 (Note 12).

4.1.1.3 In view of production, sampling, and testing variables, a commercial lot or shipment for which a nominal density has been agreed upon between the seller and the purchaser shall be considered as conforming and commercially acceptable when the density value found on a sample from the lot or shipment falls within the tolerance range of ± 0.004 of the nominal value.

4.1.1.4 If the nominal value is unknown or unspecified, classification shall be based on the tested value without tolerance consideration.

4.1.2 Classes—Each of the five types is subdivided into four classes according to composition and use as follows:

4.1.2.1 Class A—Natural color only, with or without any antioxidants or other additives in such proportions as agreed upon between the seller and the purchaser.

4.1.2.2 Class B—Colors including white and black, with or without any antioxidants or other additives in such proportions as agreed upon between the manufacturer and the purchaser.

4.1.2.3 Class C—Black (weather-resistant), containing not less than 2 % carbon black of a kind and particle size (Note 7), dispersed by such means and to such degree as necessary to impart weather resistance with or without any antioxidants or other additives in such proportions as agreed upon between the seller and the purchaser.

NOTE 7—Carbon black 35 nm or less in average particle diameter is used as required in black electrical and jacketing materials (Grades E and J) to impart maximum weather resistance.

4.1.2.4 Class D—Colored (UV resistant), including black and white, with antioxidants and UV stabilizers to allow electrical insulation and jackets to meet the requirements outlined in 12.1.12.

NOTE 8—The expected service lifetime of Class D materials is very dependent upon the specific material formulation including selected colorants. Contact your supplier for additional information regarding this issue.

4.1.3 Categories:

4.1.3.1 The four classes of each type are divided into five categories on the basis of broad ranges of flow rate in accordance with the requirements prescribed in Table 2.

NOTE 9—Some Type II and Type III polyethylene plastics of very high molecular weight cannot be categorized by flow rate. Solution viscosity is recommended as a means of distinguishing such materials.

4.1.3.2 Material supplied under these categories shall be of such nominal flow rate, within the ranges given, as agreed upon between the seller and the purchaser subject to the tolerances specified in 4.1.3.3.

4.1.3.3 In view of production, sampling, and testing variables, a commercial lot or shipment for which a nominal flow rate has been agreed upon between the seller and the purchaser shall be considered as conforming and commercially acceptable when the flow rate value found on a sample from the lot or shipment falls within the tolerance range of ± 20 % of the nominal flow rate.

4.1.3.4 If the nominal value is unknown or unspecified, classification shall be based on the tested value without tolerance consideration.

4.1.4 Grades:

4.1.4.1 If further definition is necessary, one of the grades given in Tables 3-5 shall be selected.

NOTE 10—Tables 4 and 5, are included to correspond with the grades specified in Federal Specification L-P-390C.

NOTE 11—The grade shall be associated with the appropriate type, class, and category designations; for example, IA5-E4 or IC5-J3 as required. Other grades may be added as necessary by revision of this specification in established manner. Also, it is anticipated that additional requirements may be added.

TABLE 1 Classification of Polyethylene Plastics Extrusion Materials for Wire and Cable According to Type

Type	Nominal Density, ^A g/cm ³
0	<0.910
I	0.910 to 0.925
II	>0.925 to 0.940
III	>0.940 to 0.960
IV	>0.960

^AUncolored, unfilled material (see Note 12).

TABLE 2 Classification of Polyethylene Plastics Extrusion Materials for Wire and Cable According to Category

Category	Nominal Flow Rate, g/10 min (190°C, 2.16 kg load)
1	>25
2	>10 to 25
3	>1.0 to 10
4	>0.4 to 1.0
5	0.4 max

to be added as necessary under a given grade designation by future revision to provide more meaningful characterization of the material covered by such designation.

4.1.4.2 If additional requirements specific to the application are necessary, these shall be specified by the purchaser with the agreement of the seller.

5. Basis of Purchase

5.1 The purchase order or inquiry for these materials shall state the specification number, type, class, category, and, if needed, the appropriate grade, for example, D1248-IA5-E4.

5.2 It is acceptable for further definition to be agreed upon between the seller and the purchaser as follows:

5.2.1 Nominal density.

NOTE 12—For Class B, Class C, and Class D material, the nominal density of the base resin will be identified by the manufacturer upon request.

5.2.2 Nominal flow rate.

5.2.3 *Antioxidant(s) or Other Additive(s) and Proportions:*

5.2.3.1 *Class A*—As stated in 4.1.2.1,

5.2.3.2 *Class B*—As stated in 4.1.2.2,

5.2.3.3 *Class C*—As stated in 4.1.2.3, and

5.2.3.4 *Class D*—As stated in 4.1.2.4.

5.2.4 Contamination level (see 6.2).

5.2.5 Other supplementary definition, unless grade is sufficient and is identified (see 4.1.4.1 and 4.1.4.2).

5.3 Inspection (see 13.1).

6. Materials and Manufacture

6.1 The extrusion material for wire and cable shall be polyethylene plastic in the form of powder, granules, or pellets.

6.2 The extrusion materials for wire and cable shall be as uniform in composition and size and as free of contamination as can be achieved by good manufacturing practice. If necessary, the acceptable level of contamination shall be agreed upon between the seller and the purchaser.

6.3 Unless controlled by requirements specified elsewhere (see 4.1.4.1 and 4.1.4.2), the color and translucence of extruded pieces formed under conditions recommended by the manufacturer of the material, shall be comparable within commercial match tolerances to the color and translucence of standard molded or extruded samples of the same thickness supplied in advance by the manufacturer of the material.

7. Physical Requirements

7.1 Test specimens of the material prepared as specified in 10.1, and tested in accordance with 12.1, shall conform to the requirements prescribed by the material designation for type in Table 1, for class in 4.1.2, for category in Table 2, and for grade in Tables 3-5.

8. Sampling

8.1 Sampling shall be statistically adequate to satisfy the requirements of 13.4.

8.2 A batch or lot shall be constituted as a unit of manufacture as prepared for shipment and can consist of a blend of two or more production runs.

9. Testing

9.1 The requirements identified by the material designation and otherwise specified in the purchase order (see 5.1 and 5.2) shall be verified by tests made in accordance with the directions given in 12.1.

TABLE 3 Detail Requirements for Molded Test Specimens

Property and Unit	Grade ^A									
	E1	E2	E3	E4	E5	E6	E7	E8	E9	E10
Tensile stress, min: ^B										
MPa	8	10	10	12	12	17	17	19	19	22
(psi)	(1200)	(1500)	(1500)	(1800)	(1800)	(2400)	(2400)	(2800)	(2800)	(3200)
Elongation, min, % ^B	300	400	400	500	500	400	400	400	400	400
Brittleness temperature, max, °C	-50	-60	-60	-75	-75	-45	-75	-75	-75	-75
Environmental stress-crack resistance, ^{C,D} min, f ₂₀ h	48	48	48	48	48
Thermal stress-crack resistance, h without cracking, min	96	96	168
Dissipation factor, ^E max:										
Class A										
Before milling	0.0005	0.0002	0.0005	0.0002	0.0005	0.0002	0.0005	0.0002	0.0005	0.0002
After milling	0.0005	0.0003	0.0005	0.0003	0.0005	0.0003	0.0005	0.0003	0.0005	0.0003
Class B	0.001	0.0005	0.001	0.0005	0.001	0.0005	0.001	0.0005	0.001	0.0005
Class C	0.01	0.005	0.01	0.005	0.01	0.005	0.01	0.005	0.01	0.005
Dielectric constant ^E max increase over nominal ^F :										
Class A	0.05	0.01	0.05	0.01	0.05	0.01	0.05	0.01	0.05	0.01
Class B	0.12	0.04	0.12	0.04	0.12	0.04	0.12	0.04	0.12	0.04
Class C	0.52	0.30	0.52	0.30	0.52	0.30	0.50	0.30	0.50	0.30
Volume resistivity, min, Ω·cm:										
Volume resistivity, min, -cm:										
Classes A, B	10 ¹⁵ _G	10 ¹⁵ _G	10 ¹⁵ _G	10 ¹⁵ _G	10 ¹⁵ _G	10 ¹⁵ _G	10 ¹⁵ _G	10 ¹⁵ _G	10 ¹⁵ _G	10 ¹⁵ _G
Water immersion stability										
	E11	J1	J3	J4	J5					
Tensile stress, min: ^B										
MPa	22	10	12	19	22					
(psi)	(3200)	(1500)	(1800)	(2800)	(3200)					
Elongation, min, %	400	400	500	400	400					
Brittleness temperature, max, °C	-75	-60	-75	-75	-75					
Environmental stress-crack resistance, ^{C,D} min, f ₂₀ h	48	...	24	24	24					
Thermal stress-crack resistance, h without cracking, min	168					
Dissipation factor, ^E max:										
Class A										
Before milling	0.0005					
After milling	0.0005					
Class B	0.001					
Class C	0.01	...	0.01	0.01	...					
Dielectric constant ^E max increase over nominal ^F :										
Class A	0.05					
Class B	0.12					
Class C	0.50	...	0.52	0.52	...					
Volume resistivity, min, Ω·cm:										
Volume resistivity, min, -cm:										
Classes A, B	10 ¹⁵ _G					
Water immersion stability										
	E11	J1	J3	J4	J5					

^AThe letters associated with these grades identify areas of potential applicability as indicated below:

- EE = Electrical Insulation (in some instances these materials also have the potential to serve as jacketing).
- JJ = Jacketing (in some instances these materials also have the potential to serve as primary insulation).

^BAt break.

^Cf₂₀ is the time required for failure of 20 % of the samples tested in accordance with Test Method D1693 as further directed by 12.1.6.1 – 12.1.6.4 of this specification.

^DRequirements for environmental stress-crack resistance apply only to Class B, Class C, and Class D compounds unless otherwise specified (see 5.2.5).

^EAt any frequency from 1 kHz through 1 MHz (see also 12.1.8.1 – 12.1.8.3).

^FDielectric constant is a function of density; hence, the nominal value will be different for each type. Based on published information, the nominal values for the five types covered by this specification are as follows: Type 0-2.28, Type I-2.28, Type II-2.31, Types III and IV-2.35 (Lanza, V. L., and Herrmann, D. B., *Journal of Polymer Science*, JPSCA, Vol 28, 1958, p. 622). To illustrate the manner in which the maximum limit for the dielectric constant of a particular, grade is determined, assume that a Type I, Class A material is to be supplied under Grade E2, then its maximum limit for dielectric constant will be 2.28 + 0.01 = 2.29.

^GDissipation factor and dielectric constant must not exceed the limits specified above after immersion of the test specimens in water as described in 12.1.9. However, because this test is lengthy, it need not be performed on every lot of material. Rather, the material is to be checked initially for compliance with this requirement and, after that, as often as necessary to assure continued compliance. This requirement is not applicable to weather resistant (Class C and Class D) compounds (see Note 12).

10. Specimen Preparation

10.1 Unless otherwise specified in 12.1, the test specimens shall be molded in accordance with Procedure C as found in Annex A1 of Practice D4703.

11. Conditioning

11.1 *Conditioning*—Once specimens are molded, they shall be moved to a standard laboratory atmosphere or a controlled laboratory atmosphere. For unfilled polyethylene plastics the controlled laboratory atmosphere shall be 23 ± 2°C. Test specimens

TABLE 4 Special Grades—Dielectric—Natural and Colors

	Very Low Density, Specification D1248, Type 0	Low Density, Specification D1248, Type I				Medium Density, Specification D1248, Type II		High Density, ^A Specification D1248, Types III & IV				
		Natural	Colors	Natural	Colors	Natural	Colors	D7	D8	D9	D10	D11
Grade	D0	D1	D2	D3	D4	D5	D6	D7	D8	D9	D10	D11
Tensile Stress, min: ^B												
MPa	6.9	9.7	9.7	9.7	9.7	12.4	12.4	19.3	19.3	24.1	24.1	27.6
(psi)	1000	(1400)	(1400)	(1400)	(1400)	(1800)	(1800)	(2800)	(2800)	(3500)	(3500)	(4000)
Elongation, min, % ^B	500	400	400	400	400	400	400	400	400	400	400	400
Brittleness temperature, max, °C	-60	-60	-55	-60	-55	-60	-55	-55	...	-55
Dielectric constant, max, 1 MHz	2.28	2.35	2.35	2.35	2.35	2.35	2.35	2.38	2.38	2.38	2.38	2.38
Dissipation factor, max, 1 MHz	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005
Environmental stress crack resistance, min:												
f ₂₀ h (100 % Igepal)	24	24
f ₂₀ h (10 % Igepal)	>24
Thermal stress crack resistance, min, f ₄₅ h	96	...	96
Milling stability	...	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005
After milling, dissipation factor, max												

^AGrades D7 through D11 apply to both natural and colors, including black.

^BAt break.

TABLE 5 Special Grades—Weather Resistant—Black

	Very Low Density, Specification D 1248, Type 0	Low Density, Specification D1248, Type I				Medium Density, Specification D1248, Type II			High Density, Specification D1248, Types III & IV	
		W0	W1	W2	W3	W4	W5	W6	W7	W8
Grade	W0	W1	W2	W3	W4	W5	W6	W7	W8	W9
Tensile Stress, min: ^A										
MPa	6.9	9.7	9.7	9.7	9.7	12.4	12.4	12.4	19.3	24.1
(psi)	(1000)	(1400)	(1400)	(1400)	(1400)	(1800)	(1800)	(1800)	(2800)	(3500)
Elongation, min, % ^A	500	400	400	400	400	400	400	400	400	400
Brittleness temperature, max, °C	-60	-50	-50	-50	-50	-50	-50	-50	-55	-55
Dielectric constant, max, 1 MHz	2.28	2.50	2.75	2.75	2.80	2.50	2.75	2.80	2.75	2.75
Dissipation factor, max, 1 MHz	0.0005	0.003	0.007	0.007	0.01	0.003	0.007	0.01	0.005	0.007
Environmental stress crack resistance, min:										
f ₂₀ h (100 % Igepal)	24	24
f ₂₀ h (10 % Igepal)	>24
Thermal stress crack resistance, min, f ₄₅ h	96	96
Milling stability										
After milling, dissipation factor, max		0.003	0.007	0.007	0.01	0.003	0.007	0.01	0.005	0.007
Carbon content, range, %	2.0-3.0	0.4-0.6	2.0-3.0	2.0-3.0	2.0-3.0	0.4-0.6	2.0-3.0	2.0-3.0	2.0-3.0	2.0-3.0
Absorption coefficient, min	320	...	320	320	320	...	320	320	320	320

^AAt break.

shall be—Specimens shall be stored in boxes, paper bags or envelopes, plastic bags or on racks, whichever is the most practical for the laboratory. Specimens shall be conditioned for a minimum of 40 h immediately prior to testing. It is recommended that specimens be allowed to cool for about 30 min on a bench or a rack before they are placed in any container where the specimens might come into contact with each other. For filled and reinforced polyethylene plastics or polyethylene plastic blends, which contain a co-monomer, hydrophilic pigment, or modifier of a hydrophilic nature, hydrophilic co-monomer or modifier, the specimens shall be conditioned in a standard laboratory atmosphere of 23 ± 2°C and 50 ± 10 % (Note 13) relative humidity (see Practice D618, Procedure A). For all materials to be conditioned for electrical testing, conditioning shall comply with the requirements of the standard test methods for electrical testing. In all cases the laboratory shall report both the temperature and humidity conditions during the conditioning period.

NOTE 13—The plus/minus (±) tolerances given for irradiance, temperature and relative humidity are the maximum allowable operational fluctuations of the parameter set point value under equilibrium conditions. This does not mean that the value can be set by plus/minus the amount indicated from the value specified. If the deviations are greater than the maximum allowable after the equipment has stabilized, discontinue the test and correct the cause of the problem before continuing.

11.2 Test Conditions—Unfilled polyethylene plastics shall be tested in a controlled laboratory atmosphere of 23 ± 2°C. For filled and reinforced polyethylene plastics and polyethylene plastic blends, which contain a co-monomer, hydrophilic pigment, or