



Designation: F1635 – 16

Standard Test Method for *in vitro* Degradation Testing of Hydrolytically Degradable Polymer Resins and Fabricated Forms for Surgical Implants¹

This standard is issued under the fixed designation F1635; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers *in vitro* degradation of hydrolytically degradable polymers (HDP) intended for use in surgical implants.

1.2 The requirements of this test method apply to HDPs in various forms:

1.2.1 Virgin polymer resins, or

1.2.2 Any form fabricated from virgin polymer such as a semi-finished component of a finished product, a finished product, which may include packaged and sterilized implants, or a specially fabricated test specimen.

1.3 This test method provides guidance for mechanical loading or fluid flow, or both, when relevant to the device being evaluated. The specifics of loading type, magnitude, and frequency for a given application are beyond the scope of this test method.

1.4 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

- D638 Test Method for Tensile Properties of Plastics
- D671 Test Method for Flexural Fatigue of Plastics by Constant-Amplitude-of-Force (Withdrawn 2002)³
- D695 Test Method for Compressive Properties of Rigid Plastics
- D747 Test Method for Apparent Bending Modulus of Plastics by Means of a Cantilever Beam
- D790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials
- D882 Test Method for Tensile Properties of Thin Plastic Sheet
- D1708 Test Method for Tensile Properties of Plastics by Use of Microtensile Specimens
- D1822 Test Method for Tensile-Impact Energy to Break Plastics and Electrical Insulating Materials
- D2857 Practice for Dilute Solution Viscosity of Polymers
- F748 Practice for Selecting Generic Biological Test Methods for Materials and Devices

2.2 *ISO Standards:*⁴

- ISO 31–8 Physical Chemistry and Molecular Physics - Part 8: Quantities and Units
- ISO 10993–1 Biological Evaluation of Medical Devices—Part 1 Evaluation and Testing
- ISO 10993–9 Biological Evaluation of Medical Devices—Part 9 Framework for Identification and Quantification of Potential Degradation Products
- ISO 13781 Poly(L-lactide) resins and fabricated forms for surgical implants – *In vitro* degradation testing

¹ This test method is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devices and is the direct responsibility of Subcommittee F04.15 on Material Test Methods.

Current edition approved Dec. 1, 2016. Published January 2017. Originally approved in 1995. Last previous edition approved in 2011 as F1635 – 11. DOI: 10.1520/F1635-16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

2.3 NIST Standard.⁵

NIST Special Publication SP811 Guide for the Use of the International System of Units (SI)

3. Terminology

3.1 Definitions:

3.1.1 *absorbable, adj—in the body*—an initially distinct foreign material or substance that either directly or through intended degradation can pass through or be assimilated by cells and/or tissue.

NOTE 1—See Appendix X2 for a discussion regarding the usage of absorbable and other related terms.

3.1.2 *hydrolytically degradable polymer (HDP)*—any polymeric material in which the primary mechanism of chemical degradation in the body is by hydrolysis (water reacting with the polymer resulting in cleavage of the chain).

3.1.3 *resin*—any polymer that is a basic material for plastics.⁶

4. Summary of Test Method

4.1 Samples of polymer resins, semi-finished components, finished surgical implants, or specially designed test specimens fabricated from those resins are placed in buffered saline solution at physiologic temperatures. Samples are periodically removed and tested for various material or mechanical properties at specified intervals. The required test intervals vary greatly depending on the specific polymeric composition. For example, poly(*l*-lactide) and poly(*ε*-caprolactone) degrade very slowly and can require two or more years for complete degradation. Polymers based substantially on glycolide can completely degrade in two to three months depending on the exact composition and on the size of the specimen. Degradation time is also strongly affected by specimen size, polymer molar mass, and crystallinity.

NOTE 2—The term molecular weight (abbreviated MW) is obsolete and should be replaced by the SI (Système Internationale) equivalent of either relative molecular mass (M_r), which reflects the dimensionless ratio of the mass of a single molecule to an atomic mass unit [see ISO 31–8], or molar mass (M), which refers to the mass of a mole of a substance and is typically expressed as grams/mole. For polymers and other macromolecules, use of the symbols M_w , M_n , and M_z continue, referring to mass-average molar mass, number-average molar mass, and z -average molar mass, respectively. For more information regarding proper utilization of SI units, see NIST Special Publication SP811.

5. Significance and Use

5.1 This test method is intended to help assess the degradation rates (that is, the mass loss rate) and changes in material or structural properties, or both, of HDP materials used in surgical implants. Polymers that are known to degrade primarily by hydrolysis include but are not limited to homopolymers and

copolymers of *l*-lactide, *d*-lactide, *d,l*-lactide glycolide, caprolactone, and *p*-dioxanone.⁷

5.2 This test method may not be appropriate for all types of implant applications or for all known absorbable polymers. The user is cautioned to consider the appropriateness of the test method in view of the materials being tested and their potential application (see X1.1.1).

5.3 Since it is well known that mechanical loading can increase the degradation rate of absorbable polymers, the presence and extent of such loading needs to be considered when comparing *in vitro* behavior with that expected or observed *in vivo*.

5.3.1 *Mechanically Unloaded Hydrolytic Evaluation*—Conditioning of a hydrolysable device under mechanically unchallenged hydrolytic conditions at 37°C in buffered saline is a common means to obtain a first approximation of the degradation profile of an absorbable material or device. It does not necessarily represent actual *in vivo* service conditions, which can include mechanical loading in a variety of forms (for example, static tensile, cyclic tensile, shear, bending, and so forth). If the performance of a device under its indicated use includes loading, hydrolytic aging alone is NOT sufficient to fully characterize the device.

5.3.2 *Mechanically Loaded Hydrolytic Evaluation*—The objective of loading is to approximate (at 37°C in buffered saline) the actual expected device service conditions so as to better understand potential physicochemical changes that may occur. Such testing can be considered as necessary if loading can be reasonably expected under *in vivo* service conditions. When feasible, test specimens should be loaded in a manner that simulates *in vivo* conditions, both in magnitude and type of loading. Clinically relevant cyclic load tests may include testing to failure or for a specified number of cycles followed by testing to evaluate physicochemical properties.

5.3.2.1 *Static Loading*—It is notable that for some polymeric materials it has been shown that a constant load results in the same failure mechanism (for example, creep) and is the worst case when compared to a cyclic load (where the maximum amplitude of the cyclic load is equal to the constant load). Thus, in specific cases it may be acceptable to simplify the test by using a constant load even when the anticipated *in vivo* loading is cyclic. It is incumbent upon the user of this test method to demonstrate through experiment or specific reference that this simplification is applicable to the polymer under investigation and does not alter the failure mode of the test specimen. If such evidence is not available, it is necessary to recognize that static loading and cyclic loading are measuring different material properties and are not comparable. Using one to replace the other could lead to misinterpretation of the results.

NOTE 3—Caution must be taken to ensure that fixturing does not introduce artifactual performance or degradation issues, or both. An example is the use of rigid foam block, which restricts swelling & expansion and can elevate pull out strength test results from sample compression within the block. Additionally, restricted perfusion due to the

⁵ Available from National Institute of Standards and Technology (NIST), 100 Bureau Dr., Stop 1070, Gaithersburg, MD 20899-1070, at <http://physics.nist.gov/cuu/Units/bibliography.html>.

⁶ *Polymer Technology Dictionary*, Tony Whelan ed., Chapman & Hall, 1994.

⁷ *Handbook of Biodegradable Polymers*, A.J. Domb ed., Harwood Academic Publishers, 1997.

closed cell nature of the foam can result in concentration of acidic byproducts that result in accelerated degradation when compared to a normally perfused and buffered *in vivo* condition.

NOTE 4—When performing degradation testing under load, it may be necessary to consider and monitor polymer creep during testing, which may be significant.

5.4 Absorbable devices subjected to flow conditions (for example, vascular stents, particularly those with a drug eluting component) may degrade more rapidly than the same device maintained under static degradation test conditions. When it is feasible to estimate the flow conditions that an implant will be subjected to *in vivo* and replicate them *in vitro* the degradation study should be conducted under flow conditions. However, details regarding appropriate flow modeling are beyond the scope of this test method.

5.5 Sterilization of HDP materials should be expected to cause changes in molar mass or structure, or both, of the polymers. This can affect the initial mechanical and physical properties of a material or device, as well as its subsequent rate of degradation. Therefore, if a test is intended to be representative of actual performance *in vivo*, specimens shall be packaged and sterilized in a manner consistent with that of the final device. Non-sterilized specimens may be included for comparative purposes.

6. Materials and Apparatus

6.1 *Physiologic Soaking Solution*—A phosphate-buffered saline (PBS) solution shall be used. The pH of the solution shall be maintained at 7.4 ± 0.2 (see X1.3) unless it is determined through documented literature or self-advised study that the pH should be different due to the physiological conditions of the intended application (this may require use of an alternate buffer system). Limited excursions outside of the specified pH range are tolerable provided the time weighted average pH after buffer replenishment is maintained within this range (see X1.3.1). The ionic concentration should be in the physiological range for the intended application (for example, a solution that contains 0.1 M phosphate buffer and 0.1 M NaCl would be appropriate for most tissue or blood contact devices). The solution-to-HDP mass ratio shall be as high as practical. The experimenter is cautioned that at lower ratios (that is, less buffering capacity) the solution pH may change more quickly. To provide adequate buffer capacity, solution-to-HDP mass ratio is recommended to be greater than 30:1. In accordance with 9.1.3 and X1.4, aging/testing is to be terminated if the solution temperature or pH are allowed to drift outside of the specified ranges. Higher solution/specimen ratios (for example, 100:1) will be more likely to facilitate maintenance of stable aging conditions.

6.1.1 Over the course of the study, the pH of the soaking solution should be monitored frequently and the solution shall be changed periodically in order to maintain the pH within the acceptable limits. Refer to X1.5 for additional information.

6.1.2 Other physiologic solutions, such as bovine serum, may be substituted provided the solution is properly buffered. An anti-microbial additive should be used to inhibit the growth of microorganisms in the solution during the test period but the investigator must demonstrate through literature reference or experimentation that the chosen antimicrobial does not affect

the degradation rate. Section X1.6 provides additional information. The appropriate MSDS should always be consulted concerning toxicity, safe use, and disposal of such additives.

6.2 *Sample Container*—A self-contained, inert container (bottle, jar, vial, and so forth) capable of holding the test sample and the required volume of physiologic soaking solution (see X1.7). Multiple samples may be stored in the same container provided that suitable sample separation is maintained to allow fluid access to each sample surface and to preclude sample-to-sample contact. Each container must be sealable against solution loss by evaporation.

6.3 *Constant Temperature Bath or Oven*—An aqueous bath or heated air oven capable of maintaining the samples and containers at physiologic temperatures, $37 \pm 1^\circ\text{C}$, for the specified testing periods.

6.4 *pH Meter*—A pH metering device sensitive in the physiological range (pH 6 to pH 8) with a precision of 0.02 or better.

6.5 *Balance*—A calibrated weighing device capable of measuring the mass of a sample to a precision of 0.1 % of its initial mass. A balance having precision to 0.05 % or 0.01 % will facilitate establishment of an appropriate specimen drying period.

6.6 *Other*—Additional equipment as deemed appropriate by the specific test method.

7. Sampling

7.1 *Mass Loss*—A minimum of three samples shall be tested per time period.

7.2 *Molar Mass*—A minimum of three samples shall be tested per time period.

7.3 *Mechanical Testing*—A minimum of six samples shall be tested per time period.

NOTE 5—Statistical significance may require more than the minimum number of samples to be tested.

7.4 *Solution Temperature and pH*—Soaking solutions shall be tested on a periodic basis throughout the test duration. The required test period is dependent on the degradation rate of the test polymer, the solution/specimen mass ratio, and the solution's buffering capacity; once per week is generally practical and suggested. In cases where no prior knowledge of the degradation rate is available, it is suggested that the pH be tested at least daily until a baseline is established. This increased sampling frequency may need to be repeated during periods of elevated mass loss (that is, pH change).

8. Sample and Test Specimen

8.1 All test samples shall be representative of the material under evaluation.

8.1.1 For most HDP resins, inter-lot variations in the molar mass and residual monomer content can be significant. Since these factors can strongly affect degradation rates, molar mass (or inherent viscosity) and residual monomer content of the source resin and fabricated test parts need to be understood.