



Designation: ~~D2129–05 (Reapproved 2010)~~ **D2129 – 17**

Standard Test Method for Color of Clear Electrical Insulating Liquids (Platinum-Cobalt Scale)¹

This standard is issued under the fixed designation D2129; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

- 1.1 This standard describes a test method for the visual determination of the color of clear insulating liquids.
- 1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.
- 1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

- 2.1 *ASTM Standards:*²
 - [D1193 Specification for Reagent Water](#)
 - [D1209 Test Method for Color of Clear Liquids \(Platinum-Cobalt Scale\)](#)
 - [D1500 Test Method for ASTM Color of Petroleum Products \(ASTM Color Scale\)](#)

3. Summary of Test Method

3.1 The color determined by this test method is derived by comparing the color of the test specimen with that of a series of numbered color reference standards using transmitted light under prescribed conditions. The procedure described is based on that for measuring the color of water and clear liquids according to the platinum-cobalt scale. This scale is suitable for measurements over the color range from 5 to 300. The color of test specimens darker than 300 on the platinum-cobalt scale must be measured according to the ASTM Color Scale as described in Test Method [D1500](#). The use of the platinum-cobalt scale in this way is primarily of value as an expansion of the lower part of the ASTM Color Scale, especially in the range between 0 and 1.

4. Significance and Use

4.1 Color is significant chiefly as an indicator of contamination in electrical insulating liquids. Frequently this contamination is the result of solvent action in the apparatus involved or it may indicate possible contamination. No definite relationship can be established between color and the physical and electrical characteristics of the liquid; for that reason color in itself has limited value as a measure of condition. For more precise determination of color, Test Method [D1209](#) may be used.

5. Apparatus

- 5.1 *Color Comparison Tubes*—Matched, tall-form Nessler tubes, graduated at the 50-mL mark, and provided with ground-on, optically clear glass caps.
- 5.2 *Color Comparator*—A color comparator constructed to permit visual comparison of light transmitted through tall-form Nessler tubes in the direction of their longitudinal axes. The comparator should be constructed so that white light is passed through

¹ This test method is under the jurisdiction of ASTM Committee on [D27](#) on Electrical Insulating Liquids and Gases and is the direct responsibility of Subcommittee [D27.07](#) on Physical Test.

Current edition approved Nov. 1, 2010Jan. 1, 2017. Published November 2010February 2017. Originally approved in 1962 as D2129 - 62 T. Last previous edition approved in 20052010 as ~~D2129–05~~D2129 - 05(2010). DOI: [10.1520/D2129-05R10.1520/D2129-17](#).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.