This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



Designation: C1623 - 11 C1623 - 16

Standard Specification for Manufactured Concrete Masonry Lintels¹

This standard is issued under the fixed designation C1623; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers concrete masonry lintels (beams) that are solid in cross-section, are reinforced for flexure, and are made from hydraulic cement, water, and mineral aggregates with or without the inclusion of other materials. These lintels are suitable for both loadbearing and nonloadbearing applications.

NOTE 1—This specification covers only concrete masonry lintels containing reinforcement. Due to building code imposed limitations on the design of masonry lintels, all lintels must contain reinforcement. Concrete masonry lintels are not typically manufactured using shear reinforcement (stirrups or other vertical reinforcement). Therefore, this standard does not address issues related to such. For further guidance, refer to *Building Code Requirements for Masonry Structures*, TMS 402/ACI 530/ASCE 5. Prestressed concrete lintels are not covered by this standard.

1.2 Lintels are manufactured using a no-slump concrete mix to provide a surface texture similar to that of concrete masonry. This specification applies to both machine-made and hand-tamped concrete masonry lintels intended for use in concrete masonry applications.

1.3 Concrete masonry lintels covered by this specification are made from lightweight or normal weight aggregates, or both.

1.4 This specification does not address the design or analysis of lintel capacity. Structural evaluations must be performed separately. The strength of a lintel is a function of factors including, but not limited to, the characteristics of the materials used in manufacturing (concrete materials and reinforcement), the amount and location of reinforcement, and the manufacturing and curing procedures. For design and analysis methods, refer to Building Code Requirements for Masonry Structures, TMS 402/ACI 530/ASCE 5.

1.5 This specification does not cover U-shaped lintels or those of other cross-sections that are not 100 % solid.

1.6 This specification does not cover lintels of grouted concrete masonry lintels, or precast or cast-in-place lintels of slump concrete.

1.7 The text of this standard references notes and footnotes that provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

1.8 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

2. Referenced Documents

2.1 ASTM Standards:²

A615/A615M Specification for Deformed and Plain Carbon-Steel Bars for Concrete Reinforcement A706/A706M Specification for Deformed and Plain Low-Alloy Steel Bars for Concrete Reinforcement A996/A996M Specification for Rail-Steel and Axle-Steel Deformed Bars for Concrete Reinforcement

C33 Specification for Concrete Aggregates

C140 Test Methods for Sampling and Testing Concrete Masonry Units and Related Units

C150 Specification for Portland Cement

C331 Specification for Lightweight Aggregates for Concrete Masonry Units

C595 Specification for Blended Hydraulic Cements

C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete

*A Summary of Changes section appears at the end of this standard

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959. United States

¹ This specification is under the jurisdiction of ASTM Committee C15 on Manufactured Masonry Units and is the direct responsibility of Subcommittee C15.03 on Concrete Masonry Units and Related Units.

Current edition approved Dec. 15, 2011 Dec. 15, 2016. Published January 2012 January 2017. Originally approved in 2005. Last previous edition approved in 20062011 as C1623 - 06.C1623 - 11. DOI: 10.1520/C1623-11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

C979 Specification for Pigments for Integrally Colored Concrete

C989 Specification for Slag Cement for Use in Concrete and Mortars

C1157 Performance Specification for Hydraulic Cement

C1232 Terminology of Masonry

C1240 Specification for Silica Fume Used in Cementitious Mixtures

C1262 Test Method for Evaluating the Freeze-Thaw Durability of Dry-Cast Segmental Retaining Wall Units and Related **Concrete Units**

2.2 Other StandardsStandards:³

TMS 402/ACI 530/ASCE 5- Building Code Requirements for Masonry Structures TMS 602/ACI 530.1/ASCE 6 Specification for Masonry Structures

3. Terminology

3.1 Terminology defined in Terminology C1232 shall apply for this specification.

4. Material

4.1 Cementitious Materials—Materials shall conform to the following applicable specifications: 4.1.1 Portland Cement— Specification C150.

4.1.1 Portland Cement—Specification C150.

4.1.2 Modified Portland Cement—Portland cement conforming to Specification C150, modified as follows:

(1) Limestone – If calcium carbonate is added to the cement, the CaCO₃ content shall be not less than 85 %.

(1) Limestone—If calcium carbonate is added to the cement, the CaCO₃ content shall be not less than 85 %.

(2) Limitation on Insoluble Residue—1.5 %.

(3) Limitation on Air Content of Mortar-Volume percent, 22 % max.

(4) Limitation on Loss on Ignition-7%.

(2) Limitation on Insoluble Residue-1.5 %.

(3) Limitation on Air Content of Mortar-Volume percent, 22 % max.

(4) Limitation on Loss on Ignition-7 %.

4.1.3 Blended Hydraulic Cements-Specification C595

4.1.4 Hydraulic Cement—Specification C1157.

4.1.5 Pozzolans—Specification C618.

4.1.6 Ground Granulated Blast Furnace Slag—Specification C989. Teview

4.1.7 Silica Fume—Specification C1240.

4.2 Aggregates—Aggregates shall conform to the following specifications, except that grading requirements shall not necessarily apply:

4.2.1 Normal Weight Aggregates—Specification C33. c26af6B-d7d0-43cb-a5e9-dfaff97c8b04/astm-c1623-16

4.2.2 Lightweight Aggregates—Specification C331.

4.3 Pigments for Integrally Colored Concrete—Specification C979.

4.4 Steel Reinforcement-Steel reinforcement shall consist of deformed bars conforming to Specifications A615/A615M, A706/A706M, or A996/A996M.

4.5 Other Constituents—Air-entraining agents, integral water repellents, and other constituents shall be previously established as suitable for use in concrete masonry lintels and shall conform to applicable ASTM standards or shall be shown by test or experience not to be detrimental to the durability of the concrete masonry lintels or any material customarily used in masonry construction.

5. Physical Requirements

5.1 At the time of delivery to the purchaser, the concrete within the lintel shall conform to the requirements prescribed in Table 1.

5.1.1 When higher compressive strengths than those listed in Table 1 are specified, the tested average net area compressive strength of three specimens shall equal or exceed the specified compressive strength, and the tested individual specimen net area compressive strength of all three units shall exceed 90 % of the specified compressive strength.

NOTE 2-When particular features are desired such as surface textures for appearance or bond, finish, color, or particular properties such as specific reinforcing schedules, flexural strength, weight per unit length, higher compressive strength, or fire resistance, these features are specified separately by the purchaser. Consult suppliers as to the availability of lintels having the desired features.

³ Available from The Masonry Society, 105 South Sunset Street, Suite Q, Longmont, CO 80501-6172, https://www.masonrysociety.org.