



Designation: **G29—96 (Reapproved 2010) G29 – 16**

Standard Practice for Determining Algal Resistance of Plastic Polymeric Films¹

This standard is issued under the fixed designation G29; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This practice covers the determination of the susceptibility of plastic polymeric films to the attachment and proliferation of surface-growing algae.

1.2 The values in SI units are to be regarded as the standard. The inch-pound units given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Summary of Practice

2.1 In this practice, test strips of plastic polymeric film are suspended in glass jars maintained at room temperature. The test strips are exposed to fluorescent light and in direct contact with a standardized inoculum of the filamentous blue-green alga *Oscillatoria* in culture medium. The sample test jars are re-inoculated with fresh alga every second or third day. A control using untreated plastic polymeric film is used as a basis of comparison. The inoculum is prepared with the help of a propagation apparatus made from a small fish tank. The test is terminated at the end of two weeks, or whenever the test film untreated control shows dense algal growth.

3. Significance and Use

3.1 Bodies of water, such as swimming pools, artificial ponds, and irrigation ditches often are lined with plastic polymeric films. Algae tend to grow in such bodies of water under the proper atmospheric conditions, and they can produce slimy and unsightly deposits on the film. The method described herein is useful in evaluating the degree and permanency of protection against surface growth of algae afforded by various additives incorporated in the film.

4. Apparatus

4.1 *Propagation Tank*: (see Fig. 1):

4.1.1 A small fish tank (10 gal) is used to contain a simulated cooling tower, made of redwood slats, over which an algae propagation system where culture medium is recirculated through a plastic polymeric tube with holes punched in the bottom. The bottom over the top of a polymeric mesh screen inside of the tank. This design was developed in order to provide ideal conditions for propagation of the algae that serve as inocula for each test. Three redwood slats are joined by two supports. The polymeric mesh is supported in such a way that water cascades over each slat in turn the top from a distributor tube above the upper slat. above. A small, fully immersed recirculating pump rests on the bottom of the tank and operates continuously to deliver the tank contents to the distributor tube. The light required for algal propagation is provided by a 100-W bulb placed 300 mm (12 in.) (12 in.) away from the redwood slats polymeric mesh. A timing device turns the light on for 12 h the desired light cycle each day.

4.1.2 The propagation tank, tank that is used as the permanent source of inoculum, inoculum is filled to approximately one-third capacity with the culture medium. Heavy growth of *Oscillatoria* rapidly develops on the redwood tower polymeric mesh screen and, at different phases, this growth appears light green, dark green, or black.

NOTE 1—Culture medium in the propagation tank is discarded monthly and replaced with fresh media.

4.2 *Test Chambers* (see Chambers: Fig. 2):

¹ This practice is under the jurisdiction of ASTM Committee G03 on Weathering and Durability and is the direct responsibility of Subcommittee G03.04 on Biological Deterioration.

Current edition approved June 1, 2010 Dec. 1, 2016. Published June 2010 March 2017. Originally approved in 1971. Last previous edition approved in 2002 2010 as G29 – 96 (2002) (2010). DOI: 10.1520/G0029-96R10.10.1520/G0029-16.

4.2.1 One-litre (1-qt) wide-mouth glass jars, 170 mm (6¾ in.) high by 76 mm (3 in.) in inside diameter, or equivalent, serve as test chambers wherein water containing an inoculum of the algal organisms and strips of the plastic polymeric film are maintained in contact.

4.2.2 The jars in 4.2.1 are placed in a 38-L (10-gal) fish tank, 508 by 267 by 305 mm (20 by 10 suitable glass container, such as a 38-L (10-gal) fish tank ½ by 12 in.) high, that is illuminated by four 20-W “cool white” fluorescent bulbs, arranged two on each long side of the tank, at the level of the growing algae in the jars. The lamps are mounted on a bracket that holds the outer surface of the bulbs 25 mm (1 in.) from the wall of the tank. The tank is filled with water to within 25 mm (1 in.) of the top of the exposure jars in order to create uniform temperature conditions for all jars.

4.3 *Homogenizer*—Any suitable commercial homogenizer for preparing the algal inocula.

5. Reagents and Materials

5.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.² Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

5.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean distilled water or water of equal purity.

5.3 *Culture Medium for Propagation Apparatus*—Prepare this medium by dissolving in 15 L of water the designated amounts of the following reagents:

Arnon's trace metal solution (see Note 1)	15 mL
Arnon's trace metal solution (see Note 2)	15 mL
Ethylenediamine tetraacetic acid disodium salt	0.04 g
Ferric ammonium citrate	0.85 g
Magnesium sulfate (MgSO ₄ ·7H ₂ O)	10.0 g
Potassium acid phosphate (K ₂ HPO ₄)	12.3 g
Potassium nitrate (KNO ₃)	12.1 g
Sodium citrate	2.0 g
Sulfuric acid, 10 %	10 mL

NOTE 2—Prepare this solution by combining the following reagents in the order given in the amounts designated in 1 L of water:

Boric acid	2.86 g
Copper sulfate (CuSO ₄ ·5H ₂ O)	0.079 g
Manganese chloride (MnCl ₂ ·4H ₂ O)	1.18 g
Molybdc oxide (MoO ₃)	0.018 g
Zinc sulfate (ZnSO ₄ ·7H ₂ O)	0.22 g

5.3.1 BG 11 Medium for Cyanobacteria:

	stock solution [g/100 ml]	nutrient solution [ml]
NaNO ₃	15	10
K ₂ HPO ₄ · 3H ₂ O	0.4	10
MgSO ₄ · 7H ₂ O	0.75	10
CaCl ₂ · 2H ₂ O	0.36	10
citric acid	0.06	10
ferric ammonium citrate	0.06	10
EDTA (dinatrium-salt)	0.01	10
Na ₂ CO ₃	0.2	10
Trace mineral solution ⁴	1	1
de-ionized or distilled water		919

⁴Composition of the Trace minerals solution (from Kuhl and Lorenzen 1964): Add to 1000 ml of de-ionized or distilled water:

H ₃ BO ₃	61.0 mg
MnSO ₄ · H ₂ O	169.0 mg
ZnSO ₄ · 7H ₂ O	287.0 mg
CuSO ₄ · 5 H ₂ O	2.5 mg
(NH ₄) ₆ Mo ₇ O ₂₄ · 4H ₂ O	12.5 mg

5.3.2 BG 11 Medium without sodium nitrate (BG 11–NaNO₃):

Prepare BG 11 medium without sodium nitrate (NaNO₃) and add 929 mL instead of 919 mL of water.

5.3.3 Adjust to 7.2 to 7.5 pH range if necessary. ~~The culture medium need not be sterilized.~~ Filter sterilization is recommended.

5.4 *Culture Medium for Test Chambers—Vessels*—Dilute 50 mL of the culture medium in 5.3 with 950 mL of tap de-ionized or distilled water and place this medium in the test chambers-vessels.

² *Reagent Chemicals, American Chemical Society Specifications* American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.