This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



Designation: D1792 - 06 (Reapproved 2012)^{£1} D1792 - 17

Standard Test Method for Long-Term Removability Properties of Emulsion Floor Polishes¹

This standard is issued under the fixed designation D1792; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

 $\underline{\epsilon^1 \text{ NOTE}}$ —Editorial changes were made in October 2012.

1. Scope

1.1 This test method covers the determination of the relative ease of removal of dried films of water-emulsion floor polishes from common flooring substrates under accelerated conditions, which correspond to extended service aging.

1.2 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

1.3 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:²

D1436 Test Methods for Application of Emulsion Floor Polishes to Substrates for Testing Purposes

3. Summary of Test Method

3.1 The dried films are conditioned at 37.8°C (100°F) in order to simulate service aging. This method utilizes the Gardner straight-line washability apparatus as a means for controlled removal of the dried films. A heavily weighted pad is employed as a means of arriving at a scrubbing force similar to that of hand scrubbing. In order to distinguish between the relative removal properties of different polishes, the number of oscillations required for complete removal is taken as a measure of removability.

4. Significance and Use

4.1 This test method is used to predict removability of floor polish after a treatment period that simulates aging in the field. It allows for uniform mechanical and detergent action leaving the only variable the actual removability of the polish.

5. Apparatus

5.1 Volumetric Pipet, 1-mL, graduated in 0.2-mL units.

5.2 *Applicator*—Doctor blade 51 mm (2 in.) wide by 25 mm (1 in.) deep and having 0.203-mm (0.008-in.) clearance along the 51-mm (2-in.) length.

5.3 Test Flooring Substrate—Official Vinyl Composition Tile (OVCT),³ shall be used in the test.

5.4 Oven, capable of maintaining a temperature of $37.8 \pm \frac{1.1}{1.1} \circ C (100 \pm 2 \circ F) \cdot 2 \circ F)$.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959. United States

¹ This test method is under the jurisdiction of Committee D21 on Polishes and is the direct responsibility of Subcommittee D21.04 on Performance Tests.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

³ The sole source of supply of the apparatus known to the committee at this time is Chemical Specialties Manufacturers Assn., 1913 Eye St., N.W., Washington, DC 20006. If you are aware of alternative suppliers, please provide this information to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. OVCT tile may be obtained through Armstrong Flooring from various home improvement stores. The following Armstrong tile substrates have been found to perform adequately for this test method: Armstrong Excelon Feature Tile: Black (56790), http://www.armstrong.com/ commflooringna/product_details_toolbox_magnify.jsp?item_id=47394.



5.5 Washability Apparatus—The Gardner straight-line washability machine.

5.6 Abrading Surface Nylon Polishing Floor Pad, ⁴ attached to a wood block of dimensions 89 by 38 mm ($3\frac{1}{2}$ by $1\frac{1}{2}$ in.). Presoaked in stripper solution.

5.7 Weight—The boat containing the pad is fitted to achieve a total weight of 1-kg ($2\frac{1}{2} \pm \frac{1}{4}$ -lb). The weight should be properly mounted for uniform load distribution.

iTeh Standards (https://standards.iteh.ai) Document Preview

<u>ASTM D1792-17</u>

https://standards.iteh.ai/catalog/standards/sist/2ec52850-1120-4f45-b845-225f95d896fe/astm-d1792-17

⁴ The sole source of supply of the apparatus known to the committee at this time is 3M Co., 3M Center, St. Paul, MN 55101. If you are aware of alternative suppliers, please provide this information to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend.