



**SLOVENSKI STANDARD**  
**SIST EN 12019:2000**  
**01-november-2000**

---

7 ]b\_ ]b`W]b\_cj Y`n`]h]bY!`5 bU]nY`n`cdh] bc`Ya ]g]`g\_c`gdY`lfca Yf]`c

Zinc and zinc alloys - Optical emission spectrometric analysis

Zink und Zinklegierungen - Analysenverfahren durch optische Emissionsspektrometrie

Zinc et alliages de zinc - Analyse par spectrométrie d'émission optique

**Ta slovenski standard je istoveten z: EN 12019:1997**

[SIST EN 12019:2000](https://standards.iteh.ai/catalog/standards/sist/3021a373-39b9-4ba0-b627-18a7edf0b78a/sist-en-12019-2000)

<https://standards.iteh.ai/catalog/standards/sist/3021a373-39b9-4ba0-b627-18a7edf0b78a/sist-en-12019-2000>

**ICS:**

77.120.60	Svinec, cink, kositer in njihove zlitine	Lead, zinc, tin and their alloys
-----------	--	----------------------------------

**SIST EN 12019:2000**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 12019:2000

<https://standards.iteh.ai/catalog/standards/sist/3021a373-39b9-4ba0-b627-18a7edf0b78a/sist-en-12019-2000>

EUROPEAN STANDARD

EN 12019

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 1997

ICS 77.120.60

Descriptors: zinc, zinc alloys, chemical analysis, determination, chemical composition, emission spectrophotometry, optical tests, specimen preparation

English version

## Zinc and zinc alloys - Optical emission spectrometric analysis

Zinc et alliages de zinc - Analyse par spectrométrie  
d'émission optique

Zink und Zinklegierungen - Analysenverfahren durch  
optische Emissionsspektrometrie

This European Standard was approved by CEN on 26 September 1997.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

SIST EN 12019:2000

<https://standards.iteh.ai/catalog/standards/sist/3021a373-39b9-4ba0-b627-18a7edf0b78a/sist-en-12019-2000>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

**Contents**

	Page
Foreword	3
1 Scope	4
2 Normative references	4
3 Definitions	4
3.1 ingot	4
3.2 batch	4
3.3 cast	5
3.4 sample	5
3.5 test piece	5
3.6 optical emission spectrometry	5
4 Sampling	5
5 Preparation of test pieces	5
6 Testing	5
6.1 General	5
6.2 Calibration	6
6.3 Method of testing	6
6.4 Expression of results	6
6.5 Test report	6
Annex A (informative) Selection of analytical lines	7
Annex B (normative) Reproducibility	8

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 12019:2000

<https://standards.iteh.ai/catalog/standards/sist/3021a373-39b9-4ba0-b627-18a7edf0b78a/sist-en-12019-2000>



## Foreword

This European Standard has been prepared by Technical Committee CEN/TC 209 "Zinc and zinc alloys", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 1998, and conflicting national standards shall be withdrawn at the latest by April 1998.

Within its programme of work, Technical Committee CEN/TC 209 entrusted CEN/TC 209/SC3 "Methods of analysis and testing" to prepare the following document:

EN 12019 Zinc and zinc alloys - Optical emission spectrometric analysis

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 12019:2000

<https://standards.iteh.ai/catalog/standards/sist/3021a373-39b9-4ba0-b627-18a7edf0b78a/sist-en-12019-2000>

## 1 Scope

This European Standard specifies analytical methods of testing chemical composition of zinc and zinc alloys in accordance with EN 1179, EN 1774, prEN 12844, and EN 988 by optical emission spectrometry.

Included are provisions for preparation of test pieces of zinc and zinc alloys.

## 2 Normative references

This European Standard incorporates by dated or undated references provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references, the latest edition of the publication referred to applies.

- |            |   |
|------------|---|
| EN 1774    | Zinc and zinc alloys - Alloys for foundry purposes - Ingot and liquid       |
| prEN 12844 | Zinc and zinc alloys - Castings - Specifications                            |
| EN 12060   | Zinc and zinc alloys - Method of sampling - Specifications                  |
| EN 988     | Zinc and zinc alloys - Specifications for rolled flat products for building |
| EN 1179    | Zinc and zinc alloys - Primary zinc   |

## 3 Definitions

For the purposes of this standard the following definitions apply:

**3.1 ingot:** Cast product intended for remelting [EN 1179:1995].

**3.2 batch:** Number of ingots taken from a single cast [EN 1179:1995].

### 3.3 cast

**3.3.1 cast for non-continuous casting :** Product of one furnace, or crucible melt [EN 1179:1995].

**3.3.2 cast for continuous casting:** Identified volume of liquid metal [EN 1179:1995].

**3.4 sample:** Portion of the product, representative of its chemical composition.

**3.5 test piece:** Final form of the material submitted for analysis.

**3.6 optical emission spectrometry:** The measurement of the intensity of electromagnetic radiations, emitted by the components of the sample when excited. Each element emits radiation of well defined and specific wavelength and its intensity is linked to its concentration.

## 4 Sampling

Sampling shall be in accordance with EN 12060

## iTeh STANDARD PREVIEW

### 5 Preparation of test pieces [\(standards.iteh.ai\)](https://standards.iteh.ai/)

Test pieces shall be prepared so that they are suitable for optical emission spectrometry. Shape and size of test pieces are dependent upon device and apparatus used. Surface of test pieces shall be prepared according to requirements given in the operation manual of the apparatus used.

## 6 Testing

### 6.1 General

The test shall be carried out by optical emission spectrometry using solid test pieces prepared according to clause 5. For the analysis of the impurities and alloying elements in zinc and zinc alloys as defined in EN 1179, EN 1774, prEN 12844 and EN 988 by optical emission spectrometry, different analytical lines can be used. A selection of the wavelength of analytical lines are listed in annex A.

Which one of the different analytical lines to be used is influenced by the analytical program and the type of instrument.

The reproducibility of the apparatus used shall be in accordance with the values given in annex B.

## 6.2 Calibration

The apparatus used shall be capable and suitable for the detection and determination of all elements specified in the relevant material standard (see clause 6).

The device shall be calibrated within a reasonable time in accordance with the procedures described in the operation manual. As samples, certified reference materials (CRM) shall be used primarily, reference materials (RM) secondarily and internal reference materials (IRM) last of all.

The reference material used for calibrating the device shall have similar physical and chemical properties to the sample to be analysed.

## 6.3 Method of testing

In general each test piece shall be tested at least two times. If heterogeneity or malfunction of the spectrometer are suspected additional tests shall be performed on the same sample with a new surface.

## 6.4 Expression of results

Test results shall be given as mass fraction, calculated as the arithmetic mean of all valid single results of the test sequence according to 6.3 excluding failing single test.

Results shall be expressed as defined in EN 1179, EN 1774, prEN 12844 and EN 988.

## 6.5 Test report

[SIST EN 12019:2000  
https://standards.iteh.ai/catalog/standards/sist/3021a373-39b9-4ba0-b627-18a7edf0b78a/sist-en-12019-2000](https://standards.iteh.ai/catalog/standards/sist/3021a373-39b9-4ba0-b627-18a7edf0b78a/sist-en-12019-2000)

The test report shall include the following items:

- a) identification of sample;
- b) test result of each test sequence according to 6.4;
- c) name of laboratory or testing organisation;
- d) date of test;
- e) number of this European standard (EN 12019)
- f) signature of the laboratory manager or other responsible person.



**Annexes****Annex A (informative)****Selection of analytical lines**

Analytical lines (nm) for analysis of zinc and zinc alloys by optical emission spectrometry.

**Table A.1**

Element	Analytical lines in nm
Zn	267,05;481,05;250,20
Pb	405,78;363,90;283,31
Cd	228,80;226,50;361,05;214,41
Fe	302,06; 371,99
Cu	327,30; 296,10; 324,75;510,55; 550,50; 200,00
Sn	317,50
Al	396,15; 308,22; 394,40; 256,70; 266,00
Si	288,15
Mg	285,20; 279,08; 382,93
Ni	341,48
Cr	426,43; 425,40
Ti	368,52; 365,35; 337,20; 324,19