



Designation: ~~B8—11~~ **B8 – 11 (Reapproved 2017)**

## Standard Specification for Concentric-Lay-Stranded Copper Conductors, Hard, Medium-Hard, or Soft<sup>1</sup>

This standard is issued under the fixed designation B8; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

### 1. Scope

1.1 This specification covers bare concentric-lay-stranded conductors made from round copper wires, either uncoated or coated with tin, lead, or lead alloy for general use for electrical purposes. These conductors shall be constructed with a central core surrounded by one or more layers of helically laid wires.

NOTE 1—This specification also permits conductors for use as covered or insulated electrical conductors.

NOTE 2—Sealed conductors, that are intended to prevent longitudinal water propagation and are further covered/insulated, are also permitted within the guidelines of this specification.

1.2 For the purposes of this specification, conductors are classified as follows (Explanatory **Note 1** and **Note 2**):

1.2.1 *Class AA*—For bare conductors usually used in overhead lines.

1.2.2 *Class A*—For conductors to be covered with weather-resistant (weather-proof), slow-burning materials, and for bare conductors where greater flexibility than is afforded by Class AA is required.

1.2.3 *Class B*—For conductors to be insulated with various materials such as rubber, paper, varnished cloth, and so forth, and for the conductors indicated under Class A where greater flexibility is required.

1.2.4 *Class C and Class D*—For conductors where greater flexibility is required than is provided by Class B conductors.

1.3 The SI values for density are regarded as the standard. For all other properties, the inch-pound values are to be regarded as standard and the SI units may be approximate.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**B1** Specification for Hard-Drawn Copper Wire

**B2** Specification for Medium-Hard-Drawn Copper Wire

**B3** Specification for Soft or Annealed Copper Wire

**B33** Specification for Tin-Coated Soft or Annealed Copper Wire for Electrical Purposes

**B172** Specification for Rope-Lay-Stranded Copper Conductors Having Bunch-Stranded Members, for Electrical Conductors

**B173** Specification for Rope-Lay-Stranded Copper Conductors Having Concentric-Stranded Members, for Electrical Conductors

**B174** Specification for Bunch-Stranded Copper Conductors for Electrical Conductors

**B189** Specification for Lead-Coated and Lead-Alloy-Coated Soft Copper Wire for Electrical Purposes

**B193** Test Method for Resistivity of Electrical Conductor Materials

**B246** Specification for Tinned Hard-Drawn and Medium-Hard-Drawn Copper Wire for Electrical Purposes

**B263** Test Method for Determination of Cross-Sectional Area of Stranded Conductors

**B354** Terminology Relating to Uninsulated Metallic Electrical Conductors

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B01 on Electrical Conductors and is the direct responsibility of Subcommittee B01.04 on Conductors of Copper and Copper Alloys.

Current edition approved April 1, 2014; April 1, 2017. Published May 2014; April 2017. Originally approved in 1915. Last previous edition approved in 2004 as B8 – 04; B8 – 11. DOI: 10.1520/B0008-11; 10.1520/B0008-11R17.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the [standard's Document Summary page](#) on the ASTM website.

**B787/B787M Specification for 19 Wire Combination Unilay-Stranded Copper Conductors for Subsequent Insulation**
**3. Ordering Information**

3.1 Orders for material under this specification shall include the following information:

3.1.1 Quantity of each size and class,

3.1.2 Conductor size: circular-mil area or AWG (Section 6),

3.1.3 Class (see 1.2 and Table 1),

3.1.4 Temper (see 13.2),

3.1.5 Whether coated or uncoated; if coated, designate type of coating (see 13.1 and 13.2),

3.1.6 Details of special-purpose lays, if required (see 5.4),

**TABLE 1 Construction Requirements of Concentric-Lay-Stranded Copper Conductors**

Area of Cross-Section, cmil	Size, American Wire Gage	Class AA		Class A		Class B <sup>A</sup>		Class C		Class D	
		Number of Wires	Diameter of Wires, mils	Number of Wires	Diameter of Wires, mils	Number of Wires	Diameter of Wires, mils	Number of Wires	Diameter of Wires, mils	Number of Wires	Diameter of Wires, mils
*5 000 000	...	...	...	169	172.0	217	151.8	271	135.8	271	135.8
4 500 000	...	...	...	169	163.2	217	144.0	271	128.9	271	128.9
4 000 000	...	...	...	169	153.8	217	135.8	271	121.5	271	121.5
3 500 000	...	...	...	127	166.0	169	143.9	217	127.0	271	113.6
*3 000 000	...	...	...	127	153.7	169	133.2	217	117.6	271	105.2
*2 500 000	...	...	...	91	165.7	127	140.3	169	121.6	217	107.3
*2 000 000	...	...	...	91	148.2	127	125.5	169	108.8	217	96.0
1 900 000	...	...	...	91	144.5	127	122.3	169	106.0	217	93.6
1 800 000	...	...	...	91	140.6	127	119.1	169	103.2	217	91.1
*1 750 000	...	...	...	91	138.7	127	117.4	169	101.8	217	89.8
1 700 000	...	...	...	91	136.7	127	115.7	169	100.3	217	88.5
1 600 000	...	...	...	91	132.6	127	112.2	169	97.3	217	85.9
*1 500 000	...	...	...	61	156.8	91	128.4	127	108.7	169	94.2
1 400 000	...	...	...	61	151.5	91	124.0	127	105.0	169	91.0
1 300 000	...	...	...	61	146.0	91	119.5	127	101.2	169	87.7
*1 250 000	...	...	...	61	143.1	91	117.2	127	99.2	169	86.0
1 200 000	...	...	...	61	140.3	91	114.8	127	97.2	169	84.3
1 100 000	...	...	...	61	134.3	91	109.9	127	93.1	169	80.7
*1 000 000	...	37	164.4	61	128.0	61	128.0	91	104.8	127	88.7
900 000	...	37	156.0	61	121.5	61	121.5	91	99.4	127	84.2
*800 000	...	37	147.0	61	114.5	61	114.5	91	93.8	127	79.4
*750 000	...	37	142.4	61	110.9	61	110.9	91	90.8	127	76.8
*700 000	...	37	137.5	61	107.1	61	107.1	91	87.7	127	74.2
650 000	...	37	132.5	61	103.2	61	103.2	91	84.5	127	71.5
*600 000	...	37	127.3	37	127.3	61	99.2	91	81.2	127	68.7
550 000	...	37	121.9	37	121.9	61	95.0	91	77.7	127	65.8
*500 000	...	19	162.2	37	116.2	37	116.2	61	90.5	91	74.1
450 000	...	19	153.9	37	110.3	37	110.3	61	85.9	91	70.3
*400 000	...	19	145.1	19	145.1	37	104.0	61	81.0	91	66.3
*350 000	...	12	170.8	19	135.7	37	97.3	61	75.7	91	62.0
*300 000	...	12	158.1	19	125.7	37	90.0	61	70.1	91	57.4
*250 000	...	12	144.3	19	114.7	37	82.2	61	64.0	91	52.4
*211 600	0000	7	173.9	7	173.9	19	105.5	37	75.6	61	58.9
*167 800	000	7	154.8	7	154.8	19	94.0	37	67.3	61	52.4
*133 100	00	7	137.9	7	137.9	19	83.7	37	60.0	61	46.7
*105 600	0	7	122.8	7	122.8	19	74.5	37	53.4	61	41.6
*83 690	1	3 <sup>B</sup>	167.0	7	109.3	19	66.4	37	47.6	61	37.0
*66 360	2	3 <sup>B</sup>	148.7	7	97.4	7	97.4	19	59.1	37	42.4
*52 620	3	3 <sup>B</sup>	132.5	7	86.7	7	86.7	19	52.6	37	37.7
*41 740	4	3 <sup>B</sup>	118.0	7	77.2	7	77.2	19	46.9	37	33.6
*33 090	5	...	...	...	...	7	68.8	19	41.7	37	29.9
*26 240	6	...	...	...	...	7	61.2	19	37.2	37	26.6
*20 820	7	...	...	...	...	7	54.5	19	33.1	37	23.7
*16 510	8	...	...	...	...	7	48.6	19	29.5	37	21.1
*13 090	9	...	...	...	...	7	43.2	19	26.2	37	18.8
*10 380	10	...	...	...	...	7	38.5	19	23.4	37	16.7
*6 530	12	...	...	...	...	7	30.5	19	18.5	37	13.3
*4 110	14	...	...	...	...	7	24.2	19	14.7	37	10.5
*2 580	16	...	...	...	...	7	19.2	19	11.7	...	...
*1 620	18	...	...	...	...	7	15.2	19	9.2	...	...
*1 020	20	...	...	...	...	7	12.1	19	7.3	...	...
*640	22	...	...	...	...	7	9.6	19	5.8	...	...
*404	24	...	...	...	...	7	7.6	19	4.6	...	...

\* The sizes of conductors that have been marked with an asterisk provide for one or more schedules of preferred series, and are commonly used in the industry. The sizes not marked are given simply as a matter of reference and it is suggested that their use be discouraged.

<sup>A</sup> For unidirectional/unilay constructions the number of wires shown are minimum requirements.

<sup>B</sup> Although Class AA conductors having three strands do not conform to the construction requirements of 1.1, they are listed in this table for convenience.

- 3.1.7 When physical tests shall be made (see Sections 7 and 8),
- 3.1.8 Package size (see Section 15),
- 3.1.9 Lagging, if required (see section 15.2),
- 3.1.10 Special package marking, if required (see section 15.3), and
- 3.1.11 Place of inspection (see Section 14).

#### 4. Joints

4.1 Welds and brazes may be made in rods or in wires prior to final drawing. Joints may not be made in the finished wires composing hard-drawn or medium-hard-drawn Class AA conductors of seven wires or less. In other conductors, welds and brazes may be made in the finished individual wires composing the conductor, but shall not be closer together than prescribed in Table 2.

**TABLE 2 Minimum Distance Between Joints in the Completed Conductor**

Number of Wires in Conductor	Hard or Medium-Hard					Soft
	Class AA	Class A	Class B	Class C	Class D	All Classes
3	none permitted	...	...	...	...	1 ft
7	none permitted	50 ft	50 ft	...	...	1 ft
12	50 ft	50 ft	...	...	...	1 ft
19	50 ft	50 ft	50 ft	50 ft	...	1 ft
20 to 36	50 ft	50 ft	50 ft	50 ft	...	1 ft in a layer <sup>A</sup>
37 to 60	...	25 ft	25 ft	25 ft	25 ft	1 ft in a layer <sup>A</sup>
61 and over	...	5 ft	5 ft	5 ft	5 ft	1 ft in a layer <sup>A</sup>

<sup>A</sup> Except as indicated, the limitations apply to closeness of joints throughout the completed conductor.

#### 5. Lay

5.1 For Class AA conductors composed of less than seven wires, the preferred lay is 11 times the outside diameter of the completed conductor, but shall be not less than 8 nor more than 14 times this diameter.

5.2 For Class AA conductors composed of seven wires or more, the preferred lay of a layer of wires is 13.5 times the outside diameter of that layer, but shall be not less than 10 nor more than 16 times this diameter.

5.3 For all other classes the lay of a layer of wires shall be not less than 8 nor more than 16 times the outside diameter of that layer, except that for conductors composed of 37 wires or more, this requirement shall apply only to the two outer layers. The lay of the layers other than the two outer layers shall be at the option of the manufacturer, unless otherwise agreed upon.

5.3.1 For conductors to be used in covered or insulated wires or cables, the lay length shall be not less than 8 nor more than 16 times the outer diameter of the finished conductor. For conductors of 37 wires or more, this requirement shall apply to the wires in the outer two layers. The lay of the layers other than the two outer layers shall be at the option of the manufacturer, unless otherwise agreed upon.

5.4 Other lays for special purposes shall be furnished by special agreement between the manufacturer and the purchaser (Explanatory Note 3).

5.5 The direction of lay of the outer layer shall be left-hand, and for conductors having a nominal cross-sectional area larger than No. 8 AWG, shall be reversed in successive layers, unless otherwise specified by the purchaser.

5.5.1 For conductors to be used in covered or insulated wires or cables, the direction of lay of the outer layer shall be left hand and shall be reversed in successive layers, unidirectional, or unilay, unless otherwise agreed upon.

#### 6. Construction

6.1 The areas of cross section, numbers, and diameters of wires in the various classes of concentric-lay-stranded conductors shall conform to the requirements prescribed in Table 1 (Explanatory Notes 3 and 10).

6.2 The diameters of the wires listed in Table 1 are nominal. Where “combination strand” is required in order to insulate the conductor properly (strands in the outer layer having a larger diameter than those in the inner layers) the diameters shall be subject to a tolerance of  $\pm 5\%$ , provided that the area of cross section after stranding is in accordance with Section 11.

6.3 Where compressed stranding is required in order to insulate the conductor properly, one or more layers of any stranded conductor consisting of 7 wires or more may be slightly compressed, thereby reducing the outside diameter of the conductor to the nominal values shown in Table 3, provided that the area of cross section after stranding is in accordance with Section 11.

#### 7. Physical and Electrical Tests of Conductors Stranded of Soft Wires

7.1 Tests for the electrical properties of wires composing conductors made from soft or annealed copper wire, bare or coated, shall be made before stranding.

**TABLE 3 Diameters, Areas, and Mass of Concentric-Lay-Stranded Copper Conductors (Explanatory Note 8)**

Size of Conductor,		Nominal Conductor Diameter, in. <sup>A</sup>					Area, in. <sup>2</sup>	Mass		dc Resistance at 20°C <sup>B</sup>	
		Concentric Strand			Reverse Concentric Com-pressed Class B Diameter, in.	Unilay Com-pressed <sup>C</sup> Diameter, in.		lbs/1000 ft	kg/km	Ω/1000 ft	Ω/km
cmil or AWG numbers	mm <sup>2</sup>	Class AA	Class A	Class B			Reverse Concentric Com-pressed Class B Diameter, in.				
*5 000 000 cmil	2530	...	2.580	2.581	...	...	3.927	15 890	23 649	0.00218	0.00715
4 500 000 cmil	2280	...	2.448	2.448	...	...	3.534	14 300	21 283	0.00242	0.00794
4 000 000 cmil	2030	...	2.307	2.309	...	...	3.142	12 590	18 738	0.00270	0.00886
3 500 000 cmil	1770	...	2.158	2.159	...	...	2.749	11 020	16 401	0.00308	0.0101
*3 000 000 cmil	1520	...	1.998	1.998	...	...	2.356	9 353	13 920	0.00356	0.0117
*2 500 000 cmil	1270	...	1.823	1.824	...	...	1.963	7 794	11 600	0.00427	0.0140
*2 000 000 cmil	1010	...	1.630	1.632	1.583	1.533	1.571	6 175	9 190	0.00529	0.0174
1 900 000 cmil	963	...	1.590	1.590	1.542	1.494	1.492	5 866	8 730	0.00557	0.0183
1 800 000 cmil	912	...	1.547	1.548	1.502	1.454	1.414	5 558	8 272	0.00588	0.0193
*1 750 000 cmil	887	...	1.526	1.526	1.480	1.434	1.374	5 403	8 041	0.00604	0.0198
1 700 000 cmil	861	...	1.504	1.504	1.459	1.413	1.335	5 249	7 812	0.00622	0.0204
1 600 000 cmil	801	...	1.459	1.459	1.415	1.371	1.257	4 940	7 352	0.00661	0.0217
*1 500 000 cmil	760	...	1.411	1.412	1.370	1.327	1.178	4 631	6 892	0.00705	0.0231
1 400 000 cmil	709	...	1.364	1.364	1.323	1.282	1.100	4 323	6 435	0.00756	0.0248
1 300 000 cmil	659	...	1.314	1.315	1.275	1.236	1.021	4 014	5 974	0.00814	0.0267
*1 250 000 cmil	633	...	1.288	1.289	1.250	1.212	0.9817	3 859	5 743	0.00846	0.0278
1 200 000 cmil	608	...	1.263	1.263	1.225	1.187	0.9425	3 705	5 514	0.00882	0.0289
1 100 000 cmil	557	...	1.209	1.209	1.173	1.137	0.8639	3 396	5 054	0.00962	0.0316
*1 000 000 cmil	507	1.151	1.152	1.152	1.117	1.084	0.7854	3 088	4 596	0.0106	0.0348
900 000 cmil	456	1.092	1.094	1.094	1.060	1.028	0.7069	2 779	4 136	0.0118	0.0387
*800 000 cmil	405	1.029	1.031	1.031	1.000	0.969	0.6283	2 470	3 676	0.0132	0.0433
*750 000 cmil	380	0.997	0.998	0.998	0.968	0.939	0.5890	2 316	3 447	0.0141	0.0462
*700 000 cmil	355	0.963	0.964	0.964	0.935	0.907	0.5498	2 161	3 216	0.0151	0.0495
650 000 cmil	329	0.928	0.929	0.929	0.901	0.874	0.5105	2 007	2 987	0.0163	0.0535
*600 000 cmil	304	0.891	0.891	0.893	0.866	0.840	0.4712	1 853	2 758	0.0176	0.0578
550 000 cmil	279	0.853	0.853	0.855	0.829	0.804	0.4320	1 698	2 527	0.0192	0.0630
*500 000 cmil	253	0.811	0.813	0.813	0.789	0.766	0.3927	1 544	2 298	0.0212	0.0695
450 000 cmil	228	0.770	0.772	0.772	0.749	0.727	0.3534	1 389	2 067	0.0235	0.0771
*400 000 cmil	203	0.726	0.726	0.728	0.706	0.685	0.3142	1 235	1 838	0.0264	0.0866
*350 000 cmil	177	0.710	0.679	0.681	0.661	0.641	0.2749	1 081	1 609	0.0302	0.0991
*300 000 cmil	152	0.657	0.629	0.630	0.611	0.594	0.2356	926.3	1 378.6	0.0353	0.116
*250 000 cmil	127	0.600	0.574	0.575	0.558	0.542	0.1963	771.9	1 148.8	0.0423	0.139
* No. 0000	107	0.522	0.522	0.528	0.512	0.498	0.1662	653.1	972.0	0.0500	0.164
* No. 000	85.0	0.464	0.464	0.470	0.456	0.443	0.1318	518.1	771.1	0.0630	0.207
* No. 00	67.4	0.414	0.414	0.419	0.405	0.395	0.1045	410.9	611.5	0.0795	0.261
* No. 0	53.5	0.368	0.368	0.373	0.362	0.352	0.08289	325.8	484.9	0.100	0.328
* No. 1, 3 wire	42.4	0.360	...	...	...	...	0.06573	255.9	380.9	0.126	0.413
* No. 1	42.4	...	0.328	0.332	0.322	0.313	0.06573	258.4	384.6	0.126	0.413
* No. 2, 3 wire	33.6	0.320	...	...	...	...	0.05213	202.9	301.9	0.159	0.522
* No. 2	33.6	...	0.292	0.292	0.283	...	0.05213	204.9	304.9	0.159	0.522
* No. 3, 3 wire	26.7	0.285	...	...	...	...	0.04134	160.9	239.5	0.201	0.659
* No. 3	26.7	...	0.260	0.260	0.252	...	0.04134	162.5	241.9	0.201	0.659
* No. 4, 3 wire	21.2	0.254	...	...	...	...	0.03278	127.6	189.9	0.253	0.830
* No. 4	21.2	...	0.232	0.232	0.225	...	0.03278	128.9	191.8	0.253	0.830
* No. 5	16.8	...	...	0.206	0.200	...	0.02600	102.2	152.1	0.319	1.05
* No. 6	13.3	...	...	0.184	0.178	...	0.02062	81.05	120.63	0.403	1.32
* No. 7	10.6	...	...	0.164	0.159	...	0.01635	64.28	95.67	0.509	1.67
* No. 8	8.37	...	...	0.146	0.142	...	0.01297	50.97	75.86	0.640	2.10
* No. 9	6.63	...	...	0.130	0.126	...	0.01028	40.42	60.16	0.809	2.65
* No. 10	5.26	...	...	0.116	0.113	...	0.008155	32.06	47.72	1.02	3.35
* No. 12	3.31	...	...	0.0915	0.089	...	0.005129	20.16	30.00	1.63	5.35
* No. 14	2.08	...	...	0.0726	0.071	...	0.003225	12.68	18.87	2.58	8.46
* No. 16	0.823	...	...	0.0576	...	...	0.002028	7.974	11.868	4.10	13.45
* No. 18	0.519	...	...	0.0456	...	...	0.001276	5.015	7.464	6.54	21.46
* No. 20	0.519	...	...	0.0363	...	...	0.0008023	3.154	4.694	10.3	33.8
* No. 22	0.324	...	...	0.0288	...	...	0.0005067	1.992	2.965	16.4	53.8
* No. 24	0.205	...	...	0.0228	...	...	0.0003176	1.249	1.859	26.1	85.6

\* The sizes of conductors which have been marked with a single asterisk provide for one or more schedules of preferred series, and are commonly used in the industry. The sizes not marked are given simply as a matter of reference, and it is suggested that their use be discouraged.

<sup>A</sup> To calculate the nominal diameters of Class C or Class D conductors or of any concentric-lay-stranded conductors made from round wires of uniform diameters, multiply the diameter of an individual wire (as given in Table 1) by that one of the following factors which applies:

<sup>B</sup> Resistances (dc) apply to Class B, C, and D stranding. For other classes of stranding, refer to Test Method B193. Resistance (dc) based on annealed copper.

<sup>C</sup> For conductors manufactured for subsequent covering or insulating.

Number of Wires in Conductor      Factor to Calculate  
Conductor Diameter