



Designation: **B559—12 B559 – 12 (Reapproved 2017)**

Standard Specification for Nickel-Coated, Copper-Clad Steel Wire for Electronic Application¹

This standard is issued under the fixed designation B559; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers nickel-coated, round, copper-clad steel wire for electronic application.

1.2 Nickel coatings in mass percentages of the total mass of the coated wire are as follows: 2, 4, 7, 10, and 27 %. Nickel-coated wire having different minimum mass percentages of nickel may be obtained by mutual agreement between the manufacturer and the purchaser. For information purposes, the thickness of coating in microinches provided by the percentages listed above is shown in [Table 1](#).

1.3 Four classes of nickel-coated, copper-clad steel wire are covered as follows:

1.3.1 *Class N30HS*—Nominal 30 % conductivity, hard drawn.

1.3.2 *Class N30A*—Nominal 30 % conductivity, annealed.

1.3.3 *Class N40HS*—Nominal 40 % conductivity, hard drawn.

1.3.4 *Class N40A*—Nominal 40 % conductivity, annealed.

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4.1 *Exception*—The SI values for resistivity are to be regarded as standard.

1.5 The following safety hazards caveat pertains only to the test method described in this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. (Warning—Consideration should be given to toxicity and flammability when selecting solvent cleaners.)*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards*:²

[B193 Test Method for Resistivity of Electrical Conductor Materials](#)

[B258 Specification for Nominal Diameters and Cross-Sectional Areas of AWG Sizes of Solid Round Wires Used as Electrical Conductors](#)

[B452 Specification for Copper-Clad Steel Wire for Electronic Application](#)

[E75 Test Methods for Chemical Analysis of Copper-Nickel and Copper-Nickel-Zinc Alloys \(Withdrawn 2010\)](#)³

¹ This specification is under the jurisdiction of ASTM Committee [B01](#) on Electrical Conductors and is the direct responsibility of Subcommittee [B01.06](#) on Bi-Metallic Conductors.

Current edition approved Oct. 15, 2012; April 1, 2017. Published November 2012; April 2017. Originally approved in 1972. Last previous edition approved in 2007 as [B559 – 93 \(2007\)](#); [B559 – 12](#). DOI: [10.1520/B0559-12](#); [10.1520/B0559-12R17](#).

² For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on [www.astm.org](#).

TABLE 1 Nickel Mass Percent and Thickness of Coating

Diameter		Cross-Sectional Area at 20°C			Thickness of Nickel, μ in. (for information only)				
in.	mm	cmil	in. ²	mm ²	2.0 %	4.0 %	7.0 %	10.0 %	27.0 %
0.0720	1.829	5 180	0.00407	2.63	334	637	1 181	1 703	4 892
0.0641	1.628	4 110	0.00323	2.08	298	566	1 050	1 514	4 349
0.0571	1.450	3 260	0.00256	1.65	266	505	936	1 350	3 880
0.0508	1.290	2 580	0.00203	1.31	236	450	833	1 200	3 452
0.0453	1.151	2 050	0.00161	1.04	211	401	743	1 071	3 077
0.0403	1.024	1 620	0.00128	0.823	202	357	661	953	2 738
0.0359	0.912	1 290	0.00101	0.653	167	318	589	849	2 439
0.0320	0.813	1 020	0.000804	0.519	149	283	525	757	2 174
0.0285	0.724	812	0.000638	0.412	133	252	467	686	1 937
0.0253	0.643	640	0.000503	0.324	118	224	415	598	1 719
0.0226	0.574	511	0.000401	0.259	105	200	371	535	1 536
0.0201	0.511	404	0.000317	0.205	94	178	330	475	1 366
0.0179	0.455	320	0.000252	0.162	83	158	294	423	1 216
0.0159	0.404	253	0.000199	0.128	74	141	261	376	1 080
0.0142	0.361	202	0.000158	0.102	66	126	233	336	965
0.0126	0.320	159	0.000125	0.0804	59	112	207	298	856
0.0113	0.287	128	0.000100	0.0647	53	100	185	267	768
0.0100	0.254	100	0.0000785	0.0507	47	89	164	237	680
0.0089	0.226	79.2	0.0000622	0.0401	41	80	146	211	605
0.0080	0.203	64.0	0.0000503	0.0324	...	71	131	189	544
0.0071	0.180	50.4	0.0000396	0.0255	...	63	116	168	482
0.0063	0.160	39.7	0.0000312	0.0201	...	56	103	149	428
0.0056	0.142	31.4	0.0000246	0.0159	...	50	92	132	381
0.0050	0.127	25.0	0.0000196	0.0127	...	44	82	118	340
0.0045	0.114	20.2	0.0000159	0.0103	...	40	74	106	306
0.0040	0.102	16.0	0.0000126	0.00811	66	95	272
0.0035	0.089	12.2	0.00000962	0.00621	57	83	238
0.0031	0.079	9.61	0.00000755	0.00487	51	73	211

2.3 American Chemical Society:⁴

Standard Reagents Tests

2.4 NIST Standard:⁵

NBS Handbook 100 Copper Wire Tables

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *lot*—any amount of wire of one class and size presented for acceptance at one time, such amount, however, not to exceed 10 000 lb (4500 kg) (Note 1).

NOTE 1—A lot should comprise material taken from a product regularly meeting the requirements of this specification. Inspection of individual lots of less than 500 lb (230 kg) of wire cannot be justified economically. For small lots of 500 lb (230 kg) or less, the purchaser may agree to the manufacturers' regular inspection of the product as a whole as evidence of acceptability of such small lots.

3.1.2 *sample*—a quantity of production units (coils, reels, etc.) selected at random from the lot for the purpose of determining conformance of the lot to the requirements of this specification.

3.1.3 *specimen*—a length of wire removed for test purposes from any individual production unit of the sample.

4. Ordering Information

4.1 Orders for material under this specification shall include the following information:

4.1.1 Quantity of each size.

4.1.2 Wire size (see Section 7 and Table 1).

4.1.3 Class of basis wire (see 1.3).

4.1.4 Mass percentage of nickel coating (see 1.2 and Table 1).

4.1.5 Package size (see 14.2 and Section 14). Packaging inspection, if required (see 9.1.3).

4.1.6 Special package marking, if required.

4.1.7 Place of inspection (see 13.1).

⁴ Reagent Chemicals, American Chemical Society Specifications, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmaceutical Convention, Inc. (USPC), Rockville, MD.

⁵ Available from National Institute of Standards and Technology (NIST), 100 Bureau Dr., Stop 1070, Gaithersburg, MD 20899-1070, <http://www.nist.gov>.

5. Materials and Manufacture

5.1 The basis material shall consist of copper-clad steel wire conforming to the product description, quality and specification requirements of Specification **B452**.

5.2 The nickel-coated wire shall consist of the basis wire coated with nickel (**Note 2**). The quality of the nickel-coated wire shall be such that the finished product meets the properties and requirements in this specification.

NOTE 2—Nickel on copper-clad steel wire provides a protective coating for a prevention of oxidation of the copper either during fabrication or service.

6. General Requirements

6.1 Tensile strength and elongation of the nickel-coated wire shall conform to the requirements of Specification **B452** for the applicable size and class of copper-clad steel wire.

6.2 *Resistivity*—The electrical resistivity at a temperature of 20°C shall not exceed the values prescribed in **Table 2** (Explanatory **Note 1**).

6.3 *Continuity of Coating*—The nickel coating shall be continuous. The continuity of the coating shall be determined on representative samples taken before stranding or insulating and shall be determined by the sodium polysulfide test, in accordance with **10.2**. Wire whose coating weight corresponds to a thickness less than 50 μ in. (0.00005 in.) (1.3 μm) shall not be subject to this test.

6.4 *Adherence of Coating*—The nickel coating shall be firmly adhered to the surface of the copper-clad steel wire. The adherence of coating on the wire shall be determined on representative samples taken before stranding or insulating. The adherence of coating shall be determined by the wrapping, and immersion test in accordance with **10.3**.

6.5 *Mass of Coating*—The mass of nickel coating expressed in percent of the total mass of the wire shall be not less than the percentage specified and referred to in this specification or the percentage as agreed on between the manufacturer and purchaser at the time of the placing of the order. For ease of comparison, the thickness of coating for various percentages has been included in **Table 1**.

6.6 *Joints*—Necessary joints in the wire and rods prior to final coating and drawing shall be made in accordance with good commercial practice.

7. Dimensions, Mass, and Permissible Variations

7.1 The wire sizes shall be expressed as the diameter of the wire in decimal fractions of an inch to the nearest 0.0001 in. (0.003 mm) (**Note 3**). For diameters under 0.0100 in. (0.254 mm), the wire shall not vary from the specified diameter by more than + 0.0003 in. (0.009 mm) and – 0.0001 in. (0.003 mm) and for diameters of 0.0100 in. (0.254 mm) and over, the wire shall not vary from the specified diameter by more than + 3 % and – 1 %, expressed to the nearest 0.0001 in. (0.003 mm).

NOTE 3—The values of the wire diameters in **Table 1** are given to the nearest 0.0001 in. (0.003 mm) and correspond to the standard sizes given in Specification **B258**. The use of gage numbers to specify wire sizes is not recognized in this specification because of the possibility of confusion. An excellent discussion of wire gages and related subjects is contained in *NBS Handbook 100*.

8. Workmanship, Finish, and Appearance

8.1 The nickel coating shall consist of a smooth, continuous layer, firmly adherent to the surface of the copper. The wire shall be bright and free from all imperfections not consistent with good commercial practice.

8.2 The finish of the samples taken in accordance with **Table 3** shall conform to the requirements of **8.1**. The number of units in the sample showing surface defects not consistent with commercial practice shall not exceed the allowable defect number *c* in **Table 3**. Failure to meet this requirement shall constitute failure to meet the finish conformance criterion.

TABLE 2 Resistivity

Resistivity, max at 20°C		
Class of Wire	Nickel Mass %	Ω-mm ² /m
N30A and N30HS	2	0.05906 (0.059062)
	4	0.05951 (0.059513)
	7	0.06021 (0.060210)
	10	0.06093 (0.060926)
	27	0.06543 (0.065433)
N40A and N40HS	2	0.04442 (0.044418)
	4	0.04490 (0.044902)
	7	0.04561 (0.045614)
	10	0.04636 (0.046362)
	27	0.05122 (0.051216)

TABLE 3 Sampling for Surface Finish and Packaging Inspection

Number of Units in Lot	Number of Units in Sample, n	Allowable Number of Defective Units, c
1 to 30, incl	all	0
31 to 50, incl	30	0
51 to 100, incl	37	0
101 to 200, incl	40	0
201 to 300, incl	70	1
301 to 500, incl	100	2
501 to 800, incl	130	3
Over 800	155	4

9. Sampling

9.1 The number of production units in a sample (Note 4) shall be as follows:

NOTE 4—Cumulative results secured on the product of a single manufacturer, indicating continued conformance to the criteria, are necessary to ensure an over-all product meeting the requirements of this specification. The sample size and conformance criteria given for the various characteristics are applicable only to lots produced under these conditions.

9.1.1 For tensile strength, elongation, resistivity, mass of coating and adhesion and other defects, the sample shall consist of four production units. For surface finish the sampling shall be in accordance with Table 3. From each unit, one test specimen of sufficient length shall be removed for the performance of required tests.

9.1.2 For dimensional measurements, the sample shall consist of a quantity of production units shown in Table 4 under heading “First Sample.”

9.1.3 For packaging inspection (when specified by the purchaser at the time of placing the order), the sample shall consist of a quantity of production units as shown in Table 3.

10. Test Methods

10.1 *Tensile Properties*—For tensile strength, elongation, resistivity, dimensional measurement, and the quality of the basis wire, the latest issue of Specification B452 shall apply and the tests shall be performed on the nickel-coated wire (Explanatory Note 2).

10.2 *Continuity of Coating:*

10.2.1 *Specimens:*

10.2.1.1 *Length of Specimens*—Test specimens shall each have a length of about 6 in. (150 mm). They shall be tagged or marked to correspond with the coil, spool, or reel from which they were cut.

10.2.1.2 *Treatment of Specimens*—The specimens shall be thoroughly cleaned by immersion in a suitable organic solvent for at least 3 min, then removed and wiped dry with a clean, soft cloth (Warning—See 1.5). The specimen thus cleaned shall be kept wrapped in a clean, dry cloth until tested. That part of the specimen to be immersed in the test solution shall not be handled. Care shall be taken to avoid abrasion by the cut ends.

10.2.2 *Special Solution* (sp gr 1.142)—Make concentrated solution by dissolving sodium sulfide crystals (cp) in distilled water until the solution is saturated at about 21°C (70°F), and add sufficient flowers of sulfur (in excess of 250 g/L of solution) to provide complete saturation, as shown by the presence in the solution of an excess of sulfur after the solution has been allowed to stand for at least 24 h. Make the test solution by diluting a portion of the concentrated solution with distilled water to a specific gravity of 1.142 at 15.6°C (60°F). The sodium polysulfide test solution should have sufficient strength to blacken thoroughly a piece of clean uncoated copper wire in 5 s. The test solution used for testing samples shall be considered exhausted if it fails to blacken a piece of clean copper as described above (Explanatory Note 3).

TABLE 4 Sampling for Dimensional Measurements

Number of Units in Lot	First Sample		Second Sample		
	Number of Units in Sample, n_1	Allowable Number of Defects in Sample c_1	Number of Units in Sample n_2	$n_1 + n_2$	Allowable Number of Defects in Both Samples, c_2
1 to 14, incl	all	0	0
15 to 50, incl	14	0	0
51 to 100, incl	19	0	23	42	1
101 to 200, incl	24	0	46	70	2
201 to 400, incl	29	0	76	105	3
401 to 800, incl	33	0	112	145	4
Over 800	34	0	116	150	4