



Designation: B784 – 01 (Reapproved 2017)^{ε1}

Standard Specification for Modified Concentric-Lay-Stranded Copper Conductors for Use in Insulated Electrical Cables¹

This standard is issued under the fixed designation B784; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Typos in Section 1 were corrected editorially in April 2017.

1. Scope

1.1 This specification covers bare modified concentric-lay-stranded conductors made from round copper wires, either uncoated or coated with tin, lead, or lead alloy for general use in insulated electrical cables. These conductors shall be constructed with a central core consisting of not more than seven wires, surrounded by one or more layers of helically laid wires.

1.2 For the purposes of this specification, conductors are classified as follows (Explanatory [Note 1](#) and [Note 2](#)):

1.2.1 *Class B Modified*—Conductors to be insulated with various materials such as rubber, paper, and crosslink polyethylene.

1.2.2 *Class C Modified and Class D Modified*—Conductors where greater flexibility is required than is provided by Class B Modified conductors.

1.3 The values stated in inch-pound or SI units are to be regarded separately as standard. Each system shall be used independently of the other. Combining the values from the two systems may result in non-conformance with the specification. For conductor sizes designated by AWG or kcmil sizes, the requirements in SI units are numerically converted from the corresponding requirements in inch-pound units. For conductor sizes designated by AWG or kcmil, the requirements in SI units have been numerically converted from corresponding values stated or derived in inch-pound units. For conductor sizes designated by SI units only, the requirements are stated or derived in SI units.

1.3.1 For density, resistivity and temperature, the values stated in SI units are to be regarded as standard.

NOTE 1—The significant differences in this specification from Specification [B8](#) are as follows: (1) The central core is permitted to contain up to seven wires drawn into the assembly with an infinite length of lay while Specification [B8](#) permits only one, and (2) The construction is applicable only to stranded assemblies of 19 or more wires.

¹ This specification is under the jurisdiction of ASTM Committee [B01](#) on Electrical Conductors and is the direct responsibility of Subcommittee [B01.04](#) on Conductors of Copper and Copper Alloys.

Current edition approved April 1, 2017. Published April 2017. Originally approved in 1988. Last previous edition approved in 2012 as B784 – 01 (2012). DOI: 10.1520/B0784-01R17E01.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 The following documents of the issue in effect at the date of material purchase form a part of this specification to the extent referenced herein.

2.2 *ASTM Standards*:²

[B3 Specification for Soft or Annealed Copper Wire](#)

[B8 Specification for Concentric-Lay-Stranded Copper Conductors, Hard, Medium-Hard, or Soft](#)

[B33 Specification for Tin-Coated Soft or Annealed Copper Wire for Electrical Purposes](#)

[B189 Specification for Lead-Coated and Lead-Alloy-Coated Soft Copper Wire for Electrical Purposes](#)

[B263 Test Method for Determination of Cross-Sectional Area of Stranded Conductors](#)

[B354 Terminology Relating to Uninsulated Metallic Electrical Conductors](#)

2.3 *Other Standard*:

[NBS Handbook 100](#)³

3. Ordering Information

3.1 Orders for material under this specification shall include the following information:

3.1.1 Quantity of each size and class,

3.1.2 Conductor size: circular-mil area or American Wire Gage (AWG) (Section [6](#)),

3.1.3 Class (see [1.2](#) and [Table 1](#)),

3.1.4 Temper (see [10.2](#)),

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Available from National Technical Information Service (NTIS), 5301 Shawnee Rd., Alexandria, VA 22312, <http://www.ntis.gov>.

TABLE 1 Construction Requirements of Modified Concentric-Lay-Stranded Copper Conductors

NOTE 1—See Explanatory Note 5.

Circular Mils	Size American Wire Gage	Class B Modified			Class C Modified			Class D Modified		
		Number of Wires	Diameter		Number of Wires	Diameter		Number of Wires	Diameter	
			(mils)	(mm)		(mils)	(mm)		(mils)	(mm)
5 000 000 ^A		217	151.8	3.86	271	135.8	3.45	271	135.8	3.45
4 000 000		217	144.0	3.66	271	128.9	3.27	271	128.9	3.27
4 000 000		217	135.8	3.45	271	121.5	3.09	271	121.5	3.09
3 500 000		169	143.9	3.66	217	127.0	3.23	271	113.6	2.89
3 000 000 ^A		169	133.2	3.38	217	117.6	2.99	271	105.2	2.67
2 500 000 ^A		127	140.3	3.56	169	121.6	3.09	217	107.3	2.73
2 000 000 ^A		127	125.5	3.19	169	108.8	2.76	217	96.0	2.44
1 900 000		127	122.3	3.11	169	106.0	2.69	217	93.6	2.38
1 800 000		127	119.1	3.03	169	103.2	2.62	217	91.1	2.31
1 750 000 ^A		127	117.4	2.98	169	101.8	2.59	217	89.8	2.28
1 700 000		127	115.7	2.94	169	100.3	2.55	217	88.5	2.25
1 600 000		127	112.2	2.85	169	97.3	2.47	217	85.9	2.18
1 500 000 ^A		91	128.4	3.26	127	108.7	2.76	169	94.2	2.39
1 400 000		91	124.0	3.15	127	105.0	2.67	169	91.0	2.31
1 300 000		91	119.5	3.04	127	101.2	2.57	169	87.7	2.23
1 250 000		91	117.2	2.98	127	99.2	2.52	169	86.0	2.18
1 200 000		91	114.8	2.92	127	97.2	2.47	169	84.3	2.14
1 100 000		91	109.9	2.79	127	93.1	2.36	169	80.7	2.05
1 000 000 ^A		61	128.0	3.25	91	104.8	2.66	127	88.7	2.25
900 000		61	121.5	3.09	91	99.4	2.52	127	84.2	2.14
800 000 ^A		61	114.5	2.91	91	93.8	2.38	127	79.4	2.02
750 000 ^A		61	110.9	2.82	91	90.8	2.31	127	76.8	1.95
700 000 ^A		61	107.1	2.72	91	87.7	2.23	127	74.2	1.88
650 000		61	103.2	2.62	91	84.5	2.15	127	71.5	1.82
600 000 ^A		61	99.2	2.52	91	81.2	2.06	127	66.7	1.69
550 000		61	95.0	2.41	91	77.7	1.97	127	65.8	1.67
500 000 ^A		37	116.2	2.95	61	90.5	2.30	91	74.1	1.88
450 000		37	110.3	2.80	61	85.9	2.18	91	70.3	1.79
400 000 ^A		37	104.0	2.64	61	81.0	2.06	91	66.3	1.68
350 000 ^A		37	97.3	2.47	61	75.7	1.92	91	62.0	1.57
300 000 ^A		37	90.0	2.29	61	70.1	1.78	91	57.4	1.46
250 000 ^A		37	82.2	2.09	61	64.0	1.63	91	52.4	1.33
211 000 ^A	0000	19	105.5	2.68	37	75.6	1.92	61	58.9	1.50
167 000 ^A	000	19	94.0	2.39	37	67.3	1.71	61	52.4	1.33
133 000 ^A	00	19	83.7	2.13	37	60.0	1.52	61	46.7	1.19
105 000 ^A	0	19	74.5	1.89	37	53.4	1.36	61	41.6	1.06
83 000 ^A	1	19	66.4	1.69	37	47.6	1.21	61	37.0	0.94

^A These sizes of conductors provide for one or more schedules of preferred series and commonly are used in the industry. The sizes not marked are given simply as a matter of reference and it is suggested that their use be discouraged. [B784-01\(2017\)e1](https://standards.iteh.ai/catalog/standards/sist/b784-01(2017)/e1)

[https://standards.iteh.ai/catalog/standards/sist/b784-01\(2017\)/e1](https://standards.iteh.ai/catalog/standards/sist/b784-01(2017)/e1)

3.1.5 Whether coated or uncoated; if coated, designate type of coating (see 10.1 and 10.2),

3.1.6 Details of special-purpose lays, if required (see 5.2),

3.1.7 Lagging, if required (see 14.2),

3.1.8 Special package marking, if required (Section 13),

3.1.9 Place of inspection (Section 12), and

4. Joints

4.1 Welds and brazes may be made in rods or in wires prior to final drawing. Welds and brazes may be made in the finished individual wires composing the conductor, but shall not be closer together than prescribed in Table 2.

TABLE 2 Minimum Distance Between Joints in the Completed Conductor

Number of Wires in Conductor	Soft All Classes
19	1 ft
20 and over	1 ft in a layer ^A

^A Except as indicated, the limitations apply to closeness of joints throughout the completed conductor.

5. Lay

5.1 The lay of a layer of wires shall be not less than eight nor more than sixteen times the outside diameter of that layer, except that for conductors composed of 37 wires or more, this requirement shall apply only to the two outer layers. The lay of the layers other than the two outer layers shall be at the option of the manufacturer, unless otherwise agreed upon.

5.2 Other lays for special purposes shall be furnished by special agreement between the manufacturer and the purchaser (Explanatory Note 3).

5.3 The direction of lay of the outer layer shall be left-hand unless the direction of lay is specified otherwise by the purchaser.

5.4 The direction of lay shall be reversed in successive layers, unless otherwise specified by the purchaser.

6. Construction

6.1 The areas of cross section, numbers, and diameters of wires in the various classes of concentric-lay-stranded conductors shall conform to the requirements prescribed in Table 1.