



Designation: ~~C454 – 10~~ C454 – 10 (Reapproved 2017)

Standard Test Method for Disintegration of Carbon Refractories by Alkali¹

This standard is issued under the fixed designation C454; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the behavior of carbon refractories when subjected to the action of an alkali at an elevated temperature. This destructive condition as encountered in service is accelerated in the test to show in a short time the probable behavior of the carbon refractory during use.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Significance and Use

2.1 The disintegration of carbon refractories by alkali attack at elevated temperatures is an important consideration in using these materials for certain applications. Disruption of carbon refractories in the test is sensitive to a number of variables, including alkali concentration, temperature, and the presence of water vapor. The procedure is suitable for guidance in product development and for relative comparisons in application work such as in blast furnace service.

3. Apparatus and Materials

3.1 *Sagger*—A sagger, and coke breeze passing a No. 4 (4.75-mm) sieve.

3.2 *Kiln*—The kiln shall be capable of maintaining the specified rate of heating. During the temperature holding period, the temperature distribution over the hearth shall not vary more than $\pm 15^{\circ}\text{F}$ (8°C); $\pm 15^{\circ}\text{F}$ (8°C).

3.3 *Potassium Carbonate* (K_2CO_3)—Anhydrous granular.

4. Test Specimens

4.1 Ten specimens constitute a specimen set and not more than one specimen is taken from a given carbon shape.

4.2 Two-inch (51-mm) cube specimens are cut from the shapes to a manner so as to maintain as many of the original surfaces as possible.

4.3 A hole $\frac{7}{8}$ in. (22 mm) in diameter and 1 in. (25 mm) deep is drilled into the center of one face of each specimen.

4.4 Cut a lid from a carbon shape measuring approximately 2 by 2 by $\frac{1}{4}$ in. (50 by 50 by 6 mm) for each specimen.

5. Procedure

5.1 Dry the specimens and lids at 220 to 230°F (105 to 110°C) for at least 1 h. Place 8 g of K_2CO_3 in the hole of each specimen, and then place a lid over each hole.

5.2 Place the prepared specimens in the sagger, using coke breeze as a packing material to prevent oxidation. Maintain a distance of not less than 1 in. (25 mm) between the inner wall of the sagger and any specimen, and not less than $\frac{1}{4}$ in. (6 mm)

¹ This test method is under the jurisdiction of ASTM Committee C08 on Refractories and is the direct responsibility of Subcommittee C08.04 on Chemical Behaviors. Current edition approved Nov. 1, 2010/May 1, 2017. Published December 2010/May 2017. Originally approved in 1960. Last previous edition approved in 2007/2010 as C454-83(2007)-C454-10. DOI: 10.1520/C0454-10.1520/C0454-10R17.