



IEC 60893-3-2

Edition 2.1 2011-11
CONSOLIDATED VERSION

INTERNATIONAL STANDARD

NORME INTERNATIONALE



Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes –
Part 3-2: Specifications for individual materials – Requirements for rigid laminated sheets based on epoxy resins

Matériaux isolants – Stratifiés industriels rigides en planches à base de résines thermodurcissables à usages électriques –
Partie 3-2: Spécifications pour matériaux particuliers – Prescriptions pour

stratifiés rigides en planches à base de résine époxyde





THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2011 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Central Office
3, rue de Varembé
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing 20 000 terms and definitions in English and French, with equivalent terms in 15 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC publications search - www.iec.ch/searchpub

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Glossary - std.iec.ch/glossary

65 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Catalogue IEC - webstore.iec.ch/catalogue

Application autonome pour consulter tous les renseignements bibliographiques sur les Normes internationales, Spécifications techniques, Rapports techniques et autres documents de l'IEC. Disponible pour PC, Mac OS, tablettes Android et iPad.

Electropedia - www.electropedia.org

Le premier dictionnaire en ligne de termes électroniques et électriques. Il contient 20 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans 15 langues additionnelles. Egalelement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

Recherche de publications IEC - www.iec.ch/searchpub

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études,...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

Glossaire IEC - std.iec.ch/glossary

65 000 entrées terminologiques électrotechniques, en anglais et en français, extraites des articles Termes et Définitions des publications IEC parues depuis 2002. Plus certaines entrées antérieures extraites des publications des CE 37, 77, 86 et CISPR de l'IEC.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et aussi une fois par mois par email.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: csc@iec.ch.



IEC 60893-3-2

Edition 2.1 2011-11
CONSOLIDATED VERSION

INTERNATIONAL STANDARD

NORME INTERNATIONALE



Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes –

Part 3-2: Specifications for individual materials – Requirements for rigid laminated sheets based on epoxy resins

iTech Standards
Document Preview

Matériaux isolants – Stratifiés industriels rigides en planches à base de résines thermodurcissables à usages électriques –

Partie 3-2: Spécifications pour matériaux particuliers – Prescriptions pour stratifiés rigides en planches à base de résine époxyde

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 29.035.01

ISBN 978-2-8891-2739-9

Warning! Make sure that you obtained this publication from an authorized distributor.

Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references.....	6
3 Designation	6
4 Requirements	7
Bibliography	20
Table 1 – Types of industrial rigid laminated sheets based on epoxy resins.....	8
Table 2 – Tolerances on thickness (test method: see 4.1 of IEC 60893-2).....	9
Table 3 – Flatness (test method: see 4.2 of IEC 60893-2).....	10
Table 4 – Tolerances on width of cut strips (minus tolerances only)	10
Table 5 – Property requirements	11
Table 6 – Electric strength at 90 °C in oil, perpendicular to laminations (1 min proof test or 20 s step-by-step test) (kV/mm)	16
Table 7 – Limits for water absorption (mg).....	18

Document Preview

[IEC 60893-3-2:2003](#)

<https://standards.iteh.ai/catalog/standards/iec/00edf6ce-d536-407e-b485-3d4eab3cb4e7/iec-60893-3-2-2003>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**INSULATING MATERIALS –
INDUSTRIAL RIGID LAMINATED SHEETS
BASED ON THERMOSETTING RESINS FOR ELECTRICAL PURPOSES –**

**Part 3-2: Specifications for individual materials –
Requirements for rigid laminated sheets based on epoxy resins**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This consolidated version of the official IEC Standard and its amendment has been prepared for user convenience.

IEC 60893-3-2 edition 2.1 contains the second edition (2003) [documents 15C/1522/FDIS and 15C/1536/RVD] and its amendment 1 (2011) [documents 15/505/CDV+15/540/CDV and 15/632/RVC+15/592A/RVC].

A vertical line in the margin shows where the base publication has been modified by amendment 1. Additions and deletions are displayed in red, with deletions being struck through.

International Standard IEC has been prepared by subcommittee 15C: Specifications, of IEC technical committee 15: Insulating materials.

The amendment introduces new/improved limits of CHARPY impact strength and IZOD impact strength for all types of rigid laminated sheets based on epoxy resins and new/improved limits of breakdown voltage to all EP GC types and a new/improved limit of flexural strength for the EP PC 301 and a new limit of proof tracking index for the EP GC 306 type. This amendment also introduces new types of rigid laminated sheets based on epoxy resins.

In this revision of the IEC 60893 series of specifications, new material types have been included, changes have been made to the property requirements of some existing types, a new method for testing permittivity and dissipation factor has been added, and all non-specification data for each type has been moved to a new Part 4 document – IEC 60893-4 – Typical values.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of the base publication and its amendments will remain unchanged until the stability date indicated on the IEC web site under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

iTeh Standards
(<https://standards.iteh.ai>)

IMPORTANT – The “colour inside” logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this publication using a colour printer.

<https://standards.iteh.ai/catalog/standards/iec/00ed1oce-d536-407e-b485-3d4eab5cb4e//iec-60893-3-2-2003>

INTRODUCTION

This part of IEC 60893 is one of a series which deals with industrial rigid laminated sheets based on thermosetting resins for electrical purposes.

This series consists of four parts:

Part 1: Definitions, designations and general requirements (IEC 60893-1)

Part 2: Methods of test (IEC 60893-2)

Part 3: Specifications for individual materials (IEC 60893-3)

Part 4: Typical values (IEC 60893-4)

IEC 60893-3-2 contains one of the specification sheets comprising Part 3, as follows:

Sheet 2: Requirements for rigid laminated sheets based on epoxy resins

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[IEC 60893-3-2:2003](#)

<https://standards.iteh.ai/catalog/standards/iec/00edf6ce-d536-407e-b485-3d4eab3cb4e7/iec-60893-3-2-2003>

**INSULATING MATERIALS –
INDUSTRIAL RIGID LAMINATED SHEETS
BASED ON THERMOSETTING RESINS FOR ELECTRICAL PURPOSES –**

**Part 3-2: Specifications for individual materials –
Requirements for rigid laminated sheets based on epoxy resins**

1 Scope

This part of IEC 60893 gives the requirements for industrial rigid laminated sheets for electrical purposes based on epoxy resins and different reinforcements.

Applications and distinguishing properties are given in Table 1.

Materials which conform to this specification meet established levels of performance. However, the selection of a material by a user for a specific application should be based on the actual requirements necessary for adequate performance in that application and not based on this specification alone.

2 Normative references

iTeh Standards

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60893-1:—, *Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes – Part 1: Definitions, designations and general requirements* ¹

<https://www.iteh.com/standards/iec/60893-1-2003>

<https://www.iteh.com/standards/iec/60893-2-2003>
IEC 60893-2:2003, *Industrial rigid laminated sheets based on thermosetting resins for electrical purposes – Part 2: Methods of test*

<https://www.iteh.com/standards/iec/61189-2-2006>, *Test methods for electrical materials, printed boards and other interconnection structures and assemblies – Part 2: Test methods for materials for interconnection structures*

<https://www.iteh.com/standards/iec/61249-2-21-2003>, *Materials for printed boards and other interconnecting structures – Part 2-21: Reinforced base materials, clad and unclad - Non-halogenated epoxide woven E-glass reinforced laminated sheets of defined flammability (vertical burning test), copper-clad*

3 Designation

The sheets covered by this specification are classified into types which differ in the reinforcement employed and in their distinguishing properties. The sheets are designated by:

- the IEC standard number;
- a two-letter abbreviation denoting the resin;
- a second two-letter abbreviation, denoting the reinforcement;
- a serial number;

¹ To be published

- nominal thickness x width x length in millimetres.

Example of designation: Industrial rigid laminated sheet of type EP GC 201 with a nominal thickness of 10 mm, 500 mm wide, 1 000 mm long:

Sheet IEC 60893-3-2 – EP GC 201 - 10 × 500 × 1 000.

The following abbreviations are used in this Part 3 sheet:

<i>Type of resin</i>	<i>Type of reinforcement</i>
EP Epoxy (epoxide)	CC Woven cotton cloth
	CP Cellulosic paper
	GC Woven glass cloth
	GM Glass mat
	PC Woven polyester fibre cloth

4 Requirements

In addition to the general requirements given in IEC 60893-1, the laminated sheets shall also comply with the dimensional requirements given in Tables 2, 3, and 4 as well as with the other requirements given in Tables 5, 6 and 7.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[IEC 60893-3-2:2003](#)

<https://standards.iteh.ai/catalog/standards/iec/00edf6ce-d536-407e-b485-3d4eab3cb4e7/iec-60893-3-2-2003>

Table 1 – Types of industrial rigid laminated sheets based on epoxy resins

Laminate type			Applications and distinguishing characteristics ^b
Resin	Reinforcement	Serial number ^a	
EP	CC	301	Mechanical and electrical applications. Good resistance to electrical tracking, good wear and chemical resistance (fine weave ^c)
		201	Electronic applications. Good stability of electrical properties in high humidity. Low flammability
	CG	201	Mechanical, electrical and electronic applications. Extremely high mechanical strength at moderate temperature. Very good stability of electrical properties in high humidity
		202	Similar to type EP GC 201. Low flammability
		203	Similar to type EP GC 201. High mechanical strength at elevated temperature
		204	Similar to type EP GC 203. Low flammability
		205	Similar to type EP GC 203, but with roving cloth
		306	Similar to type EP GC 203, but with improved tracking indices
		307	Similar to type EP GC 205, but with improved tracking indices
		308	Similar to type EP GC 203, but with improved thermal endurance properties
		309	Similar to EP GC 201, but with defined mechanical strength at elevated temperature
		310	Similar to EP GC 202, but with halogen free compound
		311	Similar to EP GC 204, but with halogen free compound
	GM	201	Mechanical and electrical applications. Extremely high mechanical strength at moderate temperature. Very good electrical properties in high humidity
		202	Similar to type EP GM 201. Low flammability
		203	Similar to type EP GM 201. High mechanical strength at elevated temperature
		204	Similar to type EP GM 203. Low flammability
		305	Similar to type EP GM 203, but with improved thermal endurance properties
		306	Similar to type EP GM 305, but with improved tracking indices
	PC	301	Electrical and mechanical applications. Good resistance to SF ₆ (coarse weave ^c)

^a This specification was originally based on ISO 1642 [1]², which is now obsolete. Consequently, the type designations of the 200 series types come from ISO 1642 and those of the 300 series were added later.

^b It should not be inferred from the contents of Table 1 that laminates of any particular type are necessarily unsuitable for applications other than those listed for them, or that specific laminates will be suitable for all applications within the wide description given.

^c Fabric weaves of type PC and CC reinforcements:

	Mass per unit area g/m ²	Thread count cm ⁻¹
Coarse weave	>130	≤30
Fine weave	≤130	>30
Very fine weave	≤125	>38

These values are only for information. They are not to be considered as specification values. In general, the finer weave materials have better machining characteristics.

The definition of halogen free epoxy laminated sheet is given in IEC 61249-2-21:2003:

The maximum total halogens contained in the resin plus reinforcement matrix no greater than 1500 ppm with a maximum chlorine content of 900 ppm and maximum bromine content of 900 ppm. The test method for determination of the halogen content is given in IEC 61189-2:2006.

2 The figure in square brackets refers to the bibliography.

Table 2 – Tolerances on thickness
(test method: see 4.1 of IEC 60893-2)

Nominal thickness mm	Tolerance (all types) ±mm					
	EP CC 301	EP CP 201	EP GC 201; 202 203; 204 306; 308 309; 310; 311	EP GC 205; 307	EP GM 201; 202 203; 204 305; 306	EP PC 301
0,4	–	0,07	0,10	–	–	–
0,5	–	0,08	0,12	–	–	–
0,6	–	0,09	0,13	–	–	–
0,8	0,16	0,10	0,16	–	–	–
1,0	0,18	0,12	0,18	–	–	–
1,2	0,19	0,14	0,20	–	–	0,21
1,5	0,19	0,16	0,24	–	0,30	0,24
2,0	0,22	0,19	0,28	–	0,35	0,28
2,5	0,24	0,22	0,33	–	0,40	0,33
3,0	0,30	0,25	0,37	0,50	0,45	0,37
4,0	0,34	0,30	0,45	0,60	0,50	0,45
5,0	0,39	0,34	0,52	0,70	0,55	0,52
				For EP GC 205; 307, plus only for 6 mm and above		
6,0	0,44	0,37	0,60	1,60	0,60	0,60
8,0	0,52	0,47	0,72	IEC 60893-5-2003	0,70	0,72
10,0	0,60	0,50	0,82	2,20	0,80	0,82
12,0	0,68	–	0,94	2,40	0,90	0,94
14,0	0,74	–	1,02	2,60	1,00	1,02
16,0	0,80	–	1,12	2,80	1,10	1,12
20,0	0,93	–	1,30	3,00	1,30	1,30
25,0	1,08	–	1,50	3,50	1,40	1,50
30,0	1,22	–	1,70	4,00	1,45	1,70
35,0	1,34	–	1,95	4,40	1,50	1,95
40,0	1,47	–	2,10	4,80	1,55	2,10
45,0	1,60	–	2,30	5,10	1,65	2,30
50,0	1,74	–	2,45	5,40	1,75	2,45
60,0	2,02	–	–	5,80	1,90	–
70,0	2,32	–	–	6,20	2,00	–
80,0	2,62	–	–	6,60	2,20	–
90,0	2,92	–	–	6,80	2,35	–
100,0	3,22	–	–	7,00	2,50	–

Table 3 – Flatness
(test method: see 4.2 of IEC 60893-2)

Thickness <i>d</i> mm	Length of straight edge mm	
	1 000	500
$3 < d \leq 6$	10	2,5
$6 < d \leq 8$	8	2,0
$8 < d$	6	1,5

Table 4 – Tolerances on width of cut strips
(minus tolerances only)

Nominal thickness <i>d</i> mm	Nominal width, all types mm					
	$3 < b \leq 50$	$50 < b \leq 100$	$100 < b \leq 160$	$160 < b \leq 300$	$300 < b \leq 500$	$500 < b \leq 600$
0,4	0,5	0,5	0,5	0,6	1,0	1,5
0,5	0,5	0,5	0,5	0,6	1,0	1,5
0,6	0,5	0,5	0,5	0,6	1,0	1,5
0,8	0,5	0,5	0,5	0,6	1,0	1,0
1,0	0,5	0,5	0,5	0,6	1,0	1,0
1,2	0,5	0,5	0,5	1,0	1,2	1,2
1,5	0,5	0,5	0,5	1,0	1,2	1,2
2,0	0,5	0,5	0,5	1,0	1,2	1,5
2,5	0,5	1,0	1,0	1,5	2,0	2,5
3,0	0,5	1,0	IEC 60893-2-2:2003	1,5	2,0	2,5
4,0	0,5	2,0	2,0536-407e-13,05-3d4cab3d4,0e7/iec-60893-2-2:2003	3,0	4,0	5,0
5,0	0,5	2,0	2,0	3,0	4,0	5,0

NOTE Unilateral, all-negative tolerances are normally applied to the width of cut strips, and are given in the above table. Other tolerances may be agreed upon between purchaser and supplier.