



Designation: D6817/D6817M – 17

Standard Specification for Rigid Cellular Polystyrene Geofoam¹

This standard is issued under the fixed designation D6817/D6817M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the types, physical properties, and dimensions of rigid cellular polystyrene intended for use as geofoam.

1.2 This specification does not cover the layout, placement, and workmanship for proper installation and performance of rigid cellular polystyrene geofoam.

1.3 Rigid cellular polystyrene geofoam covered by this specification may need protection from certain chemicals, environmental exposure, and concentrated loads. Additional design considerations may include thermal conductivity and buoyancy. Guidelines regarding these end-use considerations are included in [Appendix X1](#).

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

¹ This specification is under the jurisdiction of ASTM Committee D35 on Geosynthetics and is the direct responsibility of Subcommittee D35.06 on Geosynthetic Specifications.

Current edition approved June 1, 2017. Published June 2017. Originally approved in 2002. Last previous edition approved in 2015 as D6817/D6817M – 15. DOI: 10.1520/D6817_D6817M-17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- [C165 Test Method for Measuring Compressive Properties of Thermal Insulations](#)
- [C203 Test Methods for Breaking Load and Flexural Properties of Block-Type Thermal Insulation](#)
- [C303 Test Method for Dimensions and Density of Preformed Block and Board-Type Thermal Insulation](#)
- [C390 Practice for Sampling and Acceptance of Thermal Insulation Lots](#)
- [C578 Specification for Rigid, Cellular Polystyrene Thermal Insulation](#)
- [D1621 Test Method for Compressive Properties of Rigid Cellular Plastics](#)
- [D1622/D1622M Test Method for Apparent Density of Rigid Cellular Plastics](#)
- [D2863 Test Method for Measuring the Minimum Oxygen Concentration to Support Candle-Like Combustion of Plastics \(Oxygen Index\)](#)
- [D4439 Terminology for Geosynthetics](#)
- [D7557/D7557M Practice for Sampling of Expanded Polystyrene Geofoam Specimens](#)
- [E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods](#)
- [E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method](#)

3. Terminology

3.1 Definitions:

3.1.1 Terms used in this specification are defined in Terminology [D4439](#).

3.1.2 *geofoam*—block or planar rigid cellular foam polymeric material used in geotechnical engineering applications.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *EPS, XX*—number designation for expanded polystyrene geofoam type(s) having a minimum density of XX kg/m³ [lb/ft³].

3.2.2 *RCPS*—letter designation for EPS and XPS rigid cellular polystyrene geofoam covered by this specification.

3.2.3 *XPS, XX*—number designation for extruded polystyrene geofoam type(s) having a minimum density of XX kg/m³ [lb/ft³].

TABLE 1 Physical Property Requirements of RCPS Geofoam^A

Type	EPS12	EPS15	EPS19	EPS22	EPS29	EPS39	EPS46	XPS20	XPS21	XPS26	XPS29	XPS36	XPS48
Density, min., kg/m ³ [lb/ft ³]	11.2 [0.70]	14.4 [0.90]	18.4 [1.15]	21.6 [1.35]	28.8 [1.80]	38.4 [2.40]	45.7 [2.85]	19.2 [1.20]	20.8 [1.30]	25.6 [1.60]	28.8 [1.80]	35.2 [2.20]	48.0 [3.00]
Compressive Resistance, min., kPa [psi] at 1 % strain	15 [2.2]	25 [3.6]	40 [5.8]	50 [7.3]	75 [10.9]	103 [15.0]	128 [18.6]	20 [2.9]	35 [5.1]	75 [10.9]	105 [15.2]	160 [23.2]	280 [40.6]
Flexural Strength, min., kPa [psi]	69 [10.0]	172 [25.0]	207 [30.0]	240 [35]	345 [50.0]	414 [60.0]	517 [75.0]	276 [40.0]	276 [40.0]	345 [50.0]	414 [60.0]	517 [75.0]	689 [100.0]
Oxygen Index, min., volume %	24.0	24.0	24.0	24.0	24.0	24.0	24.0	24.0	24.0	24.0	24.0	24.0	24.0

^A For products that have an external skin, testing shall be undertaken with skins intact.

4. Ordering Information

- 4.1 Acquisition documents shall specify the following:
- 4.1.1 Title, number, and year of this specification.
 - 4.1.2 Type, as per [Table 1](#).
 - 4.1.3 Total product volume required of each type.

5. Materials and Manufacture

5.1 RCPS geofoam shall be formed by the expansion of polystyrene resin beads or granules in a molding process (EPS) or by the expansion of polystyrene base resin in an extrusion process (XPS). RCPS geofoam may be manufactured with reprocessed polystyrene foam (regrind).

5.2 RCPS geofoam shall be of uniform density and have essentially closed cells. RCPS geofoam is an organic material and is considered combustible. It should not be exposed to flames or other ignition sources.

6. Qualification Requirements

6.1 The physical properties listed in [Table 1](#) constitute the minimum product qualification requirements for commonly manufactured types of RCPS geofoam. The compressive resistance at 1 % strain is typically within the elastic limit of the geofoam product types in [Table 1](#) and is accepted as the compressive resistance to limit long-term deformation under structural load.

6.2 *RCPS Geofoam Types*—It is the user’s responsibility to specify the required type as in [Table 1](#) and to obtain supporting documentation regarding physical properties from the material supplier.

6.3 *Combustibility Requirements*—All RCPS geofoam shall contain sufficient flame retardants to meet a minimum oxygen index as required in [Table 1](#).

6.4 *Curing*—Unless otherwise specified in the contract, RCPS geofoam shall be cured for a minimum of 24 h before delivery and inspection.

7. Availability and Dimensional Tolerance

7.1 *Availability*—The RCPS geofoam materials covered by this specification are commonly available in the size range

shown in [Table 2](#). Specific RCPS geofoam block dimensions vary by manufacturer equipment characteristics.

7.2 *Dimensional Tolerance*—Unless otherwise specified, the acceptable length, width, thickness, flatness, and squareness tolerance criteria on RCPS geofoam shall not exceed ± 0.5 %.

8. Damage and Degradation

8.1 *Damage*—RCPS geofoam as delivered to the project site shall have no defects that will adversely affect its service and workability qualities. Material units that manifest unacceptable surface or volumetric damage shall be replaced.

8.1.1 *Surface Damage*—Damage to load-bearing RCPS geofoam surfaces shall be limited to less than 20 % of the equivalent load-bearing area of the unit.

8.1.2 *Volume Damage*—Volumetric damage of RCPS geofoam shall be limited to less than 1 % of the volume of a single unit.

8.1.3 *UV (Ultraviolet) Degradation*—Discoloration and dusting of RCPS geofoam caused by the extensive exposure to sunlight is a defect that will adversely affect its service and is grounds for rejection. Refer to [X1.6](#).

9. Inspection

9.1 *Sampling*—Unless otherwise specified in the purchase order or contract, the material shall be sampled for inspection in accordance with Practice [D7557/D7557M](#) for EPS types or Practice [C390](#) for XPS types.

9.2 *Weight*—Determine the weight of selected full-size units in accordance with Test Method [D1622/D1622M](#), or as specified.

9.3 *Dimensions*—Verify specified dimensions and tolerances, as prescribed in Test Method [D1622/D1622M](#) and [7.2](#) of this specification.

9.4 *Density*—Compute the density of test samples in accordance with Test Method [D1622/D1622M](#).

10. Acceptance or Rejection

10.1 Material that fails to conform to this specification shall be rejected promptly in writing. The manufacturer or supplier