



Designation: **E2050–12a** E2050 – 17

Standard Test Method for Determination of Total Carbon in Mold Powders by Combustion¹

This standard is issued under the fixed designation E2050; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of total carbon in mold powders in the concentration range from 1 % to 25 %.

NOTE 1—As used in this test method, “percentage” or “%” refers to a mass fraction of the form (wt / wt %) (g/100g).

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 This test method has been evaluated in accordance with Practice **E1601** and Guide **E1763**. Unless otherwise noted in the precision and bias section, the lower limit in the scope of each method specifies the lowest analyte content that may be analyzed with acceptable error (defined as a nominal 5 % risk of obtaining a 50 % or larger relative difference in results on the same test sample in two laboratories).

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E50 Practices for Apparatus, Reagents, and Safety Considerations for Chemical Analysis of Metals, Ores, and Related Materials

E135 Terminology Relating to Analytical Chemistry for Metals, Ores, and Related Materials

E882 Guide for Accountability and Quality Control in the Chemical Analysis Laboratory

E1019 Test Methods for Determination of Carbon, Sulfur, Nitrogen, and Oxygen in Steel, Iron, Nickel, and Cobalt Alloys by Various Combustion and Fusion Techniques

E1601 Practice for Conducting an Interlaboratory Study to Evaluate the Performance of an Analytical Method

E1763 Guide for Interpretation and Use of Results from Interlaboratory Testing of Chemical Analysis Methods (Withdrawn 2015)³

3. Terminology

3.1 *Definitions*—For definitions of terms used in this test method, refer to Terminology **E135**.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *mold powder, n*— *in the continuous-casting of steel*, a metallurgical flux used to provide lubrication of the mold, enhance heat transfer at the strand-mold interface, and provide thermal insulation of the liquid metal surface to prevent unwanted solidification.

¹ This test method is under the jurisdiction of ASTM Committee **E01** on Analytical Chemistry for Metals, Ores, and Related Materials and is the direct responsibility of Subcommittee **E01.02** on Ores, Concentrates, and Related Metallurgical Materials.

Current edition approved ~~June 1, 2012~~ April 1, 2017. Published ~~July 2012~~ June 2017. Originally approved in 1999. Last previous edition approved in 2012 as E2050–12–12a. DOI: ~~10.1520/E2050-12A~~ 10.1520/E2050-17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

3.2.1.1 *Discussion*—

Key chemical components of these powders are fluorides, the oxides of silicon and calcium, and carbon.

4. Summary of Test Method

4.1 Carbon in the test sample is converted in a furnace to a mixture of carbon dioxide (CO_2) and carbon monoxide (CO) by combustion in a stream of oxygen. Full conversion of ~~carbon monoxide CO to carbon~~ CO_2 ~~diioxide~~ occurs by the passage of sample gases through a catalytic heater assembly. The amount of ~~carbon~~ CO_2 ~~diioxide~~ is measured by infrared absorption. Any interference from halogens in the sample is eliminated by placement of a halogen trap between the furnace and the analyzer.

5. Significance and Use

5.1 This test method for the determination of total carbon in mold powders is primarily intended to test such materials for compliance with compositional specifications. It is assumed that all who use this test method will be trained analysts capable of performing common laboratory procedures skillfully and safely. It is expected that the work will be performed in a properly equipped laboratory and that proper waste disposal procedures will be followed. Appropriate quality control practices must be followed such as those described in Guide E882.

6. Rounding Calculated Values

6.1 Calculated values shall be rounded in accordance with Practice E29.

7. Interferences

7.1 Halogens, normally present in mold powders as fluoride, will interfere with this test method. A halogen trap, as described in 8.4, must be installed in the measure line between the furnace and analyzer to prevent this interference.

8. Apparatus

8.1 *Combustion-Infrared Absorption Carbon Analyzer*, equipped with a combustion chamber, oxygen carrier stream, halogen trap, catalytic heater assembly, and infrared absorption detector, suitable for the analysis of carbon from ± 1 to 25 % in mold powders. Instruments, such as those in Test Methods E1019, which can be shown to give equivalent results may also be used for this test method.

8.2 *Crucibles*—Use ceramic crucibles that meet or exceed the specifications of those recommended by the manufacturer of the instrument.

8.3 *Crucible Tongs*, capable of handling recommended crucibles.

8.4 *Halogen (Fluorine/Chlorine) Trap*, available from the instrument manufacturer as a kit, consisting of the parts and necessary reagents for assembly. Follow the manufacturer's instructions for the assembly, installation, use, and proper maintenance of the trap.

8.5 *Metal Scoop*, for dispensing metal chips (accelerators).

9. Reagents and Materials

9.1 *Iron Chip*, high purity (–6 mesh to +20 mesh) purity.

9.2 *Oxygen*, 99.5 % purity recommended. Other grades of oxygen may be used if low and consistent blank readings are obtained.

9.3 *Tungsten/Tin or Copper Accelerator*, high purity.

NOTE 2—Copper chip accelerator (–20 mesh to +30 mesh) may be used in place of Tungsten/Tin.

10. Hazards

10.1 For precautions to be observed in the use of reagents and apparatus in this method, refer to Practices E50 and Test Methods E1019.

10.2 Use care when handling hot crucibles and when operating furnaces to avoid personal injury by either burn or electrical shock.

11. Sampling and Sample Preparation

11.1 *Materials Safety*—Samples must be prepared, stored, and disposed of in accordance with the materials and safety guidelines in Practices E50.

11.2 *Prepared Sample*—Pulverize or grind the laboratory sample until 100 % passes a No. 100 (150- μm) sieve. Store in a suitable glass or plastic container.

TABLE 1 Statistical Information, Carbon Combustion/Infrared Method

Test Material	Number of Laboratories	Carbon Found, %	Minimum SD (S_M , E1601)	Reproducibility SD, (S_g , E1601)	Reproducibility Index (R , E1601)	$R_{rel}\%$
B	7	1.2046	0.00601	0.02960	0.08288	6.88
A	7	3.1219	0.01269	0.04843	0.13559	4.34
C	7	6.5514	0.04774	0.09215	0.25803	3.94
D	7	10.5121	0.05788	0.10579	0.29620	2.82
E	7	15.1121	0.04964	0.14730	0.41244	2.73
F	7	19.7121	0.11949	0.25294	0.70824	3.59
G	7	29.4250	0.38830	0.60179	1.6850	5.73

12. Preparation of Apparatus

12.1 Test the furnace and analyzer to ensure the absence of leaks. Prepare the analyzer for operation in accordance with directed in the manufacturer's instructions.

13. Calibration

13.1 *Calibration Reference Materials*—Tungsten carbide (6.10 % total carbon), NIST SRM 276b, or equivalent; silicon carbide (29.43 % total carbon), NIST SRM 112b, or equivalent (certified for total carbon in the vicinity of 6.1 % C and silicon carbide certified for total carbon in the vicinity of 29.4 % **Note 1**); C.

NOTE 1—As originally approved, this standard relied on National Institute of Standards and Technology SRM 276b Tungsten Carbide and SRM 112b Silicon Carbide as calibration materials. Those SRMs have been discontinued. Certified reference materials are available from other sources.

13.2 Determination of Blank:

13.2.1 Enter 1.000-g weight into the weight stack, following the instrument manufacturer's a specific mass (for example, 1.0 g) into the software, as it is recommended by the instrument manufacturer, and follow the recommended procedure.

13.2.2 Add 1.000 ± 0.005 g of accelerator and 1.000 ± 0.005 g of iron chip to the crucible. accelerators to the crucible. Type and amount of accelerators depend on sample matrix. Optimum parameters are recommended by the instrument manufacturer. Some manufacturers provide scoops that dispense a specific amount of accelerator. Once it is verified that the scoop delivers this approximate mass, it is acceptable to use this device for routine dispensing of accelerator.

13.2.3 Place the crucible on the furnace pedestal position and analyze in accordance with the manufacturer's instructions.

13.2.4 Repeat **13.2.1 – 13.2.3** a minimum of three times.

13.2.5 Enter the average blank following the routine outlined in the manufacturer's instruction manual.

13.3 Calibration Procedure:

13.3.1 Transfer 0.25 g of tungsten carbide calibration reference material-material, weighed to the nearest 1 mg, into a ceramic crucible and enter the weight mass into the weight stack, software, following the instrument manufacturer's recommended procedure.

13.3.2 Add 1.000 g ± 0.005 g of accelerator and 1.000 g ± the same type and amount of accelerators, which are used in 13.2.2. 0.005 g of iron chip, to the crucible.

13.3.3 Place the crucible on the furnace pedestal position and analyze in accordance with directed in the manufacturer's instructions.

13.3.4 Repeat **13.3.1 – 13.3.3** a minimum of three times and calibrate the instrument following the calibration procedure in accordance with directed in the manufacturer's instruction manual.

13.3.5 Verify the calibration by analyzing the calibration reference material again. The obtained value shall agree with the certificate value within the range given by the published uncertainty or it shall agree within the limits of a prediction interval calculated using **Eq 1**. The prediction interval is defined as the range of values bounded by the analysis value $-p$ and the analysis value $+p$. If the prediction interval does not encompass the certified value, determine and correct the cause, and repeat calibration (**Note 32**). Either acceptance limit criterion is acceptable for routine operation.

NOTE 2—See the instrument manufacturer's instructions concerning the troubleshooting and correcting of errant calibration.

$$p = t \times \left(1 + \frac{1}{\sqrt{n}} \right) \times s \quad (1)$$

where:

p = one-half the prediction interval;

p = magnitude of the one-sided, prediction interval,

n = number of replicates used in 13.3.4,