



Standard Specification for Seamless Nickel and Nickel-Cobalt Alloy Pipe and Tube¹

This standard is issued under the fixed designation B622; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—The Mn for N06210 in Table 1 was corrected editorially in July 2016.

1. Scope

1.1 This specification² covers seamless pipe and tube of nickel and nickel-cobalt alloys (UNS N10001, UNS N10242, UNS N10665, UNS N12160, UNS N10675, UNS N10276, UNS N06455, UNS N06007, UNS N08320, UNS N06975, UNS N06002, UNS N06985, UNS N06022, UNS N06035, UNS N06044, UNS N08135, UNS N06255, UNS N06058, UNS N06059, UNS N06200, UNS N10362, UNS N06030, UNS N08031, UNS R30556, UNS N08535, UNS N06250, UNS N06060, UNS N06230, UNS N06686, UNS N10629, UNS N06210, UNS N10624, and UNS R20033)³ as shown in **Table 1**.

1.2 Pipe and tube shall be supplied in the solution annealed and descaled condition. When atmosphere control is used, descaling is not necessary.

1.3 This specification is limited to tubes up to and including 3.5 in. (88.9 mm) outside diameter.

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Safety Data Sheet (SDS) for this product/material as provided by the manufacturer, to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:⁴

B829 Specification for General Requirements for Nickel and Nickel Alloys Seamless Pipe and Tube

E8 Test Methods for Tension Testing of Metallic Materials

E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

3. Terminology

3.1 Definitions:

3.1.1 *average diameter, n*—the average of the maximum and minimum outside diameters, or the maximum and minimum inside diameters, as determined at any cross section of the tube.

3.1.2 *pipe, n*—seamless tube conforming to the particular dimensions commercially known as standard pipe sizes (**Appendix X2**).

3.1.3 *tube, n*—a hollow product of round or any other cross section having a continuous periphery.

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved Oct. 1, 2015/June 1, 2017. Published November 2015/June 2017. Originally approved in 1977. Last previous edition approved in 2010/2015 as B622—10B622—15^{ε1}. DOI: 10.1520/B0622-15E01.10.1520/B0622-17.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SB-622 in Section II of that Code.

³ Designation established in accordance with Practice E527 and SAE J1086, Practice for Numbering Metals and Alloys (UNS).

⁴ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

TABLE 1 Chemical Requirements

	Composition Limits, %																							
	Ni	Cr	Mo	Fe	W	C	Si max	Co	Mn	V	P max	S max	Ti	Cu	Cb (Nb) +Ta	Al	Zr	La	N	B	Cb (Nb)	Ta	Ni+ Mo	Mg
Ni-Mo Alloys	remainder ^A	1.0 max	26.0-30.0	4.0-6.0	...	0.05 max	1.0	2.5 max	1.0 max	0.2-0.4	0.04	0.03	0.20 max	0.20 max	94.0-98.0	
	remainder ^A	1.0 max	26.0-30.0	2.0 max	...	0.02 max	0.10	1.0 max	1.0 max	...	0.04	0.03		
	65.0 min	1.0-3.0	27.0-32.0	1.0-3.0	3.0 max	0.01 max	0.10	3.0 max	3.0 max	0.20 max	0.030	0.010	0.20 max	0.20 max	...	0.50 max	0.10 max	0.20 max	0.20 max		
	remainder ^A	0.5-1.5	26.0-30.0	1.0-6.0	...	0.01 max	0.05	2.5 max	1.5 max	...	0.04	0.01	0.5 max	0.1-0.5		
	remainder ^A	6.0-10.0	21.0-25.0	5.0-8.0	...	0.01 max	0.10	1.0 max	1.0 max	...	0.025	0.01	...	0.5 max	0.5 max		
Ni-Mo-Cr-Fe Alloy	remainder ^A	7.0-9.0	24.0-26.0	2.0 max	...	0.03 max	0.80	1.00 max	0.80 max	...	0.030	0.015	...	0.50 max	0.50 max	0.006 max	...		
	balance	43.5-45.3	0.80-1.20	0.3 max	...	0.02 max	0.20	...	0.07-0.30	...	0.020	0.020	0.10-0.30	...	0.30 max	0.40 max	
Low C Ni-Cr-Mo Alloys	remainder ^A	14.5-16.5	15.0-17.0	4.0-7.0	3.0-4.5	0.010 max	0.08	2.5 max	1.0 max	0.35 max	0.04	0.03		
	remainder ^A	20.0-22.5	12.5-14.5	2.0-6.0	2.5-3.5	0.015 max	0.08	2.5 max	0.50 max	0.35 max	0.02	0.02		
	remainder ^A	32.25-34.25	7.60-9.00	2.00 max	0.60 max	0.050 max	0.60	1.00 max	0.50 max	0.20 max	0.030	0.015	...	0.30 max	0.40 max		
	balance	43.5-45.3	0.80-1.20	0.3 max	...	0.02 max	0.20	...	0.07-0.30	...	0.020	0.020	0.10-0.30	...	0.30 max	0.40 max		
	balance	20.0-23.0	18.5-21.0	1.5 max	0.3 max	0.010 max	0.10	0.3 max	0.50 max	...	0.015	0.010	...	0.50 max	0.40 max	0.02-0.15		
Ni-Cr-Fe-Mo-Cu Alloys	balance	22.0-24.0	15.0-16.5	1.5 max	...	0.010 max	0.10	0.3 max	0.5 max	...	0.015	0.010	...	0.50 max	0.40 max		
	remainder ^A	14.0-18.0	14.0-17.0	3.0 max	...	0.015 max	0.08	2.0 max	1.0 max	...	0.04	0.03	0.70 max	0.1-0.4		
	remainder ^A	21.0-23.5	5.5-7.5	18.0-21.0	1.0 max	0.05 max	1.0	2.5 max	1.0-2.0	...	0.04	0.03	...	1.5-2.5	1.75-2.5		
	47.0-52.0	23.0-26.0	5.0-7.0	remainder ^A	...	0.03 max	1.0	...	1.0 max	...	0.03	0.03	0.70-1.50	0.70-1.20		
	remainder ^A	21.0-23.5	6.0-8.0	18.0-21.0	1.5 max	0.015 max	1.0	5.0 max	1.0 max	...	0.04	0.03	...	1.5-2.5	0.50 max		
Ni-Fe-Cr-Mo Alloys	remainder ^A	28.0-31.5	4.0-6.0	13.0-17.0	1.5-4.0	0.03 max	0.8	5.0 max	1.5 max	...	0.04	0.02	...	1.0-2.4	0.30-1.50		
	47.0-52.0	23.0-26.0	6.0-9.0	remainder ^A	3.0 max	0.03 max	1.0	...	1.0 max	...	0.03	0.03	0.69 max	1.2 max		
	50.0-54.0	20.0-23.0	10.1-12.0	remainder ^A	0.25-1.25 max	0.020 max	0.09	...	1.00 max	...	0.030	0.005	...	0.25-1.25 max		
	25.0-27.0	21.0-23.0	4.0-6.0	remainder ^A	...	0.05 max	1.0	...	2.5 max	...	0.04	0.03	4xC min		
	33.0-38.0	20.5-23.5	4.0-5.0	remainder ^A	0.20-0.80 max	0.030 max	0.75	...	1.00 max	...	0.03	0.03		
N06002	remainder ^A	20.5-23.0	8.0-10.0	17.0-20.0	0.20-1.0	0.05-0.15	1.0	0.5-2.5	1.0 max	...	0.04	0.03		

TABLE 1 *Continued*

		Composition Limits, %																							
		Ni	Cr	Mo	Fe	W	C	Si max	Co	Mn	V	P max	S max	Ti	Cu	Cb (Nb) +Ta	Al	Zr	La	N	B	Cb (Nb)	Ta	Ni+ Mo	Mg
N06060	54.0-60.0	19.0- 22.0	12.0- 14.0	remainder ^A	0.25- 1.25	0.03	0.50	...	1.50 max	...	0.030 max	0.005 max	...	0.25- 1.25	0.50- 1.25										
Ni-Fe-Cr-Co Alloy	19.0-22.5	21.0- 23.0	2.5- 4.0	remainder ^A	2.0- 3.5	0.05- 0.15	0.20- 0.80	16.0- 21.0	0.50- 2.00	...	0.04	0.015	0.10- 0.50	0.001- 0.10	0.005- 0.10	0.10- 0.30	0.02 max	0.30 max	0.3- 1.25			
Ni-Cr-W-Mo Alloys	remainder ^A	20.0- 24.0	1.0- 3.0	3.0 max	13.0- 15.0	0.05- 0.15	0.25- 0.75	5.0 max	0.30- 1.00	...	0.03	0.015	0.50 max	...	0.005- 0.050	...	0.015 max			
Low C-Ni- Cr-Mo-Cu Alloy	Low C-Ni- Mo-Cr Alloy	22.0- 24.0	15.0- 17.0	3.0 max	...	0.010 max	0.08	2.0 max	0.50 max	...	0.025	0.010	...	1.3- 1.9	...	0.50 max									
N06200	remainder ^A	13.8- 15.6	21.5- 23.0	1.25 max	...	0.010 max	0.08	...	0.60 max	...	0.025	0.010	0.50 max		
N10362	remainder ^A	30.0-32.0	26.0- 28.0	6.0- 7.0	balance	...	0.015 max	0.3	...	2.0 max	...	0.020	0.010	...	1.0- 1.4	0.15- 0.25		
N08031	29.0-36.5	24.0- 27.0	2.5- 4.0	remainder ^A	...	0.03	0.50	...	1.0 max	...	0.03	0.03	...	1.50 max	...										
Low C-Ni- Cr-Mo-W Alloy	N06686	remainder ^A	19.0- 23.0	15.0- 17.0	5.0 max	3.0- 4.4	0.010 max	0.08	...	0.75 max	...	0.04	0.02	0.02- 0.25		
Ni-Co-Cr-Si Alloy	N12160	remainder ^A	26.0- 30.0	1.0 max	3.5 max	1.0 max	0.15	2.4- 3.0	27.0- 33.0	1.5 max	...	0.030	0.015	0.20- 0.80	1.0 max		
Cr-Ni-Fe-N Alloy	R20033	30.0-33.0	31.0- 35.0	0.50- 2.0	balance	...	0.015 max	0.50	...	2.0 max	...	0.02	0.01	...	0.3- 1.20	0.35- 0.60		
Low C-Ni- Mo-Cr-Ta Alloy	N06210	remainder ^A	18.0- 20.0	18.0- 20.0	1.0 max	...	0.015 max	0.08	1.0 max	0.5 max†	0.35 max	0.02	0.02	1.5- 2.2			

^A See 12.1.

†Editorially corrected.