



Designation: B456 – 17

Standard Specification for Electrodeposited Coatings of Copper Plus Nickel Plus Chromium and Nickel Plus Chromium¹

This standard is issued under the fixed designation B456; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers requirements for several types and grades of electrodeposited copper plus nickel plus chromium or nickel plus chromium coatings on steel, nickel plus chromium coatings on copper and copper alloys, nickel plus chromium coatings on Type 300 and 400 series stainless steel and copper plus nickel plus chromium coatings on aluminum and its alloys and zinc alloys for applications where both appearance and protection of the basis metal against corrosion are important. Five grades of coatings are provided to correspond with the service conditions under which each is expected to provide satisfactory performance: namely, extended very severe, very severe, severe, moderate, and mild. Definitions and typical examples of these service conditions are provided in [Appendix X1](#).

1.2 This specification does not cover the requirements for the plating on plastics, see Specification [B604](#).

1.3 The following hazards caveat pertains only to the test methods portions, [Appendix X2](#), [Appendix X3](#), [Appendix X4](#), and [Appendix X5](#) of this specification: *This standard does not purport to address all of safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- [B183 Practice for Preparation of Low-Carbon Steel for Electroplating](#)
- [B242 Guide for Preparation of High-Carbon Steel for Electroplating](#)
- [B252 Guide for Preparation of Zinc Alloy Die Castings for Electroplating and Conversion Coatings](#)
- [B253 Guide for Preparation of Aluminum Alloys for Electroplating](#)
- [B254 Practice for Preparation of and Electroplating on Stainless Steel](#)
- [B281 Practice for Preparation of Copper and Copper-Base Alloys for Electroplating and Conversion Coatings](#)
- [B320 Practice for Preparation of Iron Castings for Electroplating](#)
- [B368 Test Method for Copper-Accelerated Acetic Acid-Salt Spray \(Fog\) Testing \(CASS Test\)](#)
- [B380 Test Method for Corrosion Testing of Decorative Electrodeposited Coatings by the CorrodKote Procedure](#)
- [B487 Test Method for Measurement of Metal and Oxide Coating Thickness by Microscopical Examination of Cross Section](#)
- [B489 Practice for Bend Test for Ductility of Electrodeposited and Autocatalytically Deposited Metal Coatings on Metals](#)
- [B490 Practice for Micrometer Bend Test for Ductility of Electrodeposits](#)
- [B499 Test Method for Measurement of Coating Thicknesses by the Magnetic Method: Nonmagnetic Coatings on Magnetic Basis Metals](#)
- [B504 Test Method for Measurement of Thickness of Metallic Coatings by the Coulometric Method](#)
- [B530 Test Method for Measurement of Coating Thicknesses by the Magnetic Method: Electrodeposited Nickel Coatings on Magnetic and Nonmagnetic Substrates](#)

¹ This specification is under the jurisdiction of ASTM Committee [B08](#) on Metallic and Inorganic Coatings and is the direct responsibility of Subcommittee [B08.05](#) on Decorative Coatings.

Current edition approved May 1, 2017. Published June 2017. Originally approved in 1967. Last previous edition approved in 2011 as B456 – 11. DOI: 10.1520/B0456-17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- B537** Practice for Rating of Electroplated Panels Subjected to Atmospheric Exposure
- B568** Test Method for Measurement of Coating Thickness by X-Ray Spectrometry
- B571** Practice for Qualitative Adhesion Testing of Metallic Coatings
- B602** Test Method for Attribute Sampling of Metallic and Inorganic Coatings
- B604** Specification for Decorative Electroplated Coatings of Copper Plus Nickel Plus Chromium on Plastics
- B659** Guide for Measuring Thickness of Metallic and Inorganic Coatings
- B697** Guide for Selection of Sampling Plans for Inspection of Electrodeposited Metallic and Inorganic Coatings
- B762** Test Method of Variables Sampling of Metallic and Inorganic Coatings
- B764** Test Method for Simultaneous Thickness and Electrode Potential Determination of Individual Layers in Multilayer Nickel Deposit (STEP Test)
- B995** Test Method for Chloride Resistance Test for Chromium Electroplated Parts (Russian Mud Test)
- D1193** Specification for Reagent Water
- D3951** Practice for Commercial Packaging
- E50** Practices for Apparatus, Reagents, and Safety Considerations for Chemical Analysis of Metals, Ores, and Related Materials
- G85** Practice for Modified Salt Spray (Fog) Testing
- 2.2 *ISO Standards:*
- ISO 1456** Metallic coatings—Electrodeposited coatings of nickel plus chromium and of copper plus nickel plus chromium³

3. Terminology

3.1 Definitions:

3.1.1 *significant surfaces*—those surfaces normally visible (directly or by reflection) that are essential to the appearance or serviceability of the article, or both, when assembled in normal position; or that can be the source of corrosion products that deface visible surfaces on the assembled article. When necessary, the significant surfaces shall be specified by the purchaser and shall be indicated on the drawings of the parts, or by the provision of suitably marked samples.

3.1.2 *p-points*—specific points of measurement that are encouraged to be determined and agreed upon with the customer early in the contract review process. These are used for measurement of critical characteristics that vary with current density such as thickness, STEP, active sites, etc. and may be designated at multiple locations per part.

4. Classification

4.1 Five grades of coatings designated by service condition numbers and several types of coatings defined by classification numbers are covered by this specification.

4.2 Service Condition Number:

4.2.1 The service condition number indicates the severity of exposure for which the grade of coating is intended:

- SC 5 extended severe service
- SC 4 very severe service,
- SC 3 severe service,
- SC 2 moderate service, and
- SC 1 mild service.

4.2.2 Typical service conditions for which the various service condition numbers are appropriate are given in **Appendix X1**.

4.3 *Coating Classification Number*—The coating classification number comprises:

4.3.1 The chemical symbol for the basis metal (or for the principal metal if an alloy) followed by a slash mark, except in the case of stainless steel. In this case, the designation shall be SS followed by the designated AISI number followed by a slash, that is, SS463/,

4.3.2 The chemical symbol for copper (Cu) (if copper is used),

4.3.3 A number indicating the minimum thickness of the copper coating in micrometers (if copper is used),

4.3.4 A lower-case letter designating the type of copper deposit (if copper is used) (see 4.4 and 6.2.3),

4.3.5 The chemical symbol for nickel (Ni),

4.3.6 A number indicating the minimum thickness of the nickel coating, in micrometers,

4.3.7 A lower-case letter designating the type of nickel deposit (see 4.4 and 6.2.4),

4.3.8 The chemical symbol for chromium (Cr), and

4.3.9 A letter (or letters) designating the type of chromium deposit and its minimum thickness in micrometers (see 4.4 and 6.2.5).

4.4 *Symbols for Expressing Classification*—The following lower-case letters shall be used in coating classification numbers to describe the types of coatings:

- a —ductile copper deposited from acid-type baths
- b —single-layer nickel deposited in the fully-bright condition
- d —double- or triple-layer nickel coatings
- r —regular (that is, conventional) chromium
- mc —microcracked chromium
- mp —microporous chromium

4.5 *Example of Complete Classification Numbers*—A coating on steel comprising 15 µm minimum (ductile acid) copper plus 25 µm minimum (duplex) nickel plus 0.25µ m minimum (micro-cracked) chromium has the classification number: Fe/Cu15aNi25d Cr mc (see 4.3 and 6.2 for explanation of symbols).

5. Ordering Information

5.1 When ordering articles to be electroplated in conformance with this standard, the purchaser shall state the following:

5.1.1 The ASTM designation number of this standard.

5.1.2 Either the classification number of the specific coating required (see 4.3) or the substrate material and the service condition number denoting the severity of the conditions it is required to withstand (see 4.2). If the service condition number is quoted and not the classification number, the manufacturer is free to supply any of the types of coatings designated by the

³ Available from International Organization for Standardization (ISO), 1, ch. de la Voie-Creuse, Case postale 56, CH-1211, Geneva 20, Switzerland, <http://www.iso.ch>.