



Designation: C330/C330M – 17

Standard Specification for Lightweight Aggregates for Structural Concrete¹

This standard is issued under the fixed designation C330/C330M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers lightweight aggregates intended for use in structural concrete in which prime considerations are reducing the density while maintaining the compressive strength of the concrete. Procedures covered in this specification are not intended for job control of concrete.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.2.1 With regard to other units of measure, the values stated in inch-pound units are to be regarded as standard.

1.3 The text of this standard references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

NOTE 1—This specification is regarded as adequate to ensure satisfactory lightweight aggregates for most concrete. It is recognized that it may be either more or less restrictive than needed for some conditions and for special purposes, such as fire resistance, fill, and concrete constructions, the use of which is based on load tests rather than conventional design procedures.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

¹ This specification is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.21 on Lightweight Aggregates and Concrete.

Current edition approved May 1, 2017. Published July 2017. Originally approved in 1953. Last previous edition approved in 2014 as C330/C330M-14. DOI: 10.1520/C0330_C0330M-17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- C29/C29M Test Method for Bulk Density (“Unit Weight”) and Voids in Aggregate
- C31/C31M Practice for Making and Curing Concrete Test Specimens in the Field
- C33/C33M Specification for Concrete Aggregates
- C39/C39M Test Method for Compressive Strength of Cylindrical Concrete Specimens
- C40/C40M Test Method for Organic Impurities in Fine Aggregates for Concrete
- C114 Test Methods for Chemical Analysis of Hydraulic Cement
- C127 Test Method for Relative Density (Specific Gravity) and Absorption of Coarse Aggregate
- C128 Test Method for Relative Density (Specific Gravity) and Absorption of Fine Aggregate
- C136/C136M Test Method for Sieve Analysis of Fine and Coarse Aggregates
- C142/C142M Test Method for Clay Lumps and Friable Particles in Aggregates
- C151/C151M Test Method for Autoclave Expansion of Hydraulic Cement
- C157/C157M Test Method for Length Change of Hardened Hydraulic-Cement Mortar and Concrete
- C192/C192M Practice for Making and Curing Concrete Test Specimens in the Laboratory
- C496/C496M Test Method for Splitting Tensile Strength of Cylindrical Concrete Specimens
- C567/C567M Test Method for Determining Density of Structural Lightweight Concrete
- C641 Test Method for Iron Staining Materials in Lightweight Concrete Aggregates
- C666/C666M Test Method for Resistance of Concrete to Rapid Freezing and Thawing
- C702/C702M Practice for Reducing Samples of Aggregate to Testing Size
- D75/D75M Practice for Sampling Aggregates

3. Aggregate Types

3.1 Two general types of lightweight aggregates are covered by this specification, as follows:

3.1.1 Aggregates prepared by expanding, pelletizing, or sintering products such as blast-furnace slag, clay, diatomite, fly ash, shale, or slate, and

*A Summary of Changes section appears at the end of this standard

3.1.2 Aggregates prepared by processing natural materials, such as pumice, scoria, or tuff.

3.2 The aggregates shall be composed predominately of lightweight-cellular and granular inorganic material.

4. Chemical Composition

4.1 Lightweight aggregates shall not contain excessive amounts of deleterious substances, as determined by the following limits:

4.1.1 *Organic Impurities (Test Method C40/C40M)*—Lightweight aggregates that, upon being subjected to test for organic impurities, produce a color darker than the standard shall be rejected, unless it is demonstrated that the discoloration is due to small quantities of materials not harmful to the concrete.

4.1.2 *Staining (Test Method C641)*—An aggregate producing a stain index of 60 or higher shall be rejected when the deposited stain is found upon chemical analysis to contain an iron content, expressed as Fe₂O₃ equal to or greater than 1.5 mg/200 g of sample.

4.1.3 *Loss on Ignition (Test Methods C114)*—The loss on ignition of lightweight aggregates shall not exceed 5 %.

NOTE 2—Some aggregates may contain carbonates or water of hydration that contribute to loss on ignition but may not affect the quality of the product. Therefore, when evaluating an aggregate, consideration should be given to the material characteristics that cause the ignition loss.

5. Physical Properties

5.1 Lightweight aggregate under test shall meet the following requirements:

5.1.1 *Clay Lumps and Friable Particles*—The total amount of clay lumps and friable particles shall not exceed 2 % by dry mass.

5.1.2 *Grading*—The grading shall conform to the requirements shown in **Table 1**.

NOTE 3—The surfaces of pyro-processed lightweight aggregate particles finer than 75 µm (No. 200) sieves are not deleterious and may be moderately pozzolanic.

5.1.3 *Uniformity of Grading*—To ensure reasonable uniformity in the grading of successive shipments of lightweight aggregate, fineness modulus shall be determined on samples taken from shipments at intervals stipulated by the purchaser. If the fineness modulus of the aggregate in any shipment differs by more than 7 % from that of the sample submitted for

acceptance tests, the aggregate in the shipment shall be rejected, unless the supplier demonstrates that it will produce concrete of the required characteristics.

5.1.4 *Loose Bulk Density (Test Method C29/C29M)*—The dry loose bulk density of lightweight aggregates shall conform to the requirements shown in **Table 2** using a 14 L [¹/₂ cubic foot] measure.

5.1.5 *Uniformity of Loose Bulk Density*—The dry loose bulk density of lightweight aggregate shipments sampled and tested, shall not differ by more than 10 % from that of the sample submitted for acceptance tests, and shall not exceed the limits in **Table 2**.

5.1.6 *Relative Density*—When specified, the relative density shall be determined in accordance with **8.10**.

5.2 Concrete specimens containing lightweight aggregate under test shall meet the following requirements:

5.2.1 *Compressive Strength (Test Method C39/C39M), Density (Test Method C567/C567M), and Splitting Tensile Strength (Test Method C496/C496M)*—Compressive strength and density shall be an average of three specimens and the splitting tensile strength shall be the average of eight specimens. It shall be possible to produce structural concrete using the lightweight aggregates under test, so that from the same batch of concrete one or more of the compressive strength requirements and splitting tensile strength requirements in **Table 3** will be satisfied without exceeding the corresponding maximum density values.

NOTE 4—Intermediate values for strength and corresponding density values shall be established by interpolation. Materials that do not meet the minimum average splitting tensile strength requirement may be used provided the design is modified to compensate for the lower value.

5.2.2 *Natural Aggregates*—Natural aggregates, when used to replace part, or all, of the lightweight-aggregates shall comply with the applicable requirements of Specification **C33/C33M**. The test report shall record the proportion of all ingredients and the characteristics of the natural aggregates to ensure compliance with these minimum requirements.

5.2.3 *Drying Shrinkage*—The drying shrinkage of concrete specimens prepared, cured, and tested in accordance with **8.4** shall not exceed 0.07 %.

5.2.4 *Popouts*—Concrete specimens prepared in accordance with **8.4** and **8.5**, and tested in accordance with Test Method **C151/C151M** shall show no surface popouts.

TABLE 1 Grading Requirements for Lightweight Aggregate for Structural Concrete

Nominal Size Designation	Percentages (Mass) Passing Sieves Having Square Openings									
	25.0 mm (1 in.)	19.0 mm (¾ in.)	12.5 mm (½ in.)	9.5 mm (⅜ in.)	4.75 mm (No. 4)	2.36 mm (No. 8)	1.18 mm (No. 16)	300 µm (No. 50)	150 µm (No. 100)	75 µm (No. 200)
Fine aggregate: 4.75 mm to 0	100	85–100	...	40–80	10–35	5–25	...
Coarse aggregate: 25.0 mm to 4.75 mm	95–100	...	25–60	...	0–10	0–10
19.0 mm to 4.75 mm	100	90–100	...	10–50	0–15	0–10
12.5 mm to 4.75 mm	...	100	90–100	40–80	0–20	0–10	0–10
9.5 mm to 2.36 mm	100	80–100	5–40	0–20	0–10	0–10
Combined fine and coarse aggregate: 12.5 mm to 0	...	100	95–100	...	50–80	5–20	2–15	0–10
9.5 mm to 0	100	90–100	65–90	35–65	...	10–25	5–15	0–10