



Designation: C1719 – 11 (Reapproved 2017)

# Standard Test Method for Installed Precast Concrete Tanks and Accessories by the Negative Air Pressure (Vacuum) Test Prior to Backfill<sup>1</sup>

This standard is issued under the fixed designation C1719; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers procedures for testing precast concrete tanks (and installed accessories) used for on-site wastewater treatment, grease interception, grit/oil separation, water storage, or other applications requiring watertight construction and installation. This test method uses partial vacuum to demonstrate the integrity of the installed materials and the construction processes.

1.2 This test method is intended to be used to demonstrate the condition of the installed system (precast concrete tank and accessories) prior to backfill.

1.3 Testing of the system before backfill is necessary so as to preclude inadvertent structural overloading of the system components during the test.

NOTE 1—Vacuum test criteria presented in this test method are similar to those in general use. The test and criteria have been widely and successfully used in testing manholes as specified in Test Method C1244.

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee C27 on Precast Concrete Products and is the direct responsibility of Subcommittee C27.30 on Water and Wastewater Containers.

Current edition approved June 1, 2017. Published July 2017. Originally approved in 2011. Last previous edition approved in 2011 as C1719 – 11. DOI: 10.1520/C1719-11R17.

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

C822 Terminology Relating to Concrete Pipe and Related Products

C1227 Specification for Precast Concrete Septic Tanks

C1244 Test Method for Concrete Sewer Manholes by the Negative Air Pressure (Vacuum) Test Prior to Backfill

## 3. Terminology

3.1 For definitions of terms relating to tanks, see Terminology C822.

## 4. Summary of Test Method

4.1 The tank shall be set in its installed position. Required accessories and pipes shall be installed. All openings and pipes entering the tank shall be plugged. A vacuum shall be drawn and vacuum retention over a specified time period is used to determine the acceptability of the tank and installed accessories.

## 5. Significance and Use

5.1 This is not a routine test. The values recorded are applicable only to the tank being tested and at the time of testing. This test is intended only to demonstrate the sealing effectiveness of the installed system. Structural design of the tank is defined or demonstrated within the scope of other applicable specifications and test methods, including Specification C1227.

## 6. Equipment Required

6.1 A vacuum device is required and shall be capable of reliably drawing the required vacuum. Suitable vacuum devices include vane- and venturi-type pumps, vehicle vacuum systems, and high-performance shop-style vacuum cleaners.

6.2 A vacuum measuring device is required and shall be a vacuum gauge, mercury manometer, or water manometer accurate to 0.1 in. (2.5 mm) Hg [1.4 in. (35 mm) H<sub>2</sub>O]. If a

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.